
**Gas cylinders — Compatibility of cylinder
and valve materials with gas contents —**

**Part 2:
Non-metallic materials**

*Bouteilles à gaz — Compatibilité des matériaux des bouteilles et
des robinets avec les contenus gazeux —
Partie 2: Matériaux non métalliques*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 11114-2:2013](https://standards.iteh.ai/catalog/standards/sist/b3c1433c-fd0f-4c34-8de2-0d6c0ceda42d/iso-11114-2-2013)

<https://standards.iteh.ai/catalog/standards/sist/b3c1433c-fd0f-4c34-8de2-0d6c0ceda42d/iso-11114-2-2013>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 11114-2:2013](https://standards.iteh.ai/catalog/standards/sist/b3c1433c-fd0f-4c34-8de2-0d6c0ceda42d/iso-11114-2-2013)

<https://standards.iteh.ai/catalog/standards/sist/b3c1433c-fd0f-4c34-8de2-0d6c0ceda42d/iso-11114-2-2013>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references.....	1
3 Terms and definitions	1
4 Materials	2
4.1 General	2
4.2 Types of material	2
5 General considerations.....	3
6 Specific considerations	4
6.1 General	4
6.2 Non-compatibility risks.....	4
6.2.1 Violent reaction (oxidation/burning) (F)	4
6.2.2 Weight loss (W).....	5
6.2.3 Swelling of material (S)	6
6.2.4 Change in mechanical properties (M)	6
6.2.5 Other compatibility considerations	6
7 Compatibility data	7
7.1 Table of compatibility.....	7
7.2 Symbols and abbreviations.....	8
7.2.1 Symbols for compatibility	8
7.2.2 Abbreviations for materials	8
7.2.3 Abbreviations for non-compatibility risks	9
7.2.4 Examples	9
Bibliography.....	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11114-2 was prepared by Technical Committee ISO/TC 58, *Gas cylinders*, in collaboration with Technical Committee CEN/TC 23, *Transportable Gas cylinders* in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition. Clauses 4 and 6, and Table 1 of which have been technically revised. Annex A has been deleted.

ISO 11114 consists of the following parts, under the general title *Gas cylinders — Compatibility of cylinder and valve materials with gas contents*:

- *Part 1: Metallic materials;*
- *Part 2: Non-metallic materials;*
- *Part 3: Autogenous ignition test for non-metallic materials in oxygen atmosphere;*
- *Part 4: Test methods for selecting metallic materials resistant to hydrogen embrittlement.*

Introduction

This part of ISO 11114 deals with the compatibility of non-metallic materials used for gas cylinders and gas cylinder valves with the gas contents of the cylinder. Compatibility of metallic materials is treated in ISO 11114-1.

Non-metallic materials are very often used for the construction of gas cylinder valves as seals, e.g. o-ring, gland packing, seats, or as lubrication products to avoid friction. They are also commonly used to ensure sealing of the valve/cylinder connection. For gas cylinders, they are sometimes used as an internal coating or as a liner for composite materials.

Non-metallic materials not in contact with the gas are not covered by this part of ISO 11114.

This part of ISO 11114 is based on current international experience and knowledge. Some data are derived from experience involving a mixture of the gas concerned with a dilutant, where no data for single component gases were available.

This part of ISO 11114 has been written to be in conformity with the UN Recommendations on the Transport of Dangerous Goods: Model Regulations. When published it will be submitted to the UN Sub Committee of Experts on the Transport of Dangerous Goods with a request that it be included in the Model Regulations. Where there is any conflict between this part of ISO 11114 and any applicable regulation, the regulation always takes precedence.

(standards.iteh.ai)

[ISO 11114-2:2013](https://standards.iteh.ai/catalog/standards/sist/b3c1433c-fd0f-4c34-8de2-0d6c0ceda42d/iso-11114-2-2013)

<https://standards.iteh.ai/catalog/standards/sist/b3c1433c-fd0f-4c34-8de2-0d6c0ceda42d/iso-11114-2-2013>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 11114-2:2013](https://standards.iteh.ai/catalog/standards/sist/b3c1433c-fd0f-4c34-8de2-0d6c0ceda42d/iso-11114-2-2013)

<https://standards.iteh.ai/catalog/standards/sist/b3c1433c-fd0f-4c34-8de2-0d6c0ceda42d/iso-11114-2-2013>

Gas cylinders — Compatibility of cylinder and valve materials with gas contents —

Part 2: Non-metallic materials

1 Scope

This part of ISO 11114 gives guidance in the selection and evaluation of compatibility between non-metallic materials for gas cylinders and valves and the gas contents. It also covers bundles, tubes and pressure drums.

This part of ISO 11114 can be helpful for composite and laminated materials used for gas cylinders.

It does not cover the subject completely and is intended to give guidance only in evaluating the compatibility of gas/material combinations.

Only the influence of the gas in changing the material and mechanical properties is considered (for example chemical reaction or change in physical state). The basic properties of the materials, such as mechanical properties, required for design purposes are normally available from the materials supplier and are not considered in this part of ISO 11114.

The compatibility data given are related to single component gases but can be used to some extent for gas mixtures. Ceramics, glasses, and adhesives are not covered by this part of ISO 11114.

Other aspects such as quality of delivered gas are not considered.

This part of ISO 11114 is not intended to be used for cryogenic fluids (see ISO 21010).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11114-3, *Transportable gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 3: Autogenous ignition test for non-metallic materials in oxygen atmosphere*

ISO 10297, *Gas cylinders — Refillable gas cylinder valves — Specification and type testing*

ISO 15001, *Anaesthetic and respiratory equipment — Compatibility with oxygen*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 competent person
person who has the necessary technical knowledge, qualification, experience and authority to assess and approve materials for use with gases and to define any special conditions of use that are necessary

3.2 acceptable
material/gas combination that is satisfactory under normal conditions of use (as defined in Clause 5), provided that any indicated non-compatibility risks, as given in Table 1, are taken into account

3.3 not acceptable
material/single gas combination that is not safe under normal conditions of use (as defined in Clause 5)

NOTE For gas mixtures special conditions can apply.

3.4 dynamic sealing
where in normal operation the non-metallic material is used to provide a pressure seal between two surfaces that have relative motion to each other

3.5 static sealing
where in normal operation the non-metallic material is used to provide a pressure seal between two surfaces that have not relative motion to each other

iTeh STANDARD PREVIEW
(standards.iteh.ai)

4 Materials

4.1 General

ISO 11114-2:2013
<https://standards.iteh.ai/catalog/standards/sist/b3c1433c-fd0f-4c34-8de2-01c01b1d6c81/iso-11114-2-2013>

Non-metallic materials shall be suitable for the intended service. They are suitable if their compatibility is stated as acceptable in Table 1, or the necessary properties have been proved by tests or long and safe experience to the satisfaction of a competent person.

If coated materials are used the suitability of the combination shall be assessed and approved if all technical aspects have been considered and validated by a competent person. These technical aspects include but are not limited to compatibility of the coating material with the intended gas, durability of the coating during all its intended use and gas permeability through it.

4.2 Types of material

The most commonly used non-metallic materials for gas cylinders and cylinder valves can be grouped as follows:

- plastics;
- elastomers;
- fluid lubricants.

NOTE Solid lubricants are sometimes used, e.g. MoS₂.

Materials considered in this part of ISO 11114 are as follows:

- a) Plastics:
 - Polytetrafluoroethylene (PTFE);

- Polychlorotrifluoroethylene (PCTFE);
- Polyvinylidene fluoride (PVDF);
- Polyamide (PA);
- Polypropylene (PP);
- Polyetheretherketone (PEEK);
- Polypropylene sulphide (PPS);
- Polyvinyl chloride (PVC)
- Polyimide (PI);
- Polyoxymethylene (POM).

b) Elastomers:

- Butyl rubber (IIR);
- Nitrile rubber (NBR);
- Chloroprene rubber (CR);
- Fluorocarbon rubber (FKM);
- Methyl-vinyl-silicone rubber (VMQ);
- Ethylene propylene diene monomer (EPDM);
- Polyacrylate rubber (ACM);
- Polyurethane rubber (PUR);
- Methyl-fluoro-silicone rubber (FVMQ).

c) Fluid lubricants:

- Hydrocarbon (HC);
- Fluorocarbon (FC).

5 General considerations

It is important to note that these materials are generic types. Within each material type there are variations in the properties of the materials due to polymer differences and formulations used by manufacturers to modify physical and chemical properties of the material. The user of the material should therefore consult the manufacturer and if necessary carry out tests before using the material (for example for critical services such as oxygen and other oxidizing gases).

Lubricants are often used in valves to reduce friction and wear in the moving parts. For valves used for oxidizing gases or for gases supporting combustion, if lubrication is required, it shall be ensured that the lubricant is compatible for the intended application when the lubricated components are in contact with the oxidizing gas or the gas supporting combustion.

Where the lubricant is listed as "not acceptable" in Table 1 for reasons other than violent reaction (F), it may be used safely and usually satisfactorily in applications which do not involve contact in normal operation with the gas. An example of such an application is the lubrication of the valve actuating mechanism not in contact with the gas.

Where the lubricant is listed as "not acceptable" for the reason of violent reaction (F), it should not be used in any part of the system that can be contacted by the gas, even under abnormal conditions such as in the event of a failure of the gas sealing system. If there is a risk of violent reaction, appropriate safety and suitability tests shall have been carried out for the lubricant application before it is used either on the lubricant itself, as specified in ISO 11114-3, or on the lubricated equipment in which it will be used, as specified in ISO 10297.

The properties of plastics and elastomers including compatibility are dependent on temperature. Low temperature can cause hardening and the possibility of embrittlement, whereas high temperature can cause softening and the possibility of material flow. Users of such materials shall check to ensure their suitability over the entire operating temperature range specified by the cylinder and valve manufacturing standards.

Some materials become brittle at low temperatures, especially at temperatures at the lower end of the normal operating range (e.g. fluorocarbon rubber). Temperatures in the refrigerant or cryogenic ranges affect many materials and caution shall be exercised at temperatures below -50° C. This risk shall be considered in particular when transfilling by thermal siphoning at low temperature or similar procedures, or for cylinders regularly filled at low temperatures (e.g. CO₂).

6 Specific considerations

6.1 General

The compatibility of gases with non-metallic materials is affected by chemical reactions and physical influences, which can be classified as follows.

6.2 Non-compatibility risks

iTeh STANDARD PREVIEW
(standards.iteh.ai)
ISO 11114-2:2013
<https://standards.iteh.ai/catalog/standards/sist/b3c1433c-fd0f-4c34-8de2-0d6c0ceda42d/iso-11114-2-2013>

6.2.1 Violent reaction (oxidation/burning) (F)

6.2.1.1 Principle

Historically the majority of serious accidents from rapid oxidation or violent combustion have occurred with oxidizing gas supporting combustion at high pressure. Thorough investigation of all materials and factors should be conducted with great care and all data should be considered before designing or using equipment to handle oxidizing gases or gases supporting combustion.

Compatibility depends mainly on the operating conditions (pressure, temperature, gas velocity, particles, equipment design, and application). The risk shall particularly be considered with gases such as oxygen, fluorine, chlorine and nitrogen trifluoride. Most of the non-metallic materials can be ignited relatively easily when in contact with oxidizing gases (see ISO 10156) and even when in contact with gases not classified as oxidizing but still supporting combustion.

The selection of a material for use with oxygen and/or an oxygen enriched atmosphere is primarily a matter of understanding the circumstances that cause the material to react with oxygen. Most materials in contact with oxygen will not ignite without a source of ignition energy (e.g. friction, heat of compression, particle impacts, etc.). When an energy input rate, as converted to heat, is greater than the rate of heat dissipation, and the resulting heat increase is continued for sufficient time, ignition and combustion will occur.

Thus, two general factors shall be considered:

- a) the materials compatibility properties (ease of ignition and energy of combustion); and
- b) the different energy sources that will produce a sufficient increase in the temperature of the material.

These general factors should be viewed in the context of the entire system design so that the specific factors listed below will assume the proper relative significance.

The specific factors to take into consideration are

- the properties of the materials, which include the factors affecting ease of ignition and the conditions affecting potential resulting damage (heat of reaction),
- the operating conditions: e.g. pressure, temperature, oxygen and/or oxidizing gas concentrations in a gas mixture, influence of dilutant (e.g. helium), surface contamination,
- the potential sources of ignition (e.g. friction, heat of compression, heat from mass impact, heat from particle impact, static electricity, electrical arc, resonance, internal flexing),
- possible consequence (e.g. effects on the surroundings such as propagation of fire), and
- additional factors (e.g. performance requirements, prior experience, availability).

In conclusion the evaluation of compatibility of non-metallic materials is more critical than that of metallic materials, which generally perform well when in contact with oxygen.

6.2.1.2 Specifications for oxidizing gases

In accordance with 6.2.1.1, it is not possible to make a simple statement concerning the compatibility of non-metallic materials with oxidizing gases such as oxygen, chlorine, nitric oxide, nitrous oxide, nitrogen dioxide, nitrogen trifluoride, etc. (see ISO 10156).

For fluorine, which is the most oxidizing gas, all non-metallic materials would historically fall into the classification "not acceptable".

For fluorine mixtures the gases industry now has evidence of successful testing and safe history of use of PTFE and PCTFE under controlled conditions (e.g. low concentration and low pressure). Therefore following an assessment and authorisation by a competent person, these materials are acceptable in similar conditions. Oxygen and other oxidizing gases can react violently when tested with all non-metallic materials listed in 4.2 a), 4.2 b) and 4.2 c). Some materials such as PTFE and FKM are more resistant to ignition than other plastics and elastomers. HC lubricants are normally not acceptable. Under certain conditions other plastics and elastomers listed can be safely used in oxidizing service without presenting some of the disadvantages of PTFE, i.e. poor mechanical properties, and risk of release of toxic products for breathing gas applications, see ISO 15001, or FKM, i.e. swelling, poor mechanical properties at low temperature, risk of release of toxic products in breathing gas applications, etc..

Consequently, non-metallic materials may only be used if it has been proven by tests (or long and safe service experience), taking into account all the operating conditions and especially the design of the equipment, that their use is safe. ISO 11114-3 and ISO 21010 give testing methods for polymeric materials and fluid lubricants that will result in conservative value. Some non-metallic material can be safely used at higher pressure when they are tested in the final design configuration, e.g. in gas cylinder valves and regulator. Cylinder valves shall be tested according to ISO 10297 for oxygen service.

6.2.2 Weight loss (W)

6.2.2.1 Extraction

Solvent extraction of plasticizers from elastomers can cause shrinkage, especially in highly plasticized products.