

---

---

**Plastics — Plasticized poly(vinyl chloride)  
(PVC-P) moulding and extrusion  
materials —**

**Part 2:  
Preparation of test specimens and  
determination of properties**

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

*Plastiques — Matériaux à base de poly(chlorure de vinyle) plastifié  
(PVC-P) pour moulage et extrusion —*

*Partie 2: Préparation des éprouvettes et détermination des propriétés*

<https://standards.iteh.ai/catalog/standards/sist/0cbb597c-6f41-417e-a726-99e66f261d77/iso-2898-2-2008>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 2898-2:2008

<https://standards.iteh.ai/catalog/standards/sist/0cbb597c-6f41-417e-a726-99e66f261d77/iso-2898-2-2008>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2898-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This fourth edition cancels and replaces the third edition (ISO 2898-2:1997), of which it constitutes a minor revision, the main purpose of which was to update the normative references.

ISO 2898 consists of the following parts, under the general title *Plastics — Plasticized poly(vinyl chloride) (PVC-P) moulding and extrusion materials*: [ISO 2898-2:2008](https://standards.iteh.ai/catalog/standards/sist/0cbb597c-6f41-417e-a726-99c661261d77/ISO-2898-2-2008)

- *Part 1: Designation system and basis for specifications*
- *Part 2: Preparation of test specimens and determination of properties*

## **iTeh STANDARD PREVIEW** **(standards.iteh.ai)**

ISO 2898-2:2008

<https://standards.iteh.ai/catalog/standards/sist/0cbb597c-6f41-417e-a726-99e66f261d77/iso-2898-2-2008>

# Plastics — Plasticized poly(vinyl chloride) (PVC-P) moulding and extrusion materials —

## Part 2:

## Preparation of test specimens and determination of properties

### 1 Scope

This part of ISO 2898 specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of PVC-P moulding and extrusion materials. Requirements for handling test material and for conditioning both the test material before moulding and the specimens before testing are given.

Procedures and conditions for the preparation of test specimens and procedures for measuring properties of the materials from which these specimens are made are given. Properties and test methods which are suitable and necessary to characterize PVC-P moulding and extrusion materials are listed.

The properties have been selected from the general test methods in ISO 10350-1. Other test methods in wide use for, or of particular significance to, these moulding and extrusion materials are also included in this part of ISO 2898, as are the designatory properties specified in ISO 2898-1.

In order to obtain reproducible and comparable test results, it is necessary to use the methods of preparation and conditioning, the specimen dimensions and the test procedures specified herein. Values determined will not necessarily be identical to those obtained using specimens of different dimensions or prepared using different procedures.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 176:2005, *Plastics — Determination of loss of plasticizers — Activated carbon method*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 458-2, *Plastics — Determination of stiffness in torsion of flexible materials — Part 2: Application to plasticized compounds of homopolymers and copolymers of vinyl chloride*

ISO 527-2:1993, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 1183-1:2004, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 2898-1, *Plastics — Plasticized poly(vinyl chloride) (PVC-P) moulding and extrusion materials — Part 1: Designation system and basis for specifications*

ISO 3167:2002, *Plastics — Multipurpose test specimens*

ISO 3451-5:2002, *Plastics — Determination of ash — Part 5: Poly(vinyl chloride)*

ISO 10350-1, *Plastics — Acquisition and presentation of comparable single-point data — Part 1: Moulding materials*

IEC 60093, *Methods of test for volume resistivity and surface resistivity of solid electrical insulating materials*

### 3 Preparation of test specimens

#### 3.1 General

It is essential that specimens are always prepared by the same procedure (compression moulding), using the same processing conditions.

The material shall be kept in moisture-proof containers until it is required for use.

#### 3.2 Treatment of the material before moulding

Before processing, no pretreatment of the material sample is normally necessary.

#### 3.3 Compression moulding

Before compression moulding, the material shall be plasticized using a two-roll mill under the conditions specified in Table 1.

**Table 1 — Conditions for milling of material before compression moulding**

Shore hardness of material	Roll surface temperature °C	Milling time <sup>a</sup> min	Roll surface speed m/min	Speed ratio	Roll nip width mm	Roll diameter mm	Roll length mm
Up to A 80	130 to 160	Approx. 5	Approx. 10	1:1,2	Approx. 1	e.g. 150	e.g. 300
D 35 to D 50	145 to 170	Approx. 5	Approx. 10	1:1,2	Approx. 1	e.g. 150	e.g. 300
Above D 50	160 to 175	Approx. 5	Approx. 10	1:1,2	Approx. 1	e.g. 150	e.g. 300

<sup>a</sup> Measured from the moment when a sheet is formed.

Sheet material from the mill shall be stacked, preferably with sheet orientation alternating from layer to layer, in the preheated mould. Compression-moulded sheets shall then be prepared in accordance with ISO 293, using the conditions specified in Table 2.

Table 2 — Conditions for compression moulding of test specimens

Shore hardness of material	Moulding temperature °C	Average cooling rate °C/min	Demoulding temperature °C	Full pressure MPa	Full-pressure time min	Preheating pressure MPa	Preheating time min
Up to A 80	135 to 165	Not defined	Approx. 40 <sup>a</sup>	2 to 10	2 to 5	Approx. 0,3	Max. 5
D 35 to D 50	145 to 175	Not defined	Approx. 40 <sup>a</sup>	2 to 10	2 to 5	Approx. 0,3	Max. 5
Above D 50	170 to 180	Not defined	Approx. 40 <sup>a</sup>	2 to 10	2 to 5	Approx. 0,3	Max. 5

<sup>a</sup> Very soft materials may require a lower temperature.

The test specimens required for the determination of the properties shall be machined from the compression-moulded sheets in accordance with ISO 2818 or stamped.

For additional details on test specimen preparation, see Annex A.

## 4 Conditioning of test specimens

Test specimens for all determinations shall be conditioned in accordance with ISO 291 for at least 48 h at  $23\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$  and  $(50 \pm 10)\%$  relative humidity.

## 5 Determination of properties

In the determination of properties and the presentation of data, the standards, supplementary instructions and notes given in ISO 10350-1 shall be applied. All tests shall be carried out in the standard atmosphere of  $23\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$  and  $(50 \pm 10)\%$  relative humidity unless specifically stated otherwise in Tables 3 and 4.

Table 3 is compiled from ISO 10350-1, and the properties listed are those which are appropriate to PVC-P moulding and extrusion materials. These properties are those considered useful for comparisons of data generated for different thermoplastics.

Table 4 contains those properties, not found specifically in Table 3, which are in wide use or of particular significance in the practical characterization of PVC-P moulding and extrusion materials.

Table 3 — General properties and test conditions (selected from ISO 10350-1)

Property	Unit	Standard	Specimen type (dimensions in mm)	Test conditions and supplementary instructions
<b>Mechanical properties</b>				
Tensile stress at 50 % strain	MPa	ISO 527-2	ISO 3167:2002 type A specimen	Test speed 50 mm/min Distance between gauge marks 70 mm
<b>Electrical properties</b>				
Volume resistivity	$\Omega \cdot \text{m}$	IEC 60093	$\geq 80 \times \geq 80 \times 1$	Voltage 100 V
<b>Other properties</b>				
Density <sup>a</sup>	kg/m <sup>3</sup>	ISO 1183-1:2004	At least 1 g	Method A or B Report the result to two decimal places

<sup>a</sup> Designatory property.

**Table 4 — Additional properties and test conditions of particular utility to PVC-P moulding and extrusion materials**

Property	Unit	Standard	Specimen type	Test conditions and supplementary instructions
<b>Mechanical properties</b>				
Tensile stress at 100 % elongation	MPa	ISO 527-2:1993	Type 1BA specimen Thickness 2 mm	Test speed 500 mm/min
Shore A or D hardness <sup>a</sup>	—	ISO 868	Disc of diameter 50 mm or square 50 mm × 50 mm specimen Thickness 4 mm or 6 mm (type A: 6 mm only)	Force applied to specimen 50 N Take reading after 15 s ± 1 s Use Shore D if Shore A hardness > 85
<b>Thermal properties</b>				
Torsional stiffness as a function of temperature <sup>a</sup>	°C	ISO 458-2	60 mm × 60 mm × 2 mm For very flexible compounds, use a 60 mm × 60 mm × 4 mm specimen at high temperatures of test.	The values of the torsional stiffness are plotted as a function of temperature. The two temperatures at which the stiffness in torsion has values of 300 MPa and 4,1 MPa are TST 300 and TST 4,1, respectively. For ISO 2898-1, TST = 300.
<b>Other properties</b>				
Sulfated ash	% (by mass)	ISO 3451-5:2002	Pellets	Method B
Loss of plasticizers	% (by mass)	ISO 176:2005	Disc of diameter 50 mm and thickness 1 mm	Method B
<sup>a</sup> Designatory property.				

ISO 2898-2:2008

<https://standards.iteh.ai/catalog/standards/sist/0cbb597c-6f41-417e-a726-99e66f261d77/iso-2898-2-2008>



## Annex A (normative)

### Detailed description of the preparation of test specimens

#### A.1 Principle

A rough sheet of the material to be tested is prepared using a heated two-roll mill. This sheet is then compression moulded into sheets of uniform thickness. Test specimens are prepared from the moulded sheets by machining or die-cutting.

#### A.2 Preparation of preliminary sheets

##### A.2.1 Apparatus

**A.2.1.1 Two-roll mixing mill**, capable of operating satisfactorily at temperatures up to and including 180 °C. The rolls shall be cylindrical; the dimensions may be, for example: diameter 150 mm, length 300 mm.

##### A.2.2 Milling conditions

**A.2.2.1** The surface temperature of the mill rolls and the moulding temperature used subsequently (see A.3.3) shall be based on the Shore hardness value of the material.

The temperature of the rolls shall be selected to permit the material to band on the surface of the roll between 1 min and 2 min after the commencement of milling. There shall be a maximum difference of 4 °C between the rolls and  $\pm 2$  °C along the length of each roll.

**A.2.2.2** Detailed schedules for the milling of individual compositions are not included in this part of ISO 2898, but the following remarks apply to mixes of all types:

The surface speed of the rolls shall be approximately 10 m/min.

It is customary for there to be a differential speed between the two rolls. The preferred ratio is 1:1,2, the front (working) roll being the slower.

Proper mill mixing of the material requires a rolling bank. The amount of material should preferably be such that the ratio of the diameter of the rolling bank to the nip width is 10:1. The nip settings shall be determined by the desired thickness of the milled sheet. During mill mixing, the nip width shall be about 1 mm.

##### A.2.3 Procedure

Add the material to the mill rolls. Collect any material falling through the nip carefully and quickly from the tray and return to the moving mill rolls. After a sheet is formed, continue milling for approximately 5 min in such a way that optimum dispersion of all material components is obtained. This normally includes cutting the sheet, allowing it to form a roll, and re-feeding this roll into the nip. Remove the milled sheet from the rolls without stretching it.

Deviations from A.2.2 and A.2.3, if necessary, shall be included in a test report.