

Designation: D $4000 - 04^{\epsilon 1}$

Standard Classification System for Specifying Plastic Materials¹

This standard is issued under the fixed designation D 4000; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

 ϵ^1 Note—Editorial changes were made throughout in July 2006.

1. Scope*

1.1 This standard provides a classification system for tabulating the properties of unfilled, filled, and reinforced plastic materials suitable for processing into parts.

Note 1—The classification system may serve many of the needs of industries using plastic materials. The standard is subject to revision as the need requires; therefore, the latest revision should always be used.

- 1.2 The classification system and subsequent line callout (specification) is intended to be a means of identifying plastic materials used in the fabrication of end items or parts. It is not intended for the selection of materials. Material selection should be made by those having expertise in the plastics field after careful consideration of the design and the performance required of the part, the environment to which it will be exposed, the fabrication process to be employed, the inherent properties of the material not covered in this document, and the economic factors.
- 1.3 This classification system is based on the premise that plastic materials can be arranged into broad generic families using basic properties to arrange the materials into groups, classes, and grades. A system is thus established which, together with values describing additional requirements, permits as complete a description as desired of the selected material.
- 1.4 In all cases where the provisions of this classification system would conflict with the referenced ASTM specification for a particular material, the latter shall take precedence.
- Note 2—When using this classification system the two-letter, three-digit suffix system applies.
- Note 3—When a material is used to fabricate a part where the requirements are too specific for a broad material callout, it is advisable for the user to consult the supplier to secure callout of the properties to suit the actual conditions to which the part is to be subjected.
- 1.5 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the

responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

- 2.1 ASTM Standards: ²
- D 149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies
- D 150 Test Methods for AC Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulation
- D 256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics
- D 257 Test Methods for DC Resistance or Conductance of Insulating Materials
- D 395 Test Methods for Rubber Property—Compression Set
- D 412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension
- D 471 Test Method for Rubber Property—Effect of Liquids
- D 495 Test Method for High-Voltage, Low-Current, Dry Arc Resistance of Solid Electrical Insulation
- D 569 Method for Measuring the Flow Properties of Thermoplastic Molding Materials³
- D 570 Test Method for Water Absorption of Plastics
- D 573 Test Method for Rubber—Deterioration in an Air Oven
- D 575 Test Methods for Rubber Properties in Compression
- D 618 Practice for Conditioning Plastics for Testing
- D 624 Test Method for Tear Strength of Conventional Vulcanized Rubber and Thermoplastic Elastomers
- D 635 Test Method for Rate of Burning and/or Extent and Time of Burning of Plastics in a Horizontal Position
- D 638 Test Method for Tensile Properties of Plastics

¹ This classification system is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.94 on Government/Industry Standardization (Section D20.94.01).

Current edition approved Feb. 1, 2004. Published March 2004. Originally published as D 4000-82. Last previous edition D 4000-03a.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn.



- D 648 Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position
- D 695 Test Method for Compressive Properties of Rigid Plastics
- D 706 Specification for Cellulose Acetate Molding and Extrusion Compounds
- D 707 Specification for Cellulose Acetate Butyrate Molding and Extrusion Compounds
- D 747 Test Method for Apparent Bending Modulus of Plastics by Means of a Cantilever Beam
- D 785 Test Method for Rockwell Hardness of Plastics and Electrical Insulating Materials
- D 787 Specification for Ethyl Cellulose Molding and Extrusion Compounds
- D 788 Classification System for Poly(Methyl Methacrylate) (PMMA) Molding and Extrusion Compounds
- D 789 Test Methods for Determination of Solution Viscosities of Polyamide (PA)
- D 790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials
- D 792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement
- D 883 Terminology Relating to Plastics
- D 955 Test Method of Measuring Shrinkage from Mold Dimensions of Thermoplastics
- D 1003 Test Method for Haze and Luminous Transmittance of Transparent Plastics
- D 1149 Test Method for Rubber Deterioration—Surface Ozone Cracking in a Chamber
- D 1203 Test Methods for Volatile Loss From Plastics Using Activated Carbon Methods
- D 1238 Test Method for Melt Flow Rates of Thermoplastics by Extrusion Plastometer
- D 1248 Specification for Polyethylene Plastics Extrusion Materials for Wire and Cable
- D 1430 Classification System for Polychlorotrifluoroethylene (PCTFE) Plastics
- D 1434 Test Method for Determining Gas Permeability Characteristics of Plastic Film and Sheeting
- D 1435 Practice for Outdoor Weathering of Plastics
- D 1499 Practice for Filtered Open-Flame Carbon-Arc Exposures of Plastics
- D 1505 Test Method for Density of Plastics by the Density-Gradient Technique
- D 1525 Test Method for Vicat Softening Temperature of Plastics
- D 1562 Specification for Cellulose Acetate Propionate Molding and Extrusion Compounds
- D 1600 Terminology for Abbreviated Terms Relating to Plastics
- D 1693 Test Method for Environmental Stress-Cracking of Ethylene Plastics
- D 1709 Test Methods for Impact Resistance of Plastic Film by the Free-Falling Dart Method
- D 1784 Specification for Rigid Poly(Vinyl Chloride) (PVC) Compounds and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds

- D 1822 Test Method for Tensile-Impact Energy to Break Plastics and Electrical Insulating Materials
- D 1898 Practice for Sampling of Plastics³
- D 1929 Test Method for Determining Ignition Temperature of Plastics
- D 2116 Specification for FEP-Fluorocarbon Molding and Extrusion Materials
- D 2137 Test Methods for Rubber Property—Brittleness Point of Flexible Polymers and Coated Fabrics
- D 2240 Test Method for Rubber Property—Durometer Hardness
- D 2287 Specification for Nonrigid Vinyl Chloride Polymer and Copolymer Molding and Extrusion Compounds
- D 2288 Test Method for Weight Loss of Plasticizers on Heating
- D 2565 Practice for Xenon-Arc Exposure of Plastics Intended for Outdoor Applications
- D 2583 Test Method for Indentation Hardness of Rigid Plastics by Means of a Barcol Impressor
- D 2584 Test Method for Ignition Loss of Cured Reinforced Resins
- D 2632 Test Method for Rubber Property—Resilience by Vertical Rebound
- D 2843 Test Method for Density of Smoke from the Burning or Decomposition of Plastics
- D 2863 Test Method for Measuring the Minimum Oxygen Concentration to Support Candle-Like Combustion of Plastics (Oxygen Index)
- D 2951 Test Method for Resistance of Types III and IV Polyethylene Plastics to Thermal Stress-Cracking³
- D 3012 Test Method for Thermal-Oxidative Stability of Polypropylene Using a Specimen Rotator Within an Oven
- D 3029 Test Methods for Impact Resistance of Flat, Rigid Plastic Specimens by Means of a Tup (Falling Weight)³
- D 3159 Specification for Modified ETFE-Fluoropolymer Molding and Extrusion Materials
- D 3222 Specification for Unmodified Poly(Vinylidene Fluoride) (PVDF) Molding Extrusion and Coating Materials
- D 3275 Classification System for E-CTFE-Fluoroplastic Molding, Extrusion, and Coating Materials
- D 3294 Specification for Polytetrafluoroethylene (PTFE) Resin Molded Sheet and Molded Basic Shapes
- D 3295 Specification for PTFE Tubing, Miniature Beading and Spiral Cut Tubing
- D 3296 Specification for FEP-Fluorocarbon Tube
- D 3307 Specification for Perfluoroalkoxy (PFA)-Fluorocarbon Resin Molding and Extrusion Materials
- D 3350 Specification for Polyethylene Plastics Pipe and Fittings Materials
- D 3418 Test Method for Transition Temperatures of Polymers By Differential Scanning Calorimetry
- D 3595 Specification for Polychlorotrifluoroethylene (PCTFE) Extruded Plastic Sheet and Film
- D 3638 Test Method for Comparative Tracking Index of Electrical Insulating Materials
- D 3713 Test Method for Measuring Response of Solid Plastics to Ignition by a Small Flame³



- D 3801 Test Method for Measuring the Comparative Burning Characteristics of Solid Plastics in a Vertical Position
- D 3892 Practice for Packaging/Packing of Plastics
- D 3895 Test Method for Oxidative-Induction Time of Polyolefins by Differential Scanning Calorimetry
- D 3915 Specification for Rigid Poly(Vinyl Chloride) (PVC) and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds for Plastic Pipe and Fittings Used in Pressure Applications
- D 3935 Specification for Polycarbonate (PC) Unfilled and Reinforced Material
- D 3965 Specification for Rigid Acrylonitrile-Butadiene-Styrene (ABS) Materials for Pipe and Fittings
- D 3985 Test Method for Oxygen Gas Transmission Rate Through Plastic Film and Sheeting Using a Coulometric Sensor
- D 4020 Specification for Ultra-High-Molecular-Weight Polyethylene Molding and Extrusion Materials
- D 4066 Classification System for Nylon Injection and Extrusion Materials (PA)
- D 4067 Classification System for Reinforced and Filled Poly(Phenylene Sulfide) (PPS) Injection Molding and Extrusion Materials Using ASTM Methods
- D 4101 Specification for Polypropylene Injection and Extrusion Materials
- D 4181 Classification for Acetal (POM) Molding and Extrusion Materials³
- D 4203 Specification for Styrene-Acrylonitrile (SAN) Injection and Extrusion Materials
- D 4216 Specification for Rigid Poly(Vinyl Chloride) (PVC) and Related PVC and Chlorinated Poly(Vinyl Chloride) (CPVC) Building Products Compounds
- D 4329 Practice for Fluorescent UV Exposure of Plastics
- D 4349 Classification System for Polyphenylene Ether (PPE) Materials
- D 4364 Practice for Performing Outdoor Accelerated Weathering Tests of Plastics Using Concentrated Sunlight
- D 4396 Specification for Rigid Poly(Vinyl Chloride) (PVC) and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds for Plastic Pipe and Fittings Used in Nonpressure Applications
- D 4441 Specification for Aqueous Dispersions of Polytetrafluoroethylene
- D 4474 Classification System for Styrenic Thermoplastic Elastomer Injection Molding and Extrusion Materials (TES)
- D 4507 Specification for Thermoplastic Polyester (TPES) Materials³
- D 4549 Specification for Polystyrene and Rubber-Modified Polystyrene Molding and Extrusion Materials (PS)
- D 4550 Classification for Thermoplastic Elastomer-Ether-Ester (TEEE)³
- D 4617 Classification System for Phenolic Compounds (PF)
- D 4634 Specification for Styrene-Maleic Anhydride Materials (S/MA)

- D 4673 Classification System for Acrylonitrile–Butadiene–Styrene (ABS) Plastics and Alloys Molding and Extrusion Materials
- D 4745 Specification for Filled Compounds of Polytetrafluoroethylene (PTFE) Molding and Extrusion Materials
- D 4812 Test Method for Unnotched Cantilever Beam Impact Resistance of Plastics
- D 4894 Specification for Polytetrafluoroethylene (PTFE) Granular Molding and Ram Extrusion Materials
- D 4895 Specification for Polytetrafluoroethylene (PTFE) Resin Produced From Dispersion
- D 4976 Specification for Polyethylene Plastics Molding and Extrusion Materials
- D 5021 Specification for Thermoplastic Elastomer–Chlorinated Ethylene Alloy (TECEA)
- D 5033 Guide for Development of ASTM Standards Relating to Recycling and Use of Recycled Plastics
- D 5046 Classification for Fully Crosslinked Elastomeric Alloys (FCEAs)³
- D 5138 Classification System for Liquid Crystal Polymers (LCP)
- D 5203 Specification for Polyethylene Plastics Molding and Extrusion Materials from Recycled Post-Consumer (HDPE) Sources
- D 5204 Classification System for Polyamide-Imide (PAI) Molding and Extrusion Materials
- D 5205 Classification System for Polyetherimide (PEI) Materials
- D 5260 Classification for Chemical Resistance of Poly(Vinyl Chloride) (PVC) Homopolymer and Copolymer Compounds and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds
- D 5279 Test Method for Plastics: Dynamic Mechanical Properties: In Torsion
- D 5336 Specification for Polyphthalamide (PPA) Injection Molding Materials
- D 5420 Test Method for Impact Resistance of Flat, Rigid Plastic Specimen by Means of a Striker Impacted by a Falling Weight (Gardner Impact)
- D 5436 Specification for Cast Poly(Methyl Methacrylate) Plastic Rods, Tubes, and Shapes
- D 5476 Classification System for Thermoplastic Polyurethane Materials (TPU)³
- D 5575 Specification for Copolymers of Vinylidene Fluoride (VDF) with Other Fluorinated Monomers
- D 5593 Classification for Thermoplastic Elastomers—Olefinic (TEO)³
- D 5628 Test Method for Impact Resistance of Flat, Rigid Plastic Specimens by Means of a Falling Dart (Tup or Falling Mass)
- D 5630 Test Method for Ash Content in Plastics
- D 5675 Classification for Fluoropolymer Micropowders
- D 5676 Specification for Recycled Polystyrene Molding and Extrusion Materials³
- D 5857 Specification for Polypropylene Injection and Extrusion Materials Using ISO Protocol and Methodology

- D 5927 Specification for Thermoplastic Polyester (TPES) Injection and Extrusion Materials Based on ISO Test Methods
- D 5990 Classification System for Polyketone Injection Molding and Extrusion Materials (PK)
- D 6314 Specification for Fluorocarbon Perfluoromethoxy (MFA) Resin Molding and Extrusion Materials³
- D 6338 Classification System for Highly Crosslinked Thermoplastic Vulcanizates (HCTPVs)
- D 6339 Specification for Syndiotactic Polystyrene Molding and Extrusion (SPS)
- D 6358 Classification System for Poly (Phenylene Sulfide)
 Injection Molding and Extrusion Materials Using ISO
 Methods
- D 6360 Practice for Enclosed Carbon-Arc Exposures of Plastics
- D 6394 Specification for Sulfone Plastics (SP)
- D 6457 Specification for Extruded and Compression Molded Rod and Heavy-Walled Tubing Made from Polytetrafluoroethylene (PTFE)
- D 6585 Specification for Unsintered Polytetrafluoroethylene (PTFE) Extruded Film or Tape
- D 6778 Classification for Polyoxymethylene (POM, Acetal) Molding and Extrusion Materials
- D 6779 Classification System for Polyamide Molding and Extrusion Materials (PA)
- D 6835 Classification System for Thermoplastic Elastomer-Ether-Ester Molding and Extrusion Materials (TEEE)
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E 84 Test Method for Surface Burning Characteristics of Building Materials
- E 96/E 96M Test Methods for Water Vapor Transmission of Materials
- E 104 Practice for Maintaining Constant Relative Humidity by Means of Aqueous Solutions
- E 162 Test Method for Surface Flammability of Materials Using a Radiant Heat Energy Source
- F 372 Test Method for Water Vapor Transmission Rate of Flexible Barrier Materials Using an Infrared Detection Technique
- 2.2 Federal Standard:⁴
- Department of Transportation Federal Motor Vehicle Safety Standard No. 302
- 2.3 Underwriters Laboratories:⁵
- UL94 Standards for Tests for Flammability for Parts in Devices and Appliances
- 2.4 IEC and ISO Standards:⁶
- IEC 600093 Recommended Methods of Tests for Volume and Surface Resistivities of Electrical Insulation Materials
- IEC 600112 Recommended Method for Determining the Comparative Tracking Index of Solid Insulation Materials
- ⁴ Available from Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.
- ⁵ Available from Underwriters Laboratories, Inc., Publication Stock, 333 Pfingsten Rd., Northbrook, IL 60062.
- ⁶ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

- **Under Moist Conditions**
- IEC 600243 Recommended Methods of Test for Electrical Strength of Solid Insulating Materials at Power Frequencies
- IEC 600250 Recommended Methods for the Determination of the Permittivity and Dielectric Dissipation Factor of Electrical Insulation Materials at Power, Audio, and Radio Frequencies Including Metre Wavelengths
- IEC 60695-11-10 Fire Hazard Testing—Part 11-10: Test Flames—50 W Horizontal and Vertical Flame Tests
- ISO 62 Plastics—Determination of Water Absorption
- ISO 75-1 Plastics—Determination of Temperature of Deflection Under Load—Part 1: General Principles
- ISO 75-2 Plastics—Determination of Temperature of Deflection Under Load—Part 2: Plastics and Ebonite
- ISO 178 Plastics—Determination of Flexural Properties of Rigid Plastics
- ISO 179 Plastics—Determination of Charpy Impact Strength of Rigid Materials
- ISO 180 Plastics—Determination of Izod Impact Strength of Rigid Materials
- ISO 294-4 Plastics—Injection Moulding of Test Specimens of Thermoplastic Materials—Part 4: Determination of Moulding Shrinkage
- ISO 527–1 Plastics—Determination of Tensile Properties—Part 1: General Principles
- ISO 527-2 Plastics—Determination of Tensile Properties— Part 2: Test Conditions for Moulding and Extrusion Plastics
- ISO 604 Plastics—Determination of Compressive Properties
- ISO 868 Plastics—Determination of Indention Hardness by Means of a Durometer (Shore Hardness)
- ISO 877 Plastics—Determination of Resistance to Change Upon Exposure Under Glass to Daylight
- ISO 974 Plastics—Determination of the Brittleness Temperature by Impact
- ISO 1133 Plastics—Determination of the Melt Mass-Flow Rate (MFR) and the Melt Volume-Flow Rate (MVR) of Thermoplastics
- ISO 1183 Plastics—Methods for Determining the Density and Relative Density of Non-Cellular Plastics
- ISO 2039-2 Plastics—Determination of Hardness—Part 2: Rockwell Hardness
- ISO 3795 Road Vehicles, Tractors, and Machinery for Agriculture and Forestry—Determination of Burning Behavior of Interior Materials
- ISO 4577 Plastics—Polypropylene and Propylene— Copolymers—Determination of Thermal Oxidative Stability in Air-Oven Method
- ISO 4589 Plastics—Determination of Flammability by Oxygen Index
- ISO 4607 Plastics—Method of Exposure to Natural Weathering
- ISO 4892 Plastics—Methods of Exposure to Laboratory Light Sources
- ISO 4892–4 Plastics—Methods of Exposure to Laboratory Light Sources—Part 4: Open-flame Carbon-arc



 ISO 6603-1 Plastics—Determination of Multiaxial Impact Behavior of Rigid Plastics—Part 1: Falling Dart Method
 ISO 6721-1 Plastics—Determination of Dynamic Mechanical Properties—Part 1: General Principles
 ISO 6721-2 Plastics—Determination of Dynamic Mechanical

cal Properties—Part 2: Torsion-Pendulum Method

ISO 11357-1 Plastics—Differential Scanning Calorimetry—Part 1: General principles
 ISO 11357-3 Plastics—Differential Scanning Calorimetry—Part 3: Determination of Temperature and Enthalpy of Melting and Crystallization

TABLE 1 Standard Symbols for Generic Families With Referenced Standards and Cell Tables

| Standard Symb | Plastic Family Name | ASTM ^A Standard | Suggested Reference Cell Tables for Materials Without an ASTM Standard ^B | |
|---------------|--|---|---|--------|
| | | _ | Unfilled | Filled |
| ABA | acrylonitrile-butadiene-acrylate | | E | |
| ABS | acrylonitrile-butadiene-styrene | D 3965, D 4673 | _ | |
| AMMA ARP | acrylonitrile-methyl methacrylate aromatic polyester | (see LCP) | E | |
| ASA | acrylonitrile-styrene-acrylate | (See LOF) | Е | |
| CA | cellulose acetate | D 706 | | |
| CAB | cellulose acetate butyrate | D 707 | | |
| CAP | cellulose acetate proprionate | | E | D |
| CE CF | cellulose plastics, general cresol formaldehyde | | E H | D H |
| CMC | carboxymethyl cellulose | | Ë | |
| CN | cellulose nitrate | | E | D |
| CP | cellulose propionate | D 1562 | | |
| CPE | chlorinated polyethylene | D 4000 D 4704 D 5000 D 0045 D 4040 | F | |
| CPVC CS | chlorinated poly(vinyl chloride) casein | D 4396, D 1784, D 5260, D 3915, D 4216 | Н | Н |
| CTA | cellulose triacetate | | E | D |
| EC | ethyl cellulose | D 787 AND AFCS D 3275 | Ē | D |
| E-CTFE | ethylene-chlorotrifluoroethylene copolymer | D 3275 | | |
| EEA | ethylene-ethyl acrylate | | F | |
| EMA EP | ethylene-methacrylic acid epoxy, epoxide | | F H | Н |
| EPD | ethylene-propylene-diene | | - 11 | 11 |
| EPM | ethylene-propylene polymer | | F | D |
| ETFE | ethylene-tetrafluoroethylene copolymer | D 3159 T Preview | | |
| EVA | ethylene-vinyl acetate | | F | |
| FCEA | fully crosslinked elastomeric alloy | D 5046 | | |
| FEP FF | perfluoro (ethylene-propylene) copolymer furan formaldehyde | D 2116 D 3296 4000-04e1 | Н | Н |
| HCTPV | highly crosslinked thermoplastic vulanizates | D 0000 | | |
| IPS https://s | impact polystyrene / valallog/standards/sist/ / I | (see PS) d-abd3-42f8-8d0a-b5634 | | |
| LCP | liquid crystal polymer | D 5138 | | |
| MF | melamine-formaldehyde | D 4000 D 0770 | Н | Н |
| PA PAEK | polyamide (nylon) polyacryletherketone | D 4066, D 6779 | | |
| PAI | polyamide-imide | D 5204 | G | G |
| PARA | polyacryl amide | 3 525 . | <u>.</u> | ~ |
| PB | polybutene-1 | | F | |
| PBT | poly(butylene terephthalate) | (see TPES) | | |
| PC | polycarbonate | D 3935 | | |
| PCTFE PDAP | polymonochlorotrifluoroethylene poly(diallyl phthalate) | D 1430, D 3595 | Н | Н |
| PE | polyethylene | D 1248, D 4976, D 3350, D 4020, D 5203 | | |
| PEBA | polyether block amide | , | | |
| PEEK | polyetheretherketone | | | |
| PEI | polyether-imide | D 5205 | | |
| PEO PESU | poly(ethylene oxide) polyether sulfone | D 6394 | | |
| PET | poly(ethylene terephthalate), general | (see TPES) | | |
| PETG | glycol modified polyethylene terephthalate comonomer | (see TPES) | | |
| PF | phenol-formaldehyde | D 4617 | | |
| PFA | perfluoro alkoxy alkane | D 3307 | • | _ |
| PI PIB | polyimide | | G F | G |
| PIR PIR | polyketone | D 5990 | Г | |
| PMMA | Poly(methyl methacrylate) | D 788, D 5436 | | D |
| PMP | poly(4-methylpentene-1) | , | F | - |
| POM | polyoxymethylene (acetal) | D 4181, D 6778 | | |
| POP | polyphenylene oxide | (see PPE) | | |
| PP PPA | polypropylene | D 4101, D 5857 | | |
| PPA PPE | polyphthalamide polyphenylene ether | D 5336, D 6779 D 4349 | | |
| 1.174 | polyphichlylene enier | טדטד ע | | |

TABLE 1 Continued

| Standard Symbo | Plastic Family Name | ASTM ^A Standard | Suggested Reference Cell Tables for Materials Without an ASTM Standard ^B | |
|----------------|--|---|---|--------|
| | | | Unfilled | Filled |
| PPOX | poly(propylene oxide) | | | |
| PPS | poly(phenylene sulfide) | D 4067, D 6358 | | |
| PPSU | poly(phenyl sulfone) | D 6394 | G | G |
| PS | polystyrene | D 4549, D 5676 | | |
| PSU | polysulfone | D 6394 | | |
| PTFE | polytetrafluoroethylene | D 1430, D 3159, D 3222, D 3294, D 3295, | | |
| | | D 3307, D 4441, D 4745, D 4894, D 4895, | | |
| | | D 5575, D 6314, D 6457, D 6585 | | |
| PUR | polyurethane | | F | D |
| PVAC | poly(vinyl acetate) | | F | D |
| PVAL | poly(vinyl alcohol) | | F | D |
| PVB | poly(vinyl butyral) | | F | D |
| PVC | poly(vinyl chloride) | D 2287 | F | D |
| PVDC | poly(vinyl idene chloride) | | F | D |
| PVDF | poly(vinyl idene fluoride) | D 3222 | | |
| PVF | poly(vinyl fluoride) | | F | D |
| PVFM | poly(vinyl formal) | | F | D |
| PVK | poly(vinylcarbazole) | | F | D |
| PVP | poly(vinyl pyrrolidone) | | F | D |
| SAN | styrene-acrylonitrile | D 4203 | | |
| SB | styrene-butadiene | | E | D |
| SI | silicone plastics | | G | G |
| S/MA | styrene-maleic anhydride | D 4634 | | |
| SMS | styrene-methylstyrene | | E | D |
| SPS | syndiotactic polystyrene | D 6339 | | |
| TECEA | thermoplastic elastomer-chlorinated ethylene alloy | D 5021 | | |
| TEEE | thermoplastic elastomer, ether-ester | D 6835 | | |
| TEO | thermoplastic elastomer-olefinic | D 5593 | | |
| TES | thermoplastic elastomer-stryenic | D 4474 | | |
| TPE | thermoplastic elastomer | (see individual material) | | |
| TPES | thermoplastic polyester (general) | D 4507, D 5927 | | |
| TPU | thermoplastic polyurethane | D 5476 | | |
| UF | urea-formaldehyde | | Н | Н |
| UP | unsaturated polyester | | | |
| VDF | vinylidene fluoride | D 5575 | | |

AThe standards listed are those in accordance with this classification. D __ indicates that a standard is being developed by the subcommittee responsible. BCell Tables A and B have been reserved for the referenced standards and will apply to unfilled and filled materials covered in those standards.

TABLE 2 Reinforcement-Filler^A Symbols^B and Tolerance

| Symbol | Material Material | Tolerance Tolerance |
|--------|---|--|
| С | Carbon and graphite | ±2 percentage points |
| D | Alumina trihydrate | ±2 percentage points |
| E | Clay | ±2 percentage points |
| F | Cellulose | ±2 percentage points |
| G | Glass | ±2 percentage points |
| Н | Aramid | ±2 percentage points |
| J | Boron | ±2 percentage points |
| K | Calcium carbonate | ±2 percentage points |
| L | Lubricants (for example, PTFE, graphite, and so forth) | Depends upon material and process, to be specified |
| M | Mineral | ±2 percentage points |
| N | Natural organic (cotton, sisal, hemp, flax, and so forth) | ±2 percentage points |
| Р | Mica | ±2 percentage points |
| Q | Silica | ±2 percentage points |
| R | Combinations of reinforcements or fillers, or both | ±3 percentage points |
| S | Synthetic organic | ±2 percentage points |
| T | Talcum | ±2 percentage points |
| V | Metal | ±2 percentage points |
| W | Wood | ±2 percentage points |
| X | Not specified | To be specified |

^AAsh content of filled or reinforced materials, or both may be determined using either Test Method D 5630 or ISO 3451–1 where applicable.

^BAdditional symbols may be added to this table as required.