



## Standard Test Method for Ignition of Materials by Hot Wire Sources<sup>1</sup>

This standard is issued under the fixed designation D 3874; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method is intended to differentiate, in a preliminary fashion, among materials with respect to their resistance to ignition because of their proximity to electrically-heated wires and other heat sources.<sup>2</sup>

1.2 This test method applies to molded or sheet materials available in thicknesses ranging 0.25 to 6.4 mm (0.010 to 0.25 in.).

1.3 This test method applies to materials that are rigid at normal room temperatures. That is, it applies to materials for which the specimen does not deform during preparation, including especially during the wire-wrapping step described in 9.1. Examples of deformation that render this test method inapplicable include:

1.3.1 Bowing, in either a transverse or a longitudinal direction, or twisting of the specimen, during the wire-wrapping step, to a degree visible to the eye.

1.3.2 Visible indentation of the wrapped wire into the specimen.

1.4 The values stated in SI units are to be regarded as the standard. The inch-pound units given in parentheses are for information only.

1.5 This test method measures and describes the response or materials, products, or assemblies to heat and flame under controlled conditions, but does not by itself incorporate all factors required for fire hazard or fire risk assessment of the materials, products, or assemblies under actual fire conditions.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—Although this test method and IEC 695-2-20, differ in approach and in detail, data obtained using either are technically equivalent.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.21 on Fire Performance Standards.

Current edition approved Sept. 10, 1997. Published November 1997. Originally approved in 1988. Last previous edition approved in 1990 as D 3874 – 90a.

<sup>2</sup> K. N. Mathes, Chapter 4, “Surface Failure Measurements”, *Engineering Dielectrics, Vol. IIB, Electrical Properties of Solid Insulating Materials, Measurement Techniques*, R. Bartnikas, Editor, ASTM STP 926, ASTM, Philadelphia, 1987.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 1711 Terminology Relating to Electrical Insulation<sup>3</sup>

E 176 Terminology of Fire Standards<sup>4</sup>

#### 2.2 IEC Standards:

IEC 695-2-1 Fire Hazard Testing. Part 2: Test Methods, Section 20: Hot-Wire Coil Ignitability Test on Materials<sup>5</sup>

ISO/IEC Guide 52: Glossary of Fire Terms and Definitions<sup>5</sup>

### 3. Terminology

#### 3.1 Definitions:

3.1.1 Use Terminology E 176 and ISO/IEC Guide 52 for definitions of terms used in this test method and associated with fire issues. Where differences exist in definitions, those contained in Terminology E 176 shall be used. Use Terminology D 1711 for definitions of terms used in this test method and associated with electrical insulation materials.

#### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *ignition, n*—initiation of flaming produced by combustion in the gaseous phase that is accompanied by the emission of light.

### 4. Significance and Use

4.1 Under certain conditions of operation, or when malfunctions occur, it is possible that electrical equipment including, but not limited to, wires, resistors, or other conductors, become abnormally hot. When this happens, a possible result is ignition of the insulation material.

4.2 This test method assesses the relative resistance of electrical insulating materials to ignition by the effect of hot wire sources.

4.3 This test method determines the average time, in seconds, required for material specimens to ignite under the conditions of test.

4.4 Subject to limitations in precision and bias, this test method can be used to categorize materials.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 10.01.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 04.07.

<sup>5</sup> Available from International Electrotechnical Commission (IEC), 3 Rue de Varembe, Geneva, Switzerland.

## 5. Apparatus

5.1 *Heater Wire*—No. 24 AWG, Nickel-Chrome wire, that is iron free having the following nominal properties: the wire has a composition of 20 % chromium-80 % nickel, measures 0.05 mm (0.020 in.) in diameter, has a nominal cold resistance of 5.28  $\Omega$ /m (1.61 $\Omega$ /ft), and has a length-to-mass ratio of 580 m/kg (864 ft/lb).

5.2 Due to normal variations in composition, processing, sizing, and metallurgy between wire lots, it is necessary that each spool of test wire be calibrated for energized resistance in accordance with the method outlined in Annex A1.

5.3 *Supply Circuit*—A means for electrically energizing the heater wire. The supply circuit shall have the following capabilities:

5.3.1 Sufficient capacity to maintain a continuous linear 50 to 60 Hz power density of at least 0.31 W/mm (8.0 W/in.) over the length of the heater wire at or near unity power factor. Conditions of the supply circuit at 60 A and 1.5 V should result in power density approximating 0.3 W/mm.

5.3.2 A means for adjustment of voltage to achieve the desired current as determined from Annex A1. Such means for adjustment shall provide a smooth and continuous adjustment of the power level.

5.3.3 A means of measuring the power to within  $\pm 2$  %.

5.3.4 The test circuit shall be provided with an easily actuated on-off switch for the test power, and timers to record the duration of the application of test power.

5.4 *Test Chamber*—A closed chamber having a volume of at least 0.3 m<sup>3</sup> (10.5 ft<sup>3</sup>). The ratio between any two transverse dimensions shall not exceed 2.5. The test chamber shall be positively vented to the outside of the test facility, but it must be closed and unvented during the test. The chamber shall be equipped with an observation window.

5.5 *Test Fixture*—Two supporting posts positioned 70 mm (2¾ in.) apart to support the specimen in a horizontal position, at a height of 60 mm (2⅜ in.) above the bottom of the test chamber, in the approximate center of the test chamber.

5.6 *Specimen-Winding Fixture*—A fixture that will uniformly position the wire with a spacing of 6.35  $\pm$  0.05 mm (0.250  $\pm$  0.002 in.) between turns with a winding tension of 5.4  $\pm$  0.02 N (1.21  $\pm$  0.0045 lbf).

## 6. Safety Precautions

6.1 It is possible that fumes and products of incomplete combustion are liberated from the specimen when conducting this test. Avoid the inhalation of such fumes and products of combustion and exhaust them from the test chamber after each run.

6.2 Take precautions to safeguard the health of personnel against the risk of explosion or fire, the inhalation of smoke, or other products of combustion, or the exposure to the residues potentially remaining on the specimen after testing.

## 7. Test Specimens

7.1 The test specimen shall consist of a bar measuring 12.5  $\pm$  0.2 by 125  $\pm$  5 mm (½ by 5 in.) and of the thickness to be tested.

## 8. Conditioning

8.1 Condition the specimens and heater wire as follows:

8.1.1 *Sample Conditioning*—Prior to testing, maintain the samples in a dry condition. If this is not practical, dry the samples in an air-circulating oven at 70  $\pm$  2°C (158  $\pm$  3.5°F) for seven days and cool over a desiccant, such as silica gel, for a minimum of 4 h. Prior to testing, condition the dry samples for at least 40 h at 23  $\pm$  2°C (73  $\pm$  3.5°F) and 50  $\pm$  5 % relative humidity. Maintain the test facilities at 50  $\pm$  5 % relative humidity and 23°C.

8.1.2 *Heater Wire Conditioning and Calibration*—For each test, use a length of previously calibrated wire measuring approximately 250 mm (10 in.). Prior to testing, anneal each straight length by energizing the wire to dissipate 0.26 W/mm of length (6.5 W/in. of length) for 8 to 12 s to relieve the internal stresses within the wire. Calibrate the wire in accordance with Annex A1 to determine the correct current level.

## 9. Procedure

9.1 Wrap the center portion of the test specimen with a test wire, conditioned in accordance with 8.1.2, using the winding fixture as specified in 4.6 and a winding force of 5.4  $\pm$  0.02 N (1.21  $\pm$  0.0045 lbf). Apply five complete turns spaced 6.35  $\pm$  0.05 mm (¼ in.) between turns.

9.2 Position the specimen on the test fixture such that the length and width are horizontal. Securely connect the free ends of the wire to the test circuit. The connection is to be capable of transmitting the test power without significant losses, and insofar as possible, not mechanically affect the specimen during the test.

9.3 Start the test by energizing the circuit to dissipate 0.26 W/mm (6.5 W/in.) through the nickel-chrome wire. The 0.26 W/mm shall be maintained during the test.

9.4 Continue heating until the test specimen ignites (see 3.2.1). When ignition occurs, shut off the power and record the time to ignition. Discontinue the test if ignition does not occur within 120 s. For specimens that melt through the wire without ignition, discontinue the test when the specimen is no longer in intimate contact with all five turns of the heater wire.

9.5 Note the following observations:

9.5.1 The time to ignition of each specimen, and

9.5.2 The time for each specimen to melt through the wire if appropriate.

## 10. Report

10.1 Report the following information:

10.1.1 Complete identification of the material tested including type, source, and manufacturer's code number,

10.1.2 Testing room conditions,

10.1.3 Number of specimens tested,

10.1.4 Thickness of specimens tested,

10.1.5 Time to ignition for each specimen or the time at which the wire turns no longer contact the specimen,

10.1.6 Calculation and record of the average time for ignition,

10.1.7 Calibrated test current, and

10.1.8 Geometry of test chamber.