
**Imaging materials — Processed silver-
gelatin-type black-and-white films —
Specifications for stability**

*Matériaux pour l'image — Films noir et blanc de type gélatino-
argentique traités — Spécifications relatives à la stabilité*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 18901:2010](https://standards.iteh.ai/catalog/standards/sist/e18e5212-41fd-4a57-9d81-fb115d3477ce/iso-18901-2010)

[https://standards.iteh.ai/catalog/standards/sist/e18e5212-41fd-4a57-9d81-
fb115d3477ce/iso-18901-2010](https://standards.iteh.ai/catalog/standards/sist/e18e5212-41fd-4a57-9d81-fb115d3477ce/iso-18901-2010)



Reference number
ISO 18901:2010(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 18901:2010

<https://standards.iteh.ai/catalog/standards/sist/e18e5212-41fd-4a57-9d81-fb115d3477ce/iso-18901-2010>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Film base requirements	3
5 Processed film requirements	3
5.1 Storage conditions	3
5.2 Safety film.....	3
5.3 Amount of free acid	3
5.4 Tensile properties and loss in tensile properties	3
6 Requirements for the emulsion and backing layers of processed film	4
6.1 Layer adhesion	4
6.2 Emulsion flow	4
6.3 Blocking.....	4
6.4 Thiosulfate concentration.....	4
6.5 Residual silver compounds.....	5
7 Image-stability requirements	5
7.1 General	5
7.2 Radiographic films.....	5
7.3 Microfilms.....	6
7.4 Other films.....	6
8 Test methods	6
8.1 Identification of film base	6
8.2 Accelerated-ageing conditions	6
8.3 Determination of the amount of free acid	7
8.4 Tensile property test for processed film.....	8
8.5 Tape-stripping adhesion test	8
8.6 Humidity-cycling adhesion test	9
8.7 Emulsion-flow test.....	10
8.8 Blocking test.....	10
8.9 Residual silver compound test	11
8.10 Image-stability test	11
Annex A (informative) Washing and the effect of residual thiosulfate on the developed silver image	13
Annex B (informative) Effect of residual silver compounds on the developed silver image	14
Annex C (informative) Accelerated image-stability test for radiographic films	15
Annex D (informative) Accelerated image-stability test for microfilms.....	17
Annex E (informative) Accelerated image-stability test for aerial films	19
Bibliography.....	21

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 18901 was prepared by Technical Committee ISO/TC 42, *Photography*.

This second edition cancels and replaces the first edition (ISO 18901:2002), which has been technically revised.

This International Standard is one of a series of International Standards dealing with the physical properties and stability of imaging materials. To facilitate identification of these International Standards, they are assigned a number within the block from 18900 to 18999.

<https://standards.iteh.ai/catalog/standards/sist/e18e5212-41fd-4a57-9d81-fb115d3477ce/iso-18901-2010>

Introduction

Since 1930, great advances have been made in the use of photographic films for the preservation of records. The preservation of film records by governments, banks, insurance companies, industry and other enterprises has been stimulated by a recognition of the economies in storage space, organization, accessibility and ease of reproduction that result from the use of film records.

During the early development period of the art of copying documents, 35 mm nitrate motion picture film was sometimes used. This material is highly flammable and is not a safety film as specified in ISO 18906. Nitrate film is not acceptable for any record film. The manufacture of nitrate film declined after World War II and was discontinued in most countries in the 1950s.

From about 1908 to 1956, the only safety-type film bases in commercial use were cellulose acetate, cellulose acetate propionate and cellulose acetate butyrate. The useful life of these cellulose-ester-type bases is somewhat conjectural because of limited practical experience. However, the results of laboratory incubation tests indicate a useful life of at least 50 to 100 years when cellulose-ester-base films are stored under recommended conditions (see References [1], [2], [3] and [4]).

A second type of polymer safety film base was introduced commercially in 1956. This is a polyester-class material whose chemical name is polyethylene terephthalate.

NOTE Another type of polyester base, known as polyethylene naphthalate, has been used for APS (Advanced Photo System) type films since 1996.

Polyester base has several advantages over cellulose-ester base, including greater strength, stiffness, tear resistance and dimensional stability, which are important in many photographic applications (see References [5] and [6]). Accelerated ageing tests supplemented by 35 years of practical experience indicate a potential useful life of 500 years.

This International Standard provides image-stability predictions for three classes of black-and-white films in terms of LE (life expectancy) ratings. These three classes are radiographic films, microfilms and all other films. Two or three LE ratings are given for each of these film classes depending on their residual thiosulfate concentrations.

Studies on the stability of silver-gelatin-type films have investigated the effect of residual hypo on the image permanence of radiographic films, microfilms and aerial films (see References [7], [8] and [9]). This work suggested modifications to the residual hypo limits and a more quantitative image-stability test was included in the first edition of this International Standard. Residual hypo limits and image-stability tests are now included for all film categories.

This International Standard identifies certain hazards to permanence attributable to the chemical or physical characteristics of processed film and provides methods for evaluating them. Some of these are inherent film characteristics, some are related to the chemical processing procedure and some are influenced by both factors. However, storage conditions can also have a pronounced influence on film permanence. The essential requirements for longevity are proper storage temperature and humidity as well as protection from the hazards of fire, water, fungus, and atmospheric pollutants. Proper storage conditions are specified in ISO 18902 and ISO 18911.

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

ISO 18901:2010

<https://standards.iteh.ai/catalog/standards/sist/e18e5212-41fd-4a57-9d81-fb115d3477ce/iso-18901-2010>

Imaging materials — Processed silver-gelatin-type black-and-white films — Specifications for stability

1 Scope

This International Standard establishes the specifications for photographic films intended for the storage of records.

It is applicable specifically to films with a base of safety cellulose ester or polyester having silver-gelatin emulsions, processed to produce a black-and-white silver image by negative or full-reversal processing. It applies to film processed using a monobath that includes thiosulfate as the fixing agent, followed by a conventional wash. It also is applicable to silver films given a stabilizing treatment by partial or full conversion to silver sulfide, silver selenide or gold.

This International Standard is applicable to films having ultrasonic or dielectric (induction-heated) splices. It does not cover films with splices made of adhesive tape or solvent-type splices.

NOTE Solvent-type splices are suspect since they sometimes retain traces of residual solvents containing peroxide, which can pose some risk of oxidative attack on the silver image.

This International Standard is not applicable to films with chromogenic black-and-white images, colour images of any type, or to films with a magnetic recording track. It does not apply to films with silver images produced by dry or thermal processing or by diffusion-reversal processing, or to films that have been processed by a monobath using means other than a thiosulfate-type fixing solution. It is not applicable to films where the silver salts are removed by means other than thiosulfate solutions (see Reference [10]).

This International Standard is not applicable to films to which lacquers have been applied.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5-2, *Photography and graphic technology — Density measurements — Part 2: Geometric conditions for transmittance density*

ISO 5-3, *Photography and graphic technology — Density measurements — Part 3: Spectral conditions*

ISO 527-3, *Plastics — Determination of tensile properties — Part 3: Test conditions for films and sheets*

ISO 18902, *Imaging materials — Processed imaging materials — Albums, framing and storage materials*

ISO 18906, *Imaging materials — Photographic films — Specifications for safety film*

ISO 18911, *Imaging materials — Processed safety photographic films — Storage practices*

ISO 18917, *Photography — Determination of residual thiosulfate and other related chemicals in processed photographic materials — Methods using iodine-amylose, methylene blue and silver sulfide*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

emulsion layer

image or image-recording layer of silver-gelatin-type black-and-white films

NOTE There can be one or several emulsion layers.

3.2

extended-term storage conditions

storage conditions suitable for the preservation of recorded information having permanent value

NOTE The term “medium-term storage conditions” defines storage conditions suitable for the preservation of recorded information for a minimum of 10 years.

3.3

film base

plastic support for the emulsion and backing layers

3.3.1

cellulose-ester base

base for recording materials composed mainly of the cellulose esters of acetic, propionic, or butyric acids, or mixtures thereof

3.3.2

polyester base

base for recording materials composed mainly of a polymer of ethylene glycol and terephthalic acid (also referred to as polyethylene terephthalate), or a polymer of ethylene glycol and 2,6 naphthalene dicarboxylic acid (also referred to as polyethylene naphthalate)

iTeh STANDARD PREVIEW
(standards.iteh.ai)
ISO 18901:2010
<https://standards.iteh.ai/catalog/standards/sist/e18e5212-41fd-4a57-9d81-fb115d3477ce/iso-18901-2010>

3.4

full-reversal processing

reversal photographic processing that consists of development, bleach, clear, re-exposing and second development, followed by fixing and washing

3.5

life expectancy

LE

length of time that information is predicted to be acceptable in a system after dark storage at 21 °C and 50 % relative humidity (RH)

NOTE In the past, the term “archival” was used to define material that could be expected to preserve images forever, so that such images could be retrieved without significant loss when properly stored. However, as no such material exists, this is now a deprecated term and is no longer used in International Standards for imaging materials or in systems specifications.

3.6

LE designation

rating for the **life expectancy** (3.5) of recording materials and associated retrieval systems

NOTE The number following the LE symbol is a prediction of the minimum life expectancy, in years, during which information can be retrieved without significant loss when stored at 21 °C and 50 % RH, e.g. LE-100 indicates that information can be retrieved after at least 100 years of storage.

3.7**non-curl backing layer**

layer, usually made of gelatin, applied to the side of the photographic film base opposite that of the emulsion layer, for the purpose of preventing curl

NOTE 1 It is comparable to the emulsion layer in thickness and is not removed in processing.

NOTE 2 Antihalation or other layers removed in processing are excluded from this definition.

3.8**safety film**

safety photographic film

film that meets the flammability specifications defined in ISO 18906

4 Film base requirements

The base used for record films, as specified in this International Standard, shall be of a safety polyester or a cellulose-ester type and can be identified by the method described in 8.1.

Some films on a cellulose-ester-type base can have a maximum LE rating of 100. Some films on a polyester base can have a maximum LE rating of 500.

NOTE These limitations are based on historical experiences as discussed in the Introduction.

5 Processed film requirements

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5.1 Storage conditions

Films shall be stored under the conditions specified in ISO 18902 and ISO 18911.

ISO 18901:2010
fb115d3477ce/iso-18901-2010

5.2 Safety film

Film shall meet the requirements specified in ISO 18906.

5.3 Amount of free acid

The cellulose-ester base shall not have an amount of free acid greater than 0,1 ml of 0,1 mol/l sodium hydroxide solution per gram of film. The amount of free acid shall be measured in accordance with 8.3.

NOTE The degradation of cellulose-ester base is autocatalytic and proceeds rapidly when the free acid is greater than 0,5 ml of 0,1 mol/l sodium hydroxide solution.

The volume of 0,1 mol/l sodium hydroxide equivalent to the amount of free acid of the processed film shall not increase by more than 0,5 ml/l over its original value after the accelerated ageing described in 8.2.

5.4 Tensile properties and loss in tensile properties

Film specimens shall be processed and dried under the conditions used for film records.

Processed films shall be tested for tensile properties as described in 8.4 and shall have a tensile stress and elongation at break as specified in Table 1 (unheated film). The loss in tensile properties after the accelerated ageing test described in 8.2 shall not exceed the percentage specified in Table 1 (heated film).

Table 1 — Limits for tensile properties and loss in tensile properties on ageing

Film type		Tensile stress at break	Elongation at break
Unheated film: minimum permissible tensile properties	Cellulose-ester base	80 MPa ^a	15 %
	Polyester base	140 MPa	75 %
Heated film: maximum permissible loss in tensile properties compared with unheated film	Cellulose-ester base	15 %	30 %
	Polyester base	15 %	30 %
^a 1 MPa = 10 ⁶ N/m ² .			

6 Requirements for the emulsion and backing layers of processed film

6.1 Layer adhesion

6.1.1 Tape-stripping adhesion

Processed film shall not show any removal of emulsion layer or backing layer when tested as described in 8.5.

6.1.2 Humidity-cycling adhesion

The emulsion layer or backing layer of processed film shall not show separation or cracking that can impair its intended use when tested as described in 8.6.

6.2 Emulsion flow

Processed film shall not show any visual evidence of emulsion flow (caused by partial emulsion remelting) as a result of the accelerated ageing of the processed film. Emulsion flow shall be determined as described in 8.7, when the accelerated ageing is performed as described in 8.2.

6.3 Blocking

Processed film shall show no evidence of blocking (sticking), delamination or surface damage when tested as described in 8.8. A slight sticking of the film specimens that does not result in physical damage or a change in the gloss of the surface shall be acceptable.

6.4 Thiosulfate concentration

Films shall be fixed in solutions containing either sodium thiosulfate (hypo) or ammonium thiosulfate (see Reference [10]). Hypo-eliminating agents containing oxidizing agents such as peroxides or hypochlorites shall not be used.

NOTE 1 Hypo-eliminating agents contain chemicals, usually strong oxidizing agents, that decompose thiosulfate (see Annex B). These are distinguished from hypo-clearing baths, which are high ionic strength salt solutions. These facilitate the washing of thiosulfate from the film, but do not chemically alter the thiosulfate.

After processing, the concentration of thiosulfite in the film shall be determined by one of the test methods described in ISO 18917. The film shall not contain a greater concentration of residual thiosulfate, calculated as thiosulfate ions ($S_2O_3^{2-}$), than that specified in Table 2.

NOTE 2 Three methods for measuring residual-thiosulfate-based chemicals in film are described in ISO 18917. All three methods are considered to be sufficiently reliable to report thiosulfate concentrations at the level of 0,014 g/m² of $S_2O_3^{2-}$. The methylene blue method is considered to be reliable for thiosulfate concentrations of 0,007 g/m². The methylene blue and iodine amylose methods measure thiosulfate ions only. They are run within two weeks of processing.

The silver sulfide densitometric test method measures polythionate decomposition products and other residual chemicals in addition to thiosulfate. The method can be run more than two weeks after processing. To determine thiosulfate levels accurately with this method, a calibration curve for the particular film is necessary.

The analysis for thiosulfate shall be made on a film specimen from a clear area and shall be made within two weeks after processing (see Annex B). The test method does not measure any change in the specimen between the time of processing and the time of analysis, but is used to judge the state of the film after the test has been carried out.

6.5 Residual silver compounds

Processed film shall not show more than an increase of 0,02 in Status A blue density when tested in accordance with 8.9 (see Annex C).

Table 2 — Limits for thiosulfate concentration

Film type	Film classification (LE designation)	Maximum permissible concentration of thiosulfate ^b g/m ^{2c}
Radiographic films	LE-10	0,100
	LE-100	0,050
	LE-500 ^a	0,020
Microfilms	LE-100	0,030
	LE-500 ^a	0,014
Other films	LE-10	0,100
	LE-100	0,050
	LE-500 ^a	0,014
^a LE-500 film only applies to polyester-base film. ^b Values are for each side of the film that has a photographic layer or a non-curl backing layer. Very low concentrations of thiosulfate due to excessive washing may cause the silver image to be more susceptible to oxidative attack. These concentrations may be below the detection limits of ISO 18917. ^c 0,010 g/m ² = 1 µg/cm ² .		

7 Image-stability requirements

7.1 General

The specifications and test methods for image stability vary for different product types.

Visual diffuse density in accordance with ISO 5 or Status A blue density shall be measured on a densitometer which has geometric conformance to ISO 5-2 and spectral conformance to ISO 5-3. Processed film specimens shall be incubated as described in 8.10.3.

7.2 Radiographic films

An area of unexposed processed film shall be tested. The Status A blue density change of the unexposed area shall be no greater than 0,05 density units after incubation. This requirement shall apply to LE-10, LE-100 and LE-500 films.