



Designation: F748 – 06

# Standard Practice for Selecting Generic Biological Test Methods for Materials and Devices<sup>1</sup>

This standard is issued under the fixed designation F748; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice recommends generic biological test methods for materials and devices according to end-use applications. While chemical testing for extractable additives and residual monomers or residues from processing aids is necessary for most implant materials, such testing is not included as part of this practice. The reader is cautioned that the area of materials biocompatibility testing is a rapidly evolving field, and improved methods are evolving rapidly, so this practice is by necessity only a guideline. A thorough knowledge of current techniques and research is critical to a complete evaluation of new materials.

1.2 These test protocols are intended to apply to materials and medical devices for human application. Biological evaluation of materials and devices, and related subjects such as pyrogen testing, batch testing of production lots, and so on, are also discussed. Tests include those performed on materials, end products, and extracts. Rationale and comments on current state of the art are included for all test procedures described.

1.3 The biocompatibility of materials used in single or multicomponent medical devices for human use depends to a large degree on the particular nature of the end-use application. Biological reactions that are detrimental to the success of a material in one device application may have little or no bearing on the successful use of the material for a different application. It is, therefore, not possible to specify a set of biocompatibility test methods which will be necessary and sufficient to establish biocompatibility for all materials and applications.

1.4 The evaluation of tissue engineered medical products (TEMPs) may, in some cases, involve different or additional testing beyond those suggested for non-tissue-based materials and devices. Where appropriate, these differences are discussed in this practice and additional tests described.

1.5 The ethical use of research animals places the obligation on the individual investigator to determine the most efficient methods for performing the necessary testing without undue

use of animals. Where adequate prior data exists to substantiate certain types of safety information, these guidelines should not be interpreted to mean that testing should be unnecessarily repeated.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- E1202 Guide for Development of Micronucleus Assay Standards
- E1262 Guide for Performance of Chinese Hamster Ovary Cell/Hypoxanthine Guanine Phosphoribosyl Transferase Gene Mutation Assay
- E1263 Guide for Conduct of Micronucleus Assays in Mammalian Bone Marrow Erythrocytes
- E1280 Guide for Performing the Mouse Lymphoma Assay for Mammalian Cell Mutagenicity
- E1397 Practice for *In Vitro* Rat Hepatocyte DNA Repair Assay
- E1398 Practice for *In Vivo* Rat Hepatocyte DNA Repair Assay
- F619 Practice for Extraction of Medical Plastics
- F719 Practice for Testing Biomaterials in Rabbits for Primary Skin Irritation
- F720 Practice for Testing Guinea Pigs for Contact Allergens: Guinea Pig Maximization Test
- F749 Practice for Evaluating Material Extracts by Intracutaneous Injection in the Rabbit
- F750 Practice for Evaluating Material Extracts by Systemic Injection in the Mouse
- F756 Practice for Assessment of Hemolytic Properties of Materials
- F763 Practice for Short-Term Screening of Implant Materials

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is direct responsibility of Subcommittee F04.16 on Biocompatibility Test Methods.

Current edition approved Dec. 1, 2006. Published January 2007. Originally approved in 1982. Last previous edition approved in 2004 as F748 – 04. DOI: 10.1520/F0748-06.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- F813 Practice for Direct Contact Cell Culture Evaluation of Materials for Medical Devices
- F895 Test Method for Agar Diffusion Cell Culture Screening for Cytotoxicity
- F981 Practice for Assessment of Compatibility of Biomaterials for Surgical Implants with Respect to Effect of Materials on Muscle and Bone
- F1027 Practice for Assessment of Tissue and Cell Compatibility of Orofacial Prosthetic Materials and Devices
- F1408 Practice for Subcutaneous Screening Test for Implant Materials
- F1439 Guide for Performance of Lifetime Bioassay for the Tumorigenic Potential of Implant Materials
- F1877 Practice for Characterization of Particles
- F1903 Practice for Testing For Biological Responses to Particles *in vitro*
- F1904 Practice for Testing the Biological Responses to Particles *in vivo*
- F1905 Practice For Selecting Tests for Determining the Propensity of Materials to Cause Immunotoxicity
- F1906 Practice for Evaluation of Immune Responses In Biocompatibility Testing Using ELISA Tests, Lymphocyte Proliferation, and Cell Migration
- F1983 Practice for Assessment of Compatibility of Absorbable/Resorbable Biomaterials for Implant Applications
- F1984 Practice for Testing for Whole Complement Activation in Serum by Solid Materials
- F2065 Practice for Testing for Alternative Pathway Complement Activation in Serum by Solid Materials
- F2147 Practice for Guinea Pig: Split Adjuvant and Closed Patch Testing for Contact Allergens
- F2148 Practice for Evaluation of Delayed Contact Hypersensitivity Using the Murine Local Lymph Node Assay (LLNA)
- F2151 Practice for Assessment of White Blood Cell Morphology After Contact with Materials<sup>3</sup>
- F2382 Test Method for Assessment of Intravascular Medical Device Materials on Partial Thromboplastin Time (PTT)

## 2.2 Other Referenced Documents:

- ISO/AAMI/ANSI 10993-1 Biological Testing of Medical and Dental Materials and Devices - Part 1: Guidance on Selection of Tests<sup>4</sup>
- EN 30993-1 Biological Testing of Medical and Dental Materials and Devices - Part 1: Guidance on Selection of Tests<sup>4</sup>
- General Program Memorandum #G95-1 FDA<sup>5</sup> Immunotoxicity Testing Guidance-FDA<sup>5</sup>

## 3. Summary of Practice

3.1 A matrix listing biological test methods versus materials (devices) and their applications is included in [Table 1](#). The

expected duration of use of the device is also considered. Intraoperative is less than 24 h, short-term is up to and including 30 days, chronic is greater than 30 days. The position of row and column intersection is marked to indicate whether the test is recommended for a material or device for the specific application indicated. The terms relating to device or material type and application are addressed in [Section 5](#). Discussion of applicability, current state of the art, and rationale for individual test methods also appears in that section.

## 4. Significance and Use

4.1 The objective of this practice is to recommend sufficient biological testing to establish a reasonable level of confidence concerning the biological response to a material or device, while at the same time avoiding unnecessary testing.

4.2 This practice is intended to provide guidance to the materials investigator in selecting the proper procedures to be carried out for the screening of new or modified materials. Because each material and each implant situation involves its own unique circumstances, these recommendations should be modified as necessary and do not constitute the only testing that will be required for a material nor should these guidelines be interpreted as minimum requirements for any particular situation. While an attempt has been made to provide recommendation for different implant circumstances, some of the recommended testing may not be necessary or reasonable for a specific material or application.

## 5. Classification of Materials and Devices by End-Use Applications

### 5.1 General:

5.1.1 When new materials are sought for a medical application for use on humans, the material(s) may comprise the whole final device product, or may be one of many component materials in the device. The first step is a thorough literature search for previous use of the material or biocompatibility testing studies to ensure that it has not been known to produce an adverse biological response that exceeds the expected benefit in the use of the device. Note that the final fabricated product may differ chemically, physically, or biologically from the raw materials used to fabricate the product due to processing and this has to be considered when designing test protocols. For some devices, it may be necessary or desirable to take material test samples directly from the final device product. Samples should be fully representative of the finished product in terms of processing, cleaning, packaging, sterilization, and any other procedures that are performed on the materials before the device is used.

5.1.2 At this point, preliminary material screening may be employed, depending on the expertise of the organizations evaluating the materials. Since preliminary screening is normally an option to minimize the economic impact of a candidate material failing final biological tests after extensive time and effort, it is not a required procedure. The investigator should be aware that, should an adverse tissue response be observed with a final product, it may be impossible to determine which component or process is responsible without these initial screening tests.

<sup>3</sup> Withdrawn. The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

<sup>5</sup> Available from CDRH, 5600 Fishers Ln., Rockville, MD 20857.

TABLE 1 Applicable Tests

Classification of Material or Device and Application	Cell Culture Cytotoxicity	Sensitization	Skin Irritation or Intra-cutaneous	Mucous Membrane Irritation	Systemic Toxicity, Acute or Subchronic	Blood Compatibility	Hemolysis	Pyrogen Test	Short-term Implantation	Long-term Implantation	Immune Response	Genotoxicity	Carcinogenicity
External devices													
Intact surfaces (all time periods)	x	x	x										
Breached surfaces													
Intraoperative	x	x	x										
Short-Term	x	x	x		x								
Chronic	x	x	x		x							x	
External Devices Communicating with:													
Intact Natural Channels													
Intraoperative	x	x	x	x									
Short-term	x	x	x	x	x				x				
Chronic	x	x	x	x	x				x		x	x	x
Body Tissues and Fluids													
Intraoperative	x	x	x		x			i <sup>A</sup>					
Short-term	x	x	x		x			i <sup>A</sup>	x		x		
Chronic	x	x	x		x			i <sup>A</sup>	x		x	x	x
Blood Path, indirect													
Intraoperative	x	x	x		x	x	x	x					
Short-term	x	x	x		x	x	x	x					
Chronic	x	x	x		x	x	x	x			x	x	
Blood Path, direct													
Intraoperative	x	x	x		x	x	x	x					
Short-term	x	x	x		x	x	x	x	x		x		
Chronic	x	x	x		x	x	x	x	x		x	x	x
Implanted Devices principally contacting													
Bone/Tissue/tissue fluid													
Intraoperative	x	x	x		x								
Short-term	x	x	x		x			x	x				
Chronic	x	x	x		x			x	x	x	x	x	x
Blood													
Intraoperative	x	x	x		x	x	x	x					
Short-term	x	x	x		x	x	x	x	x			x	x
Chronic	x	x	x		x	x	x	x	x	x	x	x	x

<sup>A</sup> (i) Pyrogenicity testing may be considered for all devices contacting the central nervous system.

iTeh Standards  
<https://standards.itih>  
 Document Preview

ASTM F748-06

[/standards.itih.ai/catalog/standards/sist/7aac17-45ef-b21-e5687-xle932d/xstm-f748](https://standards.itih.ai/catalog/standards/sist/7aac17-45ef-b21-e5687-xle932d/xstm-f748)

5.1.3 This practice addresses two dimensions of tissue-material interactions: duration and tissue type. A third dimension, which should be considered, is the relative size difference between the host and the material, that is, to how much material surface area is the host exposed. The material surface area to body weight ratio may become a significant factor for porous materials, and devices of repeated short-term applications (for example, dialysis products). While this practice does not address the issue of “intensity factor” of increased surface area, the biocompatibility testing facility personnel should consider it in their material screening and testing protocol design.

5.1.4 For the purposes of this practice, devices and the materials that comprise them are classified as to end-use human application as outlined in 5.2-5.4.

5.1.5 In general, the testing for tissue engineered medical products (TEMPs) should address the same issues specific to the type, location, and duration of use as other medical devices and products. The selection of additional testing for compatibility criteria unique to these type of products should be conducted with these recommendations in mind.

5.1.6 When testing materials that are intended to degrade and/or be metabolized while implanted in the body (both synthetic and TEMPs), consideration should be given to the degradation or metabolic products and appropriate modifications made in test and sample selection so that the compatibility of degradation products is tested as well as the undegraded product.

## 5.2 External Devices:

5.2.1 *Devices That Contact Intact Body Surfaces Only*—examples include electrodes, splints, external prostheses, certain dressings, monitors of various types, or ostomy appliances.

5.2.2 *Devices That Contact Breached Body Surfaces*—examples include ulcer, burn, and granulation tissue dressings, or healing devices.

## 5.3 Externally Communicating Devices:

5.3.1 *Devices Communicating with Intact Natural Channels:*

5.3.1.1 *Intraoperative (<24 hours)*—examples include in-traintestinal devices (such as sigmoidoscopes, colonoscopes, stomach tubes, or gastroscopes), tracheal tubes, bronchoscopes and any parts of ancillary equipment that are in contact with materials entering the body, and irrigation sets.

5.3.1.2 *Short-term (up to and including 30 days)*—examples include contact lenses, urinary catheters, and intravaginal devices.

5.3.1.3 *Chronic (>30 days)*—examples include urinary catheters for chronic use and intrauterine devices.

5.3.2 *Devices Communicating with Body Tissues and Fluids:*

5.3.2.1 *Intraoperative (<24 hours)*—examples include hypodermic needles, penetrating electrodes, biopsy instruments, arthroscopes, laparoscopes, irrigation equipment, surgical instruments, trochars, and any parts of ancillary equipment that are in contact with materials entering the body.

5.3.2.2 *Short-term (up to and including 30 days)*—examples include cranial calipers, perfusion apparatus, drainage appara-

tus, stabilizing orthopedic devices, and any parts of ancillary equipment that are in contact with material entering the body.

5.3.2.3 *Chronic (>30 days)*—examples include percutaneous electrodes, active penetrating electrodes, stapedectomy prostheses, partial and total ossicular replacement prostheses, or tympanoplasty ventilation tubes.

5.3.3 *Blood Path, Indirect*—Products contacting blood path at one point for usually less than 24 hours, and serves as a conduit for fluid entry into the vascular system. Examples include solution administration sets, extension sets, transfer sets, or blood administration sets.

5.3.3.1 Products that are used for >24 hours or that are used repeatedly in the same patient will be considered as chronic usage and should undergo extended testing.

5.3.4 *Blood, Path, Direct*—Single recirculating blood exposure or product is in blood path generally less than 24 hours. Examples include intravenous catheters, oxygenators, extracorporeal oxygenator tubing and accessories.

5.3.5 *Blood Path, Direct, Short Term, or Chronic, or repeated exposure*—Examples include dialyzers or dialysis tubing and accessories, shunts.

## 5.4 Implanted Long-Term Devices:

5.4.1 *Devices Principally Contacting Bones*—examples include orthopedic pins, screws, replacement joints, bone prostheses, cements, or dental implants.

5.4.2 *Devices Principally Residing in the Subcutaneous Space*—examples include pacemakers, neuromuscular stimulators, facial augmentation devices, tissue expander devices, and breast prostheses.

5.4.3 *Devices Principally Contacting Soft Tissue and Tissue Fluids*—examples include drug supply devices, neuromuscular sensors, replacement tendons, penile, and other implants, cerebrospinal fluid drains, artificial larynx, vas deferens valves, or ligation clips.

5.4.4 *Devices Principally Contacting Blood*—examples include pacemaker leads, artificial arteriovenous fistulae, heart valves, vascular grafts, stents, blood monitors, internal drug delivery catheters, or ventricular assist pumps.

## 6. Selection of Test Procedures

### 6.1 General:

6.1.1 Biocompatibility testing involves tests of either the material itself, or an extract from it (see Practice F619), or both, depending on the nature of the end-use application. While this practice does not address specific chemical methods for evaluating the extractable substances or residuals from implant materials, several of the recommended tests (see 6.2, 6.7, 6.6, and 6.3) utilize extracts rather than the original material for testing. If sensitive chemical assay techniques (such as GC, HPLC, and AA) should reveal no detectable substances being extracted into the medium, consideration may be given to deletion of these tests from the test battery. The investigator is cautioned, however, that the detection limit of the analytical chemistry procedures may not be adequate to detect trace extractables that may generate a tissue response. Before analysis of extracts is substituted for actual biocompatibility testing of the extracts, validation procedures may be necessary to show the relative tissue response to levels of extractable which are slightly above the detection limit. It is particularly