
**Welding consumables — Tubular cored
electrodes for gas shielded and non-gas
shielded metal arc welding of nickel and
nickel alloys — Classification**

*Produits consommables pour le soudage — Fils-électrodes fourrés pour
soudage à l'arc avec ou sans gaz de protection du nickel et des alliages
de nickel — Classification*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 12153:2011

<https://standards.iteh.ai/catalog/standards/sist/14c19f58-82f6-43eb-853f-9f4f527d2fd1/iso-12153-2011>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 12153:2011

<https://standards.iteh.ai/catalog/standards/sist/14c19f58-82f6-43eb-853f-9f4f527d2fd1/iso-12153-2011>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 12153 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body. A complete listing of these bodies can be found at <http://www.iso.org/>.

ISO 12153:2011

<https://standards.iteh.ai/catalog/standards/sist/14c19f58-82f6-43eb-853f-9f4f527d2fd1/iso-12153-2011>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 12153:2011

<https://standards.iteh.ai/catalog/standards/sist/14c19f58-82f6-43eb-853f-9f4f527d2fd1/iso-12153-2011>

Welding consumables — Tubular cored electrodes for gas shielded and non-gas shielded metal arc welding of nickel and nickel alloys — Classification

1 Scope

This International Standard specifies requirements for the classification of tubular cored electrodes for metal arc welding with or without a gas shield of nickel and nickel alloys. It includes those compositions in which the nickel content exceeds that of any other element.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO 6947:2011, *Welding and allied processes — Welding positions*

ISO 14175, *Welding consumables — Gases and gas mixtures for fusion welding and allied processes*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1:2000, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*

ISO 80000-1:2009, *Quantities and units — Part 1: General*

3 Classification

A tubular cored electrode shall be classified according to the chemical composition of the all-weld metal as given in Table 1 and the mechanical properties of the all-weld metal listed in Table 2.

The classification designation is divided into five parts:

- a) the first part gives a symbol indicating the product/process to be identified;
- b) the second part gives a symbol indicating the chemical composition of the all-weld metal;
- c) the third part gives a symbol indicating the type of electrode core;
- d) the fourth part gives a symbol indicating the type of shielding gas;
- e) the fifth part gives a symbol indicating the welding position.

4 Symbols and requirements

4.1 Symbol for the product/process

The symbol for the tubular cored electrode used in the metal arc welding process shall be the letter “T”.

4.2 Symbol for the chemical composition of the all-weld metal

The symbol for the chemical composition of the all-weld metal shall comprise “Ni” plus four digits, as shown in Table 1. The first digits are an indicator of the class of alloy deposited, as follows:

- 4 indicates significant copper addition (nickel-copper alloys)
- 6 indicates significant chromium addition, with iron less than 25 % (by mass) (nickel-chromium-iron and nickel-chromium-molybdenum alloys)
- 10 indicates significant molybdenum addition without significant chromium addition (nickel-molybdenum alloys)

The remaining digits indicate the particular alloy deposited.

The tubular cored electrode classified in accordance with Table 1 and produced as described in Clause 5 and Clause 6 shall also fulfil the requirements of Table 2.

NOTE In addition, the chemical symbol can be used.

4.3 Symbol for the type of electrode core

The third part of the designation indicates the type of electrode core and the slag characteristics (see Table 3).

4.4 Symbol for the shielding gas

The symbols for shielding gases shall be in accordance with ISO 14175 except that the symbol NO shall be used for tubular cored electrodes without a gas shield.

4.5 Symbol for the welding position

The fifth part of the designation (see Table 4) describes the welding position in which the tubular cored electrode can be welded. PA, PB, PC, PD, PE, PF, and PG are the symbols of the welding positions in accordance with ISO 6947:2011.

5 Chemical analysis

Chemical analysis shall be performed on any suitable all-weld metal test specimen. In case of dispute, the test specimen specified in ISO 6847 shall be used. The test results shall meet the requirements of Table 1 for the classification under test. Any analytical technique may be used, but in cases of dispute, reference shall be made to established published methods.

Table 1 — Symbols and all-weld metal chemical composition requirements

Alloy symbols		Chemical composition (% by mass) ^{ab}														
Numerical	Chemical	C	Mn	Fe	Si	Cu	Ni	Co	Al	Ti	Cr	Nb ^c	Mo	V	W	Others ^d
Nickel-Copper																
Ni 4060	NiCu30Mn3Ti	0,15	4,0	2,5	1,5	27,0 to 34,0	≥62,0	—	1,0	1,0	—	—	—	—	—	—
Ni 4061	NiCu27Mn3NbTi	0,15	4,0	2,5	1,3	24,0 to 31,0	≥62,0	—	1,0	1,5	—	3,0	—	—	—	—
Nickel-Chromium																
Ni 6082	NiCr20Mn3Nb	0,10	2,5 to 3,5	3,0	0,50	0,5	≥67,0	—	0,75	18,0 to 22,0	2,0 to 3,0	2,0	—	—	—	P 0,03
Ni 6083	NiCr20Mn6Fe4Nb	0,10	4,0 to 8,0	4,0	0,8	0,5	≥60,0	—	0,5	18,0 to 22,0	1,5 to 3,0	2,0	—	—	—	—
Nickel-Molybdenum																
Ni 1013	NiMo17Cr7W	0,10	2,0 to 3,0	10,0	0,75	0,5	≥58,0	—	—	4,0 to 8,0	—	16,0 to 19,0	—	2,0 to 4,0	—	—
Nickel-Chromium-Iron																
Ni 6062	NiCr15Fe8Nb	0,08	3,5	11,0	0,75	0,5	≥62,0	—	—	13,0 to 17,0	1,5 to 4,0	—	—	—	—	P 0,03
Ni 6133	NiCr16Fe12NbMo	0,10	1,0 to 3,5	12,0	0,75	0,5	≥62,0	—	—	13,0 to 17,0	0,5 to 3,0	0,5 to 2,5	—	—	—	P 0,03 S 0,02
Ni 6182	NiCr15Fe6Mn	0,10	5,0 to 9,5	10,0	1,0	0,5	≥59,0	—	1,0	13,0 to 17,0	1,0 to 2,5	—	—	—	—	P 0,03
Ni 6152	NiCr30Fe9Nb	0,05	5,0	7,0 to 12,0	0,8	0,5	≥50,0	—	0,5	28,0 to 31,5	1,0 to 2,5	0,5	—	—	—	—
Nickel-Chromium-Molybdenum																
Ni 6002	NiCr22Fe18Mo	0,05 to 0,15	1,0	17,0 to 20,0	1,0	0,5	≥45,0	0,5 to 2,5	—	20,5 to 23,0	—	8,0 to 10,0	—	0,2 to 1,0	—	P 0,04 S 0,03
Ni 6012	NiCr22Mo9	0,03	1,0	3,5	0,7	0,5	≥58,0	—	0,4	20,0 to 23,0	1,5	8,5 to 10,5	—	—	—	—
Ni 6022	NiCr21Mo13W3	0,02	1,0	2,0 to 6,0	0,2	0,5	≥49,0	2,5	—	20,0 to 22,5	—	12,5 to 14,5	0,35	2,5 to 3,5	—	P 0,03
Ni 6059	NiCr23Mo16	0,02	1,0	1,5	0,2	0,5	≥56,0	—	—	22,0 to 24,0	—	15,0 to 16,5	—	—	—	—
Ni 6275	NiCr15Mo16Fe5W3	0,10	1,0	4,0 to 7,0	1,0	0,5	≥50,0	2,5	—	14,5 to 16,5	—	15,0 to 18,0	0,4	3,0 to 4,5	—	—

Table 1 (continued)

Alloy symbols		Chemical composition (% by mass) ^{ab}														
Numerical	Chemical	C	Mn	Fe	Si	Cu	Ni	Co	Al	Ti	Cr	Nb ^c	Mo	V	W	Others ^d
Ni 6276	NiCr15Mo15Fe6W4	0,02	1,0	4,0 to 7,0	0,2	0,5	≥50,0	2,5	—	—	14,5 to 16,5	—	15,0 to 17,0	0,35	3,0 to 4,5	P 0,03 S 0,03
Ni 6455	NiCr16Mo15Ti	0,02	1,5	3,0	0,2	0,5	≥56,0	2,0	—	0,7	14,0 to 18,0	—	14,0 to 17,0	—	0,5	—
Ni 6456	NiCr16Mo10Nb	0,10	5,0 to 8,0	10,0	0,8	0,5	≥58,0	—	—	1,0	15,0 to 18,0	1,5 to 3,0	9,0 to 11,0	—	—	—
Ni 6625	NiCr22Mo9Nb	0,10	0,50	5,0	0,50	0,5	≥58,0	—	—	0,40	20,0 to 23,0	3,15 to 4,15	8,0 to 10,0	—	—	—
Ni 6686	NiCr21Mo16W4	0,02	1,0	5,0	0,3	0,5	≥49,0	—	—	0,3	19,0 to 23,0	—	15,0 to 17,0	—	3,0 to 4,4	—
Nickel-Chromium-Cobalt-Molybdenum																
Ni 6117	NiCr22Co12Mo	0,05 to 0,15	2,5	5,0	0,75	0,5	≥45,0	9,0 to 15,0	—	—	21,0 to 26,0	1,0	8,0 to 10,0	—	—	P 0,03
Ni 6617	NiCr22Co12MoAlTi	0,05 to 0,15	2,5	5,0	0,75	0,5	≥45,0	9,0 to 15,0	1,5	0,6	21,0 to 26,0	1,0	8,0 to 10,0	—	—	—
Z ^e Any other agreed composition																

^a Unless otherwise stated, single values are maxima.

^b Phosphorus 0,020 % (by mass) max., sulfur 0,015 % (by mass) max. unless otherwise stated.

^c Up to 20 % (by mass) of the amount of Nb can be replaced by Ta.

^d Total unspecified elements shall not exceed 0,5 % (by mass).

^e Consumables for which the chemical composition is not listed shall be symbolized similarly and prefixed by the letter "Z". The chemical composition ranges are not specified and it is possible that two electrodes with the same Z classification are not interchangeable.

Table 2 — Mechanical properties of the all-weld metal

Numerical symbol	Chemical symbol	Minimum yield strength $R_{p0,2}$ MPa	Minimum tensile strength R_m MPa	Minimum elongation $5d$ %
Nickel-Copper				
Ni 4060	NiCu30Mn3Ti	200	480	27
Ni 4061	NiCu27Mn3NbTi	200	480	27
Nickel-Chromium				
Ni 6082	NiCr20Mn3Nb	360	550	22
Ni 6083	NiCr20Mn6Fe4Nb	360	600	27
Nickel-Molybdenum				
Ni 1013	NiMo17Cr7W	400	690	27
Nickel-Chromium-Iron				
Ni 6062	NiCr15Fe8Nb	360	550	22
Ni 6133	NiCr16Fe12NbMo	360	550	22
Ni 6182	NiCr15Fe6Mn	360	550	22
Ni 6152	NiCr30Fe9Nb	360	550	27
Nickel-Chromium-Molybdenum				
Ni 6002	NiCr22Fe18Mo	380	620	22
Ni 6012	NiCr22Mo9	410	650	22
Ni 6022	NiCr21Mo13W3	350	690	22
Ni 6059	NiCr23Mo16	350	690	22
Ni 6275	NiCr15Mo16Fe5W3	400	690	22
Ni 6276	NiCr15Mo15Fe6W4	400	690	22
Ni 6455	NiCr16Mo15Ti	300	690	22
Ni 6456	NiCr16Mo10Nb	400	690	27
Ni 6625	NiCr22Mo9Nb	420	690	22
Ni 6686	NiCr21Mo16W4	350	690	27
Nickel-Chromium-Cobalt-Molybdenum				
Ni 6117	NiCr22Co12Mo	400	620	22
Ni 6617	NiCr22Co12MoAlTi	400	620	22