



SLOVENSKI STANDARD

SIST ISO 5628:2013

01-marec-2013

Nadomešča:
SIST ISO 5628:1995

Papir, karton in lepenka - Ugotavljanje upogibne togosti s statično metodo - Splošna načela za dvo-, tri- in štiritočkovne metode

Paper and board -- Determination of bending stiffness -- General principles for two-point, three-point and four-point methods

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Papier et carton -- Détermination de la rigidité à la flexion -- Principes généraux pour les méthodes à deux points, à trois points et à quatre points

<https://standards.iteh.ai/catalog/standards/sist/1128bf04-0ee1-482d-9c06-993b687ff238/sist-iso-5628-2013>

Ta slovenski standard je istoveten z: ISO 5628:2012

ICS:

85.060 Papir, karton in lepenka Paper and board

SIST ISO 5628:2013 **en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 5628:2013

<https://standards.iteh.ai/catalog/standards/sist/1128bf04-0ee1-482d-9c06-993b687ff238/sist-iso-5628-2013>

INTERNATIONAL STANDARD

**ISO
5628**

Second edition
2012-01-15

Paper and board — Determination of bending stiffness — General principles for two-point, three-point and four-point methods

*Papier et carton — Détermination de la rigidité à la flexion — Principes
généraux pour les méthodes à deux points, à trois points et à quatre points*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 5628:2013](https://standards.iteh.ai/catalog/standards/sist/1128bf04-0ee1-482d-9c06-993b687ff238/sist-iso-5628-2013)

<https://standards.iteh.ai/catalog/standards/sist/1128bf04-0ee1-482d-9c06-993b687ff238/sist-iso-5628-2013>



Reference number
ISO 5628:2012(E)

© ISO 2012

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 5628:2013

<https://standards.iteh.ai/catalog/standards/sist/1128bf04-0ee1-482d-9c06-993b687ff238/sist-iso-5628-2013>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and units	1
5 Theory	2
6 Different bending test methods	3
6.1 Two-point bending method	3
6.2 Three-point bending method	4
6.3 Calculation of bending stiffness using the two-point and three-point methods	5
6.4 Four-point bending method	6
7 Apparatus	7
8 Sampling and preparation of test pieces	8
8.1 Sampling	8
8.2 Conditioning	8
8.3 Preparation of test pieces	8
9 Procedure	8
10 Evaluation and calculation	8
11 Test report	9
Bibliography	10

SIST ISO 5628:2013
<https://standards.iteh.ai/catalog/standards/sist/1128bf04-0ee1-482d-9c06-993b687ff238/sist-iso-5628-2013>

ISO 5628:2012(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 5628 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

This second edition cancels and replaces the first edition (ISO 5628:1990), which has been technically revised.

The main differences between this edition and the previous edition are the following:

- the equations for bending stiffness for two-point and three-point bending have been harmonized;
- geometrical conditions for test pieces have been added;
- some additional aspects of corrugated board have been added for four-point bending.

[SIST ISO 5628:2013](https://standards.iteh.ai/catalog/standards/sist/1128bf04-0ee1-482d-9c06-993b687ff238/sist-iso-5628-2013)

<https://standards.iteh.ai/catalog/standards/sist/1128bf04-0ee1-482d-9c06-993b687ff238/sist-iso-5628-2013>

Introduction

Bending stiffness is regarded as an important property of paper and board, and a large number of test methods have been used for its determination. This is a result, in part at least, of the wide range in the bending stiffness of paper and board. For paper and board in the grammage range 50 g/m² to 500 g/m², bending stiffness might vary by a factor of over 1 000. This wide variation is reflected in the design of instruments intended for the measurement of this property.

A second factor to be taken into account is that, in general terms, bending stiffness (as defined here) can only be determined with accuracy within certain limits with regard to the degree of deformation imposed upon the test piece. These limits depend on the dimensions of the test piece and on the test method used.

This International Standard is intended to enable the bending stiffness (as defined here) to be measured and described in a consistent way, despite the variations in material type and instrument design. It will be found that many commercially available instruments can be regarded as giving results in accordance with this International Standard for only part of the range of bending stiffness, or for only some of the materials for which they were originally designed. It is intended, therefore, that this International Standard will be used as the basis for preparing detailed methods for determining bending stiffness, using particular instruments.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 5628:2013](https://standards.iteh.ai/catalog/standards/sist/1128bf04-0ee1-482d-9c06-993b687ff238/sist-iso-5628-2013)

<https://standards.iteh.ai/catalog/standards/sist/1128bf04-0ee1-482d-9c06-993b687ff238/sist-iso-5628-2013>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 5628:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/1128bf04-0ee1-482d-9c06-993b687ff238/sist-iso-5628-2013>

Paper and board — Determination of bending stiffness — General principles for two-point, three-point and four-point methods

1 Scope

This International Standard specifies three test methods for determining the bending stiffness of paper and paperboard. The test methods differ in the type of loading mode, thus giving rise to the two-point, three-point and four-point bending test methods.

For paper and paperboard in a low thickness range, the two-point bending method and the three-point bending method are suitable.

For corrugated fibreboard and board with a higher thickness, the four-point bending method is recommended.

The measurement conditions are defined in such a way that the test piece is not subjected to any significant permanent deformation during the test, nor is the range of validity of the equations for calculating the bending stiffness exceeded.

In these bending tests, the test pieces of paper and board are regarded as “beams” as defined by the science of the strength of materials, see Reference [1].

iTeh STANDARD PREVIEW
(standards.iteh.ai)

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 534, *Paper and board — Determination of thickness, density and specific volume*

ISO 3034, *Corrugated fibreboard — Determination of single sheet thickness*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

bending stiffness

S_b

resistance that a test piece offers to bending, in the region of elastic deformation

NOTE The theories used for the determination of bending stiffness are derived under the condition that the test piece is perfectly flat at the beginning of the test. In a real situation, the test piece always deviates from flatness. It is, however, not possible to give recommendations on the magnitude of such deviations (such as curl, twist, cockle or other deviations) that can be present and still produce a valid test.

4 Symbols and units

The following symbols are used for the equations in this International Standard.