



Designation: B 949 – 06

Standard Specification for General Requirements for Zinc and Zinc Alloy Products¹

This standard is issued under the fixed designation B 949; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification establishes general requirements, unless otherwise specified in the specific product specification, for ordering information, marking, and sampling for chemical analysis common to zinc and zinc alloy products and shall apply to Specifications B 6, B 69, B 86, B 240, B 327, B 418, B 750, B 792, B 793, B 833, B 852, B 860, B 892, B 894, B 897, B 907, and B 943 to the extent referenced therein.

1.2 Although this specification establishes general requirements, it does not restrict that, by agreement between customer and supplier, these requirements may be altered by a customer to suit individual need.

1.3 The chemical composition, physical and mechanical properties, and all other requirements not included in this specification shall be prescribed in the product specification.

1.4 *Units*—The values stated in inch-pound units are to be regarded as standard except where SI units only are specified. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Data Sheet (MSDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

B 6 Specification for Zinc

B 69 Specification for Rolled Zinc

B 86 Specification for Zinc and Zinc-Aluminum (ZA) Alloy Foundry and Die Castings

B 240 Specification for Zinc and Zinc-Aluminum (ZA) Alloys in Ingot Form for Foundry and Die Castings

B 327 Specification for Master Alloys Used in Making Zinc Die Casting Alloys

B 418 Specification for Cast and Wrought Galvanic Zinc Anodes

B 750 Specification for GALFAN (Zinc-5 % Aluminum-Mischmetal) Alloy in Ingot Form for Hot-Dip Coatings

B 792 Specification for Zinc Alloys in Ingot Form for Slush Casting

B 793 Specification for Zinc Casting Alloy Ingot for Sheet Metal Forming Dies and Plastic Injection Molds

B 833 Specification for Zinc and Zinc Alloy Wire for Thermal Spraying (Metallizing) for the Corrosion Protection of Steel

B 852 Specification for Continuous Galvanizing Grade (CGG) Zinc Alloys for Hot-Dip Galvanizing of Sheet Steel

B 860 Specification for Zinc Master Alloys for Use in Hot Dip Galvanizing

B 892 Specification for ACuZinc5 (Zinc-Copper-Aluminum) Alloy in Ingot Form for Die Castings

B 894 Specification for ACuZinc5 (Zinc-Copper-Aluminum) Alloy Die Castings

B 897 Specification for the Configuration of Zinc and Zinc Alloy Jumbo and Block Ingot

B 899 Terminology Relating to Non-ferrous Metals and Alloys

B 907 Specification for Zinc, Tin and Cadmium Base Alloys Used as Solders

B 908 Practice for the Use of Color Codes for Zinc Casting Alloy Ingot

B 914 Practice for Color Codes on Zinc and Zinc Alloy Ingot for Use in Hot-Dip Galvanizing of Steel

B 943 Specification for Zinc and Tin Alloy Wire Used in Thermal Spraying for Electronic Applications

E 55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition

E 88 Practice for Sampling Nonferrous Metals and Alloys in Cast Form for Determination of Chemical Composition

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.04 on Zinc and Cadmium.

Current edition approved Dec. 1, 2006. Published January 2007.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E 634 Practice for Sampling of Zinc and Zinc Alloys for Optical Emission Spectrometric Analysis

3. Terminology

3.1 For terms related to non-ferrous metals and alloys, refer to Terminology **B 899**.

4. Ordering Information

4.1 Include the following minimum information when placing orders for zinc and zinc alloy products under this specification:

- 4.1.1 ASTM designation and year of issue (see Scope),
- 4.1.2 Quantity (weight),
- 4.1.3 Alloy or grade, or both, (when applicable),
- 4.1.4 Size,
- 4.1.5 Delivery schedule.
- 4.1.6 Marking (Section 10), and
- 4.1.7 Whether certification is required (Section 9).

4.2 Additional ordering information for specific zinc and zinc alloy products:

4.2.1 There may be additional information required when ordering specific products. These may be found in the product specifications listed in 2.1 (Specifications **B 6** through **B 897** and **B 907** and **B 943**).

5. Chemical Requirements

5.1 Final product (ingots, slabs, jumbos, etc.) shall conform to the chemical composition requirements prescribed in the applicable product specification (see 2.1: Specifications **B 6** through **B 897**, **B 907**, and **B 943**).

5.2 Conformance shall be determined by the manufacturer by analyzing samples taken at the time the final product is poured or samples taken from the ingots.

5.2.1 If the producer has determined the chemical composition of the metal during the course of manufacture, he shall not be required to sample and analyze the finished product.

5.2.2 *Method of Analysis*—At the discretion of the producer, the determination of chemical composition shall be made in accordance with suitable spectrochemical or chemical methods.

6. Sampling for Determination of Chemical Composition

6.1 *Samples for Spectrochemical and Other Methods of Analysis*—Samples for spectrochemical and other methods of analysis shall be suitable for the form of material being analyzed and the type of analytical method used.

6.2 *Sampling During Production of Ingots, Slabs, Blocks or Jumbos, and Wrought Products:*

6.2.1 *Sampling During Casting*—Samples may be taken from the pour during the casting of zinc and zinc alloys.

6.2.1.1 Samples for spectrochemical methods may be cast as pins or discs in accordance with Practice **E 634** for spectrochemical analyses or may be cast in a form or by a method the producer has determined will generate a homogeneous and representative sample.

6.2.1.2 The producer should determine the sampling regimen that will efficiently result in samples that are representative of the product. As a suggested minimum, at least two samples sets shall be taken for batches of 25 tons (22.7 mTons)

or less. At least three sample sets shall be taken for batches up to 150 tons (136 mTons). The average chemical analyses shall be determined from these samples. Unless otherwise agreed in the contact or purchase order, sampling procedure will be the manufacturer's choice.

6.2.2 Samples held at the producer's plant shall be retained for not less than 90 days.

6.3 *Sampling of Ingot, Slabs, or Blocks and Jumbos and Wrought Product in the Event of a Dispute or if the Alloy is at the Customer's Plant*—The sample for chemical analysis shall be taken based on the form of the product.

6.3.1 *Ingot, Slabs, or Product in an Easily Sampled Form*—If the alloy is in the form of standard ingots, slabs, etc. at the customer's plant, the sample for chemical analysis shall be taken in accordance with 6.3.1.1 through 6.3.1.6, inclusive.

6.3.1.1 *Selection of Portion*—A portion representative of the total shipment or order shall be selected at random for the final sample. The portion preferably shall be taken during loading or unloading. Not less than five ingots shall be taken at random from each car or truckload of the same alloy for sampling. Each heat in the shipment shall be represented. If the shipment is less than a carload lot, one sample ingot shall be taken for each 10 000 lb (4540 kg) or fraction thereof. When it is deemed necessary, a sample may be taken from each melt of 1000 lb (454 kg) or more.

6.3.1.2 *Preparation of Sample*—The product shall be cleaned thoroughly to rid the surface of extraneous material. Then the samples for chemical analysis shall be taken by sawing, milling, or drilling in such a manner as to be representative of the average cross section of the ingot. The weight of a prepared sample shall be not less than 300 g.

6.3.1.3 The saw drill, or cutter used for taking the sample shall be thoroughly cleaned. No lubricant shall be used in the operation, and the sawings or metal chips shall be carefully treated with a magnet to remove any particles or iron introduced in taking the sample.

NOTE 1—Sampling by sawing is not recommended for Special High Grade zinc because complete removal of the final traces of adventitious iron from sawings is difficult.

6.3.1.4 *Drilling*—Two holes shall be drilled, preferably from the bottom or brand side of each ingot or slab, at two points located along one diagonal of the slab so that each point is halfway between the center and one extremity of the diagonal. If two holes from each ingot or slab do not yield the weight of sample prescribed in 6.3.1.6, a third hole shall be drilled at the center of each. Each hole shall be bored completely through, care being taken to avoid starting the drill in a depression and to adjust the feed to give drillings 0.010 to 0.020 in. (0.25 to 0.51 mm) in thickness. The drill used preferably shall be non-ferrous tipped (such as carbide, Ti-N, etc.) The diameter of the drill shall be 1/2 in. (12.7 mm) for Special High Grade zinc, and shall be 5/16 in. (7.9 mm) for other grades of zinc. The drillings shall be broken or cut with clean shears into pieces not over 1/2 in. in length and mixed thoroughly.

6.3.1.5 *Sawing*—Using, preferably, a heat treated high-speed steel saw, make two cuts completely across and through the ingot or slab from one long side to the other. Each cut shall