
Upodobitveni materiali - Kompaktni diski (CD-ROM) - Metoda za določanje pričakovane življenjske dobe na podlagi učinkov zaradi temperature in relativne vlage

Imaging materials - Compact discs (CD-ROM) - Method for estimating the life expectancy based on the effects of temperature and relative humidity

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Matériaux pour l'image - Disques compacts (CD-ROM) - Méthode d'estimation de l'espérance de vie basée sur les effets de la température et de l'humidité relative

[https://standards.iteh.ai/catalog/standards/sist/993bce06-8e7e-403c-a892-](https://standards.iteh.ai/catalog/standards/sist/993bce06-8e7e-403c-a892-5f8973b96115/sist-iso-18921-2011)

[5f8973b96115/sist-iso-18921-2011](https://standards.iteh.ai/catalog/standards/sist/993bce06-8e7e-403c-a892-5f8973b96115/sist-iso-18921-2011)

Ta slovenski standard je istoveten z: ISO 18921:2008

ICS:

35.220.30	Optične shranjevalne naprave	Optical storage devices
37.040.99	Drugi standardi v zvezi s fotografijo	Other standards related to photography

SIST ISO 18921:2011

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 18921:2011

<https://standards.iteh.ai/catalog/standards/sist/993bce06-8e7e-403c-a892-5f8973b96115/sist-iso-18921-2011>

**Imaging materials — Compact discs
(CD-ROM) — Method for estimating
the life expectancy based on the effects
of temperature and relative humidity**

*Matériaux pour l'image — Disques compacts (CD-ROM) — Méthode
d'estimation de l'espérance de vie basée sur les effets de la
température et de l'humidité relative*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 18921:2011

<https://standards.iteh.ai/catalog/standards/sist/993bce06-8e7e-403c-a892-5f8973b96115/sist-iso-18921-2011>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 18921:2011](https://standards.iteh.ai/catalog/standards/sist/993bce06-8e7e-403c-a892-5f8973b96115/sist-iso-18921-2011)

<https://standards.iteh.ai/catalog/standards/sist/993bce06-8e7e-403c-a892-5f8973b96115/sist-iso-18921-2011>

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Purpose and assumptions	3
4.1 Purpose	3
4.2 Assumptions	3
5 Measurements	3
5.1 Block error rate (BLER).....	3
5.2 Test equipment	3
5.3 Test specimen.....	4
6 Accelerated stress test plan.....	4
6.1 General	4
6.2 Stress conditions	5
6.3 Accelerated test cell specimen population.....	7
6.4 Time intervals	8
6.5 Test plan	8
6.6 Measurement conditions	8
7 Data evaluation	8
7.1 Eyring acceleration model.....	8
7.2 Failure distribution model.....	9
7.3 Acceleration factors	9
7.4 Survivor analysis.....	10
8 Disclaimer	10
Annex A (informative) Step analysis outline	11
Annex B (informative) Example of test plan and data analysis.....	12
Bibliography.....	19

ISO 18921:2008(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 18921 was prepared by Technical Committee ISO/TC 42, *Photography*.

This second edition cancels and replaces the first edition (ISO 18921:2002), of which it constitutes a minor revision.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

The following changes have been made to the first edition:

- modification of definition 3.8 (life expectancy); [SIST ISO 18921:2011](https://standards.iteh.ai/catalog/standards/sist/993bce06-8e7e-403c-a892-5f8973b96115/sist-iso-18921-2011)
- modification of 5.1 on block error rate; [5f8973b96115/sist-iso-18921-2011](https://standards.iteh.ai/catalog/standards/sist/993bce06-8e7e-403c-a892-5f8973b96115/sist-iso-18921-2011)
- correction of Equations (1) and (2) in 7.1;
- updating of normative and bibliographical references;
- removal of the original Annex A.

Imaging materials — Compact discs (CD-ROM) — Method for estimating the life expectancy based on the effects of temperature and relative humidity

1 Scope

This International Standard specifies a test method for estimating the life expectancy (LE) of information stored on compact disc (CD-ROM) media, including CD audio, but excluding recordable media. Only the effects of temperature and relative humidity on the media are considered.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/IEC 10149¹⁾, *Information technology — Data interchange on read-only 120 mm optical data disks (CD-ROM)*

SIST ISO 18921:2011

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

cumulative distribution function

$F(t)$

probability that a random unit drawn from the population fails by time t , or the fraction of all units in the population which fails by time t

3.2

survivor function

$R(t)$

probability that a unit drawn from the population will survive at least time t , or the fraction of units in the population that will survive at least time t

NOTE $R(t) = 1 - F(t)$.

3.3

baseline

condition representing the disc at time of manufacture

NOTE This is customarily the initial parameter measurement taken prior to any application of stress. The designation is usually $t = 0$ for a stress time equal to zero hours.

1) Equivalent to ECMA 130.

ISO 18921:2008(E)

3.4
block error rate
BLER
 ratio of erroneous blocks to total blocks measured at the input of the first (C1) decoder (before any error correction is applied)

NOTE The more commonly reported value for BLER is the number of erroneous blocks per second measured at the input of the C1-decoder during playback at the standard (1X) data rate.

[IEC 60908:1999]

3.5
CD-ROM
 compact disc-read only medium

3.6
end-of-life
 occurrence of any loss of information

3.7
information
 signal or image recorded using the system

3.8
life expectancy
LE
 length of time that information is predicted to be retrieved in a system at 23 °C and 50 % relative humidity (RH)

3.8.1
standard life expectancy
SLE
 minimum life span, predicted with 95 % confidence, of 95 % of the product stored at a temperature not exceeding 25 °C and a relative humidity (RH) not exceeding 50 % RH

3.9
retrievability
 ability to access information as recorded

3.10
stress
 experimental variable to which the specimen is exposed for the duration of the test interval

NOTE In this International Standard, the stress variables are confined to temperature and relative humidity.

3.11
system
 combination of recording medium, hardware, software and documentation necessary to retrieve information

3.12
test cell
 device that controls the stress to which the specimen is exposed

3.13
test pattern
 distribution of the characters 1 and 0 within a block and the block-to-block variation

4 Purpose and assumptions

4.1 Purpose

The purpose of this International Standard is to establish a methodology for estimating the life expectancy of information stored on CD-ROMs. This methodology provides a technically and statistically sound procedure for obtaining and evaluating accelerated test data.

4.2 Assumptions

The validity of the procedure defined by this International Standard relies on three assumptions:

- the dominant failure mechanism acting at the usage condition is the same as at the accelerated conditions;
- the dominant failure mechanism is appropriately modelled by an Eyring acceleration model;
- life expectancy is appropriately modelled by the two parameter Weibull distribution (see [1] in the Bibliography). The shape parameter of the Weibull distribution is assumed to be independent of the stress level.

5 Measurements

5.1 Block error rate (BLER)

The objective of measuring the block error rate (BLER) is to establish a practical estimation of the system's ability to read the pre-recorded bits using a standard drive. This International Standard considers BLER to be a high level estimate of the performance of the system. A change in BLER in response to the time at an elevated temperature and humidity is the principal quality parameter.

IEC 60908 states that the BLER averaged over any 10 s shall be less than 3×10^{-2} . At the standard (1X) data rate, the total number of blocks per second entering the C1-decoder is 7 350. Thus, an equivalent limit on BLER is 220 blocks per second.

For the purposes of this International Standard, recorded data are considered to have reached end-of-life when the BLER, measured as erroneous blocks per second, exceeds 220 anywhere on the disc, i.e. when the maximum BLER exceeds 220. It is recognized that the correlation between actual loss of information and maximum BLER is very system dependent. A BLER of 220 is an arbitrary level chosen as a predictor of the onset of uncorrectable errors and thereby end-of-life.

5.2 Test equipment

5.2.1 Compact disc test system

Any compact disc test system (tester) that is in accordance with ISO/IEC 10149 may be used. The make, model and version of the test equipment (including software) shall be reported with the test results.

5.2.2 Calibration and repeatability

Calibration according to the tester manufacturer's procedure shall be performed prior to any measurement data being collected. A calibration disc shall be available from the tester manufacturer.

ISO 18921:2008(E)

In addition to the calibration disc, one control disc shall be maintained at ambient conditions and its maximum BLER measured before and after each data collection interval. A control chart shall be maintained for this control disc with $\pm 3 \sigma$ action limits. The mean and standard deviation of the control disc shall be established by collecting at least five measurements. Should any individual maximum BLER reading exceed the action limit, the problem shall be corrected and all data collected since the last valid control point shall be remeasured.

If it becomes necessary to replace the tester, a method shall be followed for correlating tester outputs (see [2] in the Bibliography).

5.3 Test specimen

A test specimen is any disc that meets ISO/IEC 10149 specifications and contains representative data extending to within 2 mm of the maximum recording diameter.

6 Accelerated stress test plan**6.1 General**

A CD-ROM of good manufacture should last several years or even decades. Consequently, it is necessary to conduct accelerated ageing studies in order to develop a life expectancy estimate. The key is conducting and evaluating a test plan that will provide the information necessary to satisfactorily evaluate the particular product.

iTeh STANDARD PREVIEW

Many accelerated life test plans follow a rather traditional approach in sampling, experimentation and data evaluation. These "traditional plans" share the following characteristics:

- a) the total number of specimens is evenly divided amongst all the accelerated stresses;
- b) each stress is evaluated at the same time increments;
- c) the Arrhenius relationship is used as the acceleration model;
- d) the least squares method is used for all regressions;
- e) the calculated life expectancy is for the mean or median life rather than for the first few failure percentiles.

On the other hand, "optimum test plans" have been proposed which differ in significant aspects from traditional plans. These plans have the following characteristics:

- two and only two acceleration levels for each stress;
- a large number of specimens distributed mostly in the lowest stress levels;
- the need to know the failure distribution, a priori, in order to develop the plan.

The maximum effectiveness of a plan can either be estimated before the test starts or determined after the results have been obtained. As each CD-ROM system has different characteristics, a specific, detailed optimum plan is impossible to forecast.

This test plan borrows from the optimum plan, the traditional plan, previous experience with the systems, test equipment and accelerated test stresses to put together a "compromise test plan". Modifications of this plan will be required to design the best plan for other applications. The methodology shall be applicable to all CD-ROM media assessments.

6.2 Stress conditions

6.2.1 Levels

As mentioned in 6.1, an optimum test plan utilizes only two stress levels for each parameter evaluated, since in an ideal case the relationship between changes in the parameter investigated and changes in stress is known. The compromise test plan documented in this International Standard does not make such an assumption; therefore, three different stress levels per parameter shall be used so that the linearity of the parameter function versus the stress level may be demonstrated.

The test plan shall have the majority of test specimens placed at the lowest stress condition. This minimizes the estimation error at this condition and results in the best estimate of the degradation rate at a level close to the usage condition. The greater number of specimens at the lower stress also tends to equalize the number of failures observed by test completion.

6.2.2 Conditions

For implementing the test plan documented in this International Standard, five stress conditions shall be used. The minimum distribution of specimens among the stress points that shall be used is shown in Table 1. For improved precision, additional specimens and conditions may be used if desired.

Table 1 — Summary of stress conditions

Test cell number	Test stress		Number of specimens	Incubation duration h	Minimum total time h	Intermediate RH RH(int) ^b %	Minimum equilibrium duration h
	T(inc) ^a °C	RH(inc) ^a %					
1	80	85	10	500	2 000	31	6
2	80	70	10	500	2 000	31	8
3	80	55	15	500	2 000	31	4
4	70	85	15	750	3 000	33	8
5	60	85	30	1 000	4 000	36	11

^a T(inc) and RH(inc) are the stress incubation temperature and relative humidity.

^b RH(int) is the intermediate relative humidity that at T(inc) supports the same equilibrium moisture absorption in polycarbonate as that supported at room ambient temperature and relative humidity.

6.2.3 Temperature (T)

The temperature levels chosen for this test plan are based on the following:

- there shall be no change of phase within the test system over the test temperature range; this restricts the temperature to greater than 0 °C and less than 100 °C;
- the temperature level shall not be so high that plastic deformation occurs.

The typical substrate material for CD-ROMs is polycarbonate (glass transition temperature ~ 150 °C). The glass transition temperature of other layers may be lower. Experience with high temperature testing of CD-ROMs indicates that an upper limit of 80 °C is practical for most applications.