
**Imaging materials — Optical disc
media — Storage practices**

*Matériaux pour l'image — Milieux pour disque optique — Pratiques de
stockage*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 18925:2008](https://standards.iteh.ai/catalog/standards/sist/018f68c6-53bf-43dc-80ad-3fb8a2ecec1a9/iso-18925-2008)

[https://standards.iteh.ai/catalog/standards/sist/018f68c6-53bf-43dc-80ad-
3fb8a2ecec1a9/iso-18925-2008](https://standards.iteh.ai/catalog/standards/sist/018f68c6-53bf-43dc-80ad-3fb8a2ecec1a9/iso-18925-2008)



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 18925:2008

<https://standards.iteh.ai/catalog/standards/sist/018f68c6-53bf-43dc-80ad-3fb8a2ecea9/iso-18925-2008>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Environmental conditions	4
4.1 Humidity and temperature limits	4
4.2 Contaminants and gaseous impurities	4
4.3 Magnetic fields.....	4
5 Materials	5
6 Enclosures	5
6.1 General requirements	5
6.2 Labelling.....	5
7 Preparation.....	5
7.1 General	5
7.2 Acclimatization	5
8 Storage housing	6
9 Storage rooms	6
10 Fire-protective storage.....	7
11 Identification, inspection and cleaning	7
11.1 Identification	7
11.2 Inspection.....	7
11.3 Cleaning.....	8
Annex A (informative) Temperature-relative humidity relationship.....	9
Annex B (informative) Temperature and humidity acclimatization.....	10
Bibliography.....	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 18925 was prepared by Technical Committee ISO/TC 42, *Photography*.

This second edition cancels and replaces the first edition (ISO 18925:2002), of which it constitutes a minor revision.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

The following changes have been made to the first edition:

- modification of definition 3.12 (life expectancy); [ISO 18925:2008](https://standards.iteh.ai/catalog/standards/sist/018f68c6-53bf-43dc-80ad-3fb8a2ece1a9/iso-18925-2008)
- updating of normative and bibliographical references;
- removal of the original Annex A.

Introduction

Use of optical disc material is becoming widespread in audio, video and computer applications. Preservation of this information is becoming of increasing concern to society, particularly as the recorded information becomes older and frequently of greater value to libraries, archives, museums, government agencies and commercial organizations.

The stability of optical discs is dependent upon that of the complete system. This includes the stability of the material itself, the equipment on which it is run and, in systems, upon the necessary software. ISO 18921 specifies a methodology for estimating the life expectancy of the CD-ROM. Other optical discs will be addressed in future International Standards. These standards consider only the effects of temperature and humidity and do not include other factors such as light, corrosive gases and particulates. International Standards are not available on the life expectancy of hardware and the problems associated with hardware wearing out or becoming obsolete.

It is advisable that optical disc users store discs under conditions that will extend their life and handle the material so that it will not be subjected to stress and undergo physical breakdown during use. This International Standard addresses the concerns of long-term storage.

A major component of a large number of optical discs is the polycarbonate substrate. Polycarbonate is a very durable material, but it does absorb moisture and there is always an equilibrium between the ambient humidity and the moisture content of the disc. Polycarbonate is susceptible to decomposition under certain conditions and given a suitable catalyst.

The second component of most optical discs is the reflective layer. This layer is usually some highly reflective metal such as aluminium, silver or gold. Each of these materials is subject to reaction with various chemicals that can be found in the environment. Aluminium, for example, combines readily with oxygen to form aluminium oxide. Silver combines with sulfur to tarnish and form silver sulfides. Gold is known to react with chlorine to form gold chlorides.

A third component of these discs is some type of seal coat. This is typically a UV-cured polymer whose purpose is to protect the reflective layer and any other material layers in the disc.

A fourth component, in the case of some recordable optical discs, is the dye layer. For magneto-optic or phase change discs, additional layers are also included.

Regardless of the inherent stability of the various disc layers, it is known that good storage conditions will extend the life of all optical discs. While a good storage environment cannot reverse any degradation that has already occurred, it can slow down additional deterioration.

A single storage condition is described in this International Standard. This condition is intended for discs that contain recorded information of long-term value. Various manufacturers' studies indicate that the life expectancy of well manufactured optical discs is in excess of 50 years under typical room ambient conditions (see [1] and [2] in the Bibliography).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 18925:2008

<https://standards.iteh.ai/catalog/standards/sist/018f68c6-53bf-43dc-80ad-3fb8a2ecea9/iso-18925-2008>

Imaging materials — Optical disc media — Storage practices

1 Scope

This International Standard establishes extended-term storage conditions for optical discs and provides recommendations concerning the storage conditions, storage facilities, enclosures and inspection for optical discs. It is applicable to discs made for audio, video, instrumentation and computer use.

Recommendations are general in nature and it is advisable that the manufacturer's cautions for specific material be considered. Relaxation from these recommendations, whether before or after recording, will generally result in shortened life expectancy.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/IEC 15486:1998, *Information technology — Data interchange on 130 mm optical disk cartridges of type WORM (Write Once Read Many) using irreversible effects — Capacity: 2,6 Gbytes per cartridge*

NFPA 75, *Standard for the Protection of Electronic Computer/Data Processing Equipment*¹⁾

<https://standards.iteh.ai/catalog/standards/sist/018f68c6-53bf-43dc-80ad-3fb8a2ecec1a9/iso-18925-2008>

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

blister

localized delamination that looks like a bubble

3.2

compact disc

CD

optical disc format in which the information layer is located at one surface of a substrate and the data can be read by an optical beam

NOTE CD is the subject of IEC 60908.

3.2.1

compact disc-recordable

CD-R

recordable optical disc in which information can be recorded to certain areas in the compact disc format

NOTE Information can be recorded once and read many times.

1) Available from the National Fire Protection Association, 1 Batterymarch Park, P.O. Box 9101, Quincy, MA 02269-9101, USA.

3.2.2

**compact disc read-only memory
CD-ROM**

optical disc to which information is transferred during manufacture to certain areas in the compact disc format

NOTE 1 Information can be read many times.

NOTE 2 CD-ROM is the subject of ISO/IEC 10149.

3.2.3

**compact disc-rewritable
CD-RW**

recordable optical disc in which information can be recorded to certain areas in the compact disc format

NOTE Information can be erased and new information recorded many times and read many times.

3.3

container

box, can or carton used for storage and shipping of recording materials

3.4

**digital versatile disc
DVD**

digital video disc (deprecated)

optical disc format in which one or more information layers are located between two substrates and the data can be read by an optical beam

**ITeh STANDARD PREVIEW
(standards.iteh.ai)**

3.5

delamination

separation of a laminate into its constituent layers

[ISO 18925:2008](https://standards.iteh.ai/catalog/standards/sist/018f68c6-53bf-43dc-80ad-3fb8a2ecec1a9/iso-18925-2008)

3.6

dew point

temperature at which moisture begins to condense on a surface

<https://standards.iteh.ai/catalog/standards/sist/018f68c6-53bf-43dc-80ad-3fb8a2ecec1a9/iso-18925-2008>

NOTE See **relative humidity** (3.16).

EXAMPLE The more humid the air, the higher the dew point temperature.

3.7

enclosure

folder, envelope, sleeve or clam shell intended for physical protection against mechanical damage

3.8

extended-term storage conditions

storage conditions suitable for the preservation of recorded information having permanent value

3.9

fire-protective storage

facilities designed to protect records against excessive temperatures, water and other fire-fighting agents, and steam developed by insulation of safes or caused by the extinguishing of fires and collapsing structures

3.10

insulated record container

storage box designed to withstand elevated temperatures and conforming to national standards and regulations

3.11

isoperm lines

lines of constant life plotted as a function of temperature and relative humidity

3.12**life expectancy****LE**

length of time that information is predicted to be retrieved in a system at 23 °C and 50 % relative humidity (RH)

3.13**magnetic field intensity**

level of the magnetic field at a point in space

3.14**medium**

material on which the information is recorded

NOTE Plural is media.

3.15**MO disc**

optical disc in which the information is recorded using magneto-optical technology in some specified format

NOTE Information can be recorded, read many times and overwritten many times.

3.16**relative humidity****RH**

ratio, defined as a percentage, of the existing partial vapour pressure of water to the vapour pressure at saturation

NOTE It is usually, but not always, equal to the percentage of the amount of moisture in the air to that at saturation.

3.17**storage environment**

conditions for storing materials, i.e. temperature, relative humidity, cleanliness of facilities and atmospheric pollutants

3.18**storage housing**

physical structure supporting materials and their enclosures

NOTE It can consist of drawers, racks, shelves or cabinets.

3.19**system**

combination of material, hardware, software and documentation necessary for recording and/or retrieving information

3.20**WORM disc**

optical disc in which the data in specified areas can be written only once and read multiple times by an optical beam