



Designation: D 3935 – 02

Standard Specification for Polycarbonate (PC) Unfilled and Reinforced Material¹

This standard is issued under the fixed designation D 3935; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers unfilled and reinforced polycarbonate and polycarbonate copolymer materials suitable for injection molding, blow molding, and extrusion. Some of these compositions may also find use for compression molding or application from solution.

1.2 The properties in this specification are those required for identifying the compositions covered. There may be other requirements necessary for identifying particular characteristics important to specific applications. Those may be specified by using the suffixes in accordance with Section 5.

1.3 The values stated in SI units are to be regarded as the standard.

NOTE 1—This specification is similar to ISO 7391 – 1987 in title only. The technical content is significantly different.

1.4 The following hazard caveat pertains only to the test methods portion, Section 12, of this specification. *This standard does not purport to address all safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability or regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- D 256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics²
- D 638 Test Method for Tensile Properties of Plastics²
- D 648 Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position²
- D 790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials²

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved March 10, 2002. Published May 2002. Originally published as D 3935 – 80. Last previous edition D 3935 – 94 (2001).

² Annual Book of ASTM Standards, Vol 08.01.

- D 792 Test Method for Specific Gravity (Relative Density) and Density of Plastics by Displacement²
- D 883 Terminology Relating to Plastics²
- D 1238 Test Method for Melt Flow Rates of Thermoplastics by Extrusion Plastometer²
- D 1600 Terminology for Abbreviated Terms Relating to Plastics²
- D 2584 Test Method for Ignition Loss of Cured Reinforced Resins³
- D 3892 Practice for Packaging/Packing of Plastics⁴
- D 4000 Classification System for Specifying Plastic Materials⁴
- D 5630 Test Method for Ash Content in Plastics⁴
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁵
- E 169 Practices for General Techniques of Ultraviolet-Visible Quantitative Analysis⁶
- 2.2 ISO Standard:⁷
- ISO 7391–1987 Plastics—Polycarbonate Molding and Extrusion Materials (Part 1: Designation—1987) (Part 2: Preparation of Test Specimens and Determination of Properties)

3. Terminology

3.1 *Definitions*—The terminology used in this specification is in accordance with Terminologies D 883 and D 1600. The polycarbonate materials will be designated PC as specified in Terminology D 1600.

4. Classification

4.1 Unfilled polycarbonate materials are classified into groups according to their composition. These groups are subdivided into classes and grades as shown in Table PC

³ Annual Book of ASTM Standards, Vol 08.02.

⁴ Annual Book of ASTM Standards, Vol 08.03.

⁵ Annual Book of ASTM Standards, Vol 14.02.

⁶ Annual Book of ASTM Standards, Vol 14.01.

⁷ Available from American National Standards Institute, 25 W. 43rd St., 4th Floor, New York, NY 10036.

TABLE PC Polycarbonate Materials and Detail Requirements

Note— The values are for naturals; colors may be different.

Group	Description	Class	Description	Grade	Description ^A	Flow Rate, ^B Test Method D 1238, g/10 min	Specific Gravity, Test Method D 792	Izod Impact, ^C Test Methods D 256, J/m, min	Tensile	Elongation	Flexural	Deflection					
									Yield Strength ^D	at Break ^D	Modulus, ^E Test Methods D 790, MPa, min	Tempera- ture, Test Method D 648, ^F °C, min					
01	PC	1	general purpose	1		>24	1.19–1.22				use Table B						
				2		15 to 30	1.19–1.22			use Table B							
				3		12 to 20	1.19–1.22	640	55	100	2000	126					
				4		9 to 18	1.19–1.22	750	60	105	2100	126					
				5		6 to 13	1.19–1.22	750	60	110	2200	128					
				6		4 to 8	1.19–1.22	750	60	110	2200	128					
				7		<5	1.19–1.22	780	60	110	2200	130					
				0	other				
				2	flame-retarded ^G	1		>24	1.19–1.22					use Table B			
						2		15 to 30	1.19–1.22				use Table B				
						3		12 to 20	1.19–1.22	640	55	100	2000	126			
						4		9 to 18	1.19–1.22	640	60	100	2100	126			
						5		6 to 13	1.19–1.22	640	60	105	2200	128			
						6		4 to 8	1.19–1.22	640	60	110	2200	128			
						7		<5	1.19–1.22	640	60	110	2200	130			
		0	other						
		3	UV ^H stabilized			1		>24	1.19–1.22					use Table B			
						2		15 to 30	1.19–1.22				use Table B				
						3		12 to 20	1.19–1.22	640	55	100	2000	124			
						4		9 to 18	1.19–1.22	750	60	105	2100	124			
						5		6 to 13	1.19–1.22	750	60	110	2100	126			
						6		4 to 8	1.19–1.22	750	60	110	2200	126			
						7		<5	1.19–1.22	750	60	110	2200	128			
				0	other				
				4	impact-modified	1		6 to 15	1.18–1.22	375 ^I	50	90	1900	121			
						0	other			
						5	FDA ^J compliant formulations	1		>24	1.19–1.22					use Table B	
								2		15 to 30	1.19–1.22				use Table B		
								3		12 to 20	1.19–1.22	640	55	100	2000	126	
								4		9 to 18	1.19–1.22	750	60	105	2100	126	
5								6 to 13	1.19–1.22	750	60	110	2200	128			
6		4 to 8	1.19–1.22					750	60	110	2200	128					
7		<5	1.19–1.22					780	60	110	2200	130					
0	other					
0	other					
02	PC copolymer-flame retarded	1	general purpose					1		>24	1.22–1.26				use Table B		
								2		15 to 30	1.22–1.26				use Table B		
								3		12 to 20	1.22–1.26	80	60	100	2100	128	
								4		9 to 18	1.22–1.26	80	60	110	2200	128	
				5				6 to 13	1.22–1.26	90	60	110	2200	130			
				6				4 to 8	1.22–1.26	90	60	110	2200	130			
				7		<5	1.22–1.26	90	60	110	2200	132					
				0	other					
				2	UV ^H stabilized	1		>24	1.22–1.26					use Table B			
						2		15 to 30	1.22–1.26				use Table B				
						3		12 to 20	1.22–1.26	80	60	100	2100	126			
						4		9 to 18	1.22–1.26	80	60	110	2200	126			
						5		6 to 13	1.22–1.26	90	60	110	2200	128			
						6		4 to 8	1.22–1.26	90	60	110	2200	130			
						7		<5	1.22–1.26	90	60	110	2200	130			
		0	other							
		0	other							
		03	PC copolymer high-heat resin			1	general purpose	1		TBD	1.18–1.22	80	63	40	1700	150	
								0	other	
								0	other	
						2	UV ^H stabilized	1		TBD	1.18–1.22	80	63	40	1700	148	
								0	other	
								0	other	
				3	impact-modified	1		TBD	use Table B	...		
						0	other			
						0	other			
				4	FDA ^J compliant formulation	1		TBD	1.18–1.22	80	63	40	1700	150			
						0	other			
						0	other			
				04	PC copolymer homopolymer intermediate heat blends	1	general purpose	1		TBD	1.18–1.22	480	65	60	1900	138	
0	other									
0	other									

TABLE Continued

Note— The values are for naturals; colors may be different.

Group	Description	Class	Description	Grade	Description ^A	Flow Rate, ^B Test Method D 1238, g/10 min	Specific Gravity, Test Method D 792	Izod Impact, ^C Test Methods D 256, J/m, min	Tensile Yield Strength ^D	Elongation at Break ^D	Flexural Modulus, ^E Test Methods D 790, MPa, min	Deflection Tempera- ture, Test Method D 648, ^F °C, min
									Test Method D 638, MPa, min	Test Method D 638, MPa, min	D 790, MPa, min	D 648, ^F °C, min
		2	UV ^H stabilized	1		TBD	1.18–1.22	480	65	60	1900	136
		0		0	other
		3	impact-modified	1		TBD	use Table B
		0		0	other
		4	FDA ^J compliant formulation	1		TBD	1.18–1.22	480	65	60	1900	138
		0	other	0	other
		0	other	0	other
05	PC copolymer low-heat standard flow	1	general purpose	1		>50	1.18–1.22	use Table B
				2		nominal 45	1.18–1.22	570	50	100	2070	104
				3		nominal 29	1.18–1.22	620	50	100	2070	106
				4		nominal 18	1.18–1.22	770	50	100	2160	107
				5		nominal 10	1.18–1.22	810	50	100	2200	108
				0	other
		2	UV ^H stabilized	1		>50	1.18–1.22	use Table B
				2		nominal 45	1.18–1.22	570	50	100	2070	102
				3		nominal 29	1.18–1.22	620	50	100	2070	104
				4		nominal 18	1.18–1.22	770	50	100	2160	105
				5		nominal 10	1.18–1.22	810	50	100	2200	106
				0	other
		3	impact-modified	0	other
		4	FDA ^J compliant formulations	1		>50	1.18–1.22	use Table B
				2		nominal 45	1.18–1.22	570	50	100	2070	104
				3		nominal 29	1.18–1.22	620	50	100	2070	106
				4		nominal 18	1.18–1.22	770	50	100	2160	107
				5		nominal 10	1.18–1.22	810	50	100	2200	108
				0	other
		5	flame-retarded ^G	1		TBD	1.18–1.22	use Table B
		0	other	0	other
		0	other	0	other
06	PC copolymer low-heat easy flow	1	general purpose	1		TBD	1.18–1.22	use Table B
		0	other	0	other
		2	UV stabilized ^H	1		TBD	1.18–1.22	use Table B
		0	other	0	other
		3	impact-modified	1		TBD	1.17–1.22	use Table B
		0	other	0	other
		4	FDA ^J compliant formulations	1		TBD	1.18–1.22	use Table B
		0	other	0	other
		5	flame-retarded ^G	1		TBD	1.18–1.22	use Table B
		0	other	0	other
		0	other	0	other
99	PC other ^I	0	other	0	other

^A All grades are listed by performance requirements.

^B Use condition 300/1.2 for Groups 01, 02, and 05. Define the conditions for other groups in the suffixes as needed.

^C Test specimens are 3.2 mm thick, with a notch radius of 0.25 mm, tested by Method A.

^D Test specimens are Type I tensile bars, 3.2 mm thick, tested at a crosshead speed of 50 mm/min.

^E Test specimens are 3.2 by 12.7 mm, tested by Method I, Procedure A (Tangent), at a crosshead speed of 1.3 mm/min and a span-to-depth ratio of 16 to 1.

^F Test specimens are 3.2 mm thick, tested at 1820 kPa, and are not annealed before testing.

^G Use suffix letter F, with the appropriate digits allowed in Classification D 4000, to define specific requirements.

^H Refer to Practices E 169 for testing procedure. Specific requirements shall be stated in the purchase order or contract.

^I Test specimens for Group 1, Class 4, Grade 1 are 6.4 mm thick with a notch radius of 0.25 mm and are tested by Method A.

^J Manufactured in compliance with Food Additive Regulation 21CFR177.1580 governing polycarbonate resins for food-contact applications..

NOTE 2—An example of this classification system is as follows: the designation PC0214 indicates:

- PC = polycarbonate as found in Terminology D 1600,
- 02 = polycarbonate copolymer-flame retarded (group),
- 1 = general purpose (class), and
- 4 = requirements given in Table PC.

4.1.1 To facilitate the specification of new, special, or recycled materials, the “other” category (0) for class or grade, or both, may be used as indicated in Table PC. The properties of these materials may be specified using Tables A, B, or R as they apply.

4.2 Reinforced, pigmented, filled, and lubricated versions of polycarbonate materials may be classified in accordance with Tables PC and A, B, or R. Table PC is used to specify basic materials, and Tables A or B are used to specify the property requirements after the addition of reinforcement, pigments, fillers, or lubricants at the nominal level indicated (see 4.2.1). Table R is used for recycled materials.