
**Textiles — Tests for colour fastness —
Part J03:
Calculation of colour differences**

Textiles — Essais de solidité des teintures —

Partie J03: Calcul des écarts de couleur

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 105-J03:2009](https://standards.iteh.ai/catalog/standards/sist/e063420a-6f28-44d8-9a96-51fd9e6aaf84/iso-105-j03-2009)

<https://standards.iteh.ai/catalog/standards/sist/e063420a-6f28-44d8-9a96-51fd9e6aaf84/iso-105-j03-2009>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 105-J03:2009

<https://standards.iteh.ai/catalog/standards/sist/e063420a-6f28-44d8-9a96-51fd9e6aaf84/iso-105-j03-2009>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Principle.....	1
3 Procedure	2
3.1 Calculation of CIELAB values	2
3.2 Calculation of CIELAB colour differences values.....	3
3.3 Calculation of the CMC colour difference, $\Delta E_{\text{cmc}(l:c)}$.....	4
4 Test report.....	5
Annex A (informative) Interpretation of results	6
Annex B (informative) Representative test data	7
Annex C (informative) Computer program for calculating colour difference	8
Bibliography.....	10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 105-J03:2009](https://standards.iteh.ai/catalog/standards/sist/e063420a-6f28-44d8-9a96-51fd9e6aaf84/iso-105-j03-2009)

<https://standards.iteh.ai/catalog/standards/sist/e063420a-6f28-44d8-9a96-51fd9e6aaf84/iso-105-j03-2009>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 105-J03 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

This second edition cancels and replaces the first edition (ISO 105-J03:1995), of which it constitutes a technical revision and incorporates ISO 105-J03:1995/Cor.1:1996 and ISO 105-J03:1995/Cor.2:2006. Subclause 3.1 has been replaced with the current CIE recommended form. The equations produce identical results, but the decimal numbers are replaced by fractions, so as not to limit precision.

ISO 105 was previously published in thirteen parts, each designated by a letter (e.g. "Part A"), with publication dates between 1978 and 1985. Each part contained a series of "sections", each designated by the respective part letter and by a two-digit serial number (e.g. "Section A01"). These sections are now being republished as separate documents, themselves designated "parts" but retaining their earlier alphanumeric designations. A complete list of these parts is given in ISO 105-A01.

Textiles — Tests for colour fastness —

Part J03: Calculation of colour differences

1 Scope

This part of ISO 105 provides a method of calculating the colour difference between two specimens of the same material, measured under the same conditions, such that the numerical value $\Delta E_{\text{cmc}}(l:c)$ for the total colour difference quantifies the extent to which the two specimens do not match. It permits the specification of a maximum value (tolerance) which depends only on the closeness of match required for a given end-use and not on the colour involved, nor on the nature of the colour difference. The method also provides a means for establishing the ratio of differences in lightness to chroma and to hue.

NOTE Annex A gives guidance on the interpretation of results. Annex B provides sample test data for use in checking computer programs. Annex C contains a sample computer program for calculating colour difference.

2 Principle

The CIE¹⁾ 1976 $L^*a^*b^*$ (CIELAB) colour space has been modified to enhance its visual uniformity when calculating the colour difference between two specimens. The modifications to CIELAB by the CMC equation provide a numerical value, ΔE_{cmc} , which describes the colour difference between a sample and a reference in a more nearly uniform colour space. This permits the use of a single-number tolerance (“acceptability tolerance” or “pass/fail tolerance”) for judging the acceptability of a colour match in which the tolerance is independent of the colour of the reference. The ellipsoid semi-axes (lS_L , cS_C and S_H) used to derive ΔE_{cmc} provide a means to interpret the three separate components of colour difference (lightness, chroma and hue) in manners suitable for a wide range of uses.

The equation for ΔE_{cmc} describes an ellipsoidal boundary (with axes in the directions of lightness, chroma and hue) centred about a reference. The agreed-upon ΔE_{cmc} acceptability tolerance describes a volume within which all specimens are acceptable matches to the reference.

The colour difference is composed of three components that comprise the differences between the reference and the specimen. These are as follows.

a) A **lightness** component that is weighted by a lightness tolerance ($\Delta L^*/lS_L$). This is represented as ΔL_{cmc} .

If the ΔL_{cmc} is positive, the specimen is lighter than the reference. If the ΔL_{cmc} is negative, the specimen is darker than the reference;

b) A **chroma** component that is weighted by the chroma tolerance ($\Delta C^*_{ab}/cS_C$). This is represented as ΔC_{cmc} .

If the ΔC_{cmc} is positive, the specimen is more chromatic than the reference. If the ΔC_{cmc} is negative, the specimen is less chromatic than the reference;

1) Commission Internationale de l'Éclairage, Central Bureau, Kegelgasse 27, A-1030 Vienna, Austria.

c) A hue component that is weighted by the hue tolerance ($\Delta H_{ab}^*/S_H$). This is represented as ΔH_{cmc} .

If the ΔH_{cmc} is positive, the hue difference of the specimen is anti-clockwise from the reference in the CIELAB a^*, b^* diagram. If the ΔH_{cmc} is negative, the hue difference of the specimen is clockwise from the reference in the CIELAB a^*, b^* diagram.

3 Procedure

3.1 Calculation of CIELAB values

Calculate the CIELAB $L^*, a^*, b^*, C_{ab}^*, h_{ab}$ values from the X, Y, Z tristimulus values for both the reference and specimen as follows:

$$L^* = 116 \left[f(Q_y) \right] - 16$$

$$a^* = 500 \left[f(Q_x) - f(Q_y) \right]$$

$$b^* = 200 \left[f(Q_y) - f(Q_z) \right]$$

where

$$Q_x = (X/X_n); Q_y = (Y/Y_n); Q_z = (Z/Z_n)$$

and

$$f(Q_i) = (Q_i)^{1/3} \text{ if } Q_i > (6/29)^3$$

else

$$f(Q_i) = (841/108) Q_i + 4/29 \text{ if } Q_i \leq (6/29)^3$$

where

i varies as $X, Y,$ and Z

$$C_{ab}^* = (a^{*2} + b^{*2})^{1/2}$$

$h_{ab} = \arctan(b^*/a^*)$ expressed on a 0° to 360° scale with the a^* positive axis being 0° and the b^* positive axis at 90° .

For these equations, X_n, Y_n and Z_n are the tristimulus values of the illuminant/observer combination in which it is desired to calculate CMC($l:c$) colour differences. The preferred illuminant/observer combination is D65/10°. Table 1 gives the values for this and five other combinations.

Table 1 — Tristimulus values for six illuminant/observer combinations

Illuminant/observer combinations	Tristimulus values		
	X_n	Y_n	Z_n
D65/10°	94,811	100,00	107,304
D65/2°	95,047	100,00	108,883
C/10°	97,285	100,00	116,145
C/2°	98,074	100,00	118,232
A/10°	111,144	100,00	35,200
A/2°	109,850	100,00	35,585

3.2 Calculation of CIELAB colour differences values

Calculate the CIELAB colour differences ΔL^* , Δa^* , Δb^* , ΔC^*_{ab} , ΔE^*_{ab} , ΔH^*_{ab} , using the following equations, in which the subscripts R and S refer respectively to the reference and specimen CIELAB values:

$$\Delta L^* = L^*_S - L^*_R;$$

$$\Delta a^* = a^*_S - a^*_R;$$

$$\Delta b^* = b^*_S - b^*_R;$$

$$\Delta C^*_{ab} = C^*_{ab,S} - C^*_{ab,R};$$

$$\Delta E^*_{ab} = \left[(\Delta L^*)^2 + (\Delta a^*)^2 + (\Delta b^*)^2 \right]^{1/2}$$

$$\Delta H^*_{ab} = pq \left[(\Delta E^*_{ab})^2 - (\Delta L^*)^2 - (\Delta C^*_{ab})^2 \right]^{1/2}$$

where

$$p = 1 \text{ if } m \geq 0$$

or

$$p = -1 \text{ if } m < 0$$

$$\text{and } q = 1 \text{ if } |m| \leq 180$$

or

$$q = -1 \text{ if } |m| > 180$$

where $m = h_{ab,S} - h_{ab,R}$

in which [...] indicates that the *positive* value is to be used regardless of the sign of the expression between the two lines.

or the equivalent

$$\Delta H^*_{ab} = t \left[2 \left(C^*_{ab,S} C^*_{ab,R} - a^*_S a^*_R - b^*_S b^*_R \right) \right]^{1/2}$$

where

$$t = 1 \quad \text{if } a^*_S b^*_R \leq a^*_R b^*_S$$

or

$$t = -1 \quad \text{if } a^*_S b^*_R > a^*_R b^*_S$$

3.3 Calculation of the CMC colour difference, $\Delta E_{cmc}(l:c)$

3.3.1 The CMC colour difference is obtained from the following equation:

$$\Delta E_{cmc}(l:c) = \left[(\Delta L^* / S_L)^2 + (\Delta C^*_{ab} / c S_C)^2 + (\Delta H^*_{ab} / S_H)^2 \right]^{1/2}$$

Calculate the ellipsoid semi-axes from the L^*_R , $C^*_{ab,R}$ and the $h_{ab,R}$ of the reference as follows:

$$S_L = 0,040\,975 L^*_R / (1 + 0,017\,65 L^*_R) \text{ if } L^*_R \geq 16$$

or

$$S_L = 0,511 \text{ if } L^*_R < 16;$$

$$S_C = \left[0,063\,8 C^*_{ab,R} / (1 + 0,013\,1 C^*_{ab,R}) \right] + 0,638;$$

$$S_H = (FT + 1 - F) S_C$$

where

$$F = \left\{ \left(C^*_{ab,R} \right)^4 / \left[\left(C^*_{ab,R} \right)^4 + 1\,900 \right] \right\}^{1/2};$$

$$T = 0,36 + \left| 0,4 \cos(35 + h_{ab,R}) \right| \text{ if } h_{ab,R} \geq 345^\circ \text{ or } h_{ab,R} \leq 164^\circ$$

or

$$T = 0,56 + \left| 0,2 \cos(168 + h_{ab,R}) \right| \text{ if } 164^\circ < h_{ab,R} < 345^\circ.$$

3.3.2 The value of l is usually set to 2,0. The value of c shall always remain at 1,0. This fixes the ratio of the three semi-axes to best correlate with visual assessment of typical textile samples. Other values of l may be required in cases where the surface characteristics significantly differ from those of flat textiles.

4 Test report

The test report shall include the following information:

- a) the number and year of publication of this part of ISO 105, i.e. ISO 105-J03:2009;
- b) all details necessary for complete identification of the sample and reference specimen(s) tested;
- c) identification of the spectrophotometer or colorimeter, including the CIE geometry type, with which the input data was obtained;
- d) the $\Delta E_{\text{cmc}}(l:c)$ value(s) of the test specimen(s);
- e) the values of l and c [e.g. CMC(2:1)];
- f) the illuminant and observer conditions used in the calculations (e.g. D65/10°);
- g) if applicable, the acceptability tolerance used in making pass/fail judgements (see Annex A);
- h) if required, the CMC component colour differences, ΔL_{cmc} , ΔC_{cmc} and ΔH_{cmc} ;
- i) if required, the CIELAB L^* , a^* , b^* , C_{ab}^* , and h_{ab} values for references and test specimen(s) and the associated ΔL^* , Δa^* , Δb^* , ΔC_{ab}^* and ΔH_{ab}^* values;
- j) the date of the test report.

iTech STANDARD PREVIEW
(standards.iteh.ai)

ISO 105-J03:2009

<https://standards.iteh.ai/catalog/standards/sist/e063420a-6f28-44d8-9a96-51fd9e6aaf84/iso-105-j03-2009>