

---

---

**Aluminium oxide primarily used for  
production of aluminium — Method for  
calculating the  $\text{Al}_2\text{O}_3$  content of smelter-  
grade alumina**

*Oxyde d'aluminium principalement utilisé pour la production  
d'aluminium — Méthode de calcul de la teneur en  $\text{Al}_2\text{O}_3$  de l'alumine  
pour électrolyse*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 12315:2010

<https://standards.iteh.ai/catalog/standards/sist/8427562e-86b1-4b10-8716-8cf81e1dde5e/iso-12315-2010>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 12315:2010

<https://standards.iteh.ai/catalog/standards/sist/8427562e-86b1-4b10-8716-8cf81e1dde5e/iso-12315-2010>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 12315 was prepared by Technical Committee ISO/TC 226, *Materials for the production of primary aluminium*.

This International Standard is based on AS 2879.11, *Alumina — Guide to reporting Al<sub>2</sub>O<sub>3</sub> content of smelter-grade alumina*, prepared by the Standards Australia Committee MN/9, *Alumina and Materials Used in Aluminium Production*.

ISO 12315:2010

<https://standards.iteh.ai/catalog/standards/sist/8427562e-86b1-4b10-8716-8cf81e1dde5e/iso-12315-2010>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 12315:2010

<https://standards.iteh.ai/catalog/standards/sist/8427562e-86b1-4b10-8716-8cf81e1dde5e/iso-12315-2010>

# Aluminium oxide primarily used for production of aluminium — Method for calculating the $\text{Al}_2\text{O}_3$ content of smelter-grade alumina

## 1 Scope

This International Standard describes methods for calculating and reporting the  $\text{Al}_2\text{O}_3$  content of smelter-grade alumina, on either a dry or ignited basis, from the results of the determinations in accordance with ISO 806 and AS 2879.7.

NOTE Typical values of a smelter-grade alumina, if reported on a dry basis, would be in the range of 98,5 % to 98,9 % and, if reported on an ignited basis, would be in the range of 99,4 % to 99,7 % mass fraction.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 806, *Aluminium oxide primarily used for the production of aluminium — Determination of loss of mass at 300 °C and 1 000 °C* <https://standards.iteh.ai/catalog/standards/sist/8427562e-86b1-4b10-8716-8cf81e1dde5e/iso-12315-2010>

AS 2879.7, *Alumina — Determination of trace elements — Wavelength dispersive X-ray fluorescence spectrometric method*<sup>1)</sup>

## 3 Principle

From the determination of trace elements in accordance with AS 2879.7, where the elements are determined on an undried (“as-received” basis) by X-ray fluorescence spectrometry analysis, and the loss of mass at 300 °C and 1 000 °C is determined in accordance with ISO 806, the proportion by mass is calculated and expressed as a percentage.

The  $\text{Al}_2\text{O}_3$  content of alumina, expressed as a percentage (mass fraction), is calculated by subtracting the percentage of trace elements from the total, expressed as 100 %. The  $\text{Al}_2\text{O}_3$  content of alumina can be expressed on a dried basis or an ignited basis.

The dried basis method eliminates the effect of loss of mass after heating to 300 °C, under defined conditions. The ignited basis method eliminates the loss of mass after heating to 1 000 °C, under defined conditions.

Sulfur (S) shall be determined and included as its oxide,  $\text{SO}_2$ , in the sum of impurities term,  $\Sigma I$ , if the alumina is derived from heavy-fuel-oil calcination. Sulfur from this source is largely present as adsorbed  $\text{SO}_2$ . There is no standard method for determining sulfur in alumina.

---

1) To be replaced by ISO 23201, *Aluminium oxide primarily used for production of aluminium — Determination of trace elements — Wavelength dispersive X-ray fluorescence spectrometric method* (under preparation).

NOTE 1 By industry convention, these mass losses are often referred to as “moisture on ignition (MOI)” and “loss on ignition (LOI)”, respectively.

NOTE 2 When sulfur is determined, it is traditionally reported as SO<sub>3</sub>, not SO<sub>2</sub>.

#### 4 Procedures

The determinations shall be as follows.

- a) Determine the impurities according to AS 2879.7.
- b) Determine the loss of mass at 300 °C (moisture content, MOI) and loss of mass on ignition at 1 000 °C (LOI) (on a dry or “as-received” basis) in accordance with ISO 806.
- c) Determine the sulfur, reported as SO<sub>3</sub>, if the alumina is derived from heavy-fuel-oil calcination.

#### 5 Calculations and expression of results

Calculate and express the results as follows:

- a) Al<sub>2</sub>O<sub>3</sub> content determined on an ignited at 1 000 °C basis:

- 1) for loss on ignition of alumina determined on a dried at 300 °C basis, the Al<sub>2</sub>O<sub>3</sub> content, expressed as a percentage, is calculated using Equation (1).

$$w_{Al_2O_3, 1000,d} = 100 - \frac{100}{100 - w_{300} - w_{\Delta 1000,d} + \frac{w_{\Delta 1000,d} \times w_{300}}{100}} \times (\Sigma I) \tag{1}$$

where

- $w_{Al_2O_3, 1000,d}$  is the Al<sub>2</sub>O<sub>3</sub> content determined on an ignited at 1 000 °C basis, expressed as a percentage;
- $w_{300}$  is the loss of mass at 300 °C, expressed as a percentage;
- $w_{\Delta 1000,d}$  is the loss of mass on ignition (300 °C to 1 000 °C), expressed on a dried at 300 °C basis;
- $\Sigma I$  is the sum of trace elements determined in accordance with AS 2879.7. SO<sub>3</sub> shall be included in this sum, if required.

- 2) for loss on ignition of alumina determined on an “as-received” basis calculate the Al<sub>2</sub>O<sub>3</sub> content, expressed as a percentage, using Equation (2).

$$w_{Al_2O_3, 1000,ar} = 100 - \frac{100}{(100 - w_{300} - w_{\Delta 1000,ar})} \times (\Sigma I) \tag{2}$$

where

- $w_{Al_2O_3, 1000,ar}$  is the Al<sub>2</sub>O<sub>3</sub> content determined on an ignited at 1 000 °C basis, expressed as a percentage;
- $w_{300}$  is the loss of mass at 300 °C, expressed as a percentage;

- $w_{\Delta 1\,000,ar}$  is the loss of mass on ignition (300 °C to 1 000 °C) expressed on an “as-received” basis;
- $\Sigma I$  is the sum of the trace-element oxides determined in accordance with AS 2879.7. SO<sub>3</sub> shall be included in this sum, if required.

b) Al<sub>2</sub>O<sub>3</sub> content determined on a dried at 300 °C basis:

- 1) for loss on ignition of alumina determined on a dried at 300 °C basis, the Al<sub>2</sub>O<sub>3</sub> content, expressed as a percentage, is calculated using Equation (3).

$$w_{Al_2O_3, 300,d} = 100 - w_{\Delta 1\,000,d} - \frac{100}{(100 - w_{300})} \times \Sigma I \quad (3)$$

where

- $w_{Al_2O_3, 300,d}$  is the Al<sub>2</sub>O<sub>3</sub> content determined on a dried at 300 °C basis, expressed as a percentage;
- $w_{300}$  is the loss of mass at 300 °C, expressed as a percentage;
- $w_{\Delta 1\,000,d}$  is the loss of mass on ignition (300 °C to 1 000 °C) on a dried basis;
- $\Sigma I$  is the sum of the trace-element oxides determined in accordance with AS 2879.7. SO<sub>3</sub> shall be included in this sum, if required.

- 2) for loss on ignition of alumina determined on an “as-received” basis calculate the Al<sub>2</sub>O<sub>3</sub> content, expressed as a percentage, is calculated using Equation (4).

$$w_{Al_2O_3, 300,ar} = 100 - \frac{100}{(100 - w_{300})} \times (w_{\Delta 1\,000,ar} + \Sigma I) \quad (4)$$

where

- $w_{Al_2O_3, 300,ar}$  is the Al<sub>2</sub>O<sub>3</sub> content determined on a dried at 300 °C basis, expressed as a percentage;
- $w_{300}$  is the loss of mass at 300 °C, expressed as a percentage;
- $w_{\Delta 1\,000,ar}$  is the loss of mass on ignition (300 °C to 1 000 °C), expressed on an “as-received” basis;
- $\Sigma I$  is the sum of the trace-element oxides determined in accordance with AS 2879.7. SO<sub>3</sub> shall be included in this sum, if required.

## 6 Test report

The test report should include the following information:

- a reference to this International Standard;
- the date on which the sample was taken;
- the date of the determinations and calculations;
- details necessary for the complete identification of the material tested;

## ISO 12315:2010(E)

- e) whether the  $\text{Al}_2\text{O}_3$  content was determined and calculated on a dried at 300 °C or ignited at 1 000 °C basis;
- f) the  $\text{Al}_2\text{O}_3$  content, recorded to the nearest first decimal place.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 12315:2010

<https://standards.iteh.ai/catalog/standards/sist/8427562e-86b1-4b10-8716-8cf81e1dde5e/iso-12315-2010>



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 12315:2010

<https://standards.iteh.ai/catalog/standards/sist/8427562e-86b1-4b10-8716-8cf81e1dde5e/iso-12315-2010>