
**Leather — Determination of water
resistance of flexible leather —**

Part 1:
**Repeated linear compression
(penetrometer)**

*Cuir — Détermination de l'imperméabilité à l'eau des cuirs souples —
Partie 1: Compression linéaire répétée (pénétromètre)*

*iteh Standards
(<https://standards.iteh.ai>)
Document Preview*

[ISO 5403-1:2011](https://standards.iteh.ai/catalog/standards/iso/adae26f1-2b6c-4b69-979a-1f080453b019/iso-5403-1-2011)

<https://standards.iteh.ai/catalog/standards/iso/adae26f1-2b6c-4b69-979a-1f080453b019/iso-5403-1-2011>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 5403-1:2011](https://standards.iteh.ai/catalog/standards/iso/adae26f1-2b6c-4b69-979a-1f080453b019/iso-5403-1-2011)

<https://standards.iteh.ai/catalog/standards/iso/adae26f1-2b6c-4b69-979a-1f080453b019/iso-5403-1-2011>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 5403-1 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, in collaboration with the Physical Test Commission of the International Union of Leather Technologists and Chemists Societies (IUP Commission, IULTCS), in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

This first edition of ISO 5403-1 cancels and replaces ISO 5403:2002, which has been technically revised. Subclause 5.3 has been revised and the formula in 7.2 has been corrected. The main reason for revision was to align part 1 with part 2 and editorial changes have therefore also been made.

ISO 5403 consists of the following parts, under the general title *Leather — Determination of water resistance of flexible leather*:

- *Part 1: Repeated linear compression (penetrometer)*
- *Part 2: Repeated angular compression (Maeser)*

Leather — Determination of water resistance of flexible leather —

Part 1: Repeated linear compression (penetrometer)

1 Scope

This part of ISO 5403 specifies a method for determining the dynamic water resistance of leather by means of repeated linear compression. It is applicable to all flexible leathers but is particularly suitable for leathers intended for footwear applications.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 2419, *Leather — Physical and mechanical tests — Sample preparation and conditioning*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*

3 Principle

A test piece is formed into the shape of a trough and flexed while partially immersed in water. The time taken for water to penetrate through the test piece is measured. The method also allows for the percentage mass of the water absorbed and the mass of the water transmitted through the test piece to be determined.

NOTE This test method uses compression-type flexing, whereas the test method of ISO 5403-2 for water resistance imparts folding-type flexing on the leather specimens. Given the two completely different flexing actions, it is not possible to compare the results obtained from the two test methods.

4 Apparatus, reagents and materials

Usual laboratory apparatus is required and, in particular, the following.

4.1 Test machine, including the parts described in 4.1.1 to 4.1.3. (See also Annex A.)

4.1.1 One or more pairs of cylinders, 30,0 mm ± 0,5 mm in diameter, made of inert rigid material, mounted with their axes horizontal and co-axial. One cylinder shall be fixed and the other moveable along the direction of its axis such that the maximum separation of the cylinders is 40,0 mm ± 0,5 mm.

4.1.2 Electric motor, which drives the moveable cylinder backwards and forwards along its axis with a crank motion of 50 cycles/min \pm 5 cycles/min and an amplitude of 1,0 mm \pm 0,1 mm, 1,50 mm \pm 0,15 mm, 2,0 mm \pm 0,2 mm or 3,0 mm \pm 0,3 mm about its mean position.

NOTE The four amplitudes of the crank motion are such that the test piece is compressed by 5 %, 7,5 %, 10 % or 15 % respectively when the cylinders approach one another.

4.1.3 Tank, made from non-corroding material, holding distilled or deionized water, in which the test piece can be partially immersed.

The test machine may also include an electrical circuit that indicates when water has penetrated through the test piece.

4.2 Ring-shaped clamps, with internal diameter adjustable between 30 mm and 40 mm.

4.3 Press knife, the inner wall of which is a rectangle of 60 mm \pm 1 mm \times 75 mm \pm 1 mm, conforming to the requirements of ISO 2419.

4.4 Distilled or deionized water, of grade 3 in accordance with ISO 3696:1987.

4.5 Balance, weighing to 0,001 g.

4.6 Clock, reading to 1 s.

4.7 Abrasive paper, grade P180, as defined in the P-series grit-size standard published by the Federation of European Producers of Abrasive Products, cut into rectangles of 65 mm \pm 5 mm \times 45 mm \pm 5 mm, fixed to a flat, rigid base of the same size and weighted to give a total mass of 1,0 kg \pm 0,1 kg. A fresh piece of abrasive paper shall be used for each test.

4.8 Absorbent cloth, cut into rectangles of 120 mm \pm 5 mm \times 40 mm \pm 5 mm, machine washed prior to first use following the cycle recommended by the cloth manufacturer.

A suitable cloth is terry towelling (frotté) in 100 % cotton and weighing about 300 g/m². The absorbency of this material might not be optimal when new, and therefore the cloths shall be washed before the first use.

4.9 Auxiliary apparatus, to determine the stiffness of the test piece, consisting of one pair of cylinders of 30,0 mm \pm 0,5 mm in diameter mounted with their axes horizontal and co-axial, a means of moving the cylinders together, a means of measuring the reduction in distance between the cylinders, to the nearest 0,1 mm, and a means of measuring the force exerted along the axes of the cylinder to the nearest 5 N.

5 Sampling and sample preparation

5.1 Sample in accordance with ISO 2418. Cut four test pieces by applying the press knife (4.3) to the grain (or to the outer surface when worn). Cut two test pieces with the longer side parallel to the backbone and two test pieces with the longer side perpendicular to the backbone.

If there is a requirement for more than two hides or skins to be tested in one batch, then only one test piece in each direction need be taken from each hide or skin, provided that the overall total is not less than two test pieces in each direction.

5.2 Prepare the four test pieces using the following method.

Lightly buff the grain (or the outer surface when worn) by placing the test-piece grain (or the outer surface when worn) upwards on a flat surface. Place the weighted abrasive paper (4.7) on the test piece and move the abrasive paper ten times backwards and forwards along the full length of the test piece without applying any more downward force than is applied by the weighted abrasive.

NOTE In some situations, it might be more appropriate to flex a sample for 20 000 cycles using the method and apparatus specified in ISO 5402-1.