

SLOVENSKI STANDARD

SIST ISO 2137:2008

01-april-2008

Nadomešča:
SIST ISO 2137:1996

Naftni proizvodi in maziva - Določevanje penetracije s stožcem za mazalne masti in vazeline

Petroleum products and lubricants - Determination of cone penetration of lubricating greases and petrolatum

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 2137:2008](https://standards.iteh.ai/catalog/standards/sist/a9c924a6-2d1f-470d-8537-b1574/iso-2137-2008)

<https://standards.iteh.ai/catalog/standards/sist/a9c924a6-2d1f-470d-8537-b1574/iso-2137-2008>

Ta slovenski standard je istoveten z: ISO 2137:2007

ICS:

75.080	Naftni proizvodi na splošno	Petroleum products in general
75.100	Maziva	Lubricants, industrial oils and related products

SIST ISO 2137:2008

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 2137:2008

<https://standards.iteh.ai/catalog/standards/sist/a9c924a6-2d1f-470d-8537-5097f06b1574/sist-iso-2137-2008>

INTERNATIONAL STANDARD

ISO
2137

Third edition
2007-12-01

Petroleum products and lubricants — Determination of cone penetration of lubricating greases and petrolatum

*Produits pétroliers et lubrifiants — Détermination de la pénétrabilité au
cône des graisses lubrifiantes et des pétrolatums*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 2137:2008](https://standards.iteh.ai/catalog/standards/sist/a9c924a6-2d1f-470d-8537-5097f06b1574/sist-iso-2137-2008)

[https://standards.iteh.ai/catalog/standards/sist/a9c924a6-2d1f-470d-8537-
5097f06b1574/sist-iso-2137-2008](https://standards.iteh.ai/catalog/standards/sist/a9c924a6-2d1f-470d-8537-5097f06b1574/sist-iso-2137-2008)



Reference number
ISO 2137:2007(E)

© ISO 2007

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 2137:2008

<https://standards.iteh.ai/catalog/standards/sist/a9c924a6-2d1f-470d-8537-5097f06b1574/sist-iso-2137-2008>

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	2
3 Terms and definitions	2
4 Principle.....	2
5 Apparatus	3
6 Sampling.....	5
7 Procedures for determining the cone penetration of lubricating grease — Full-scale methods	14
7.1 Procedure for unworked penetration.....	14
7.2 Procedure for worked penetration	15
7.3 Procedure for prolonged worked penetration	16
7.4 Procedure for block penetration	16
8 Procedures for determining the cone penetration of lubricating grease — Half- and quarter-scale cone method.....	17
8.1 General.....	17
8.2 Procedure for unworked penetration.....	17
8.3 Procedure for worked penetration.....	18
9 Procedure for determining the cone penetration of petrolatum.....	18
9.1 Preparation of the test portion	18
9.2 Penetration measurement.....	19
10 Calculation.....	19
10.1 Calculation of full-scale penetration.....	19
10.2 Conversion to full-scale penetration for the half- and quarter-scale cones.....	19
11 Expression of results	19
12 Precision.....	20
12.1 General.....	20
12.2 Repeatability.....	20
12.3 Reproducibility.....	20
13 Test report	21
Bibliography	22

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2137 was prepared by Technical Committee ISO/TC 28, *Petroleum products and lubricants*.

This third edition cancels and replaces the second edition (ISO 2137:1985), which has been technically revised.

ITEH STANDARD PREVIEW
(standards.iteh.ai)
SIST ISO 2137:2008
<https://standards.iteh.ai/catalog/standards/sist/a9c924a6-2d1f-470d-8537-5097f06b1574/sist-iso-2137-2008>

Introduction

ISO 2137 was first published in 1972. A second edition was issued in 1985. This third edition cancels and replaces the first two editions, of which it constitutes a technical revision. The revision mainly concerns the dimensional tolerances of the various cones, to better fit with what is available from laboratory equipment suppliers. This revision is necessary because of all the quality plans and data integrity programmes established by numerous laboratories to comply with the various ISO quality standards. These quality standards require the total compliance of the cones with the dimensions indicated in ISO 2137. Unfortunately, most of the cones available do not conform to ISO 2137:1985 and users were obliged to establish waivers, which was difficult to justify to quality auditors. In the present edition of ISO 2137, the dimensional tolerances have been enlarged to allow most of the cones to fulfil the new requirements. A round-robin test has been performed with cones conforming to these new requirements and has demonstrated that the precision of the method is not altered by this change in the tolerances. Tolerances have been retained only on the characteristics where it has been established that they have a direct impact on the penetration determination, i.e. tip angle, tip height, tip top thickness, tip base diameter, cone angle, total mass of cone plus movable attachments.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 2137:2008](https://standards.iteh.ai/catalog/standards/sist/a9c924a6-2d1f-470d-8537-5097f06b1574/sist-iso-2137-2008)

<https://standards.iteh.ai/catalog/standards/sist/a9c924a6-2d1f-470d-8537-5097f06b1574/sist-iso-2137-2008>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 2137:2008

<https://standards.iteh.ai/catalog/standards/sist/a9c924a6-2d1f-470d-8537-5097f06b1574/sist-iso-2137-2008>

Petroleum products and lubricants — Determination of cone penetration of lubricating greases and petrolatum

WARNING — The use of this International Standard can involve hazardous materials, operations and equipment. This International Standard does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this International Standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard specifies several methods for the empirical estimation of the consistency of lubricating greases and petrolatum by measuring the penetration of a standardized cone.

The National Lubricating Grease Institute (NLGI) classifies greases according to their consistency, as measured by the 60 strokes worked penetration. The NLGI classification includes nine consistency numbers or grades, each grade corresponding to a given range of worked penetration. The NLGI classification is given in ISO 6743-99.

Clause 7 of this International Standard specifies four procedures for determining the consistency of lubricating greases by measuring the penetration of a full-scale cone. These procedures cover the measurement of unworked, worked, prolonged worked, and block penetrations. Penetrations up to 500 units can be measured.

Clause 8 of this International Standard specifies methods for determining the consistency of lubricating greases when only small samples are available, by the use of cones a half-scale or quarter-scale of that used in Clause 7. The methods are applicable to greases having penetrations of 175 units to 385 units with the full-scale cone and are intended for use only if the size of the test sample prevents the use of cones described in Clause 7. They are not intended to replace the full-scale penetration as described in Clause 7, although a conversion to full-scale penetration is given in 10.2. See 8.1 for the limitations on the use of one-quarter-scale cones due to the poor precision.

NOTE 1 Unworked penetrations do not generally represent the consistency of greases in use as effectively as do worked penetrations. The latter are usually preferred for inspecting lubricating greases.

NOTE 2 Penetration of block greases can be obtained on those products that are sufficiently hard to hold their shape. These greases generally have penetrations below 85 units.

Clause 9 of this International Standard specifies a method for the determination of the consistency of petrolatum by measurement of the penetration of a full-scale cone, having penetrations up to 300 units. This method can also be used to estimate the consistency of slack waxes.

ISO 2137:2007(E)

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ASTM D 4057, *Standard Practice for Manual Sampling of Petroleum and Petroleum Products*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

cone penetration

distance that a standardized cone penetrates into a test portion under standardized conditions of load, time, and temperature

NOTE 1 The cone penetration is expressed in units of 0,1 mm.

NOTE 2 Adapted from ISO 1998-2:1998, 2.80.001.

3.2

working

subjecting a lubricating grease to the shearing action of a grease worker

3.3

unworked penetration

cone penetration of a test portion that has received only minimum disturbance in transfer from the sample container to the cup of the grease worker

[SIST ISO 2137:2008](https://standards.iteh.ai/catalog/standards/sist/a9c924a6-2d1f-470d-8537-5097f06b1574/sist-iso-2137-2008)

<https://standards.iteh.ai/catalog/standards/sist/a9c924a6-2d1f-470d-8537-5097f06b1574/sist-iso-2137-2008>

3.4

worked penetration

cone penetration of a test portion after it has been subjected to a defined number of strokes in a grease worker

3.5

prolonged worked penetration

cone penetration of a test portion which has been worked more than the defined number of strokes in worked penetration (see 3.4)

3.6

block penetration

cone penetration determined on a test portion which is sufficiently hard to hold its shape without a container

4 Principle

The cone penetration of lubricating grease is determined at 25 °C by releasing the cone assembly from the penetrometer and allowing the cone to drop for 5 s, and measuring the extent of the penetration.

Unworked penetrations are determined on test portions transferred with a minimum of disturbance to a container suitable for test purposes.

Worked penetrations are determined immediately after working the test portion for 60 double strokes in a standard grease worker.

Prolonged worked penetrations are determined on test portions worked more than 60 double strokes.

Block penetrations are determined on a freshly prepared face of a cube cut from a block of grease with a standard cutter.

The cone penetration of petrolatum is determined by first melting and cooling a test sample under specified conditions, and then measuring the penetration as for lubricating grease.

5 Apparatus

5.1 Penetrometer, similar to that shown in Figure 1, capable of measuring, in tenths of a millimetre, the penetration of a cone in a material.

The cone assembly or the table of the penetrometer shall be adjustable to enable accurate placement of the tip of the cone on the level surface of the material while maintaining a “zero” reading on the indicator. The cone shall fall, when released, without appreciable friction for at least 62 mm. The tip of the cone shall not hit the bottom of the sample container. The instrument shall be provided with level jig screws and a spirit level to maintain the cone shaft in a vertical position.

NOTE The measurement of the penetration depth is performed using either mechanical devices (mechanical indicator) or electronic devices (digital indicator).

5.2 Cones

5.2.1 Full-scale cone, consisting of a conical body of magnesium or other suitable material with a detachable, hardened steel tip.

Dimensions and tolerances shall be as shown in Figure 2. The total mass of the cone shall be $102,50 \text{ g} \pm 0,05 \text{ g}$ and that of its movable attachments shall be $47,50 \text{ g} \pm 0,05 \text{ g}$. The attachments consist of a rigid shaft having a stop at its upper end and a suitable means at its lower end for engaging the cone. The interior construction may be modified to achieve the specified mass, provided that the general contour and mass distribution are not altered. The outer surface shall be polished to a very smooth finish.

NOTE For penetrations up to 400 units, the optional cone as shown in Figure 3 can be used.

5.2.2 One-half-scale cone and shaft, made of steel, stainless steel or brass with a hardened steel tip of 45 Rockwell C hardness to 50 Rockwell C hardness, and constructed to conform to the dimensions and tolerances shown in Figure 4.

The shaft may be made of stainless steel. The total mass of the cone and its movable attachments shall be $37,50 \text{ g} \pm 0,05 \text{ g}$. The mass of the cone shall be $22,500 \text{ g} \pm 0,025 \text{ g}$. The mass of the movable attachments shall be $15,000 \text{ g} \pm 0,025 \text{ g}$.

5.2.3 One-quarter-scale cone and shaft, consisting of a conical body of plastics or other low-density material with a hardened steel tip of 45 Rockwell C hardness to 50 Rockwell C hardness, and constructed to conform to the dimensions and tolerances shown in Figure 5.

The shaft may be constructed of magnesium alloy. The total mass of the cone and its movable attachments shall be $9,380 \text{ g} \pm 0,025 \text{ g}$. The total mass of the cone and its movable attachments may be adjusted by adding small shot to the cavity of the shaft.

5.3 Grease workers

5.3.1 Full-scale grease worker, conforming to the dimensions shown in Figure 6.

The sizes of non-dimensioned parts are not critical and may be varied according to individual requirements. Other methods of fastening the cover and securing the worker may be used. The grease worker may be constructed for either manual or mechanical operation. The design shall be such that a rate of 60 strokes per minute ± 10 strokes per minute, with a minimum length of 63 mm, can be maintained. A suitable thermometer, standardized at 25°C , shall be provided for insertion through the vent valve.

ISO 2137:2007(E)

5.3.2 One-half-scale grease worker, conforming to the dimensions given in Figure 7.

Other methods of fastening the cover and securing the worker may be used. The worker may be constructed for either manual or mechanical operation. The design shall be such that a rate of 60 strokes per minute ± 10 strokes per minute, with a minimum length of 35 mm, can be maintained.

5.3.3 One-quarter-scale grease worker, conforming to the dimensions given in Figure 8.

Other methods of fastening the cover and securing the worker may be used. The worker may be constructed for either manual or mechanical operation. The design shall be such that a rate of 60 strokes per minute ± 10 strokes per minute, with a minimum length of 14 mm, can be maintained.

5.3.4 Overflow-ring (optional), conforming in principle to the illustration shown in Figure 6.

This is a useful aid for returning displaced grease to the grease worker cup. The overflow ring shall be positioned at least 13 mm below the rim of the cup while making a penetration measurement. A rim 13 mm high is helpful.

5.4 Grease cutter, having a sharp, rigidly mounted, bevelled blade, essentially as shown in Figure 9.

It is necessary that the blade be straight and sharpened as shown.

5.5 Water bath, capable of being maintained at $25,0\text{ }^{\circ}\text{C} \pm 0,5\text{ }^{\circ}\text{C}$ and holding the assembled grease worker.

If the bath is to be used for samples for unworked penetrations, a means shall be provided for protecting the grease surface from water. A cover shall also be provided to maintain the air temperature above the sample at $25\text{ }^{\circ}\text{C}$.

An air bath, maintained at $25,0\text{ }^{\circ}\text{C} \pm 0,5\text{ }^{\circ}\text{C}$, is required for determining block penetration; a tightly sealed container placed in the water bath will suffice.

NOTE A constant-temperature test room or an air bath can be used instead of a water bath.

5.6 Thermometer, calibrated at $25\text{ }^{\circ}\text{C}$, for the water bath or air bath.**5.7 Oven**, capable of maintaining a temperature of $85\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$, for melting the petrolatum samples.**5.8 Spatula**, corrosion-resistant, square-ended, with a stiff blade approximately 32 mm wide and at least 150 mm long; for tests with half- and quarter-scale cones, the width should be approximately 13 mm.**5.9 Timer**, graduated in 0,1 s.**5.10 Test-portion containers** (for petrolatum), cylindrical, having a flat bottom $100\text{ mm} \pm 5\text{ mm}$ in diameter and 65 mm or more in depth, constructed of metal at least 1,6 mm thick and, if necessary, each provided with a well-fitting watertight cover (see 9.1.3).

Containers of the "ointment box" type having somewhat flexible sides should not be used, for these permit slight working of the petrolatum, due to flexing of the sides in handling.