



Designation: E1771 – 07

Standard Test Method for Determination of Copper in Anode and Blister Copper¹

This standard is issued under the fixed designation E1771; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This test method describes the electrolytic determination of copper in commercial anode (99.0 to 99.8%) and blister copper (92.0 to 98.0 %).

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific hazards statements are given in Section 9.

2. Referenced Documents

2.1 *ASTM Standards:*²

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E53 Test Method for Determination of Copper in Unalloyed Copper by Gravimetry

E135 Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials

E255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition

E478 Test Methods for Chemical Analysis of Copper Alloys

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Terminology

3.1 *Definitions*—For definitions and terms used in this test method, refer to Terminology E135.

4. Summary of Test Method

4.1 After dissolution of the sample, the solution is evaporated to dryness and fumes expelled by heat. The salt is

dissolved in nitric acid, the solution is filtered, the acidity is adjusted, and the copper is electrolytically plated and weighed as the metal.

5. Significance and Use

5.1 This test method for the determination of copper in anode (99.0 to 99.8 %) and blister copper (92.0 to 98.0 %) is primarily intended as a referee method, to test such materials for compliance with compositional specifications. It is assumed that users of this test method will be trained analysts capable of performing common laboratory procedures skillfully and safely. It is expected that work will be performed in a properly equipped laboratory.

5.2 This test method is intended to determine the copper content of commercial anode and blister copper. Those elements that interfere are removed by precipitation or volatilization, or both. Copper is electrodeposited as the metal and weighed.

5.3 This method will also be found useful for the electrolytic determination of copper in some copper alloys and scrap.

6. Interferences

6.1 Commonly present elements, which co-deposit or partially co-deposit with copper are precipitated, (for example, silver as the chloride), or volatilized, (for example, antimony, arsenic, selenium), as metal bromides. Molybdenum also will co-deposit with copper to produce a dark plate. When less than 6 mg is present, the addition of 1 mg of sodium chloride will prevent deposition.

6.2 This test method does not address interferences caused by tungsten and bismuth.

7. Apparatus

7.1 Electrodes for Electroanalysis

7.1.1 *Electrodes*—Recommended stationary type platinum electrodes are described in 7.1.2 and 7.1.3. The surface of the platinum electrodes should be smooth, clean, and bright to promote uniform deposition and good adherence. Deviations from the exact size and shape are allowable. In instances where it is desirable to decrease the time of deposition and agitation of the electrolyte is permissible, a generally-available rotating type of electrode may be employed. Cleaning of the electrolyte by sandblasting is not recommended.

¹ This test method is under the jurisdiction of ASTM Committee E01 on Analytical Chemistry for Metals, Ores, and Related Materials and is the direct responsibility of Subcommittee E01.05 on Cu, Pb, Zn, Cd, Sn, Be, their Alloys, and Related Metals.

Current edition approved Feb. 1, 2007. Published February 2007. Originally approved in 1995. Last previous edition approved in 2001 as E1771 – 95 (2001). DOI: 10.1520/E1771-07.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.