



Designation: D4591 – 07

Standard Test Method for Determining Temperatures and Heats of Transitions of Fluoropolymers by Differential Scanning Calorimetry¹

This standard is issued under the fixed designation D4591; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This test method defines conditions for the use of differential scanning calorimetry (DSC) with fluoropolymers. It covers the use of DSC analyses with the fluoropolymers, PTFE, PVDF, PCTFE, and PVF and their copolymers PFA, MFA, FEP, ECTFE, EFEP, VDF/HFP, VDF/TFE/HFP, VDF/CTFE. The test method is applicable to the analysis of powders as well as samples taken from semi-finished or finished products. The nature of fluoropolymers is such that special procedures are needed for running DSC analysis and interpreting the results.

1.2 The values stated in SI units as detailed in [IEEE/ASTM SI-10](#) are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is currently no ISO standard that duplicates this test method. ISO 12086-1 and ISO 12086-2 cover similar testing and reference this test method for testing conditions.

2. Referenced Documents

2.1 ASTM Standards:²

[D1600 Terminology for Abbreviated Terms Relating to Plastics](#)

[D3418 Test Method for Transition Temperatures and Enthalpies of Fusion and Crystallization of Polymers by Differential Scanning Calorimetry](#)

[D4894 Specification for Polytetrafluoroethylene \(PTFE\) Granular Molding and Ram Extrusion Materials](#)

[D4895 Specification for Polytetrafluoroethylene \(PTFE\)](#)

Resin Produced From Dispersion

[E473 Terminology Relating to Thermal Analysis and Rheology](#)

[E793 Test Method for Enthalpies of Fusion and Crystallization by Differential Scanning Calorimetry](#)

[IEEE/ASTM SI-10 Standard for Use of the International System of Units \(SI\) \(the Modern Metric System\)](#)

2.2 ISO Standards:³

[ISO 12086-1 Plastics—Fluoropolymer Dispersion and Molding and Extrusion Materials—Part 1: Designation and Specification](#)

[ISO 12086-2 Plastics—Fluoropolymer Dispersion and Molding and Extrusion Materials—Part 2: Preparation of Test Specimen and Determination of Properties](#)

3. Terminology

3.1 Definitions:

3.1.1 *differential scanning calorimetry (DSC)*—a technique in which the difference in energy inputs into a substance and a reference material is measured as a function of temperature, while the substance and reference material are subjected to a controlled increase or decrease in temperature.

3.1.2 Refer to Terminology [E473](#) for general terminology used in this test method.

3.2 Abbreviated Terms:

3.2.1 Abbreviations used in this test method are in accordance with Terminology [D1600](#).

3.2.2 PTFE—polytetrafluoroethylene.

3.2.3 PFA—perfluoro(alkoxy alkane) resin.

3.2.4 FEP—perfluoro(ethylene-propene) copolymer.

3.2.5 ETFE—ethylene-tetrafluoroethylene copolymer.

3.2.6 PVDF—poly(vinylidene fluoride).

3.2.7 PCTFE—polymonochlorotrifluoroethylene.

3.2.8 ECTFE—ethylene-monochlorotrifluoroethylene copolymer.

3.2.9 EFEP—ethylene-perfluoroethylene-propene copolymer.

3.2.10 VDF/HFP—vinylidene fluoride-hexafluoropropene copolymer.

¹ This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved March 1, 2007. Published March 2007. Originally approved in 1987. Last previous edition approved in 2001 as D4591 - 01. DOI: 10.1520/D4591-07.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

*A Summary of Changes section appears at the end of this standard.

3.2.11 VDF/TFE—vinylidene fluoride-tetrafluoroethylene copolymer.

3.2.12 VDF/TFE/HFP—vinylidene fluoride-tetrafluoroethylene-hexafluoropropene copolymer.

3.2.13 VDF/CTFE—vinylidene fluoride-chlorotrifluoroethylene copolymer.

3.2.14 PVF—poly(vinyl fluoride).

3.2.15 MFA—perfluoromethylvinylether-tetrafluoroethylene copolymer.

3.2.16 SSG—standard specific gravity.

4. Significance and Use

4.1 DSC analysis may be used with fluoropolymers to achieve at least four different objectives as follows:

4.1.1 To measure transition temperatures to aid in the identification of the various fluoropolymers, individually or in mixtures;

4.1.2 To compare the relative levels of crystalline content of two or more specimens of a sample of a fluoropolymer relative to another sample by measuring the heat of fusion;

NOTE 2—Absolute values of crystalline content cannot be determined until values for heats of fusion of the completely crystalline polymers are available.

4.1.3 To characterize PTFE (DSC thermal curves determined on powders or products of PTFE that have never been melted convey appreciable information about details of morphology and molecular structure);⁴

4.1.4 To supplement the test for standard specific gravity (SSG) described in Specifications D4894 and D4895 by using the heat of crystallization of pure PTFE homopolymer, depending on the relative molecular weight of the specimen. The scopes of these specifications, however, include PTFE resins modified with small amounts of comonomers, and many commercial PTFE resins are modified in this manner. These modifications can have profound effects on crystallization behavior. Published relationships⁴ between heat of crystallization and molecular weight refer to pure PTFE homopolymers and, therefore, cannot be applied to the modified resins.

5. Apparatus

5.1 *Differential Scanning Calorimeter*, capable of heating and cooling rates of at least 10.0 °C/min and of recording automatically the differential heat flow between a specimen and a reference material as a function of time, both to the required sensitivity and precision. For comparison purposes, the same heating rate shall be used for all calibrations and test runs. Thermal curves are recorded using a computerized data collection system or on a time-based recorder. The resulting curves are used for the measurement of peak areas either by computer integration or an alternative area measuring procedure. The instrument should have a sensitivity for heat flow sufficient to provide a precision of $\pm 1\%$ when run using a suitable standard for calibration, such as indium. The instru-

ment must have a precision of $\pm 1\%$ for either the computerized data collections or over a time-base range of 0.1 to 2.0 min/cm of chart.

NOTE 3—Most DSC systems report data with a temperature ordinate. The temperature values are directly related to time based on the heating or cooling rate. Integrated areas measured from the DSC curves will be directly proportional to the differential caloric input.

NOTE 4—Noncomputerized area measurement shall be done with a precision of $\pm 1\%$ or better.

5.2 *Specimen Holders and Covers*, made from aluminum or other materials of high thermal conductivity that do not react with the specimen. It is preferable to use holders designed for the particular DSC instrument being used. For holders for which the cover has the shape of a small cup, the top should be inserted with the open side of the cup up.

5.3 *Nitrogen*, or other inert gas supply for purging purposes.

5.4 *Balance*, with capacity greater than 15 mg, capable of weighing to the nearest 0.01 mg.

6. Procedure

6.1 *General Requirements*—In general, Test Method D3418 shall be used whenever possible. There are instances, however, when following Test Method D3418 will not give the desired results, will not provide information needed for proper interpretation of the resultant thermal curve, or will require more time for the analysis than need be spent for results having suitable precision. Examples of these instances include the following:

6.1.1 The requirement that scans be started at room temperature, a provision usually not required with all fluoropolymers;

6.1.2 At times the thermal curve that results from the analysis provides information that cannot be interpreted in a useful manner by Test Method D3418, but can be interpreted following the procedures of Section 7.

6.2 *Calibration*—The procedures for calibration provided in Test Method E793 shall be used. The comments in Test Method D3418 are helpful when reviewed. The calibration is carried out by using an appropriate amount of at least two selected standards weighed to the nearest 0.01 mg. Select the standard materials so that their range includes the first-order transition temperature(s) of the fluoropolymer being tested. It has been found that only one standard is needed to validate the instrument between calibrations.

6.3 A standard specimen mass shall be in the range of 9 to 10 mg weighed to an accuracy of 0.01 mg. For routine analysis, a nonstandard specimen size may be used in cases where equivalence to the standard mass has been established for particular properties. A specimen mass different from the standard shall be reported.

NOTE 5—Thermal curves from such analyses not using the standard specimen mass range may not compare with curves obtained using the standard mass range. Due to the sensitivity of the peak, T_m , to the specimen size, the results may be outside the expected precision and bias.

6.4 Place the test specimen in the DSC sample pan, cover with pan cover, and crimp. Place the pan with specimen in the DSC sample holder or cell at the heating cycle starting temperature.

⁴ Sperati, C. A., "Polytetrafluoroethylene: History of Its Development and Some Recent Advances" (67 references), *High Performance Polymers: Their Origin and Development*, Seymour and Kirshenbaume (eds), Marcel Dekker, New York, 1986, p. 274.