



Designation: D4969 – 07

Standard Specification for Polytetrafluoroethylene–(PTFE) Coated Glass Fabric¹

This standard is issued under the fixed designation D4969; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers glass fabric impregnated, coated, and sintered on both sides with PTFE to a nominal thickness of 0.318 mm (0.015 in.) or less.

1.2 The PTFE-coated glass fabric is for electrical, chemical, and mechanical uses.

1.3 The PTFE-coated glass fabric of this specification does not pertain to structural fabric, single-sided PTFE coatings, or materials used for laminates.

1.4 The values stated in SI units as detailed in [IEEE/ASTM SI-10](#).

NOTE 1—There is no ISO standard that covers information included in this specification. The dielectric test is mentioned in [ISO 12086-2](#) and [ISO 13000-1 and 2](#).

2. Referenced Documents

2.1 *ASTM Standards*:²

[D123 Terminology Relating to Textiles](#)

[D149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies](#)

[D257 Test Methods for DC Resistance or Conductance of Insulating Materials](#)

[D374 Test Methods for Thickness of Solid Electrical Insulation](#)

[D579 Specification for Greige Woven Glass Fabrics](#)

[D618 Practice for Conditioning Plastics for Testing](#)

[D737 Test Method for Air Permeability of Textile Fabrics](#)

[D751 Test Methods for Coated Fabrics](#)

[D883 Terminology Relating to Plastics](#)

[D902 Test Methods for Flexible Resin-Coated Glass Fabrics and Glass Fabric Tapes Used for Electrical Insulation](#)

[D1424 Test Method for Tearing Strength of Fabrics by Falling-Pendulum \(Elmendorf-Type\) Apparatus](#)

[D3892 Practice for Packaging/Packing of Plastics](#)

[D4441 Specification for Aqueous Dispersions of Polytetrafluoroethylene](#)

[IEEE/ASTM SI-10 Standard for Use of the International System of Units \(SI\): The Modern Metric System](#)

2.2 *ISO Standard*:³

[ISO 12086-2 Plastics—Fluoropolymer Dispersions and Moulding and Extrusion Materials—Part 2: Preparation of Test Specimens and Determination of Properties](#)

[ISO 13000-1 and 2 Plastics—Polytetrafluoroethylene \(PTFE\) Semi-Finished Products](#)

3. Terminology

3.1 *Definitions*:

3.1.1 Definitions of terms relating to plastics used in this specification shall be in accordance with Definitions [D883](#). Definitions of terms relating to textiles used in this specification shall be in accordance with Terminology [D123](#).

3.1.2 *structural fabric*—PTFE-coated fabric to a thickness of greater than 0.381 mm (0.015 in.).

3.1.3 *lot, n*—one production run or a uniform blend of two or more production runs.

4. Classification

4.1 There shall be six types of PTFE-coated glass fabrics as described in [Table 1](#).

4.2 Use a one-line system to specify materials covered by this specification. The system uses redefined cells to refer to specific aspects of this specification, as illustrated below as follows.

Standard Number Block	Specification				Special Notes
	Type	Grade	Class		
Example: ASTM D4969-XX	IV	–	–	,	

For this example, the line call out would be: ASTM D4969 – XX, IV – –, Porosity 15–30 CFM, and would specify a Type IV porous product which is referenced in [Table 1](#) with no grade or class since these subcategories do not appear in this specification. A comma is used as the separator between the standard number and the type. Separators are not needed between the type, grade, and class because they are, in turn, Roman numerals, Arabic digits, and uppercase letters, as

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 PTFE-Coated Glass Fabric Types

Type	Name	General Description and Common Application
I	Premium	Smooth, defect-free, primarily used as a dielectric application, release sheet, and Military Specification material.
II	Standard	Regular-grade material primarily used for mechanical applications where temperature and easy-release characteristics are required.
III	Mechanical	Regular-grade material primarily used for mechanical applications where smoothness is not a critical requirement.
IV	Porous	Permeable material, with a range of porosity primarily used as a release sheet in molding.
V	Tear resistant	Smooth, flexible, and tear-resistant material for mechanical applications requiring flexible materials.
VI	Conductive	Regular-grade material primarily used for static discharge.

provided in Section B8 of *Form and Style for ASTM Standards*. Provision for “Special Notes” is included so that other information can be provided when required. An example would be in this specification where porosity would be defined as 15–30 CFM. When special notes are used, they should be preceded by a comma.

5. Materials and Manufacture

5.1 *Glass Fabric*—The base material used in the manufacture of the products of this specification shall be a woven glass fabric produced in accordance with Specification D579. A guideline for generally acceptable substrate fabrics for the common thickness of PTFE/glass fabric products is given in Table 2.

5.2 *Coating*—The glass fabric is impregnated or coated with polytetrafluoroethylene in accordance with Specification D4441. When necessary, use additives to aid the dispersion to achieve the required properties and performance of the final product.

6. Physical Requirements

6.1 The coating shall penetrate and adhere to the fabric and shall be substantially free of wrinkles, creases, blisters, and other imperfections.

6.2 Color:

6.2.1 The material will have a natural color that varies from off-white to dark brown when viewed by the unaided eye. The usual color is tan.

6.2.2 If color is required by the customer, specify it.

6.2.3 Color will be uniform from roll to roll within a lot.

6.2.4 Other colors for products that contain pigments, fillers, and additives will be agreed upon between the suppliers and the customers.

6.3 *Thickness*—The thickness of the glass fabric is dependent on glass style and percent PTFE coating. Tolerances are typically ±10 % of the finished thickness. Thickness shall be tested in accordance with Test Methods D374.

NOTE 2—Typically, glass and coated glass products are manufactured to a weight per unit area.

6.4 *Breaking Strength*—When tested in accordance with Methods D902, the breaking strength shall be at least 80 % of the specified value stated in Table 6 of Specification D579.

NOTE 3—Reduction of tensile strength is due to added heat required for coating.

6.5 *Edge Tear Strength*—(Elmendorf) Tears shall be tested in accordance with Test Method D1424. Tear values are dependent upon glass style and additives added to the PTFE. Typical Tear Resistant (Type 5) products exhibit two times the values of their counterparts. Conductive (Type 6) products exhibit one half the values of their counterparts. Test values and tolerances shall be determined by the supplier and the customer.

6.6 *Mass*—A sample shall be prepared in accordance with Method D751. The amount of PTFE added shall be agreed upon between the customer and the supplier and shall have a tolerance of ±5 % of the total coated product weight.

6.7 *Widths*—The coated glass fabric shall be furnished in the widths and tolerances indicated in Table 3, when tested in accordance with Method D751.

6.8 *Conductivity*—For Type 6 material, conductivity shall be tested in accordance with Test Methods D257, using the Flat Metal Plate Method, and a comparison bridge. Material shall be deemed conductive when the resistivity is below 10⁶ Ω/square.

6.9 *Dielectric Breakdown*—Type I only.

6.9.1 *Dielectric Breakdown Voltage*—When tested in accordance with Test Methods D149 and Methods D902, with a ¼-in. electrode, the dielectric breakdown voltage for the various thickness shall be as specified in Table 4.

TABLE 2 Acceptable Substrate Fabrics for Common Thickness of PTFE Glass Fabric Products

PTFE/Glass Fabrics Thickness.		Generally Acceptable Woven Glass Fabrics Style Number
mm	(in.)	
0.051	(0.002)	104, 106
0.076	(0.003)	108, 1080
0.102	(0.004)	112, 113, 2113
0.127	(0.005)	116, 1165, 2116, 2165
0.152	(0.006)	116, 1165, 2116
0.203	(0.008)	125, 1528, 7628
0.254	(0.010)	128, 1528, 7628
0.356	(0.014)	141, 1142

TABLE 3 Widths of PTFE-Coated Glass Fabric

Nominal Widths		Tolerances	
mm	(in.)	mm	(in.)
3.17 to <12.7	(1/8 to <1/2)	0.397	(±1/64)
12.7 to <38.1	(1/2 to <1/2)	0.794	(±1/32)
38.1 to <76.2	(1 1/2 to <3)	1.587	(±1/16)
76.2 to <305	(3 to <12)	1.411	(±1/8)
305 or greater	(12 or greater)	6.35	(±1/4)