



Designation: C1372 – 04<sup>ε2</sup>

# Standard Specification for Dry-Cast Segmental Retaining Wall Units<sup>1</sup>

This standard is issued under the fixed designation C1372; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

<sup>ε1</sup> NOTE—An editorial change was made to the title in June 2004.

<sup>ε2</sup> NOTE—A heading in Table 1 was editorially corrected in March 2007.

## 1. Scope\*

1.1 This specification covers dry-cast segmental retaining wall units of concrete, machine-made from hydraulic cement, water, and suitable mineral aggregates with or without the inclusion of other materials. The units are intended for use in the construction of mortarless segmental retaining walls.

NOTE 1—When particular features are desired, such as weight classification, higher compressive strength, surface texture, finish, color, or other special features, such properties should be specified separately by the purchaser. Local suppliers should be consulted as to availability of units having the desired features.

1.2 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

- C33 Specification for Concrete Aggregates
- C140 Test Methods for Sampling and Testing Concrete Masonry Units and Related Units
- C150 Specification for Portland Cement
- C331 Specification for Lightweight Aggregates for Concrete Masonry Units
- C595 Specification for Blended Hydraulic Cements
- C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- C989 Specification for Slag Cement for Use in Concrete and Mortars

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of C15.03 on Concrete Masonry Units and Related Units

Current edition approved Jan. 1, 2004. Published February 2004. Originally approved in 1997. Last previous edition approved in 2003 as C1372 – 03. DOI: 10.1520/C1372-04E02.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- C1157 Performance Specification for Hydraulic Cement
- C1209 Terminology of Concrete Masonry Units and Related Units<sup>3</sup>
- C1232 Terminology of Masonry
- C1262 Test Method for Evaluating the Freeze-Thaw Durability of Dry-Cast Segmental Retaining Wall Units and Related Concrete Units

## 3. Terminology

3.1 Terminology defined in Terminology C1209 and Terminology C1232 shall apply for this specification.

3.2 *Definitions*:

3.2.1 *Dry-cast, adj*—manufacturing concrete products using low frequency, high amplitude vibration to consolidate concrete of stiff or extremely dry consistency in a form.

3.2.2 *segmental retaining wall unit, n*—unit manufactured of concrete for the construction of dry-stacked earth retaining walls.

3.2.3 *segmental retaining wall unit, dry-cast, n*—a segmental retaining wall unit manufactured of concrete using a dry-cast process.

## 4. Materials

4.1 *Cementitious Materials*—Materials shall conform to the following applicable specifications:

4.1.1 *Portland Cements*—Specification C150.

4.1.2 *Modified Portland Cement*—Portland cement conforming to Specification C150, modified as follows:

4.1.2.1 *Limestone*—Limestone, with a minimum 85 % Calcium Carbonate (CaCO<sub>3</sub>) content, shall be permitted to be added to the cement, provided these requirements of Specification C150 as modified are met:

(1) Limitation on Insoluble Residue—1.5 %.

(2) Limitation on Air Content of Mortar—Volume percent, 22 % max.

(3) Limitation on Loss of Ignition—7 %.

4.1.3 *Blended Hydraulic Cements*—Specification C595.

4.1.4 *Hydraulic Cement*—Specification C1157.

4.1.5 *Pozzolans*—Specification C618.

<sup>3</sup> Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

\*A Summary of Changes section appears at the end of this standard.