

---

---

**Plastics piping systems for hot and cold  
water installations — Chlorinated  
poly(vinyl chloride) (PVC-C) —**

**Part 1:  
General**

iTeh **AMENDMENT 1**  
**(standards.iteh.ai)**

*Systèmes de canalisations en plastique pour les installations d'eau  
chaude et froide — Poly(chlorure de vinyle) chloré (PVC-C) —*

*ISO 15877-1:2009/Amd 1:2010*  
<https://standards.iteh.org/standards/iso/620c114-f20a-4a4e-8124-921ca4343075/iso-15877-1-2009-amd-1-2010>  
**Partie 1: Généralités**  
**AMENDEMENT 1**



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 15877-1:2009/Amd 1:2010](https://standards.iteh.ai/catalog/standards/sist/6e20c114-f20a-4a4e-8124-921ca4343075/iso-15877-1-2009-amd-1-2010)

<https://standards.iteh.ai/catalog/standards/sist/6e20c114-f20a-4a4e-8124-921ca4343075/iso-15877-1-2009-amd-1-2010>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 15877-1:2009 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 155, *Plastics piping systems and ducting systems*, in collaboration with ISO Technical Committee TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 2, *Plastics pipes and fittings for water supplies*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

[ISO 15877-1:2009/Amd 1:2010](https://standards.iteh.ai/catalog/standards/sist/6e20c114-f20a-4a4e-8124-921ca4343075/iso-15877-1-2009-amd-1-2010)

<https://standards.iteh.ai/catalog/standards/sist/6e20c114-f20a-4a4e-8124-921ca4343075/iso-15877-1-2009-amd-1-2010>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 15877-1:2009/Amd 1:2010

<https://standards.iteh.ai/catalog/standards/sist/6e20c114-f20a-4a4e-8124-921ca4343075/iso-15877-1-2009-amd-1-2010>

# Plastics piping systems for hot and cold water installations — Chlorinated poly(vinyl chloride) (PVC-C) —

## Part 1: General

### AMENDMENT 1

PVC-C Type I piping systems for low-temperature heating applications have been used successfully in some countries for more than 30 years. Therefore, this amendment proposes to add to ISO 15877-1, Class 4 as defined in ISO 10508, for the conditions of service used in these countries (4 bar and 6 bar).

*Page 7, Clause 4*

Delete the existing title for Table 1, and insert the following title:

**“Table 1 — Classification of service conditions for Type I [Classes 1, 2 and 4]  
and Type II [Classes 1, 2, 4 and 5] PVC-C materials”**

*Page 8, 5.1*

Delete the existing second paragraph, and insert the following new text:

“This part of ISO 15877 is applicable to two types of PVC-C, Type I (suitable for Classes 1, 2 and 4) and Type II (suitable for Classes 1, 2, 4 and 5). Systems comprising pipes and fittings produced from a combination of Type I and Type II materials shall only be suitable for Classes 1, 2 or 4.”

*Page 10, A.1*

Delete the existing text, and insert:

“This annex specifies a test method for verifying the malfunction temperature,  $T_{mal}$ , 95 °C or 100 °C, as applicable, of chlorinated poly(vinyl chloride) Type I (PVC-C, Type I) material for piping systems intended to be used for hot and cold water installations and for heating systems (for classification of service conditions, see Clause 4).”

*Page 11, A.5*

Before the existing text, insert:

**“A.5.1 Malfunction temperature,  $T_{mal}$ , 95 °C”**

After the existing text, insert:

**“A.5.2 Malfunction temperature,  $T_{mal}$ , 100 °C”**

Conduct the following procedure using an assembly as given in Figure A.1, set up by solvent cementing the components. Store the components which have been connected by solvent cement for setting for at least 24 h

at ambient temperature. Then condition the solvent cemented joints by filling the assembly with water at  $(95 \pm 2) ^\circ\text{C}$  for 48 h without applying any pressure. After the conditioning, drain the water off.

Refill the assembly with water at  $(95 \pm 2) ^\circ\text{C}$  which is circulated by a pump and apply a pressure of 6 bar to the assembly.

Maintain the water temperature at  $(95 \pm 2) ^\circ\text{C}$  and pressure at  $(6 \pm 0,5)$  bar for 500 h, followed by a temperature at  $(100 \pm 2) ^\circ\text{C}$  and a pressure at  $(6 \pm 0,5)$  bar for at least 500 h, during which the assembly shall be continuously monitored for leaktightness.”

*Page 11, A.6, items d) and e)*

Delete the existing text, and insert:

- “d) test temperature(s), in degrees Celsius, as applicable;
- e) total time under pressure, in hours;”

## **iTeh STANDARD PREVIEW** **(standards.iteh.ai)**

<https://standards.iteh.ai/catalog/standards/sist/6e20c114-f20a-4a4e-8124-921ca4343075/iso-15877-1-2009-amd-1-2010>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 15877-1:2009/Amd 1:2010

<https://standards.iteh.ai/catalog/standards/sist/6e20c114-f20a-4a4e-8124-921ca4343075/iso-15877-1-2009-amd-1-2010>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 15877-1:2009/Amd 1:2010  
<https://standards.iteh.ai/catalog/standards/sist/6e20c114-f20a-4a4e-8124-921ca4343075/iso-15877-1-2009-amd-1-2010>

---

---

**ICS 23.040.20; 91.140.60**

Price based on 2 pages