



Standard Test Method for Preparation of Extractive-Free Wood¹

This standard is issued under the fixed designation D1105; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the preparation of extractive-free wood and is applicable to all North American woods. Extractives in wood consist of materials that are soluble in neutral solvents and that are not a part of the wood.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific precautionary statements are given in 4.2.

2. Significance and Use

2.1 Extractives are materials soluble in neutral solvents. They are not generally considered part of the wood polymer structure. These materials should be removed before any chemical analysis of the wood. Ethanol-benzene extracts waxes, fats, some resins, and portions of wood gums. Hot water extracts tannins, gums, sugars, starches, and coloring matter.

3. Apparatus

3.1 *Soxhlet Extraction Apparatus*—A glass Soxhlet extraction apparatus of suitable size for containing the sample, and fritted-glass or Alundum extraction thimbles of medium to coarse porosity, will be required. Bags of cotton cloth of fine weave and thoroughly washed, of a suitable size to fit within the body of the extractor, are also satisfactory in place of the thimbles. Alternatively, a small wad of cotton or a wire screen may be placed in the discharge tube of the extractor and the entire body of the extractor filled with the wood sample. A thin wire screen disk placed over the top of the material will prevent channeling by the dripping condensate.

4. Reagents

4.1 *Ethyl Alcohol (95 %)*.

¹ This test method is under the jurisdiction of ASTM Committee D07 on Wood and is the direct responsibility of Subcommittee D07.01 on Fundamental Test Methods and Properties.

Current edition approved April 1, 2007. Published April 2007. Originally approved in 1950. Last previous edition approved in 2001 as D1105 – 96 (2001). DOI: 10.1520/D1105-96R07.

4.2 *Ethanol-Toluene Mixture*—Mix 1.0 absolute ethanol and 427 mL toluene. (**Warning**—Avoid inhalation of vapors and contact with skin.)

5. Sample

5.1 The sample shall consist of air-dry sawdust that has been reduced by means of a Wiley mill so as to pass through a 250- μm sieve and be retained on a 180- μm sieve.

6. Procedure

6.1 Place a suitable quantity of the sample in the extraction thimble, being certain that the wood does not extend above the level of the top of the siphon tube. Extract for 4 h with ethanol-toluene mixture in the Soxhlet extraction apparatus. Transfer the wood to a Büchner funnel, remove the excess solvent with suction, and wash the thimble and wood with alcohol to remove the toluene. Return the wood to the extractor and continue the extraction with ethanol for 4 h, or longer if necessary, until the ethanol siphons over colorless.

6.2 If the thimble is nearly full, a Gooch crucible of suitable size may be placed in the rim of the thimble to keep the sample together. Extraction with each solvent should be carried out at a rate of not less than four siphonings per hour. Remove the wood from the thimble, spread it out in a thin layer, and allow it to dry in the air until free of alcohol. Transfer the material to a 7.5-L Erlenmeyer or Florence flask and extract successively with three 1-L portions of distilled water, heating the flask with each change of water for 1 h in a hot-water bath at 100°C. The water should be at boiling temperature before the addition of the wood and the flask in the bath should be entirely surrounded by the boiling water. After the third extraction with water is complete, filter on a Büchner funnel, wash with 500 mL of boiling distilled water, and allow the extracted material to become thoroughly dry in the air.

7. Precision and Bias

7.1 Statements of precision and bias are not applicable to this method.

8. Keywords

8.1 extractive-free wood; wood