

---

---

**Paper and board — Determination of  
air permeance (medium range) —**

**Part 5:  
Gurley method**

*Papier et carton — Détermination de la perméabilité à l'air (plage de  
valeurs moyennes) —*

*Partie 5: Méthode Gurley*

*iteh Standards*  
*(<https://standards.iteh.ai>)*  
*Document Preview*

[ISO 5636-5:2013](https://standards.iteh.ai/catalog/standards/iso/152366af-0ac9-4581-b164-cba8d94fe127/iso-5636-5-2013)

<https://standards.iteh.ai/catalog/standards/iso/152366af-0ac9-4581-b164-cba8d94fe127/iso-5636-5-2013>



iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[ISO 5636-5:2013](https://standards.iteh.ai/catalog/standards/iso/152366af-0ac9-4581-b164-cba8d94fe127/iso-5636-5-2013)

<https://standards.iteh.ai/catalog/standards/iso/152366af-0ac9-4581-b164-cba8d94fe127/iso-5636-5-2013>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword .....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
<b>5 Apparatus and materials</b> .....	<b>2</b>
<b>6 Sampling</b> .....	<b>4</b>
<b>7 Conditioning</b> .....	<b>4</b>
<b>8 Preparation of test pieces</b> .....	<b>4</b>
<b>9 Calibration</b> .....	<b>4</b>
<b>10 Procedure</b> .....	<b>4</b>
<b>11 Calculation and expression of results</b> .....	<b>5</b>
11.1 Calculation of air permeance .....	5
11.2 Reporting the results .....	5
11.3 Standard deviation and coefficient of variation .....	5
<b>12 Test report</b> .....	<b>5</b>
<b>Annex A (normative) Volume check — Gurley apparatus</b> .....	<b>7</b>
<b>Annex B (informative) Variations in apparatus</b> .....	<b>9</b>
<b>Annex C (informative) Precision data</b> .....	<b>10</b>
<b>Bibliography</b> .....	<b>12</b>

[ISO 5636-5:2013](https://standards.iteh.ai/catalog/standards/iso/152366af-0ac9-4581-b164-cba8d94fe127/iso-5636-5-2013)

<https://standards.iteh.ai/catalog/standards/iso/152366af-0ac9-4581-b164-cba8d94fe127/iso-5636-5-2013>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

This third edition cancels and replaces the second edition (ISO 5636-5:2003), which has been technically revised. In this third edition mainly editorial changes have been made and also precision data has been added as informative Annex C.

ISO 5636 consists of the following parts, under the general title *Paper and board — Determination of air permeance (medium range)*:

- *Part 3: Bendtsen method*
- *Part 4: Sheffield method*
- *Part 5: Gurley method*
- *Part 6: Oken method*

NOTE 1 *Part 1: General method* will be withdrawn after the third editions of Parts 3, 4 and 5 have been published, as it was considered redundant.

NOTE 2 *Part 2: Schopper method* was withdrawn in 2006 as it was considered obsolete.

NOTE 3 *Part 6: Oken method* is being prepared.

# Paper and board — Determination of air permeance (medium range) —

## Part 5: Gurley method

### 1 Scope

This part of ISO 5636 specifies the Gurley method for determining the air permeance of paper and board using an air resistance tester, the Gurley apparatus.

It is applicable to papers and boards which have air permeances between  $0,1 \mu\text{m}/(\text{Pa}\cdot\text{s})$  and  $100 \mu\text{m}/(\text{Pa}\cdot\text{s})$  when tested with the Gurley apparatus.

It is unsuitable for rough-surfaced materials, which cannot be securely clamped to avoid leakage.

This part of ISO 5636 may also be used to determine the air resistance of paper and board.

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 48, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD)*

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 385, *Laboratory glassware — Burettes*

ISO 3104, *Petroleum products — Transparent and opaque liquids — Determination of kinematic viscosity and calculation of dynamic viscosity*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1

##### air permeance

mean air flow rate through unit area under unit pressure difference in unit time, under specified conditions

Note 1 to entry: Air permeance is expressed in micrometres per pascal second [ $1 \text{ ml}/(\text{m}^2\cdot\text{Pa}\cdot\text{s}) = 1 \mu\text{m}/(\text{Pa}\cdot\text{s})$ ].

Note 2 to entry: This property is called air permeance, and not air permeability, because it is reported as a sheet property and is not standardized with respect to thickness to give a material property per unit thickness.

### 3.2

#### air resistance

time required for a specific volume of air under unit pressure to pass through unit area

Note 1 to entry: Air resistance is expressed in seconds per 100 millilitres [s/(100 ml)].

## 4 Principle

The air is compressed by the weight of a vertical cylinder floating in a liquid. A test piece is in contact with the compressed air and the cylinder falls steadily as air passes through the test piece. The time for a given volume of air to pass through the test piece, i.e. the air resistance is measured and from this the air permeance is calculated.

## 5 Apparatus and materials

**5.1 Gurley apparatus**, see [Figure 1](#), that consists of an outer cylinder (see [5.1.3](#)) partly filled with sealing fluid (see [5.2](#)) and an inner cylinder (see [5.1.4](#)) having an open top, sliding freely in the outer cylinder. Air pressure, provided by the weight of the inner cylinder, is applied to the test piece held between clamping plates (see [5.1.1](#)) in a circular orifice.

**5.1.1 Clamping plates** are at the base of the apparatus, and a central feed tube directs the pressurized air to the clamping plates. Some versions of this apparatus use a hand-tightened capstan (jackscrew) arrangement to tighten the clamping plates together, others are equipped with a dead weight of 901 g loading a lever arm and others use a pneumatic system. The recommended clamping force is  $(180 \pm 30)$  N. This mechanism provides a technique to give uniform loading, and thus minimize the operator influence on the test. Controlled clamping force is the preferred method of clamping the test piece.

**5.1.2 Rubber gasket** attached to the clamping plate on the side exposed to the air pressure prevents leakage of air between the surface of the paper and the clamping plate. The gasket consists of a thin, elastic, oil-resistant, non-oxidizing material, having a smooth surface, a thickness of 0,7 mm to 1,0 mm and a hardness of 50 IRHD (International Rubber Hardness Degrees) in accordance with ISO 48. The inside diameter of the gasket is about 28,6 mm and the outside diameter is about 34,9 mm. The aperture of the gasket is concentrically aligned with the aperture in the clamping plates. To align and protect the gasket in use, it is cemented to a groove machined in the upper clamping plate. The groove is concentric with the aperture in the opposing plate, has an internal diameter of  $(28,50 \pm 0,15)$  mm and a depth of  $(0,45 \pm 0,05)$  mm. Its outside diameter is  $(35,2 \pm 0,1)$  mm for convenience in inserting and attaching the gasket. The gasket, when mounted inside the concentric groove, defines the measurement area and shall have an inside diameter of  $(28,6 \pm 0,1)$  mm (642 mm<sup>2</sup> area). The gasket should be changed at regular intervals.

**5.1.3 Outer cylinder** with a height of 254 mm and an internal diameter of 82,6 mm. The inner surface has three or four bars, not less than 190 mm and not greater than 245,5 mm in length and 2,4 mm square or 2,4 mm diameter, spaced equidistantly to serve as guides for the inner cylinder.

**5.1.4 Inner cylinder**, graduated in units of 50 ml and with a full-scale reading of at least 300 ml. It may have 25 ml graduations between the 0 ml and 100 ml markings. The scale markings represent true volumes enclosed within the inner cylinder and shall be accurate to within 3%. The exact volume of the inner cylinder may be checked by means of the procedure given in Annex A. The cylinder has a height of  $(254,0 \pm 0,5)$  mm, an external diameter of  $(76,2 \pm 0,5)$  mm and an internal diameter about 74 mm such that the mass of the cylinder assembly is  $(567,0 \pm 0,5)$  g.

**5.1.5 Volumes** referred to are nominal volumes and should, in principle be increased by the volume of fluid displaced by the walls of the inner cylinder during the test. In practice, since this error is common to all instruments of this type, it is ignored.