



Designation: F22 – 02 (Reapproved 2007)

## Standard Test Method for Hydrophobic Surface Films by the Water-Break Test<sup>1</sup>

This standard is issued under the fixed designation F22; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This test method covers the detection of the presence of hydrophobic (nonwetting) films on surfaces and the presence of hydrophobic organic materials in processing ambients. When properly conducted, the test will enable detection of molecular layers of hydrophobic organic contaminants. On very rough or porous surfaces, the sensitivity of the test may be significantly decreased.

1.2 The values stated in SI units are to be regarded as the standard. The inch-pound values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**D351 Classification for Natural Muscovite Block Mica and Thins Based on Visual Quality**

### 3. Terminology

3.1 *Definitions:*

3.1.1 *hydrophilic*—having a strong affinity for water, wettable.

3.1.2 *hydrophobic*—having little affinity for water, nonwettable.

### 4. Summary of Test Method

4.1 The water-break test is performed by withdrawing the surface to be tested, in a vertical position, from a container

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee E21 on Space Simulation and Applications of Space Technology and is the direct responsibility of Subcommittee E21.05 on Contamination.

Current edition approved April 1, 2007. Published April 2007. Originally approved in 1962. Last previous edition approved in 2002 as F22 – 02. DOI: 10.1520/F0022-02R07.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

overflowing with water. The interpretation of the test is based upon the pattern of wetting. In the absence of hydrophobic films, the draining water layer will remain as a film over the surface. In areas where hydrophobic materials are present on the surface, the draining water layer will break up into a discontinuous film within one minute.

### 5. Significance and Use

5.1 The water-break test as described in this test method is nondestructive and may be used for control and evaluation of processes for the removal of hydrophobic contaminants. The test may also be used for the detection and control of hydrophobic contaminants in processing ambients. For this application, a surface free of hydrophobic films is exposed to the ambient and subsequently tested.

### 6. Interferences

6.1 Loss of sensitivity may result from either of the following factors:

- 6.1.1 The presence of hydrophilic substances on the surface to be tested, in the test equipment, or in the test materials, or
- 6.1.2 An unusually rough or porous surface condition.

### 7. Apparatus

- 7.1 *Overflow Container*, such as a glass beaker.
- 7.2 *Low Power Microscope*, (5 to 50 $\times$ ) and light source for observation of small piece parts.

### 8. Reagents and Materials

8.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society,<sup>3</sup> where such specifications are available. Other grades may be used, provided it is first ascertained that the reagent is of

<sup>3</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.