

Designation: D4208 - 02(Reapproved 2007)

Standard Test Method for Total Chlorine in Coal by the Oxygen Bomb Combustion/Ion Selective Electrode Method¹

This standard is issued under the fixed designation D4208; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

- 1.1 This test method covers the analysis of total chlorine in coal.
- 1.2 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

D1193 Specification for Reagent Water

D3173 Test Method for Moisture in the Analysis Sample of Coal and Coke

D3180 Practice for Calculating Coal and Coke Analyses from As-Determined to Different Bases

E144 Practice for Safe Use of Oxygen Combustion Bombs E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Summary of Test Method

3.1 Total chlorine is determined in this method by combusting a weighed sample in an oxygen bomb with dilute base adsorbing the chlorine vapors. The bomb is rinsed into a beaker with water and following the addition of an ionic strength adjuster, the chloride is determined by ion-selective electrode.

4. Significance and Use

4.1 The purpose of this test method is to measure the total chlorine content of coal. The chlorine content of coals may be useful in the evaluation of slagging problems, corrosion in engineering processes, and in the total analysis of coal and

¹ This test method is under the jurisdiction of ASTM Committee D05 on Coal and Coke and is the direct responsibility of Subcommittee D05.21 on Methods of Analysis.

coke. When coal samples are combusted in accordance with this method, the chlorine is quantitatively retained and is representative of the total chlorine content of the whole coal.

5. Apparatus

- 5.1 Combustion Bomb, constructed of materials that are not affected by the combustion process or products. The bomb must be designed so that all liquid combustion products can be quantitatively recovered by washing the inner surfaces. There must be no gas leakage during the test. The bomb must be capable of withstanding a hydrostatic-pressure test to 3000 psig (approximately 20 MPa) at room temperature without stressing any part beyond its elastic limit.
- 5.2 Water Bath—A container large enough to hold the combustion bomb and enough cooling water to dissipate the heat generated during the combustion process. The container shall be designed to allow a constant flow of water around the combustion bomb.
- 5.3 Combustion Crucibles—Samples shall be burned in an open crucible of platinum, quartz, or acceptable base-metal alloy.
- 5.4 Firing Wire, 100-mm, nickel-chromium alloy, No. 34B & S gage, or platinum, No. 34 or No. 38B & S gage.
- 5.5 Firing Circuit—A 6 to 16-V alternating or direct current is required for ignition purposes with an ammeter or pilot light in the circuit to indicate when current is flowing. A step-down transformer connected to an alternating-current lighting circuit or batteries can be used. (Warning—The ignition circuit switch shall be of the momentary double-contact type, normally open, except when held closed by the operator. The switch should be depressed only long enough to fire the charge.)
 - 5.6 Balance, analytical, with a sensitivity of 0.1 mg.
- 5.7 Specific-Ion Meter—A pH meter with an expandable millivolt scale, specific-ion meter, sensitive to 0.1 mV, suitable for method of standard addition determinations.³

Current edition approved May 1, 2007. Published May 2007. Originally approved in 1982. Last previous edition approved in 2002 as D4208 – 88 $(2002)^{c1}$. DOI: 10.1520/D4208-02R07.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Midgley, D., and Torrance, K., *Potentiometric Water Analysis*, John Wiley and Sons, 1978.