NOTICE: This standard has either been superseded and replaced by a new version or withdrawn. Contact ASTM International (www.astm.org) for the latest information



Designation: D 4244 – 95 (Reapproved 2001)

An American National Standard

### Standard Specification for General-Purpose, Heavy-Duty, and Extra-Heavy-Duty Acrylonitrile-Butadiene/Poly(Vinyl Chloride) (NBR/PVC) Jackets for Wire and Cable<sup>1</sup>

This standard is issued under the fixed designation D 4244; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

#### 1. Scope

1.1 This specification covers durable, crosslinked black or colored acrylonitrile-butadiene/poly(vinyl chloride) (NBR/ PVC) compounds suitable for use as outer coverings or jackets on electrical cables for general-purpose, heavy-duty, and extraheavy-duty service.

1.2 General-purpose and heavy-duty jackets are not recommended for installation at a temperature lower than  $-25^{\circ}$ C and extra-heavy-duty jackets at a temperature lower than  $-10^{\circ}$ C.

1.3 Compounds are based on a fluxed blend of an acrylonitrile-butadiene synthetic rubber and poly(vinyl chloride) resin.

1.4 The values stated in inch-pound units are the standard, except in cases where SI units are more appropriate. The values given in parentheses are for information only.

#### 2. Referenced Documents

2.1 ASTM Standards:

- D 470 Test Methods for Crosslinked Insulations and Jackets for Wire and Cable<sup>2</sup>
- D 1499 Practice for Filtered Open-Flame Carbon-Arc Exposures of Plastics<sup>3</sup>
- G 23 Practice for Operating Light-Exposure Apparatus

<sup>2</sup> Annual Book of ASTM Standards, Vol 10.01.

<sup>3</sup> Annual Book of ASTM Standards, Vol 08.01.

(Carbon-Arc Type) With and Without Water for Exposure of Nonmetallic Materials<sup>4</sup>

# 3. Test Applicable for Black Sunlight and Weather Resistant Materials

3.1 A black jacket shall retain a minimum of 80 % of its unexposed tensile strength and elongation after 720 h of exposure in a dual carbon-arc apparatus. Prepare the specimens in accordance with Test Methods D 470 for physical tests of insulations and jackets. Perform the test in accordance with Practice D 1499 using Method 1 of Practice G 23. This test is not applicable to colored jackets.

#### 4. Physical Properties

4.1 Jackets shall conform to the requirements for physical properties prescribed in Table 1.

#### 5. Sampling

5.1 Unless otherwise specified, sample the jacket in accordance with Test Methods D 470.

## 6. Test Methods -02e98cbfefde/astm-d4244-952001

6.1 Unless otherwise specified, test the jacket in accordance with Test Methods D 470.

#### 7. Keywords

7.1 acrylonitrile-butadiene/poly(vinyl chloride) jacket; crosslinked jacket; extra-heavy-duty jacket; general-purpose jacket; heavy-duty jacket; rubber jacket

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.18 on Solid Insulations, Non-Metallic Shieldings and Coverings for Electrical and Telecommunication Wires and Cables.

Current edition approved Feb. 15, 1995. Published April 1995. Originally published as D 4244 – 83. Last previous edition D 4244 – 89.

<sup>&</sup>lt;sup>4</sup> Discontinued; see 1996 Annual Book of ASTM Standards, Vol 14.02.