

---

---

**Copper, lead, zinc and nickel sulfide  
concentrates — Determination of  
arsenic —**

**Part 1:  
Iron hydroxide concentration and  
inductively coupled plasma atomic  
emission spectrometric method**

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

*Concentrés sulfurés de cuivre, de plomb et de zinc — Dosage de  
l'arsenic*

*Partie 1: Méthode par digestion acide, co-précipitation avec le fer et  
plasma induit par haute fréquence*



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 13547-1:2014

<https://standards.iteh.ai/catalog/standards/sist/61ced248-5877-424d-b6e9-760c1f434013/iso-13547-1-2014>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Principle</b> .....	<b>2</b>
<b>4 Reagents</b> .....	<b>2</b>
<b>5 Apparatus</b> .....	<b>3</b>
<b>6 Sample</b> .....	<b>4</b>
6.1 Laboratory sample.....	4
6.2 Test sample.....	4
6.3 Test portion.....	4
<b>7 Procedure</b> .....	<b>4</b>
7.1 Number of determinations.....	4
7.2 Blank test.....	4
7.3 Dissolution of the test portion.....	4
7.4 Removal of lead sulfate.....	5
7.5 Dissolution of the insoluble residue.....	5
7.6 Separation of arsenic.....	5
7.7 Preparation of test solutions.....	6
7.8 Preparation of calibration solutions.....	6
7.9 Preparation of arsenic calibration curve.....	6
7.10 Determination of arsenic content in test solutions.....	6
<b>8 Expression of results</b> .....	<b>7</b>
<b>9 Precision</b> .....	<b>7</b>
9.1 Expression of precision.....	7
9.2 Procedure for obtaining the final result.....	8
9.3 Between-laboratories precision.....	8
9.4 Check of trueness.....	9
<b>10 Test report</b> .....	<b>10</b>
<b>Annex A (normative) Procedure for the preparation and determination of the mass of a pre-dried test portion</b> .....	<b>11</b>
<b>Annex B (normative) Flowsheet of the procedure for the acceptance of analytical values for test samples</b> .....	<b>13</b>
<b>Bibliography</b> .....	<b>14</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

ISO 13547 consists of the following parts, under the general title *Copper, lead, zinc and nickel sulfide concentrates — Determination of arsenic*:

- Part 1: Iron hydroxide concentration and inductively coupled plasma atomic emission spectrometric method
- Part 2: Acid digestion and inductively coupled plasma atomic emission spectrometric method

# Copper, lead, zinc and nickel sulfide concentrates — Determination of arsenic —

## Part 1:

## Iron hydroxide concentration and inductively coupled plasma atomic emission spectrometric method

**WARNING** — This International Standard may involve hazardous materials, operations, and equipment. It is the responsibility of the user of this International Standard to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

### 1 Scope

This International Standard specifies an iron hydroxide concentration and inductively coupled plasma atomic emission spectrometric (ICP-AES) method for the determination of the mass fraction of arsenic in copper, lead, zinc, and nickel sulfide concentrates as follows:

- a) for copper sulfide concentrates, the method is applicable to the determination of mass fractions of arsenic from 0,05 % to 2,0 %;
- b) for lead sulfide concentrates, the method is applicable to the determination of mass fractions of arsenic from 0,05 % to 1,0 %;
- c) for zinc sulfide concentrates, the method is applicable to the determination of mass fractions of arsenic from 0,05 % to 0,6 %;
- d) for nickel sulfide concentrates, the method is applicable to the determination of mass fraction of arsenic from 0,05 % to 1,0 %.

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 4787, *Laboratory glassware — Volumetric instruments — Methods for testing of capacity and for use*

ISO 8466-2, *Water quality — Calibration and evaluation of analytical methods and estimation of performance characteristics — Part 2: Calibration strategy for non-linear second-order calibration functions*

ISO 9599, *Copper, lead and zinc sulfide concentrates — Determination of hygroscopic moisture in the analysis sample — Gravimetric method*

ISO 12743:2006, *Copper, lead, zinc and nickel concentrates — Sampling procedures for determination of metal and moisture content*

ISO Guide 35:2006, *Reference materials — General and statistical principles for certification*

### 3 Principle

The test portion is decomposed in nitric and sulphuric acids. Arsenic is coprecipitated in ammonia solution by the carriers of iron hydroxide to be separated from the matrix. The arsenic content is determined by comparison against iron-matched standards using ICP-AES.

### 4 Reagents

During the analysis, use only reagents of recognized analytical grade and distilled water, or water of equivalent purity.

**4.1 Sodium hydroxide (NaOH)**, AR grade.

**4.2 Arsenic trioxide (As<sub>2</sub>O<sub>3</sub>)**, AR grade.

**4.3 Iron(III) chloride hexahydrate (FeCl<sub>3</sub>•6H<sub>2</sub>O)**, AR grade (<0,000 05 % arsenic).

**4.4 Ammonium chloride (NH<sub>4</sub>Cl)**, AR grade.

**4.5 Ammonium acetate**, AR grade.

**4.6 Nitric acid** ( $\rho_{20}$  1,42 g/mL), AR grade.

**4.7 Nitric acid**, dilute (1 + 1).

Slowly, add 50 ml of nitric acid (4.6) to 50 ml of water while stirring.

**4.8 Hydrochloric acid** ( $\rho_{20}$  1,16 g/mL), AR grade.

**4.9 Hydrochloric acid**, dilute (1 + 1).

Slowly add 50 ml of hydrochloric acid (4.8) to 50 ml of water while stirring.

**4.10 Sulphuric acid** ( $\rho_{20}$  1,840 g/mL), AR grade.

**4.11 Sulphuric acid**, dilute (1 + 1).

Slowly add 50 ml of sulphuric acid (4.10) to 50 ml of water while stirring.

**4.12 Sulphuric acid**, dilute (1 + 50).

Slowly add 20 ml of sulphuric acid (4.10) to 1 000 ml of water while stirring.

The addition of sulphuric acid to water generates heat and shall be performed with adequate precautions.

**4.13 Hydrofluoric acid** ( $\rho_{20}$  1,13 g/mL).

**4.14 Aqueous ammonia** ( $\rho_{20}$  0,91 g/mL).

**4.15 Ammonia solution** (1 + 99).

**4.16 Iron(III) chloride solution** (10 g/l).

Dissolve 48,4 g iron (III) chloride hexahydrate (4.3) in 200 ml of water. Add 10 ml of hydrochloric acid (4.8) and make up to 1 000 ml with water and mix.

**4.17 Sodium hydroxide solution** (20 % w/v).

Weigh 20,0 g of sodium hydroxide (4.1) in a polytetrafluoroethylene beaker (5.6). Add 50 ml of water and allow the solid to dissolve. Dilute the solution to 100 ml and store in a labelled polyethylene container.

**4.18 Saturated solution of potassium chlorate in nitric acid.**

Superfluous potassium chlorate is added into the nitric acid and then the deposited solution is allowed to form the saturated solution.

**4.19 Ammonium acetate** (25 % w/v).

Dissolve 25,0 g of ammonium acetate (4.5) into 100 ml water.

**4.20 Arsenic standard solution**, 1 ml contains 1 mg of As.

Weigh 1 320,3 g of arsenic trioxide (4.2) to the nearest 0,1 mg, Transfer to a 400 ml beaker and add 5 ml of sodium hydroxide solution (4.17). Warm slightly to dissolve. When dissolution is complete, cool and add 40 ml of nitric acid (4.6). Transfer to a 1 000 ml volumetric flask containing 60 ml of nitric acid (4.6). Fill up nearly to the mark with water, mix, and equilibrate at room temperature then fill up exactly to the mark and mix again. Store in a labelled container.

Alternatively, purchase a suitable high quality prepared standard.

Before use, compare this International Standard against a traceable National Standard to ensure suitability for use.

**4.21 Arsenic standard solution**, 1 ml contains 0,2 mg of As.

Pipette 40 ml of arsenic standard solution (4.20) into a 200 ml volumetric flask containing 2 ml hydrochloric acid (4.8). Fill up nearly to the mark with water, mix, and equilibrate at room temperature then fill up exactly to the mark and mix again. Store in a labelled glass container.

**5 Apparatus**

All laboratory glassware and equipment shall be shown to be free of arsenic contamination.

**5.1 Balance**, sensitive to  $\pm 0,000$  1 g.**5.2 Ordinary laboratory glassware**, complying with ISO 648 and ISO 1042 and used in accordance with ISO 4787.**5.3 Inductively coupled plasma atomic emission spectrometer (ICP-AES).**

The emission wavelength should be set to 193,696 nm or 197,197 nm.

**5.4 Insoluble filter paper**, Whatman®<sup>1)</sup> No. 40 or equivalent.**5.5 Coprecipitation filter paper**, Whatman®<sup>1)</sup> No. 1 or equivalent.

1) This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO.

**5.6 Polytetrafluoroethylene beaker**, 200 ml capacity.

## 6 Sample

### 6.1 Laboratory sample

Laboratory samples shall be taken and prepared in accordance with the procedures described in ISO 12743.

As arsenic may evaporate from samples at elevated temperatures, consideration should be given to preparing a separate chemical analysis sample as described in ISO 12743:2006, 16.2.

### 6.2 Test sample

Prepare an air-equilibrated test sample and a hygroscopic moisture test sample in accordance with ISO 9599.

NOTE A test sample is not required if pre-dried test portions are to be used (see [Annex A](#)).

### 6.3 Test portion

Taking multiple increments, extract approximately 0,5 g from the test sample and weigh to the nearest 0,1 mg. At the same time, as test portions are being weighed for analysis, weigh test portions for the determination of hygroscopic moisture in accordance with ISO 9599.

Alternatively, the method specified in [Annex A](#) may be used to prepare pre-dried test portions directly from the laboratory sample.

Obtain an approximate concentration for the iron in the sample as required in step [7.6](#).

<https://standards.iteh.ai/catalog/standards/sist/61ced248-5877-424d-b6e9-760c1f434013/iso-13547-1-2014>

## 7 Procedure

### 7.1 Number of determinations

Carry out the determinations, at least in duplicate, as far as possible under repeatability conditions on each test sample.

NOTE Repeatability conditions exist where mutually independent test results are obtained with the same method on identical test material, in the same laboratory, by the same operator using the same equipment within short intervals of time.

### 7.2 Blank test

Carry out a blank test in parallel with the analysis using the same quantities of all reagents, but omitting the test portion. The purpose of the blank test in this method is to check the quality of reagents. If a significant value is obtained as a result of the blank test, check all reagents and rectify the problem.

### 7.3 Dissolution of the test portion

Transfer the test portion into a 300 ml narrow-necked conical beaker. Moisten with 5 ml of water. Add 15 ml of the saturated solution of potassium chlorate in nitric acid ([4.18](#)), cover the beaker with a watch glass, place the conical beaker on a hotplate, and heat gently until all nitrogen oxides are expelled. Add 15 ml of diluted sulphuric acid ([4.11](#)) and heat the solution until strong white fumes have evolved then cool.



If the residue appears dark (indicating the presence of carbon), slowly add a small amount of nitric acid (4.6) to the hot solution until the solution becomes colourless, then heat until strong white fumes have evolved.

Add 50 ml of water and bring to boil, then allow cooling.

Filter the solution through an insoluble filter paper (5.4) in a 250 ml conical beaker. Wash the 300 ml conical beaker and filter paper thoroughly with dilute sulphuric acid (4.12) and collect the filtrate in the same 250 ml conical beaker.

If acid-insoluble material is present, treat this residue as the procedure in 7.5, otherwise proceed to step 7.6.

In the case of lead concentrates, proceed to step 7.4.

#### 7.4 Removal of lead sulfate

Quantitatively, transfer the precipitate into a 250 ml conical beaker with small amount of water. Add 15 ml of ammonium acetate solution (4.19) and place the conical beaker on the hotplate and heat until dissolution of the  $\text{PbSO}_4$ .

Cool the solution to room temperature and filter through an insoluble filter paper (5.4), then wash the insoluble residue with dilute sulphuric acid (4.12). Reject the filtrate and washing solution. If acid insoluble material is present, then treat this residue as the procedure in 7.5, otherwise proceed to step 7.6.

### iTeh STANDARD PREVIEW

#### 7.5 Dissolution of the insoluble residue (standards.iteh.ai)

Quantitatively, transfer the insoluble residue into a 200 ml polytetrafluoroethylene beaker (5.6) with a small quantity of deionised water. Add 5 ml of nitric acid (4.6), 2 ml of dilute sulphuric acid (4.11) and 3 ml to 5 ml of hydrofluoric acid (4.8). Heat the solution until the evolution of white sulphuric acid fumes to remove silicon dioxide then allow to cool. Dissolve the soluble salts with 10 ml of deionised water and 10 ml of nitric acid (4.6). Proceed to step 7.6.

#### 7.6 Separation of arsenic

Quantitatively, transfer the solution from step 7.5 and the filtrate from step 7.3 into a 300 ml conical beaker and dilute to approximately 150 ml with water. Add 5 g of ammonium chloride (4.4) to the solution and agitate to dissolve. Add sufficient iron chloride solution (4.16) to give a total mass of 150 mg of iron in the filtrate.

If the mass of iron from the test portion is above 150 mg, then do not add any iron chloride solution (4.16). Add sufficient aqueous ammonia (4.14) to effect complete precipitation then add an extra 10 ml of aqueous ammonia. Bring it to boil and leave boiling for 1 min.

Immediately, filter through the coprecipitation filter paper (5.5) and wash several times with warm ammonia solution (4.15). Store the coprecipitation filter paper in the original conical beaker.

Repeat the separation on the filtrate by evaporating the filtrate down to approximately 150 ml. Add 15 ml of dilute sulfuric acid (4.12) and mix, then add 5 g of ammonium chloride (4.4) to the solution and agitate to dissolve. Add sufficient iron chloride solution (4.16) to give a total mass of 150 mg iron in the filtrate. Add sufficient aqueous ammonia (4.14) to effect complete precipitation then add an extra 10 ml of aqueous ammonia. Bring to boil and leave boiling for 1 min.

Immediately, filter through the co-precipitation filter paper (5.5) and wash several times with warm ammonia solution (4.15). Reject the filtrate and washing solution.

Wash both iron precipitates from filter paper into a 400 ml beaker with water. Remove all the iron from the papers by gently adding 20 ml of hydrochloric acid (4.8) over the whole paper to dissolve the iron.

Complete the transfer of iron by washing the filter paper with small quantities of warm water. Complete the dissolution of all the iron precipitate by swirling and if necessary, very gentle heating.

## 7.7 Preparation of test solutions

Quantitatively, transfer the solutions from step 7.6 to a 200 ml volumetric flask and dilute to approximately 150 ml of deionized water. Allow this solution to cool to room temperature, then dilute to 200 ml of water and mix again.

## 7.8 Preparation of calibration solutions

Using arsenic standard (4.21), prepare a series of calibration standards as per Table 1. Transfer the appropriate volumes of arsenic standard (4.21) using pipettes into 100 ml volumetric flasks containing 10 ml of hydrochloric acid (4.8) and 15 ml of iron chloride solution (4.16). Fill up nearly to the mark with water, mix, and equilibrate at room temperature, then fill up exactly to the mark and mix again.

Table 1 — Calibrating solutions

Volume of arsenic standard ml	Arsenic mass µg	Concentration of arsenic µg/ml
0	0	0
0,5	100	1,0
1	200	2,0
2	400	4,0
5	1 000	10,0
10	2 000	20,0
20	4 000	40,0
30	6 000	60,0
35	7 000	70,0

## 7.9 Preparation of arsenic calibration curve

Set up the ICP-AES (5.3) according to the guidelines set out in 5.3. Adjust the instrument read-out scale to zero. Aspirate each calibration solution as prepared in step 7.8 through the ICP-AES and record the emission intensities. Manually or electronically plot a curve of the average emission intensities versus the mass (µg) of arsenic.

Use ISO 8466-2 as a guide to determine the acceptability of the calibration curve.

## 7.10 Determination of arsenic content in test solutions

After calibrating the ICP-AES (5.3), determine the arsenic content in the test solutions (7.8). Adjust the instrument read-out scale to zero. Aspirate the first duplicate of each sample through the ICP-AES and record the emission intensities checking the zero regularly.

Check the calibration of the instrument, then aspirate the second duplicate of each sample in the reverse order through the ICP-AES and record the emission intensities checking the zero regularly.

Determine the mass of arsenic in each test sample ( $F_{As}$ , in µg) from the curve determined in 7.9.

If more than 10 µg of arsenic is found in the blank test, then this shall be investigated and the results for the samples shall not be reported.

## 8 Expression of results

The mass fraction of arsenic in the test portion ( $w_{As}$ ), expressed as a percentage, is given by the following formula:

$$w_{As} = \frac{F_{As} - F_{As \text{ blank}}}{M \times 10^6} \times 100 K \quad (1)$$

where

$F_{As}$  is the mass of arsenic found in test sample aliquot, in  $\mu\text{g}$ ;

$F_{As \text{ blank}}$  is the mass of arsenic found in the blank test, in  $\mu\text{g}$ ;

$M$  is the mass of the test portion, in g.

$K$  is the hygroscopic moisture conversion factor, calculated using the following formula:

$$K = 100 \div (100 - H) \quad (2)$$

where

$H$  is the hygroscopic moisture content of the sample, expressed as a percentage, determined using ISO 9599.

NOTE If pre-dried test samples are used,  $H = 0$ .

## 9 Precision

ISO 13547-1:2014  
<https://standards.iteh.ai/catalog/standards/sist/61ced248-5877-424d-b6e9-760c1f434013/iso-13547-1-2014>

### 9.1 Expression of precision

The precision of this analytical method is expressed by the following formulae.

a) For copper sulfide concentrates

$$s_r = 0,0038\bar{X} + 0,0026 \quad (3)$$

$$s_L = 0,0155\bar{X} + 0,0102 \quad (4)$$

b) For lead sulfide concentrates

$$s_r = 0,009\bar{X} + 0,002 \quad (5)$$

$$s_L = 0,040\bar{X} + 0,001 \quad (6)$$

c) For zinc sulfide concentrates

$$s_r = 0,014\bar{X} \quad (7)$$

$$s_L = 0,047\bar{X} \quad (8)$$

d) For nickel sulfide concentrates