



Standard Practice for Rehabilitation of Existing Pipelines and Conduits by the Inversion and Curing of a Resin-Impregnated Tube^{1, 2}

This standard is issued under the fixed designation F 1216; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice describes the procedures for the reconstruction of pipelines and conduits (4 to 108-in. diameter) by the installation of a resin-impregnated, flexible tube which is inverted into the existing conduit by use of a hydrostatic head or air pressure. The resin is cured by circulating hot water or introducing controlled steam within the tube. When cured, the finished pipe will be continuous and tight-fitting. This reconstruction process can be used in a variety of gravity and pressure applications such as sanitary sewers, storm sewers, process piping, electrical conduits, and ventilation systems.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. For specific precautionary statements, see 7.4.2.*

2. Referenced Documents

2.1 ASTM Standards:³

- D 543 Practices for Evaluating the Resistance of Plastics to Chemical Reagents
- D 638 Test Method for Tensile Properties of Plastics
- D 790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials
- D 903 Test Method for Peel or Stripping Strength of Adhesive Bonds

¹ This practice is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.67 on Trenchless Plastic Pipeline Technology.

Current edition approved June 1, 2007. Published June 2007. Originally approved in 1989. Last previous edition approved 2007 as F 1216 – 07a.

² The following report has been published on one of the processes: Driver, F. T., and Olson, M. R., "Demonstration of Sewer Relining by the Insituform Process, Northbrook, Illinois," EPA-600/2-83-064, Environmental Protection Agency, 1983. Interested parties can obtain copies from the Environmental Protection Agency or from a local technical library.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D 1600 Terminology for Abbreviated Terms Relating to Plastics

D 3839 Guide for Underground Installation of "Fiberglass" (Glass-Fiber Reinforced Thermosetting-Resin) Pipe

F 412 Terminology Relating to Plastic Piping Systems

2.2 AWWA Standard:

Manual on Cleaning and Lining Water Mains, M 28⁴

2.3 NASSCO Standard:

Recommended Specifications for Sewer Collection System Rehabilitation⁵

NOTE 1—An ASTM specification for cured-in-place pipe materials appropriate for use in this standard is under preparation and will be referenced in this practice when published.

3. Terminology

3.1 Definitions are in accordance with Terminology F 412 and abbreviations are in accordance with Terminology D 1600, unless otherwise specified.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *cured-in-place pipe (CIPP)*—a hollow cylinder containing a nonwoven or a woven material, or a combination of nonwoven and woven material surrounded by a cured thermosetting resin. Plastic coatings may be included. This pipe is formed within an existing pipe. Therefore, it takes the shape of and fits tightly to the existing pipe.

3.2.2 *inversion*—the process of turning the resin-impregnated tube inside out by the use of water pressure or air pressure.

3.2.3 *lift*—a portion of the CIPP that has cured in a position such that it has pulled away from the existing pipe wall.

4. Significance and Use

4.1 This practice is for use by designers and specifiers, regulatory agencies, owners, and inspection organizations who are involved in the rehabilitation of conduits through the use of a resin-impregnated tube inverted through the existing conduit. As for any practice, modifications may be required for specific job conditions.

⁴ Available from American Water Works Association (AWWA), 6666 W. Quincy Ave., Denver, CO 80235, http://www.awwa.org.

⁵ Available from the National Association of Sewer Service Companies, 101 Wymore Rd., Suite 501, Altamonte, FL 32714.

5. Materials

5.1 *Tube*—The tube should consist of one or more layers of flexible needled felt or an equivalent nonwoven or woven material, or a combination of nonwoven and woven materials, capable of carrying resin, withstanding installation pressures and curing temperatures. The tube should be compatible with the resin system used. The material should be able to stretch to fit irregular pipe sections and negotiate bends. The outside layer of the tube should be plastic coated with a material that is compatible with the resin system used. The tube should be fabricated to a size that, when installed, will tightly fit the internal circumference and the length of the original conduit. Allowance should be made for circumferential stretching during inversion.

5.2 *Resin*—A general purpose, unsaturated, styrene-based, thermoset resin and catalyst system or an epoxy resin and hardener that is compatible with the inversion process should be used. The resin must be able to cure in the presence of water and the initiation temperature for cure should be less than 180°F (82.2°C). The CIPP system can be expected to have as a minimum the initial structural properties given in **Table 1**. These physical strength properties should be determined in accordance with Section 8.

6. Design Considerations

6.1 *General Guidelines*—The design thickness of the CIPP is largely a function of the condition of the existing pipe. Design equations and details are given in Appendix X1.

7. Installation

7.1 *Cleaning and Inspection:*

7.1.1 Prior to entering access areas such as manholes, and performing inspection or cleaning operations, an evaluation of the atmosphere to determine the presence of toxic or flammable vapors or lack of oxygen must be undertaken in accordance with local, state, or federal safety regulations.

7.1.2 *Cleaning of Pipeline*—All internal debris should be removed from the original pipeline. Gravity pipes should be cleaned with hydraulically powered equipment, high-velocity jet cleaners, or mechanically powered equipment (see **NASSCO Recommended Specifications for Sewer Collection System Rehabilitation**). Pressure pipelines should be cleaned with cable-attached devices or fluid-propelled devices as shown in **AWWA Manual on Cleaning and Lining Water Mains, M 28**.

7.1.3 *Inspection of Pipelines*—Inspection of pipelines should be performed by experienced personnel trained in

locating breaks, obstacles, and service connections by closed-circuit television or man entry. The interior of the pipeline should be carefully inspected to determine the location of any conditions that may prevent proper installation of the impregnated tube, such as protruding service taps, collapsed or crushed pipe, and reductions in the cross-sectional area of more than 40 %. These conditions should be noted so that they can be corrected.

7.1.4 *Line Obstructions*—The original pipeline should be clear of obstructions such as solids, dropped joints, protruding service connections, crushed or collapsed pipe, and reductions in the cross-sectional area of more than 40 % that will prevent the insertion of the resin-impregnated tube. If inspection reveals an obstruction that cannot be removed by conventional sewer cleaning equipment, then a point repair excavation should be made to uncover and remove or repair the obstruction.

7.2 *Resin Impregnation*—The tube should be vacuum-impregnated with resin (wet-out) under controlled conditions. The volume of resin used should be sufficient to fill all voids in the tube material at nominal thickness and diameter. The volume should be adjusted by adding 5 to 10 % excess resin for the change in resin volume due to polymerization and to allow for any migration of resin into the cracks and joints in the original pipe.

7.3 *Bypassing*—If bypassing of the flow is required around the sections of pipe designated for reconstruction, the bypass should be made by plugging the line at a point upstream of the pipe to be reconstructed and pumping the flow to a downstream point or adjacent system. The pump and bypass lines should be of adequate capacity and size to handle the flow. Services within this reach will be temporarily out of service.

7.3.1 Public advisory services will be required to notify all parties whose service laterals will be out of commission and to advise against water usage until the mainline is back in service.

7.4 *Inversion:*

7.4.1 *Using Hydrostatic Head*—The wet-out tube should be inserted through an existing manhole or other approved access by means of an inversion process and the application of a hydrostatic head sufficient to fully extend it to the next designated manhole or termination point. The tube should be inserted into the vertical inversion standpipe with the impermeable plastic membrane side out. At the lower end of the inversion standpipe, the tube should be turned inside out and attached to the standpipe so that a leakproof seal is created. The inversion head should be adjusted to be of sufficient height to cause the impregnated tube to invert from point of inversion to point of termination and hold the tube tight to the pipe wall, producing dimples at side connections. Care should be taken during the inversion so as not to over-stress the felt fiber.

7.4.1.1 An alternative method of installation is a top inversion. In this case, the tube is attached to a top ring and is inverted to form a standpipe from the tube itself or another method accepted by the engineer.

NOTE 2—The tube manufacturer should provide information on the maximum allowable tensile stress for the tube.

7.4.2 *Using Air Pressure*—The wet-out tube should be inserted through an existing manhole or other approved access

TABLE 1 CIPP Initial Structural Properties^A

Property	Test Method	Minimum Value	
		psi	(MPa)
Flexural strength	D 790	4 500	(31)
Flexural modulus	D 790	250 000	(1 724)
Tensile strength (for pressure pipes only)	D 638	3 000	(21)

^AThe values in Table 1 are for field inspection. The purchaser should consult the manufacturer for the long-term structural properties.

by means of an inversion process and the application of air pressure sufficient to fully extend it to the next designated manhole or termination point. The tube should be connected by an attachment at the upper end of the guide chute so that a leakproof seal is created and with the impermeable plastic membranes side out. As the tube enters the guide chute, the tube should be turned inside out. The inversion air pressure should be adjusted to be of sufficient pressure to cause the impregnated tube to invert from point of inversion to point of termination and hold the tube tight to the pipe wall, producing dimples at side connections. Care should be taken during the inversion so as not to overstress the woven and nonwoven materials.

NOTE 3—Warning: Suitable precautions should be taken to eliminate hazards to personnel in the proximity of the construction when pressurized air is being used.

7.4.3 Required Pressures—Before the inversion begins, the tube manufacturer shall provide the minimum pressure required to hold the tube tight against the existing conduit, and the maximum allowable pressure so as not to damage the tube. Once the inversion has started, the pressure shall be maintained between the minimum and maximum pressures until the inversion has been completed.

7.5 Lubricant—The use of a lubricant during inversion is recommended to reduce friction during inversion. This lubricant should be poured into the inversion water in the downtube or applied directly to the tube. The lubricant used should be a nontoxic, oil-based product that has no detrimental effects on the tube or boiler and pump system, will not support the growth of bacteria, and will not adversely affect the fluid to be transported.

7.6 Curing:

7.6.1 Using Circulating Heated Water—After inversion is completed, a suitable heat source and water recirculation equipment are required to circulate heated water throughout the pipe. The equipment should be capable of delivering hot water throughout the section to uniformly raise the water temperature above the temperature required to effect a cure of the resin. Water temperature in the line during the cure period should be as recommended by the resin manufacturer.

7.6.1.1 The heat source should be fitted with suitable monitors to gage the temperature of the incoming and outgoing water supply. Another such gage should be placed between the impregnated tube and the pipe invert at the termination to determine the temperatures during cure.

7.6.1.2 Initial cure will occur during temperature heat-up and is completed when exposed portions of the new pipe appear to be hard and sound and the remote temperature sensor indicates that the temperature is of a magnitude to realize an exotherm or cure in the resin. After initial cure is reached, the temperature should be raised to the post-cure temperature recommended by the resin manufacturer. The post-cure temperature should be held for a period as recommended by the resin manufacturer, during which time the recirculation of the water and cycling of the boiler to maintain the temperature continues. The curing of the CIPP must take into account the existing pipe material, the resin system, and ground conditions (temperature, moisture level, and thermal conductivity of soil).

7.6.2 Using Steam—After inversion is completed, suitable steam-generating equipment is required to distribute steam throughout the pipe. The equipment should be capable of delivering steam throughout the section to uniformly raise the temperature within the pipe above the temperature required to effect a cure of the resin. The temperature in the line during the cure period should be as recommended by the resin manufacturer.

7.6.2.1 The steam-generating equipment should be fitted with a suitable monitor to gage the temperature of the outgoing steam. The temperature of the resin being cured should be monitored by placing gages between the impregnated tube and the existing pipe at both ends to determine the temperature during cure.

7.6.2.2 Initial cure will occur during temperature heat-up and is completed when exposed portions of the new pipe appear to be hard and sound and the remote temperature sensor indicates that the temperature is of a magnitude to realize an exotherm or cure in the resin. After initial cure is reached, the temperature should be raised to post-cure temperatures recommended by the resin manufacturer. The post-cure temperature should be held for a period as recommended by the resin manufacturer, during which time the distribution and control of steam to maintain the temperature continues. The curing of the CIPP must take into account the existing pipe material, the resin system, and ground conditions (temperature, moisture level, and thermal conductivity of soil).

7.6.3 Required Pressures—As required by the purchase agreement, the estimated maximum and minimum pressure required to hold the flexible tube tight against the existing conduit during the curing process should be provided by the seller and shall be increased to include consideration of the external ground water, if present. Once the cure has started and dimpling for laterals is completed, the required pressures should be maintained until the cure has been completed. For water or steam, the pressure should be maintained within the estimated maximum and minimum pressure during the curing process. If the steam pressure or hydrostatic head drops below the recommended minimum during the cure, the CIPP should be inspected for lifts or delaminations and evaluated for its ability to fully meet the applicable requirements of 7.8 and Section 8.

7.7 Cool-Down:

7.7.1 Using Cool Water After Heated Water Cure—The new pipe should be cooled to a temperature below 100°F (38°C) before relieving the static head in the inversion standpipe. Cool-down may be accomplished by the introduction of cool water into the inversion standpipe to replace water being drained from a small hole made in the downstream end. Care should be taken in the release of the static head so that a vacuum will not be developed that could damage the newly installed pipe.

7.7.2 Using Cool Water After Steam Cure—The new pipe should be cooled to a temperature below 113°F (45°C) before relieving the internal pressure within the section. Cool-down may be accomplished by the introduction of cool water into the section to replace the mixture of air and steam being drained from a small hole made in the downstream end. Care should be