INTERNATIONAL STANDARD

First edition 2012-02-01

Plain bearings — Pad materials for tilting pad bearings

Paliers lisses — Matériaux des patins pour paliers à patins oscillants

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 14287:2012</u> https://standards.iteh.ai/catalog/standards/sist/0284c771-1664-4dd2b588-f7b70902303f/iso-14287-2012



Reference number ISO 14287:2012(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 14287:2012</u> https://standards.iteh.ai/catalog/standards/sist/0284c771-1664-4dd2b588-f7b70902303f/iso-14287-2012



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Page

Contents

Forewo	ordi	v
Introdu	uction	v
1	Scope	1
2	Normative references	1
3	Requirements	1
3.1	General	1
3.2	Metallic materials	1
3.3	Polymer materials	2
3.4	Back metal materials	3
3.5	Pivot materials	3
Annex	A (informative) Guidance on properties and selection of materials	4

iTeh STANDARD PREVIEW (standards.iteh.ai)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 14287 was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 7, *Special types of plain bearings*.

iTeh STANDARD PREVIEW (standards.iteh.ai)

Introduction

Tilting pad bearings support loads equally with their pads, which are pivoted at the supporting points on their back surfaces. This configuration allows the pads to tilt freely; it serves to keep the shape of the oil film on the sliding surface in optimum condition and improve load-carrying capabilities.

Such bearings are normally used as thrust and journal bearings for rotating machineries; they operate under static load conditions with lubricating oil applied. They have been used for many years and have a long history. As a result of developments in high-speed, high-performance rotating machineries, many various types of pad materials have been put into practical use.

iTeh STANDARD PREVIEW (standards.iteh.ai)

iTeh STANDARD PREVIEW (standards.iteh.ai)

Plain bearings — Pad materials for tilting pad bearings

Scope 1

This International Standard specifies requirements for materials based on metals, polymers, back metals and pivots for the manufacture of tilting pad bearings.

Normative references 2

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4381, Plain bearings — Tin casting alloys for multilayer plain bearings

ISO 4383, Plain bearings — Multilayer materials for thin-walled plain bearings

Requirements 3

iTeh STANDARD PREVIEW 3.1 General

The sliding surface of a pad may be composed of a metal bearing material or a polymer material, which is typically bonded to the back metal, depending on the conditions for operation of the bearing. Alloys are in accordance with ISO 4381; materials are in accordance with ISO 4383. Guidance for the selection of pad surface layer materials is given in Annex A

b588-f7b70902303f/iso-14287-2012

3.2 Metallic materials

3.2.1 Typical materials

The chemical composition of some typical materials based on metal are given in Table 1.

3.2.2 Tin-based whitemetals

Tin-based whitemetals are used as general-purpose metallic materials. They are provided with linings by casting, in general.

Whitemetals are characterized by good castability. However, attention should be paid to guality problems, such as bonding strength with the back metal, segregation and blow holes.

To ensure appropriate strength/softness of a whitemetal alloy, the combination of Sb and Cu described in Table 1 is used in many applications.

Lead-based whitemetals are rarely used because of their effects on the environment.

3.2.3 Aluminium bearing alloys

Aluminium-based bearing alloys are used for high-speed operation under high-load and high-temperature conditions. Al-Sn alloys, i.e. alloys which are made by adding tin to aluminium, are the most commonly used aluminium bearing alloys. To improve sliding characteristics at high speed, 40 % Sn-Al alloy is typically used.

The pad of a bearing manufactured from such an alloy is formed from a bimetal strip consisting of an aluminium alloy, which is roll-bonded to carbon steel. The pad of a journal bearing made from such an alloy can have

uneven alloy thickness along the slide direction because it is formed by bending; it is possible to correct the thickness to make it even.

3.2.4 Lead-bronze bearing alloys

Lead-bronze bearing alloys are used under operating conditions equivalent to those for aluminium-bearing alloys or under higher load and higher temperature conditions. However, lead-bronze bearing alloys have limited uses. Lead-bronze bearing alloys are high in hardness; they normally require surface hardening (quench hardening, etc.) on the sliding surfaces of mating parts.

The pad of a bearing manufactured from such an alloy, as in the case of an aluminium bearing alloy, is typically formed from a bimetal strip. Although it is a rare case, it can take the form of a copper alloy (solid or cast) with a steel backing.

	Chemical composition				
Chemical element	mass fraction, %				
	Tin-based whitemetals	Aluminium bearing alloys	Lead-bronze bearing alloys		
Sn	Remainder	35 to 42	8 to 12		
AI	0,01	Remainder			
Cu	3 to 5	0,7 to 1,3	Remainder		
Sb	i Testo to TANI	JARD PREVIE	0,5		
Pb	0,5 (stand	ards itat ai)	7 to 13		
Zn	0,01		0,75		
Ni	IS	0.14287.2012,0,15	0,5		
Si	https://standards.iteh.ai/catal	og/standards/sis90284c771-1664-	4dd2- —		
Fe	0,08 b588-f7b709	02303f/iso-14 2 8 7 -2012	0,35		
Bi	0,08	—	—		
As	0,01	_	_		

Table 1 — Chemical composition of metal materials

3.3 Polymer materials

Bearings with pads having polymer layers on their sliding surfaces, which are characterized by polymer-specific tribological characteristics, are in use.

Polyether-etherketone (PEEK) and polytetrafluoro-ethylene (PTFE) polymer materials are available. Bearings composed of such materials are provided with special measures to allow for bonding to the back metal. A porous metal layer is used as the bonding interface layer and its voids are impregnated with a polymer layer material to form a sliding surface layer. Thus, the metal interface layer is joined with the back metal. PEEK polymer materials contain some PTFE in order to improve sliding characteristics.

The chemical composition of some typical polymer materials are given in Table 2.

Two types of electrical conductivities are provided: conductive and non-conductive, which are determined depending on the elements added. Non-conductive polymer materials have the advantage of preventing electro-erosion without an additional insulator.

		Chemical composition mass fraction, %			
Chemical element					
	PEEK	PEEK material			
PEEK	Remainder	Remainder	—		
PTFE	1 to 3	8 to 12	Remainder		
CF	27 to 33	—	10 to 20		
MoS ₂	—	—	4 to 6		
CF carbon fibre					
MoS ₂ molybdenum	n disulfide				

Table 2 — Chemical composition of polymer materials

3.4 Back metal materials

Low-carbon steels containing approximately 0,10 % C to 0,35 % C are often used as back metal materials. The carbon content of a back metal material is typically determined using a combination of a surface layer bearing material and a bonding process.

In the case of bearings operating under high-speed and high-temperature conditions, a copper alloy may be used as a back metal, although it is a rare case. Back metals of the copper alloy are usually Cu-Cr (copper chromium) alloy, which are expected to decrease pad temperature by approximately 10 °C to 20 °C because of their excellent thermal conductivity. TANDARD PREVIEW

3.5 Pivot materials

(standards.iteh.ai)

Pivots are subjected to concentrated loads and may be separated from the pads. Pivot materials are very hard and are fixed to pads. A typical example of a pivot is a flat, cylindrical one. It is press-fitted on to the back surface of a pad and is then secured by caulking. High-carbon chromium bearing steels containing approximately 0,95 % C to 1,10 % C are commonly used pivot material and thermally treated, in general.

The shape of a pivot is designed to have different curvatures with respect to the circumferential and axial directions to allow the pad to tilt freely in the circumferential and axial directions.

Pivots may be installed on the bearing casing side on their designs.