
**Petroleum and natural gas industries —
Drilling fluid materials — Specifications
and tests**

AMENDMENT 1: Barite 4,1

*Industries du pétrole et du gaz naturel — Produits pour fluides
de forage — Specifications et essais*
AMENDEMENT 1: Baryte 4,1

ISO 13500:2008/Amd 1:2010

<https://standards.iteh.ai/catalog/standards/sist/9d6e0e3c-35b6-4a85-bcb7-d02ac224e431/iso-13500-2008-amd-1-2010>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 13500:2008/Amd 1:2010](https://standards.iteh.ai/catalog/standards/sist/9d6e0e3c-35b6-4a85-bcb7-d02ac224e431/iso-13500-2008-amd-1-2010)

<https://standards.iteh.ai/catalog/standards/sist/9d6e0e3c-35b6-4a85-bcb7-d02ac224e431/iso-13500-2008-amd-1-2010>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 13500:2008 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 3, *Drilling and completion fluids, and well cements*.

Amendment 1 to ISO 13500:2008¹⁾ covers the physical properties and testing of the newly available drilling fluid product, Barite 4,1. It constitutes an alternative to the specifications of Clause 7²⁾, which cover the physical properties and testing of Barite, and is not intended to replace Clause 7.

[ISO 13500:2008/Amd 1:2010](https://standards.iteh.ai/catalog/standards/sist/9d6e0e3c-35b6-4a85-bcb7-d02ac224e431/iso-13500-2008-amd-1-2010)

<https://standards.iteh.ai/catalog/standards/sist/9d6e0e3c-35b6-4a85-bcb7-d02ac224e431/iso-13500-2008-amd-1-2010>

-
- 1) Amendment 1 to ISO 13500:2008 also constitutes Amendment 1 to API Specification 13A.
 - 2) ISO 13500:2008, Clause 7, is equivalent to API Specification 13A, Section 7.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 13500:2008/Amd 1:2010](https://standards.iteh.ai/catalog/standards/sist/9d6e0e3c-35b6-4a85-bcb7-d02ac224e431/iso-13500-2008-amd-1-2010)

<https://standards.iteh.ai/catalog/standards/sist/9d6e0e3c-35b6-4a85-bcb7-d02ac224e431/iso-13500-2008-amd-1-2010>

Petroleum and natural gas industries — Drilling fluid materials — Specifications and tests

AMENDMENT 1: Barite 4,1

Page 82

Add the following new clause immediately after Subclause 19.8.3.

20 Barite 4,1

20.1 Principle

20.1.1 Drilling grade barite is produced from commercial barium sulfate-containing ores. The manufacturer shall retain certificates of analysis or similar documentation on these commercial barium sulfate ores. It may be produced from a single ore or a blend of ores and may be a straight-mined product or processed by beneficiation methods, i.e. washing, tabling, jigging, or flotation. It may contain accessory minerals other than the barium sulfate (BaSO_4) mineral. Because of mineral impurities, commercial barite may vary in colour from off-white to grey to red or brown. Common accessory minerals are silicates such as quartz and chert, carbonate compounds such as siderite and dolomite, and metallic oxide and sulfide compounds. Although these minerals are normally insoluble, they can, under certain conditions, react with other components in some types of drilling fluids and cause adverse changes in the drilling fluid properties. (See Annex A for more details.)

20.1.2 Drilling grade barium sulfate meeting the Barite 4,1 physical and chemical specifications listed in Table 19 is not intended to meet the requirements of performance tests described in ISO and API publications. Additionally, it is not intended to be used as a reference or calibration material as specified in ISO and API publications.

20.1.3 End users should be aware that the material described in this clause has a lower density than Barite as specified in Clause 7. Drilling fluid formulations should be developed to accommodate this lower density material. Maximum practical drilling fluid density for specific formulations may be lower than attainable with Barite as specified in Clause 7.

20.1.4 End users should review fluid engineering calculations to determine where density differences between Barite 4,1, as specified in this clause, and Barite, as specified in Clause 7, will require revisions to these calculations.

20.1.5 Barite 4,1 shall be deemed to meet the requirements of this International Standard if a composite sample representing no more than one day's production conforms to the chemical and physical specifications of Table 19, represents the product produced, and is controlled by the manufacturer.

Table 19 — Barite 4,1 physical and chemical requirements

Requirement	Standard
Density	4,10 g/ml, minimum
Water-soluble alkaline earth metals, as calcium	250 mg/kg, maximum
Residue greater than 75 µm	Maximum mass fraction, 3,0 %
Particles less than 6 µm in equivalent spherical diameter	Maximum mass fraction, 30 %

20.2 Reagents and apparatus — Density by Le Chatelier flask

20.2.1 Kerosene or mineral spirits.

20.2.2 Oven, regulated to 105 °C ± 3 °C (220 °F ± 5 °F).

20.2.3 Desiccator, with calcium sulfate (CAS No. 7778-18-9) desiccant or equivalent.

20.2.4 Le Chatelier flask, with graduations of 0,1 ml, clamped or weighted to prevent flotation in water bath.

20.2.5 Constant-temperature bath, transparent at 32 °C ± 0,5 °C regulated to ±0,1 °C (90 °F ± 1,0 °F regulated to ±0,2 °F) [e.g. approximately 40 l aquarium (fish tank) with heater/circulator attachment, or functional equivalent].

20.2.6 Balance, with an accuracy of 0,01 g.

20.2.7 Pipette, volumetric, of 10 ml capacity.

20.2.8 Magnifying glass.

20.2.9 Dowel, wooden, approximately 8 mm (1/3 in) in diameter and 30 cm (12 in) in length, or a functional equivalent.

20.2.10 Tissue paper, absorbent.

NOTE Laboratory grade tissues are non-absorbent and thus unsuitable for use in this test procedure.

20.2.11 Weighing dish, low-form, with spout, of approximately 100 ml capacity, or a functional equivalent.

20.2.12 Brush, small, fine bristle.

20.3 Procedure — Density by Le Chatelier flask

20.3.1 Take approximately 100 g of Barite 4,1 which has been oven dried for at least 2 h and cooled to room temperature in a desiccator.

20.3.2 Fill a clean Le Chatelier flask to approximately 20 mm (0,8 in) below the zero mark with kerosene.

20.3.3 Place the flask upright in the constant-temperature bath. The level of water in the bath shall be higher than the 24 ml graduation of the flask, but below the stopper level. Ensure flask is stabilized by use of clamps or weights.

20.3.4 Allow the flask and contents to equilibrate for a minimum of 1 h. Using the magnifying glass with care to keep eyes at meniscus level, read the volume at the lowest portion of the curved interface, and record the initial volume to the nearest 0,05 ml without removing the flask from the constant-temperature bath. Record as V_1 .

If the kerosene level is above or below the $-0,2$ ml to $+1,2$ ml volume range after equilibrating, use the 10 ml pipette to add or remove kerosene in order for it to come within this range. Allow the flask to equilibrate for at least 1 h and record the initial volume as in 20.3.4.

20.3.5 Remove the Le Chatelier flask from the bath, wipe dry, and remove the stopper. Roll several lengths of tissue paper diagonally along the length of the dowel, and use this assembly as a swab to dry the inside neck of the flask. Do not allow the swab to come into contact with the kerosene in the flask.

20.3.6 Weigh $80 \text{ g} \pm 0,05 \text{ g}$ dried Barite 4,1 into the weighing dish and carefully transfer to the Le Chatelier flask. Take care to avoid splashing the kerosene or plugging the flask with Barite 4,1 at the bulb. This is a slow process, requiring repeated transfers of small amounts of Barite 4,1. Use a brush to transfer any residual Barite 4,1 into the flask, then replace the stopper. Record the mass as m .

20.3.7 If necessary, carefully tap the neck of the flask with the wooden dowel, or agitate carefully from side to side, to dislodge any Barite 4,1 clinging to the walls. Do not allow kerosene to come into contact with the ground glass stopper joint of the flask.

20.3.8 Gently roll the flask along a smooth surface at no more than 45° from vertical, or twirl the upright flask at the neck vigorously between the palms of both hands, to remove entrained air from the Barite 4,1 sample. Repeat this procedure until no more bubbles can be seen rising from the Barite 4,1.

20.3.9 Return the flask to the bath and let stand for at least 0,5 h.

20.3.10 Remove the flask from the bath and repeat 20.3.8 to remove any remaining air from the Barite 4,1 sample.

20.3.11 Immerse the flask in the bath again for at least 1 h.

20.3.12 Record the final volume in the same manner as described in 20.3.4. Record the volume as V_2 .

20.4 Calculation — Density by Le Chatelier flask

Calculate the density, ρ , in grams per millilitre, according to Equation (53):

$$\rho = \frac{m}{(V_2 - V_1)} \quad (53)$$

where

m is the sample mass, expressed in grams;

V_1 is the initial volume, expressed in millilitres;

V_2 is the final volume, expressed in millilitres.

Record the calculated density.

20.5 Reagents and apparatus — Water-soluble alkaline earths as calcium

20.5.1 Aqueous EDTA solution, composed of $3,72 \text{ g} \pm 0,01 \text{ g}$ of the disodium salt of ethylenediaminetetraacetic acid dihydrate [disodium salt of (ethylenedinitrilo)tetraacetic acid dihydrate] (CAS No. 6381-92-6) diluted to a final volume of 1 000 ml with deionized water in a volumetric flask.

20.5.2 Buffer solution, comprising $67,5 \text{ g} \pm 0,01 \text{ g}$ of ammonium chloride (CAS No. 12125-02-9) and $570 \text{ ml} \pm 1 \text{ ml}$ of 15 mol/l ammonium hydroxide (CAS No. 1336-21-6) solution diluted to a final volume of 1 000 ml with deionized water in a volumetric flask.

20.5.3 Hardness indicator solution, comprising 1,00 g \pm 0,01 g of Calmagite (CAS No. 3147-14-6), or equivalent [1-(1-hydroxy-4-methylphenylazo)-2-naphthol-4-sulfonic acid] diluted to a final volume of 1 000 ml with deionized water in a volumetric flask.

20.5.4 Deionized (or distilled) water.

20.5.5 Balance, of capacity exceeding 100 g with an accuracy of 0,01 g.

20.5.6 Erlenmeyer flask, of 250 ml nominal capacity, equipped with a tight-fitting stopper.

20.5.7 Graduated cylinder, of 100 ml to 150 ml capacity (TC) with 1 ml graduations.

20.5.8 Titration vessel, e.g. beaker, of 100 ml to 150 ml capacity.

20.5.9 Serological pipettes or burette, with graduations of 0,1 ml.

20.5.10 Volumetric pipettes (TD), of 10 ml capacity or equivalent.

20.5.11 Filter press, low-pressure/low-temperature, in accordance with ISO 10414-1:2008, Clause 7, or filtration funnel.

20.5.12 Filter paper, Whatman 50, or equivalent.

20.5.13 Glass container, small.

20.5.14 Wrist-action shaker, optional.

20.5.15 Volumetric flask, of 1 000 ml capacity.

20.5.16 Stirring rod.

STANDARD PREVIEW
(standards.iteh.ai)
ISO 13500:2008/Amd 1:2010
<https://standards.iteh.ai/catalog/standards/sist/9d6e0e3c-35b6-4a85-bcb7-324e4311c-13500-2008-amd-1-2010>

20.6 Procedure — Water-soluble alkaline earth metals as calcium

20.6.1 Weigh 100 g \pm 0,05 g of Barite 4,1. Transfer to the Erlenmeyer flask and add 100 ml \pm 1 ml of deionized water. Stopper the flask and shake for at least 5 min during an approximate 1 h interval or by an optional mechanical shaking apparatus for 20 min to 30 min.

20.6.2 After shaking, filter the suspension through the low-pressure filter cell or funnel using two sheets of filter paper and collect filtrate in a suitable glass container.

20.6.3 Add 50 ml \pm 1 ml deionized water to the titration vessel. Add about 2 ml of hardness buffer and sufficient hardness indicator to achieve a distinct blue colour. Swirl to mix.

A solution whose colour is other than distinct blue at this point indicates contamination of the equipment and/or water. Find and eliminate the source of contamination and rerun the test.

20.6.4 Using the volumetric pipette, measure 10 ml of the filtrate into the titrating vessel. Swirl to mix. A blue colour indicates an absence of calcium hardness and the test is then complete. A wine-red colour will develop if calcium and/or magnesium are present. Record as V_4 .

20.6.5 If hardness is present, begin stirring and titrate with EDTA solution to the blue endpoint. The endpoint of the titration is best described as the point at which additional EDTA produces no further red to blue change. The EDTA volume used to produce the blue endpoint will be used in the calculation in 20.7. Record as V_3 .

If the endpoint is unclear or unobtainable, other tests shall be performed. Results and methodology of these tests shall be recorded.

20.7 Calculation — Water-soluble alkaline earths as calcium

Calculate the soluble alkaline earth metals as calcium, w_{AEM} , in milligrams per kilogram, according to Equation (54).

$$w_{\text{AEM}} = 400 \left(\frac{V_3}{V_4} \right) \quad (54)$$

where

V_3 is the volume of EDTA used, expressed in millilitres;

V_4 is the volume of filtrate used, expressed in millilitres.

Record the calculated value.

20.8 Reagents and materials — Residue of diameter greater than 75 µm

20.8.1 Sodium hexametaphosphate (CAS No. 10124-56-8).

20.8.2 Oven, regulated to 105 °C ± 3 °C (220 °F ± 5 °F).

20.8.3 Desiccator, with calcium sulfate (CAS No. 7778-18-9) desiccant or equivalent.

20.8.4 Balance, with an accuracy of 0,01 g.

20.8.5 Mixer (e.g. Multimixer® Model 9B with 9B29X impellers or equivalent), having each spindle fitted with a single sine-wave impeller, approximately 25 mm (1 in) in diameter, mounted flash side up.

20.8.6 Container, of approximate dimensions 180 mm (7,1 in) deep, 97 mm (3-5/6 in) d top, 70 mm (2,75 in) d bottom (e.g. Hamilton Beach® mixer cup No. M110-D³⁾, or equivalent).

20.8.7 Sieve, 75 µm, conforming to the requirements of ASTM E161, of approximate dimensions 76 mm (3,0 in) diameter and 69 mm (2,75 in) from top of frame to wire cloth.

NOTE Supplier's verification that sieve conforms to ASTM E161 is satisfactory evidence of compliance.

20.8.8 Spray nozzle with 1/4 TT body (Spraying Systems Co., No. TG 6.5 tip with 1/4 TT body⁴⁾, or equivalent), attached to water line with 90° elbow.

20.8.9 Water pressure regulator, capable of regulating to 69 kPa ± 7 kPa (10 psi ± 1 psi).

20.8.10 Evaporating dish or functional equivalent.

20.8.11 Wash bottle.

20.9 Procedure — Residue of diameter greater than 75 µm

20.9.1 If required, equilibrate approximately 60 g of dried Barite 4,1 in a desiccator.

3) Hamilton Beach® mixer cup No. M110-D is an example of a suitable product available commercially. This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of this product.

4) Spraying Systems Co., No. TG 6.5 tip with 1/4 TT body is an example of a suitable product available commercially. This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of this product.