
Structural steels —

Part 4:

Technical delivery conditions for high-yield-strength quenched and tempered structural steel plates

Aciers de construction —
iTeh STANDARD PREVIEW
Partie 4: Conditions techniques de livraison pour tôles en acier
(standards.iteh.ai)
de construction trempé et revenu à haute limite d'élasticité

ISO 630-4:2012

<https://standards.iteh.ai/catalog/standards/sist/7a3824ca-85f8-4d52-b889-1a3951df6db7/iso-630-4-2012>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 630-4:2012

<https://standards.iteh.ai/catalog/standards/sist/7a3824ca-85f8-4d52-b889-1a3951df6db7/iso-630-4-2012>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification and designation	2
4.1 Classification	2
4.2 Grades and qualities	2
4.3 Normative annexes	2
5 Information to be supplied by purchaser	2
5.1 Mandatory information	2
5.2 Options	2
6 Requirements	3
6.1 Steelmaking process	3
6.2 Deoxidation	3
6.3 Delivery condition	3
6.4 Chemical composition	3
6.5 Mechanical properties	3
6.6 Surface conditions	4
6.7 Internal soundness	4
6.8 Dimensions and tolerances on dimensions, shape and mass	4
7 Inspection	4
8 Sampling — Frequency of testing	4
8.1 Verification	4
8.2 Test units	4
9 Test methods	4
10 Marking	4
Annex A (normative) Steel grades S460Q, S500Q, S550Q, S620Q, S690Q, S890Q and S960Q: Chemical composition and mechanical properties	5
Annex B (normative) Steel grades SG460Q, SG500Q, and SG700Q: Chemical composition and mechanical properties	11
Bibliography	15

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 630-4 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 3, *Steels for structural purposes*.

This first edition cancels and replaces ISO 630:1995, which has been technically revised. It incorporates ISO 630:1995/Amd 1:2003.

ISO 630 consists of the following parts, under the general title *Structural steels*:

- *Part 1: General technical delivery conditions for hot-rolled products*
- *Part 2: Technical delivery conditions for structural steels for general purposes*
- *Part 3: Technical delivery conditions for fine-grain structural steels*
- *Part 4: Technical delivery conditions for high-yield-strength quenched and tempered structural steel plates*

The following parts are under preparation:

- *Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance*
- *Part 6: Technical delivery conditions for seismic improved structural steels for building*

Structural steels —

Part 4: Technical delivery conditions for high-yield-strength quenched and tempered structural steel plates

1 Scope

This part of ISO 630 specifies qualities for high-yield-strength quenched and tempered structural steels. This part of ISO 630 applies to steel plates rolled on a reversing mill which are used in the quenched and tempered condition and normally intended for welded or bolted structures.

This part of ISO 630 does not include the following structural steels, some of which are covered by other International Standards:

- Sheet and strip — refer to ISO TC 17/SC 12, *Continuous mill flat rolled products*;
- Tubular products — refer to ISO TC 5/SC 1, *Steel tubes*.

NOTE Lists of standards covered by ISO/TC 17/SC 12 and ISO/TC 5/SC 1 are available on the ISO Web site.

This part of ISO 630 covers 10 grades. Grades S460Q, S500Q, S550Q, S620Q, S690Q, S890Q and S960Q are covered in Annex A. Grades SG460Q, SG500Q, and SG700Q are covered in Annex B.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 630–1, *Structural steels — Part 1: General technical delivery conditions for hot-rolled products*

ISO 643, *Steels — Micrographic determination of the apparent grain size*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 630-1 and the following apply.

3.1

quenching

operation which consists of cooling a ferrous product more rapidly than in still air from a high temperature above A_{c1}

NOTE A_{c1} is the temperature at which austenite begins to form during heating.

3.2

tempering

heat treatment applying to a ferrous product, generally after quench hardening, or another heat treatment to bring the properties to the required level, and consisting of heating to specific temperatures ($< A_{c1}$) and soaking for an appropriate duration, followed by cooling at an appropriate rate

NOTE Additionally, the following may apply: processes of direct quenching plus tempering.

3.3 fine-grain steel
steel with fine-grain structure with an equivalent index of ferritic grain size ≤ 6 determined in accordance with ISO 643
See 6.1.

4 Classification and designation

4.1 Classification

The steel grades specified in this part of ISO 630 shall be classified as non-alloy quality or alloy special steels.

4.2 Grades and qualities

This document specifies 10 grades. Grades S460Q, S500Q, S550Q, S620Q, S690Q, S890Q and S960Q are covered in Annex A. Grades SG460Q, SG500Q, and SG700Q are covered in Annex B.

Each grade is available in up to five qualities. These grades and qualities differ in their specified mechanical properties and impact energy requirements.

Quality A: no impact test

Quality C: impact testing at 0 °C

Quality D: impact testing at -20 °C

Quality E: impact testing at -40 °C

Quality F: impact testing at -60 °C

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[ISO 630-4:2012](https://standards.iteh.ai/catalog/standards/sist/7a3824ca-85f8-4d52-b889-1a3951df6db7/iso-630-4-2012)

4.3 Normative annexes

<https://standards.iteh.ai/catalog/standards/sist/7a3824ca-85f8-4d52-b889-1a3951df6db7/iso-630-4-2012>

The requirements of Annex A or Annex B are to be regarded separately. Each annex is independent of the other without combining in any way.

5 Information to be supplied by purchaser

5.1 Mandatory information

The information that shall be supplied by the purchaser at the time of the order is specified in ISO 630-1.

5.2 Options

The options of ISO 630-1 apply (see ISO 630-1). In addition, the following options apply to products according to this part of ISO 630. If the purchaser does not indicate a wish to implement any of these options at the time of the order, the products shall be supplied in accordance with the basic specification (see 5.1).

- a) Testing of impact properties in the transverse direction using Charpy V-notch test pieces in accordance with ISO 630-1.
- b) Testing of tensile and impact properties at a frequency per each plate as heat-treated.
- c) On special request of the purchaser, the manufacturer shall inform the purchaser at the time of the order which of the alloying elements appropriate to the steel grade required will be deliberately added to the material to be delivered and reported in the heat analysis.
- d) On special request of the purchaser, the manufacturer shall inform the purchaser at the time of the order which of the alloying elements appropriate to the steel grade required will be deliberately added to the

material to be delivered and reported in the product analysis. The product analysis shall be carried out at an agreed frequency when specified at the time of the order.

6 Requirements

See ISO 630-1.

6.1 Steelmaking process

See ISO 630-1.

If a special steelmaking process has been specified, this shall be reported in the inspection document.

The steels shall have a fine-grain practice containing sufficient amounts of nitrogen-binding elements.

6.2 Deoxidation

The steels specified in this specification shall be fully killed.

6.3 Delivery condition

The products covered by this part of ISO 630 are delivered in the quenched and tempered condition. The delivery condition is indicated in the inspection document.

6.4 Chemical composition

iTech STANDARD PREVIEW
(standards.iteh.ai)

6.4.1 Heat analysis

The chemical composition determined by heat analysis shall comply with the specified values in Table A.1 or Table B.1.

ISO 630-4:2012
<https://standards.iteh.ai/catalog/standards/sist/7a5824ca-851b-4d52-b889-1a3951df6db7/iso-630-4-2012>

6.4.2 Product analysis

The product analysis of grades S460Q, S500Q, S550Q, S620Q, S690Q, S890Q and S960Q shall comply with the values given in Table A.2.

The permitted deviations on analysis of grades SG460Q, SG500Q, and SG700Q, relative to the values for heat analysis, are given in Table B.2.

6.4.3 Carbon equivalent values

The carbon equivalent value (CEV) requirements for Annex A grades are given in Table A.3 and for Annex B grades in Table B.3.

For determining the CEV, the following International Institute for Welding (IIW) formula shall be used:

$$\text{CEV} = \text{C} + \text{Mn}/6 + (\text{Cr} + \text{Mo} + \text{V})/5 + (\text{Ni} + \text{Cu})/15$$

6.5 Mechanical properties

6.5.1 Tensile properties

The tensile properties at ambient temperature shall comply with the values specified in Table A.4 or Table B.4.

6.5.2 Charpy V-notch impact tests

The impact properties of Charpy V-notch test pieces shall comply with the values specified in Table A.5 or Table B.5. The orientation of the specimens shall be longitudinal, unless a transverse orientation is agreed between the purchaser and manufacturer (see 5.2, ISO 630-1, and the values in Table A.6).

6.6 Surface conditions

See ISO 630-1.

6.7 Internal soundness

See ISO 630-1.

6.8 Dimensions and tolerances on dimensions, shape and mass

See ISO 630-1.

7 Inspection

Specific inspection shall be required for all grades.

8 Sampling — Frequency of testing

8.1 Verification

The verification of mechanical properties shall be by heat.

[ISO 630-4:2012](https://standards.iteh.ai/catalog/standards/sist/7a3824ca-85f8-4d52-b889-1a3951df6db7/iso-630-4-2012)

8.2 Test units

<https://standards.iteh.ai/catalog/standards/sist/7a3824ca-85f8-4d52-b889-1a3951df6db7/iso-630-4-2012>

8.2.1 Annex A

The test unit shall contain products of the same form, grade, quality, and delivery condition, and of the same thickness range as specified in Table A.4 for the yield strength and shall be taken by heat:

— 40 tons or part thereof.

8.2.2 Annex B

The test unit shall be taken on each plate as heat treated.

9 Test methods

See ISO 630-1.

10 Marking

See ISO 630-1.

Annex A
(normative)

**Steel grades S460Q, S500Q, S550Q, S620Q, S690Q, S890Q and S960Q:
Chemical composition and mechanical properties**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 630-4:2012

<https://standards.iteh.ai/catalog/standards/sist/7a3824ca-85f8-4d52-b889-1a3951df6db7/iso-630-4-2012>

Table A.1 — Chemical composition (heat analysis) ^a

Grade	Quality	C	Si	Mn	P	S	N	B	Cr	Cu	Mo	Nb	Ni	Ti	V	Zr
		% max.	% max.	% max.	% max.	% max.	% max.	% max.	% max.	% max.	% max.	% max. ^b	% max.	% max. ^b	% max. ^b	% max. ^b
All grades	D E, F	0,20	0,80	1,70	0,025 0,020	0,015 0,010	0,015	0,005 0	1,50	0,50	0,70	0,06	2,0	0,05	0,12	0,15

^a Depending on the thickness of the product and the manufacturing conditions, the manufacturer may add to the steel one or several alloying elements up to the maximum values given in order to obtain the specified properties (see 6.4.1).

^b There shall be at least 0,015 % of a grain-refining element present. Aluminium is also one of these elements. The minimum content of 0,015 % applies to soluble aluminium, this value is regarded as attained if the total aluminium content is at least 0,018 %; in case of dispute, the soluble aluminium content shall be determined.

TeH STANDARD PREVIEW
(standards.iteh.ai)

ISO 630-4:2012

standards.iteh.ai/catalog/standards/sist/7a3824ca-85f8-4d52-b889-1a3951df6db7/iso-630-4-2012

Table A.2 — Chemical composition (product analysis) based on Table A.1^a

Grade	Quality	C	Si	Mn	P	S	N	B	Cr	Cu	Mo	Nb	Ni	Ti	V	Zr
All grades	D	max. 0,22	max. 0,86	max. 1,80	max. 0,030	max. 0,017	max. 0,016	max. 0,006 0	max. 1,60	max. 0,55	max. 0,74	max. 0,07	max. 2,1	max. 0,07	max. 0,14	max. 0,17
	E, F				max. 0,025	0,012										

^a Depending on the thickness of the product and the manufacturing conditions, the manufacturer may add to the steel one or several alloying elements up to the maximum values given in order to obtain the specified properties (see 6.4.2).

^b There shall be at least 0,010 % of a grain-refining element present. Aluminium is also one of these elements. The minimum content of 0,010 % applies to soluble aluminium, this value is regarded as attained if the total aluminium content is at least 0,013 %; in case of dispute, the soluble aluminium content shall be determined.

STANDARD PREVIEW
(standards.iteh.ai)

ISO 630-4:2012

<http://standards.iteh.ai/catalog/standards/sist/7a3824ca-85f8-4d52-b889-1a3951df6db7/iso-630-4-2012>