
**Textiles — Professional care, drycleaning
and wetcleaning of fabrics and
garments —**

Part 2:

**Procedure for testing performance when
cleaning and finishing using
tetrachloroethene**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

*Textiles — Entretien professionnel, nettoyage à sec et nettoyage à l'eau
des étoffes et des vêtements —*

*Partie 2: Mode opératoire pour évaluer la résistance au nettoyage et à
la finition lors du traitement au tétrachloroéthylène*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 3175-2:2010

<https://standards.iteh.ai/catalog/standards/sist/565d874b-420d-47ed-92af-6eaf52783a49/iso-3175-2-2010>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Reagents.....	2
5 Apparatus	2
6 Conditioning	3
7 Test specimens.....	3
8 Procedure	3
8.1 Procedure for normal materials	4
8.2 Procedures for sensitive and very sensitive materials	5
9 Test report.....	5
Bibliography.....	7

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[ISO 3175-2:2010](https://standards.iteh.ai/catalog/standards/sist/565d874b-420d-47ed-92af-6eaf52783a49/iso-3175-2-2010)

<https://standards.iteh.ai/catalog/standards/sist/565d874b-420d-47ed-92af-6eaf52783a49/iso-3175-2-2010>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 3175-2 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 2, *Cleansing, finishing and water resistance tests*.

This second edition cancels and replaces the first edition (ISO 3175-2:1998), of which it constitutes a minor revision. It also incorporates Technical Corrigendum ISO 3175-2:1998/Cor.1:2002.

ISO 3175 consists of the following parts, under the general title *Textiles — Professional care, drycleaning and wetcleaning of fabrics and garments*:

- *Part 1: Assessment of performance after cleaning and finishing*
- *Part 2: Procedure for testing performance when cleaning and finishing using tetrachloroethene*
- *Part 3: Procedures for testing performance when cleaning and finishing using hydrocarbon solvents*
- *Part 4: Procedure for testing performance when cleaning and finishing using simulated wetcleaning*

Introduction

Drycleaning is a process for cleaning textiles in an organic solvent that dissolves oils and fats and disperses particulate dirt substantially without the swelling and creasing associated with washing or wet cleaning. Small quantities of water may be incorporated in the solvent with the aid of a surfactant for the purpose of obtaining better soil and stain removal. Some moisture-sensitive articles are preferably drycleaned without the addition of water to the solvent. A surfactant is often used to assist with soil removal and reduce the risk of greying, but it should be borne in mind that surfactants contain varying amounts of water in their formulations.

Drycleaning is normally followed by an appropriate restorative finishing procedure. In most cases, this comprises some form of steam treatment and/or hot pressing.

Properties of the textile or garment may change progressively on drycleaning and steaming and/or pressing and in some cases a single treatment can give little indication of the extent of dimensional and other changes that can arise after repeated treatments and which can affect the useful life of the article. Generally, most of the potential changes become apparent after three to five of the drycleaning and finishing treatments specified in this part of ISO 3175.

The properties which should be considered in an assessment for drycleanability together with the methods for their assessment are given in ISO 3175-1.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 3175-2:2010](https://standards.iteh.ai/catalog/standards/sist/565d874b-420d-47ed-92af-6eaf52783a49/iso-3175-2-2010)

<https://standards.iteh.ai/catalog/standards/sist/565d874b-420d-47ed-92af-6eaf52783a49/iso-3175-2-2010>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 3175-2:2010

<https://standards.iteh.ai/catalog/standards/sist/565d874b-420d-47ed-92af-6eaf52783a49/iso-3175-2-2010>

Textiles — Professional care, drycleaning and wetcleaning of fabrics and garments —

Part 2: Procedure for testing performance when cleaning and finishing using tetrachloroethene

1 Scope

This part of ISO 3175 specifies drycleaning procedures for tetrachloroethene (perchloroethylene), using commercial drycleaning machines, for fabrics and garments. It comprises a procedure for normal materials and procedures for sensitive and very sensitive materials.

NOTE Various solvents can be used for drycleaning, of which tetrachloroethene is the most common in many countries. For this reason, this method prescribes the use of tetrachloroethene.

iTeh STANDARD PREVIEW

2 Normative references (standards.iteh.ai)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies. [standards/sist/565d874b-420d-47ed-92af-6eaf52783a49/iso-3175-2-2010](https://standards.iteh.ai/standards/sist/565d874b-420d-47ed-92af-6eaf52783a49/iso-3175-2-2010)

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 3175-1, *Textiles — Professional care, drycleaning and wetcleaning of fabrics and garments — Part 1: Assessment of performance after cleaning and finishing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

material

garment, composite or fabric

3.2

composite test specimen

test specimen consisting of all component parts used in the finished item, and combined in a representative assembly

3.3

normal material

material which is able to withstand the normal drycleaning process as specified in this part of ISO 3175 without modification

3.4 sensitive material

material which may require restrictions as to mechanical action and/or drying temperatures and/or water additions

EXAMPLES Acrylics, silk, crepe.

3.5 very sensitive material

material which may require greatly reduced mechanical action and/or greatly reduced drying temperatures and/or no addition of water

EXAMPLES Polyvinylchloride (PVC), modacrylic, novelty tweeds, angora.

NOTE After giving careful consideration to the comments on progressive change in the introduction, textile items which perform satisfactorily for purpose in the procedures intended for normal and sensitive materials in Table 1 may be labelled with the **P** and **P** symbols, respectively, as described in ISO 3758. There is no care label equivalent to the procedure for very sensitive materials and information on the required processing can only be given in words.

4 Reagents

4.1 Tetrachloroethene, CCl₂ = CCl₂ distilled, sold for the purpose of drycleaning.

4.2 Sorbitan mono-oleate.

In order to prevent foaming, it is important to use redistilled, clean solvent solution and not overfill the still.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5 Apparatus

ISO 3175-2:2010

<https://standards.iteh.ai/catalog/standards/sist/565d874b-420d-47ed-92af>

SAFETY PRECAUTIONS — When using commercial drycleaning equipment, official regulations and normal safety precautions should be observed.

5.1 Drycleaning machine, consisting of a commercial reversible rotating cage type, totally enclosed machine, intended for use with tetrachloroethene. The diameter of the rotating cage shall be 600 mm minimum and 1 080 mm maximum. Its depth shall be 300 mm minimum. It shall be fitted with three or four lifters. The speed shall be such as to give a *g*-factor of between 0,5 and 0,8 for cleaning and between 60 and 120 for extraction.

NOTE The *g*-factor is calculated according to the following formula:

$$g = 5,6 n^2 d \times 10^{-7}$$

where

n is the rotational frequency, in rotations per minute;

d is the rotating cage diameter, in millimetres.

5.1.1 The machine shall be fitted with the means to control solvent and air temperature as required (see Table 1).

5.1.2 The machine shall have suitable facilities to allow the emulsion (see 8.1.3) to be introduced gradually into the solvent between the cage and drum below the level of the solvent.

5.1.3 The machine shall be equipped with a means of measuring the temperature of the solvent during washing and either the incoming or the outgoing air during drying to within ±2 °C.

5.2 Apparatus for applying the appropriate finishing treatment to the test pieces, consisting of the following:

5.2.1 Iron, with an approximate mass of 1,5 kg and a sole surface area of 150 cm² to 200 cm².

5.2.2 Steam press, consisting of two bucks, one fixed and the other movable, each buck having a surface area of approximately 0,35 m². Steam being conducted to the bucks shall be released under a pressure of approximately 500 kPa. The pressure exerted by the bucks shall be approximately 350 kPa.

5.2.3 Steam table, having a shape and dimensions suitable to the dimensions of the specimens. The steam shall be released at a pressure of approximately 500 kPa.

5.2.4 Steam former (mannequin), which may or may not be specific in shape for garments. The steam shall be released at a pressure of approximately 500 kPa.

5.2.5 Steam cabinet, which needs to be specific in shape for garments. The steam shall be released at a pressure of approximately 500 kPa.

5.3 Ballast, consisting of clean textile pieces which shall be either white or of a light colour and which shall consist of approximately 80 % wool pieces and 20 % cotton pieces by mass. Each piece shall comprise two layers of fabric sewn together at the edges and shall be (300 ± 30) mm square.

NOTE If it is agreed that an alternative ballast (composition or fibre) is to be used, this can be included in the test report.

6 Conditioning

iTeh STANDARD PREVIEW
(standards.iteh.ai)

The specimens and ballast shall be conditioned for at least 16 h in one of the standard atmospheres for conditioning and testing textiles specified in ISO 139. Specimens shall be tested immediately after removal from the conditioning atmosphere, otherwise they shall be placed in sealed plastic bags and tested within 30 min.

7 Test specimens

7.1 Garments shall be tested as is.

7.2 Composite test specimens (3.2).

7.3 Fabrics shall be cut into test pieces, preferably not smaller than 500 mm square and stitched on all sides with polyester thread to prevent unravelling.

7.4 If assessments/comparisons are required according to ISO 3175-1, at least two identical test specimens shall be required (one for comparison, one for testing).

Testing may be an iterative procedure since alternative processes of varying severity may be used, and it is advisable to obtain sufficient specimens for all the testing which may be required.

8 Procedure

NOTE Selection of the procedure to be used (normal, sensitive or very sensitive) depends on the textile item (see examples in 8.2). It also takes into consideration the end use of the item since this has a bearing on the likely type and degree of soiling. Generally, the less severe the process, the less effective is the cleaning. Localized staining and stain removal are outside the scope of this part of ISO 3175.