



Designation: D5869 – 07a

Standard Practice for Dark Oven Heat Exposure of Roofing and Waterproofing Materials¹

This standard is issued under the fixed designation D5869; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice establishes a procedure and conditions of temperature and time for heat exposure of roofing and waterproofing materials and systems in the presence of air.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

D883 Terminology Relating to Plastics

D1079 Terminology Relating to Roofing and Waterproofing

D1566 Terminology Relating to Rubber

E145 Specification for Gravity-Convection and Forced-Ventilation Ovens

E230 Specification and Temperature-Electromotive Force (EMF) Tables for Standardized Thermocouples

E1137/E1137M Specification for Industrial Platinum Resistance Thermometers

E2251 Specification for Liquid-in-Glass ASTM Thermometers with Low-Hazard Precision Liquids

3. Terminology

3.1 *Definitions*—For definitions of terms used in this practice, refer to Terminologies D883, D1079, and D1566.

¹ This practice is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.02 on Steep Roofing Products and Assemblies.

Current edition approved July 1, 2007. Published July 2007. Originally approved in 1995. Last previous edition approved in 2007 as D5869 – 07. DOI: 10.1520/D5869-07A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Summary of Practice

4.1 Specimens of roofing and waterproofing materials are exposed to heat in a dark forced-ventilation oven at a specified elevated temperature for a known period of time.

4.2 This practice specifies an exposure temperature of $70 \pm 3^\circ\text{C}$ ($158 \pm 5^\circ\text{F}$) in a forced-ventilation oven.

4.3 This practice permits the selection of the duration of heat exposure from three specified time periods, which are 35, 90, and 180 ± 0.25 consecutive days. The duration selected must be included in any report of results obtained by using this practice.

NOTE 1—The time period to be used should be specified in any standard that refers to this practice. European standards for polymer-modified bituminous materials specify 180 days at 70°C . For research purposes, selection of other time periods and temperatures are permitted, provided that the precise duration is stated in any report of results.

4.4 This practice is also used to condition test specimens for time periods much shorter than 35 days for the purpose of conditioning material before testing. When used for this purpose, the shorter conditioning time shall be specified in any report of test results.

5. Significance and Use

5.1 Roofing and waterproofing materials and systems undergo changes in physical properties as a result of being subjected to heat. They also undergo changes in physical properties as they age in service. Since service conditions vary widely, any relationship between changes observed in this practice and changes in service must be established by the user of this practice.

6. Apparatus

6.1 *Oven*—The oven shall have forced ventilation, shall be electrically heated, and shall conform to the requirements of Specification E145, Type IIB. The oven shall be of sufficient size to accommodate the size and number of specimens selected by the user of this practice.

6.2 *Thermometer*—The thermometer shall be an ASTM thermometer, conforming to the requirements for thermometer S12C (or S12F) in accordance with Specification E2251. As an alternate, any other thermometric device used shall be at least: (I) of equal accuracy to that of the thermometer specified in