

---

---

**Thermal performance in the built  
environment — Determination of air  
permeance of building materials**

*Performance thermique en environnement bâti — Détermination de  
la perméance à l'air des matériaux de construction*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 14857:2014](https://standards.iteh.ai/catalog/standards/sist/363378e2-975a-4244-a930-f0bf19c8a207/iso-14857-2014)

[https://standards.iteh.ai/catalog/standards/sist/363378e2-975a-4244-a930-  
f0bf19c8a207/iso-14857-2014](https://standards.iteh.ai/catalog/standards/sist/363378e2-975a-4244-a930-f0bf19c8a207/iso-14857-2014)



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 14857:2014](https://standards.iteh.ai/catalog/standards/sist/363378e2-975a-4244-a930-f0bf19c8a207/iso-14857-2014)

<https://standards.iteh.ai/catalog/standards/sist/363378e2-975a-4244-a930-f0bf19c8a207/iso-14857-2014>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
Introduction.....	v
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Sampling and conformity control.....</b>	<b>1</b>
<b>5 Test specimens.....</b>	<b>1</b>
5.1 Number.....	1
5.2 Dimensions.....	1
5.3 Preparation.....	2
5.4 Conditioning.....	2
<b>6 Principle.....</b>	<b>2</b>
<b>7 Apparatus.....</b>	<b>2</b>
<b>8 Procedures.....</b>	<b>3</b>
8.1 Specimen installation.....	3
8.2 Test procedure.....	4
<b>9 Calculation and expression of results.....</b>	<b>6</b>
9.1 Standard temperature and pressure.....	6
<b>10 Precision.....</b>	<b>6</b>
<b>11 Test report.....</b>	<b>7</b>
<b>Annex A (normative) Procedure for estimating errors in derived quantities.....</b>	<b>13</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 1, *Test and measurement methods*.

<https://standards.iteh.ai/catalog/standards/sist/363378e2-975a-4244-a930-f0bf19c8a207/iso-14857-2014>

## Introduction

This International Standard contains the requirements for testing various building materials to determine their suitability to be used as an air barrier material.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 14857:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/363378e2-975a-4244-a930-f0bf19c8a207/iso-14857-2014>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 14857:2014

<https://standards.iteh.ai/catalog/standards/sist/363378e2-975a-4244-a930-f0bf19c8a207/iso-14857-2014>

# Thermal performance in the built environment — Determination of air permeance of building materials

## 1 Scope

This International Standard specifies the equipment and procedures to determine the air permeance of building materials at various pressure differentials and then assigning an air permeance rate at a reference pressure differential rate ( $\Delta P$ ) of 75 Pa.

This method is intended for testing materials independent of a substrate using a 1 m × 1 m specimen size. The results of this test method can be used to determine whether a material qualifies to function as an air barrier material.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7345, *Thermal insulation — Physical quantities and definitions*

ISO 9229, *Thermal insulation — Vocabulary*

ISO 12576-1, *Thermal insulation — Insulating materials and products for buildings — Conformity control systems — Part 1: Factory-made products* [ISO 14857:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/363378e2-975a-4244-a930-f0bf19c8a207/iso-14857-2014>

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 7345 and ISO 9229 and the following apply.

### 3.1

#### air permeance

rate of air flow (L/s), per unit area (m<sup>2</sup>) and per unit static pressure differential (Pa)

## 4 Sampling and conformity control

The procedures described in ISO 12576-1 shall be applied for the purposes of sampling and conformity control.

## 5 Test specimens

### 5.1 Number

The number of test specimens shall be five.

### 5.2 Dimensions

The test specimens shall be 1,2 m × 1,2 m. Where the manufactured product is less than 1,2 wide, the length shall be increased to provide the same area.

### 5.3 Preparation

From the sample obtained in accordance with [Clause 4](#), cut the material to 1,2 m × 1,2 m. For fluid-applied products, the material shall be installed on a release material or a substrate and then the materials shall be removed from the release material or substrate after curing.

### 5.4 Conditioning

The test specimens shall be conditioned for seven days at

(23 ± 2) °C and (50 ± 10) % relative humidity

or

(23 ± 5) °C and  $\left(50^{+20}_{-10}\right)$  % relative humidity

or

(27 ± 5) °C and  $\left(65^{+20}_{-10}\right)$  % relative humidity

unless other conditions are given in the relevant material standard.

## 6 Principle

A test specimen is subjected to various air pressure differentials and the air permeance is measured.

## 7 Apparatus

The schematic of the apparatus is shown in [Figure 1](https://standards.iteh.ai/catalog/standards/sist/363378e2-975a-4244-a930-1f1111111111/iso-14857-2014)

**7.1 Test chamber**, shall be constructed with a 1 m × 1 m test opening in the top and which will accept a 1,2 m × 1,2 m specimen.

In some cases, the size could be modified for materials which are manufactured with a width less than 1,2 m. In all cases, the test opening shall be 1 m<sup>2</sup>. The depth of the test chamber shall be 400 mm. A compression frame 0,1 m wide shall be installed around the outside of the test chamber at the top of the test chamber. The compression frame shall be stiff and fastened solidly to the test chamber to limit deflection. Observation panels shall be installed on two sides of the test frame to allow observation of the material installed in the test chamber.

The test chamber shall be sealed with two parallel strips of medium-density gasket material at all sealing points of the test chamber so that the extraneous air leakage shall not be measurable at 700 Pa.

A second compression frame the same size and shape of the compression frame on the test chamber shall be constructed and the corners sealed.

**7.2 Air flow measuring devices**, shall be used which can measure of 1 × 10<sup>-7</sup> m<sup>3</sup>/s (0,000 1 L/s) up to 1 × 10<sup>-2</sup> m<sup>3</sup>/s (1,0 L/s) with an accuracy of ±3 %.

**7.3 Static pressure differential measuring devices**, shall be used which can measure up to 500 Pa with an accuracy of ±0,5 %.

**7.4 Laboratory barometric pressure measuring device**, shall be used which can measure pressure with ±3 % of the reading.



**7.5 Piping**, shall be used to connect the test chamber to the variable pressure differential equipment.

The piping shall be airtight. The pipe connection to the test chamber shall contain an air filter so that the air flow measuring device shall not be affected by dust or suspended particulates. The piping shall be designed so that the flow regime upstream and downstream of the air flow measuring device shall not affect the device's accuracy. The piping shall contain a flow control device to regulate the static pressure across the test specimen within  $\pm 0,5$  % of the pressure reading. The piping shall contain a temperature measuring device with an accuracy of  $\pm 0,5$  °C, to measure the temperature of the air flowing in the piping.

**7.6 Variable pressure differential equipment**, shall be an equipment with a variable control to produce a static pressure across the test specimen within  $\pm 0,5$  % of the pressure reading.

The equipment shall be able to produce both positive and negative pressures.

**7.7 Pressure limit device**, shall be installed to control over-pressure and shall be set at 1 000 Pa.

**7.6 Self-adhesive gasket material**, strips of self-adhesive gasket material shall be installed on both compression frames (one constructed as part of the test chamber and the second on used to hold the specimen in place) and the corners shall be glued or fused.

**7.7 Air impermeable material**, non-permeable flexible material (such as 0,15-mm thick polyethylene film) is used to wrap the specimen to determine the air leakage of the test apparatus before conducting the air permeance test of the material.

**7.8 Clamping devices**, twelve clamping devices (such as C-clamps) used to clamp the two compression frames together after the specimen has been installed in the test chamber.

THE STANDARD PREVIEW

(standards.iteh.ai)

ISO 14857:2014

[https://standards.iteh.ai/catalog/standards/sist/363378e2-975a-4244-a930-](https://standards.iteh.ai/catalog/standards/sist/363378e2-975a-4244-a930-f0bf19c8a207/iso-14857-2014)

[f0bf19c8a207/iso-14857-2014](https://standards.iteh.ai/catalog/standards/sist/363378e2-975a-4244-a930-f0bf19c8a207/iso-14857-2014)

## 8 Procedures

### 8.1 Specimen installation

Cut the air impermeable material to 1,4 m × 1,4 m.

#### 8.1.1 Self-supporting materials

Remove the protective paper from one side of the self-adhered, medium-density gasket strip and install onto the edges of the test specimen in a manner that the area inside the strips is 1 m × 1 m. Fuse or glue the corners. Install a second strip of medium-density gasket material outside the first strip and fuse or glue the corners.

Remove the protective paper on the top side of the self-adhered gasket material and install the test specimen with the gasket material side down onto the centre of a piece of flexible air impermeable material. Ensure that the gasket strip is adhered to the flexible air impermeable material.

On the top side of the specimen, remove the protective paper from self-adhered gasket material and install onto the edges of the test specimen in a manner that the area inside the strips is 1 m × 1 m and that the gasket is positioned over the gasket strip on the other side of the test specimen. Fuse or glue the corners. Install a second strip of self-adhesive gasket material outside the first strip and over gasket material on the other side of the test specimen. Fuse or glue the corners.

Cut the air impermeable material as shown in [Figure 2](#).

Wrap the air impermeable material over the edges of the test specimen as shown in [Figure 3](#) and press into the self-adhering, medium-density gasket strips. Tape the joints with construction tape.

Cut and remove all excess air impermeable material from inside the self-adhesive gasket material, leaving an opening to the test specimen of 1 m × 1 m.

Install the test specimen assembly onto the compression frame attached to the test chamber with the air impermeable material facing up as shown in [Figure 4](#).

Install the second compression frame over the test specimen assembly and clamp into place using three clamping devices on each side of the test apparatus.

View the installed test specimen through the observation panels and confirm that it has been properly installed.

### 8.1.2 Non-self-supporting materials

The procedure for non-self-supporting material shall be the same as above with the addition of a rigid support. An open grill or wire mesh/screen with a square grid of a minimum of 25 mm × 25 mm opening (or equivalent means of support) shall be used. The wire mesh/screen shall be welded or otherwise mechanically supported to a solid metal frame.

Remove the protective paper from one side of the self-adhered, medium-density gasket strip and install onto the edges of the test specimen in a manner that the area inside the strips is 1 m × 1 m. Fuse or glue the corners. Install a second strip of medium-density gasket material outside the first strip and fuse or glue the corners.

Remove the protective paper on the top side of the self-adhered gasket material and install the test specimen with the gasket material side down onto the centre of the open grill or wire mesh/screen. Ensure that the gasket strip is adhered to the open grill or wire mesh/screen.

On the top side of the open grill or wire mesh/screen, remove the protective paper from self-adhered gasket material and install onto the edges of the open grill or wire mesh/screen in a manner that the area inside the strips is 1 m × 1 m and that the gasket is positioned over the gasket strip on the other side of the open grill or wire mesh/screen. Fuse or glue the corners. Install a second strip of self-adhesive gasket material outside the first strip and over gasket material on the other side of the open grill or wire mesh/screen. Fuse or glue the corners.

Cut the air impermeable material as shown in [Figure 2](#).

Wrap the air impermeable material over the edges of the test specimen as shown in [Figure 3](#) and press into the self-adhering, medium-density gasket strips. Tape the joints with construction tape.

Cut and remove all excess air impermeable material from inside the self-adhesive gasket material, leaving an opening to the test specimen of 1 m × 1 m.

Install the test specimen assembly onto the compression frame attached to the test chamber with the air impermeable material facing up as shown in [Figure 5](#).

Install the second compression frame over the test specimen assembly and clamp into place using three clamping devices on each side of the test apparatus.

View the installed test specimen through the observation panels and confirm that it has been properly installed.

## 8.2 Test procedure

### 8.2.1 Calibration

Construct a calibration specimen using a 1,1 m × 1,1 m piece of (19 ± 3) mm thick of plywood with a 150 mm hole in the centre of the plywood.

Manufacture an orifice plate from 3 mm stainless steel 200 mm in diameter centred on the hole. The orifice plate shall have an interior square edge diameter of (25,4 ± 0,1) mm.

Install two rows of self-adhesive gasket material around the outside of the orifice plate. Fuse or glue where the ends of the self-adhesive gasket material meet. Centre the orifice plate on the plywood and secure the orifice plate to the plywood using wood screws. Install a sealant along the edge of the orifice plate where it meets the plywood.

Install a suitable adhesive tape over the hole in the orifice plate.

Install the calibration specimen into the test apparatus and determine the extraneous air leakage of the test assembly by conducting the test in accordance with [8.2.2](#).

Remove the adhesive tape from the hole in the orifice plate and determine the air flow rate at 75 Pa pressure difference ( $\Delta P$ ). The air flow rate shall be  $\pm 5\%$  of the predetermined flow rate of 3,47 L/s.

NOTE Other orifice plates with different diameters can be made to provide different flow rates.

### 8.2.2 Control tests

The air leakage of the open grill or wire mesh/screen shall not be measureable. This shall be confirmed by measuring the air flow rate of the test apparatus at a specific pressure difference without any test specimen being installed. The open grill or wire mesh/screen shall be installed and the flow rate of the test apparatus at the same pressure difference shall be measured. The flow rate shall be within 5 %.

### 8.2.3 Specimen tests

Install the specimens in accordance with [8.1](#).

Measure the extraneous air leakage ( $Q_{ei}$ ) of the test apparatus with the specimen installed at 25 Pa, 50 Pa, 75 Pa, 100 Pa, 150 Pa, and 300 Pa static pressure differentials ( $\Delta P$ ).

Cut and remove the air impermeable material covering the test specimen which is inside the compression frame and the self-adhered gasket material. The opening shall be 1 m  $\times$  1 m.

Measure the total air leakage ( $Q_{ti}$ ) at 25 Pa, 50 Pa, 75 Pa, 100 Pa, 150 Pa, and 300 Pa static pressure differentials ( $\Delta P$ ) in both a positive flow and a negative flow.

Determine if the measurement process has affected the air permeance of the material by re-measuring the total air leakage at 300 Pa, 150 Pa, 100 Pa, 75 Pa, 50 Pa, and 25 Pa static pressure differentials ( $\Delta P$ ) and compare to the original values. If the difference in the air leakage rate at the same pressure difference is greater than 10 %, the cause of the air leakage rate change shall be determined.