
**Plastics — Polyamide (PA) moulding and
extrusion materials —**

**Part 2:
Preparation of test specimens and
determination of properties**

*Plastiques — Matériaux polyamides (PA) pour moulage et extrusion —
Partie 2: Préparation des éprouvettes et détermination des propriétés*
**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

ISO 1874-2:2012

<https://standards.iteh.ai/catalog/standards/sist/bc540a36-689b-419d-b1b6-3c1e326290f8/iso-1874-2-2012>



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 1874-2:2012

<https://standards.iteh.ai/catalog/standards/sist/bc540a36-689b-419d-b1b6-3c1e326290f8/iso-1874-2-2012>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Preparation of test specimens	2
3.1	Treatment of the material before moulding	2
3.2	Injection moulding	3
3.3	Laser sintering	3
4	Conditioning of test specimens	5
4.1	Conditioning states of the test specimen	5
4.2	Dry-as-moulded (DAM) state	5
4.3	Moist state	6
5	Determination of properties	6
Annex A (normative) Specimen preparation using laser sintering		9

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 1874-2:2012](https://standards.iteh.ai/catalog/standards/sist/bc540a36-689b-419d-b1b6-3c1e326290f8/iso-1874-2-2012)

<https://standards.iteh.ai/catalog/standards/sist/bc540a36-689b-419d-b1b6-3c1e326290f8/iso-1874-2-2012>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1874-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This fourth edition cancels and replaces the third edition (ISO 1874-2:2006), which has been technically revised. It also incorporates the Amendment ISO 1874-2:2006/Amd.1:2010.

ISO 1874 consists of the following parts, under the general title *Plastics — Polyamide (PA) moulding and extrusion materials*:

- Part 1: Designation system and basis for specification
- Part 2: Preparation of test specimens and determination of properties

iTeh STANDARD PREVIEW
(standards.iteh.ai)
ISO 1874-2:2012
<https://standards.iteh.ai/catalog/standards/sist/bc540a36-689b-419d-b1b6-3c1e326290f8/iso-1874-2-2012>

Plastics — Polyamide (PA) moulding and extrusion materials —

Part 2: Preparation of test specimens and determination of properties

1 Scope

This part of ISO 1874 specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of polyamide moulding and extrusion materials. Requirements for handling test material and for conditioning both the test material before moulding and the specimens before testing are given.

Procedures and conditions for the preparation of test specimens and procedures for measuring properties of the materials from which these specimens are made are given. Properties and test methods that are suitable and necessary to characterize polyamide moulding and extrusion materials are listed.

The properties have been selected from the general test methods in ISO 10350-1. Other test methods in wide use for, or of particular significance to, these moulding and extrusion materials are also included in this part of ISO 1874, as are the designatory properties viscosity number and tensile modulus of elasticity given in ISO 1874-1.

2 Normative references

The following normative documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

- <https://standards.iteh.ai/catalog/standards/sist/bc540a36-689b-419d-b1b6-3c1e32629018/iso-1874-2-2012>
ISO 62, *Plastics — Determination of water absorption*
- ISO 75-2, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite*
- ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*
- ISO 179-2, *Plastics — Determination of Charpy impact properties — Part 2: Instrumented impact test*
- ISO 291, *Plastics — Standard atmospheres for conditioning and testing*
- ISO 294-1, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens*
- ISO 294-3, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 3: Small plates*
- ISO 294-4, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 4: Determination of moulding shrinkage*
- ISO 307, *Plastics — Polyamides — Determination of viscosity number*
- ISO 472, *Plastics — Vocabulary*
- ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*
- ISO 1110, *Plastics — Polyamides — Accelerated conditioning of test specimens*
- ISO 1133-2, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 2: Method for materials sensitive to time-temperature history and/or moisture*

ISO 1183-1, *Plastics — Methods for determining the density and relative density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 1183-2, *Plastics — Methods for determining the density and relative density of non-cellular plastics — Part 2: Density gradient column method*

ISO 1183-3, *Plastics — Methods for determining the density and relative density of non-cellular plastics — Part 3: Gas pycnometer method*

ISO 1874-1, *Plastics — Polyamide (PA) moulding and extrusion materials — Part 1: Designation system and basis for specification*

ISO 3167, *Plastics — Multipurpose test specimens*

ISO 3451-4, *Plastics — Determination of ash — Part 4: Polyamides*

ISO 8256, *Plastics — Determination of tensile-impact strength*

ISO 10350-1, *Plastics — Acquisition and presentation of comparable single-point data — Part 1: Moulding materials*

ISO 11357-3, *Plastics — Differential scanning calorimetry (DSC) — Part 3: Determination of temperature and enthalpy of melting and crystallization*

ISO 15512, *Plastics — Determination of water content*

ISO 27547-1, *Plastics — Preparation of test specimens of thermoplastic materials using mouldless technologies — Part 1: General principles, and laser sintering of test specimens*

IEC 60093, *Methods of test for volume resistivity and surface resistivity of solid electrical insulating materials*

IEC 60112, *Method for the determination of the proof and the comparative tracking indices of solid insulating materials*

IEC 60243-1, *Electric strength of insulating materials — Test methods — Part 1: Tests at power frequencies*

IEC 60250, *Recommended methods for the determination of the permittivity and dielectric dissipation factor of electrical insulating materials at power, audio and radio frequencies including metre wavelengths*

IEC 60296, *Fluids for electrotechnical applications — Unused mineral insulating oils for transformers and switchgear*

IEC 60695-11-10, *Fire hazard testing — Part 11-10: Test flames — 50 W horizontal and vertical flame test methods*

3 Preparation of test specimens

3.1 Treatment of the material before moulding

Before processing, the material sample shall have reached room temperature.

Before processing, the moisture content of the material sample shall not exceed 0,2 % (mass fraction) in the case of PAs having a viscosity number ≤ 200 ml/g, and not exceed 0,1 % (mass fraction) in the case of PAs having a viscosity number > 200 ml/g. For PA46, PA6T/66, PA6T/XT, PA6T/6I/66, PA6T/6I, PA6I/6T and PA NDT/INDT, the moisture content shall be less than 0,1 % (mass fraction).

The moisture content of filled or reinforced materials shall be expressed as a percentage of the total mass of the compound. The moisture content shall be determined in accordance with ISO 15512 and the viscosity number in accordance with ISO 307.

To ensure that the moisture content remains low, it is recommended that the sample material in the feed hopper of the injection-moulding machine be blanketed with a suitable gas (dried air, nitrogen or argon, for example). Better results may be obtained using a dehumidifier hopper drier.

If test specimens are to be prepared by laser sintering (see 3.3 and Annex A), follow the instructions given in Annex A for treatment of the material before processing.

3.2 Injection moulding

For the acquisition and presentation of comparable data, injection-moulded specimens are used so that valid comparisons between materials can be made. These data represent the most basic approach to the designation of the properties of materials.

Injection-moulded specimens shall be prepared in accordance with ISO 294-1, using the conditions specified in Table 1. Such specimens shall be prepared by injection moulding from dry granules. It is essential that the specimens are always prepared by the same procedure using the same processing conditions. The material shall be kept in sealed, moisture-proof containers until it is required for use.

Besides injection moulding, other methods are also used to manufacture PA parts, e.g. extrusion, blow moulding and methods using mouldless technologies. Different methods of manufacture can lead to significantly different properties, and it might be useful to measure these properties using test specimens prepared by the same method. For specimen preparation using laser sintering, see 3.3.

3.3 Laser sintering

Although injection-moulded specimens are the only ones to be used to measure designatory properties, it is sometimes useful to prepare specimens using the same techniques as are used in parts manufacture (see 3.2).

For specimen preparation using laser sintering, see Annex A.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 1874-2:2012

<https://standards.iteh.ai/catalog/standards/sist/bc540a36-689b-419d-b1b6-3c1e326290f8/iso-1874-2-2012>

Table 1 — Conditions for injection moulding of test specimens

Material ^{a, b}	Viscosity number ^c ml/g	Filler content %	Plasticizer content %	Melt temperature °C	Mould temperature °C
PA6	≤ 160	0	0	250	80
	> 160 but ≤ 200	0	0	260	80
	> 200	0	0	270	80
	≤ 120	> 0 but ≤ 70	0	270	80
	> 120 but ≤ 200	> 0 but ≤ 70	0	290	80
PA6/66	≤ 160	0	0	230	50
	> 160	0	0	250	50
PA66	≥ 100	0	0	290	80
	≤ 160	> 0 but ≤ 50	0	290	80
	≤ 160	> 50 but ≤ 70	0	300	100
PA66/6	≤ 200	≤ 70	0	290	80
PA46	≤ 260	≤ 70	0	315	120
PA69	≤ 200	0	0	270	80
PA610	≤ 200	0	0	270	80
PA612	≤ 250	0	0	250	80
	≤ 250	> 0 but ≤ 70	0	290	80
PA11	≤ 150	0	≥ 0	210	80
	> 150 but ≤ 200	0	≥ 0	230	80
	> 200 but ≤ 240	0	≥ 0	250	80
	≤ 130	> 0 but ≤ 30	0	220	80
	≤ 130	> 30 but ≤ 50	0	230	80
	> 130 but ≤ 240	> 0 but ≤ 20	0	250	80
	> 130 but ≤ 240	> 20 but ≤ 50	0	260	80
	PA12	≤ 130	≤ 10	≤ 5	200
> 130 but ≤ 200	≤ 10	≤ 5	220	80	
> 200	≤ 10	≤ 5	240	80	
≤ 130	0	> 5	200	60	
> 130 but ≤ 200	0	> 5	210	60	
> 200	0	> 5	220	60	
≤ 130	> 10 but ≤ 30	0	230	80	
≤ 130	> 30 but ≤ 70	0	250	80	
> 130 but ≤ 240	> 10 but ≤ 30	0	240	80	
> 130 but ≤ 240	> 30 but ≤ 70	0	260	80	

^a For the definition of PA and the symbols used to indicate the chemical structure of polyamide materials, see ISO 472 and ISO 1874-1, respectively.

^b For the polyamides mentioned in this table, with the exception of PA46, PA6T/66, PA6T/XT, PA6T/6I, PA6I/6T, PA6T/6I/66, PA66/6I and PA9T, the injection velocity shall be 200 mm/s ± 100 mm/s. For PA46, PA6T/66, PA6T/XT, PA6T/6I, PA6I/6T, PA6T/6I/66, PA66/6I and PA9T, the injection velocity shall be 300 mm/s ± 100 mm/s.

^c The preferred reference solvent according to ISO 307.

Table 1 (continued)

Material ^{a, b}	Viscosity number ^c ml/g	Filler content %	Plasticizer content %	Melt temperature °C	Mould temperature °C
PA MXD6	≤ 130	0	0	250	130
	> 130 but ≤ 160	0	0	260	130
	≤ 130	> 0 but ≤ 50	0	270	100
	≤ 130	> 50 but ≤ 70	0	280	130
	> 130 but ≤ 160	> 0 but ≤ 50	0	280	130
	> 130 but ≤ 160	> 50 but ≤ 70	0	290	130
PA6T/XT	≤ 160	≤ 70	0	325	150
PA6T/66	≤ 160	≤ 70	0	325	100
PA6T/6I	≤ 200	≤ 70	0	325	130
PA6I/6T	≤ 200	≤ 70	0	325	130
PA6T/6I/66	≤ 200	≤ 70	0	325	130
PA66/6I	≤ 160	≤ 70	0	290	90
PA9T	≤ 200	≤ 70	0	320	140
PA NDT/INDT	≤ 160	0	0	280	80
	≤ 120	> 0 but ≤ 50	0	300	80

^a For the definition of PA and the symbols used to indicate the chemical structure of polyamide materials, see ISO 472 and ISO 1874-1, respectively.

^b For the polyamides mentioned in this table, with the exception of PA46, PA6T/66, PA6T/XT, PA6T/6I, PA6I/6T, PA6T/6I/66, PA66/6I and PA9T, the injection velocity shall be 200 mm/s ± 100 mm/s. For PA46, PA6T/66, PA6T/XT, PA6T/6I, PA6I/6T, PA6T/6I/66, PA66/6I and PA9T, the injection velocity shall be 300 mm/s ± 100 mm/s.

^c The preferred reference solvent according to ISO 307.

4 Conditioning of test specimens

4.1 Conditioning states of the test specimen

Separate sets of test specimens for determination of properties shall be conditioned in two different ways: one set dry-as-moulded and the other in the moist state.

Properties shall be determined on specimens in the dry-as-moulded state, or on specimens in the moist state, or on specimens in both states. The state of the specimens shall be stated in the test report.

4.2 Dry-as-moulded (DAM) state

Test specimens are considered to be in the DAM state when they have been placed, immediately after moulding, in a moisture-proof container and stored at 23 °C ± 2 °C for at least 24 h. The moisture content of DAM specimens shall not exceed 0,2 % (mass fraction). The intentional addition of water to reach this moisture content is not allowed, nor is drying of specimens with moisture contents above this limit.

To maintain absorbed moisture at a low level, DAM specimens shall be tested in as short a time as possible (maximum 15 min) after removal from the moisture-proof container.

Annealing specimens prior to testing is not allowed.