
**Textiles — Cotton fibres — Evaluation
of maturity by the air flow method**

*Textiles — Fibres de coton — Évaluation de la maturité par la
méthode à courant d'air*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 10306:2014](https://standards.iteh.ai/catalog/standards/sist/dbe5bc53-cef1-4e8d-8959-ec875d7880cb/iso-10306-2014)

[https://standards.iteh.ai/catalog/standards/sist/dbe5bc53-cef1-4e8d-8959-
ec875d7880cb/iso-10306-2014](https://standards.iteh.ai/catalog/standards/sist/dbe5bc53-cef1-4e8d-8959-ec875d7880cb/iso-10306-2014)



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 10306:2014

<https://standards.iteh.ai/catalog/standards/sist/dbe5bc53-cef1-4e8d-8959-ec875d7880cb/iso-10306-2014>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus and materials	2
6 Atmosphere for conditioning and testing	3
7 Sampling and number of specimens	3
8 Procedure	3
9 Calculations and expression of results	3
10 Test report	4
Annex A (normative) Operation of the air flow instrument “Fineness/Maturity Tester”	5
Annex B (normative) Method for instrument calibration	6

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 10306:2014](https://standards.iteh.ai/catalog/standards/sist/dbe5bc53-cef1-4e8d-8959-ec875d7880cb/iso-10306-2014)

<https://standards.iteh.ai/catalog/standards/sist/dbe5bc53-cef1-4e8d-8959-ec875d7880cb/iso-10306-2014>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 38, *Textiles*, Subcommittee SC 23, *Fibres and yarns*.

This second edition cancels and replaces the first edition (ISO 10306:1993), of which it constitutes a minor revision.

Introduction

The term “cotton fibre maturity” is commonly used to signify the relative degree of fibre wall development. The measurement of the relative degree of wall thickening is too laborious for most practical purposes, therefore the determination of the maturity of cotton fibres is done by indirect methods. A microscopic method is described in ISO 4912:1981. This method has been used as a reference method for the industrial evaluation of the maturity of cotton fibres using air flow instruments, which is the object of this standard.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 10306:2014](https://standards.iteh.ai/catalog/standards/sist/dbe5bc53-cef1-4e8d-8959-ec875d7880cb/iso-10306-2014)

<https://standards.iteh.ai/catalog/standards/sist/dbe5bc53-cef1-4e8d-8959-ec875d7880cb/iso-10306-2014>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 10306:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/dbe5bc53-cef1-4e8d-8959-ec875d7880cb/iso-10306-2014>

Textiles — Cotton fibres — Evaluation of maturity by the air flow method

1 Scope

This International Standard specifies a method for the evaluation of the maturity of loose randomized cotton fibres by measuring the resistance to air flow of a plug of cotton fibres under two prescribed conditions. The method is applicable to cotton taken at random from bales. Laps and slivers or other sources of lint cotton may be tested, however results may differ if fibres are taken from bales.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139:2005, *Textiles — Standard atmospheres for conditioning and testing*

ISO 1130:1975, *Textile fibres — Some methods of sampling for testing*

ISO 2403:2014, *Textiles — Cotton fibres — Determination of micronaire value*

ISO 4912:1981, *Textiles — Cotton fibres — Evaluation of maturity — Microscopic method*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4912:1981 and ISO 2403:2014 apply. The following terms and definitions are repeated here for the convenience of the user.

3.1

immature fibre

fibre which, upon swelling, either assumes a spiral form or lies flat, thinly outlined and almost transparent

Note 1 to entry: It has a wall thickness of less than one-fourth of the maximum fibre width.

[SOURCE: ISO 4912:1981]

3.2

mature fibres

fibres, the cell walls of which have developed sufficiently so that upon swelling, they become unconvoluted and almost rod-like in shape

Note 1 to entry: Such fibres have a wall thickness equal to or greater than one-fourth of the maximum fibre width.

[SOURCE: ISO 4912:1981]

3.3

maturity ratio, M

ratio of the degree of wall thickening to a standard degree of thickening selected arbitrarily to equal 0,577

[SOURCE: ISO 4912:1981]

3.4

percent maturity, P_m

average percentage of mature fibres in a sample, based on the total number of fibres

[SOURCE: ISO 4912:1981]

3.5

micronaire value

measure of the air permeability of a mass of cotton under specified conditions, expressed in terms of an arbitrary scale, the so-called micronaire scale

Note 1 to entry: The micronaire scale is based on a range of cottons to which micronaire values have been assigned by international agreement.

[SOURCE: ISO 2403:2014]

4 Principle

Air is passed through a test specimen consisting of a plug of well-opened randomized cotton fibres. For the same mass of fibres the permeability is measured by two different compressions of the plug. For each compression, air is passed through the plug at a specified rate and the pressure drop across the plug is indicated on a pressure gauge and expressed as the height, in millimetres, of a water column. The pressure drop obtained at low compression of the plug is designated PL and the other, at high compression, is designated PH. These two pressures may be used to calculate a maturity ratio and fibre linear density or a percentage of mature fibres using appropriate formulae. The micronaire value is determined solely from the PL value.

(standards.iteh.ai)

5 Apparatus and materials

ISO 10306:2014

5.1 Balance, of sufficient capacity to weigh the test specimen required for the air flow instrument used, with a sensitivity of better than 0,005 g.

5.2 Air flow instrument (see [Annex A](#)).

The principal parts comprising the air flow instrument are:

5.2.1 Compression cylinder, with perforated end, of such dimensions that with the specified mass of specimen each cubic centimetre of the cylinder shall contain 0,191 1 g of cotton at low compression and 0,382 1 g of cotton at high compression.

5.2.2 Means of measuring air permeability of the specimen, comprising for example:

- a) a suitable air pump;
- b) two valves or other means for controlling the flow of air through the specimen or the pressure drop across the specimen in the compression cylinder;
- c) means for setting the required rate of air flow through the specimen and a gauge for measuring the air pressure drop across the specimen.

NOTE Details of certain commercially available instruments which comply with this specification are given in [Annexes A](#) and [B](#). The method of calibration of air flow instruments is described in [Annex B](#).

5.3 International calibration cotton standards

Reference cotton used for the calibration of air flow instruments is described in [B.2.2](#).

5.4 Specimen preparation apparatus

Any blending apparatus is considered suitable if it produces randomly oriented samples.

NOTE Apparatus that produces webs of predominantly parallel fibres is not suitable.

6 Atmosphere for conditioning and testing

6.1 Condition test samples in the standard atmosphere for 4 h in moving air or alternatively for 12 h in still air. Preconditioning is not required.

6.2 Weigh and test the specimen in the standard atmosphere for conditioning (see ISO 139:2005).

7 Sampling and number of specimens

The sampling scheme, the number of specimens to be tested and the number of measurements to be made on each specimen will normally be determined by the material specification or will be agreed between the interested parties. In the absence of any instructions, test at least two specimens, making two tests on each. Samples of raw cotton from bales may be taken according to the method described in ISO 1130:1975.

The mass of the test specimens shall be as specified by the manufacturer of the air flow instrument.

iTeh STANDARD PREVIEW (standards.iteh.ai)

8 Procedure

8.1 Before each series of measurements, make the necessary preliminary adjustments appropriate to the instrument in use (see [Annexes A and B](#)). 10306:2014

[https://standards.iteh.ai/catalog/standards/sist/dbe5bc53-cef1-4e8d-8959-](https://standards.iteh.ai/catalog/standards/sist/dbe5bc53-cef1-4e8d-8959-ec875d7880cb/iso-10306-2014)

8.2 Divide the weighed specimen with the fingers into four to six portions, tease each portion out randomly until about 50 mm to 70 mm in diameter and place each portion successively into the sample holder until the entire specimen is loaded. Carefully insert the first portion so as to fill in the bottom edges of the sample holder by pushing it well into the bottom of the sample holder and outwards to the edges. Take care to insert all the specimen and not to lose any of the fibres. Insert the compression plunger and lock it in its position. Avoid fibres sticking between the cylinder wall and the compression plunger.

8.3 Cause air to flow through the specimen at the appropriate flow rate for the low compression of the plug and after 10 s note the reading, PL, on the pressure scale of the instrument to an accuracy of 1 mm of the water column. Next cause air to flow through the specimen at the appropriate flow rate for the high compression of the plug and after 10 s note the reading, PH, on the pressure scale of the instrument to the same accuracy of 1 mm of the water column.

8.4 Remove the test specimen from the cylinder and reinsert it, reversing the individual portions, and repeat the procedure given in [8.2](#) and [8.3](#).

8.5 Repeat the procedure given in [8.2](#) to [8.4](#) on a second test specimen taken from the same sample.

If the PL or PH readings of the two successive specimens from the same sample differ by more than 5 %, it is recommended to examine a new specimen from the same sample and to calculate the average readings for all specimens tested.

9 Calculations and expression of results

Average the two readings of each pressure drop, PL and PH, taken for each specimen tested from a sample. Using each pair of average readings, PL and PH, calculate the maturity ratio, M , or the percent