



Standard Test Method for Ductility of Oriented Electrical Steel¹

This standard is issued under the fixed designation A 721; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This test method covers determination of the ductility of grain-oriented silicon steel by use of an apparatus known variously as a tinner's brake, hand folder, or an apron brake.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.3 The values stated in either customary (cgs-emu and inch-pound) units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with this test method.

2. Referenced Documents

2.1 ASTM Standards:

A 34 Practice for Sampling and Procurement Testing of Magnetic Materials²

A 876/A 876M Specification for Flat-Rolled, Grain-Oriented, Silicon-Iron, Electrical Steel, Fully Processed Types²

E 290 Test Methods for Bend Testing of Material for Ductility³

3. Summary of Test Method

3.1 A test specimen representing the full width of grain-oriented steel to be tested is bent through an angle of about 160° in a tinner's brake. The number of breaks, or fractures, occurring along the bend determines the ductility class rating.

4. Significance and Use

4.1 This is a specialized bend test for grain-oriented steel not covered under the provisions of Test Methods E 290.

4.2 This test is applicable to grain-oriented silicon steel such as covered in Specifications A 876/A 876M in commercial

thicknesses and widths up to 36 in. [910 mm].

5. Apparatus

5.1 The machine required to perform this test is known variously as a tinner's brake, hand folder, or an apron brake.

5.2 The brake shall be at least 36 in. [910 mm] wide with an opening capacity of approximately 0.035 in. [0.9 mm].

5.2.1 The nose bar shall have a 0.031-in. [0.8-mm] radius.

5.2.2 The bending bar must be movable through an angle of at least 160°.

5.2.3 The movable table or apron shall move around the end of the nose bar at a distance of approximately 0.25 in. [6.35 mm].

6. Test Specimen

6.1 Two specimens are required and they shall be selected from the same general location as that of the magnetic test specimens in accordance with Practice A 34.

6.2 The specimens shall be cut transversely to the rolling direction and have a length equal to the sheet or strip width and a minimum dimension of 3 in. [80 mm] in the direction of rolling.

6.3 The specimens shall be free of rust, ripples, and scratches.

7. Procedure

7.1 The test specimen shall be at a temperature of $25 \pm 5^\circ\text{C}$ at the start of the test.

7.2 Insert the test specimen into the brake and clamp with the direction of rolling perpendicular to the nose bar and 0.5 to 1.5 in. [12 to 40 mm] under the nose bar thereby allowing the balance of the specimen width to rest against the bending bar.

7.3 Bend the specimen around the nose bar at a uniform rate by rotating the bending bar through an angle of 160°.

7.4 Remove the specimen from the machine and without straightening the bend, examine the outside face of the bend for surface breaks, without magnification.

7.5 Count the breaks and measure for length.

8. Interpretation of Results

8.1 Classify each test specimen according to length of number of breaks as shown in the following table which is based on giving a larger numerical class rating corresponding to the larger number of breaks and poorer ductility.

¹ This test method is under the jurisdiction of ASTM Committee A-6 on Magnetic Properties and is the direct responsibility of Subcommittee A06.01 on Test Methods.

Current edition approved Oct. 10, 1997. Published December 1998. Originally published as A 721 – 75. Last previous edition A 721 – 92.

² Annual Book of ASTM Standards, Vol 03.04.

³ Annual Book of ASTM Standards, Vol 03.01.