



DRAFT INTERNATIONAL STANDARD ISO/DIS 1432.2

ISO/TC 45/SC 2

Secretariat: JISC

Voting begins on
2012-02-28

Voting terminates on
2012-04-28

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Rubber, vulcanized or thermoplastic — Determination of low-temperature stiffening (Gehman test)

Caoutchouc vulcanisé ou thermoplastique — Détermination de la rigidité à basse température (Essai Gehman)

[Revision of third edition (SO 1432:1988) and ISO 1432:1988/Cor.1:2003]

ICS 83.060

ITeH STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/fb641669-a233-4d93-aed1-99d172-dbb8a0/iso-1432-2013>

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

Pour accélérer la distribution, le présent document est distribué tel qu'il est parvenu du secrétariat du comité. Le travail de rédaction et de composition de texte sera effectué au Secrétariat central de l'ISO au stade de publication.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/fb641669-a233-4d93-aed1-99d172dbb8a0/iso-1432-2013>

Copyright notice

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	1
5 Calibration	2
6 Test piece	3
6.1 Preparation of test piece	3
6.2 Conditioning of test piece	3
7 Procedure	3
7.1 Mounting of test piece	3
7.2 Stiffness measurements in liquid media	4
7.3 Stiffness measurement in gaseous media	4
7.4 Crystallization	4
8 Number of tests	4
9 Expression of results	5
9.1 Torsional modulus	5
9.2 Relative modulus	5
9.3 Apparent torsional modulus of rigidity	5
10 Test report	6
Annex A (normative) Calibration Schedule	9
A.1 Inspection	9
A.2 Schedule	9
A.3 Calibration of torsion wire	10
Bibliografi	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1432 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This fourth edition cancels and replaces the third edition (ISO 1432:1988), which has been technically revised to allow automatic computerized instruments and it also incorporates Technical Corrigendum 1 from 2003.

Rubber, vulcanized or thermoplastic — Determination of low-temperature stiffening (Gehman test)

WARNING - Persons using this International Standard should be familiar with normal laboratory practice. This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

WARNING 2 — Certain procedures specified in this International Standard might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This International Standard specifies a static procedure, known as the Gehman test, for determining the relative stiffness characteristics of vulcanized or thermoplastic rubbers over a temperature range from room temperature to approximately -150 °C.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 18899:2004, Rubber — Guide to the calibration of test equipment

ISO 23529, Rubber — General procedures for preparing and conditioning test pieces for physical test methods

3 Principle

The torsional stiffness is measured as a function of temperature, starting from a low temperature. The stiffness is measured by connecting the test piece in series with a calibrated spring wire and measuring the angle of twist of the test piece when the top of the wire is turned through 180°.

4 Apparatus

4.1 Torsion apparatus, consisting of a torsion head, capable of being turned 180° in a plane normal to the torsion wire. The top of the wire is fastened to the torsion head. The bottom of the wire is fastened to the test piece clamp. A device for “friction-free” indication or recording of angle by mechanical or electrical means shall be provided permitting convenient and exact adjustment of the zero point. The indicating or recording system shall allow reading or recording of the angle of twist to the nearest degree. It is advantageous to make the vertical portion of the stand from material of poor thermal conductivity. The base of the stand shall be of stainless steel or other corrosion-resistant material. The principle is shown in figure 1.

4.2 Torsional wires, made of tempered spring wire, of length $65 \text{ mm} \pm 8 \text{ mm}$, and having nominal torsional constants of 0,7 mN.m, 2,8 mN.m and 11,2 mN.m.

In cases of dispute, the 2,8 mN.m wire shall be used.

4.3 Test piece rack, made of material of poor thermal conductivity, for holding the test piece in a vertical position in the heat transfer medium. The rack may be constructed to hold several test pieces. The rack is attached to a stand. It is advantageous to make the vertical portion of the stand from material of poor thermal conductivity. The base of the stand shall be of stainless steel or other corrosion-resistant material.

Two clamps shall be provided for holding each test piece. The bottom clamp shall be attached to the test piece rack.

The top clamp acts as an extension of the test piece and is connected to the torsion wire by a rod.

4.4 Heat-transfer medium, liquid or gaseous, which remains fluid at the test temperature and which does not appreciably affect the material being tested, as prescribed in ISO 23529.

Gases may be employed as the heat transfer medium provided the design of the apparatus is such that results obtained using them will duplicate those obtained with liquids.

NOTE The following fluids have been used satisfactorily:

- a) for temperatures down to -60°C , silicone fluids of kinematic viscosity of about $5 \text{ mm}^2/\text{s}$ at ambient temperature, which are usually suitable owing to their chemical inertness towards rubbers, their non-flammability and their non-toxicity;
- b) for temperatures down to -73°C , ethanol;
- c) for temperatures down to -120°C , methylcyclohexane cooled by liquid nitrogen (found to be satisfactory with the use of suitable apparatus).

4.5 Temperature-measuring device, capable of measuring temperature to within $0,5^\circ\text{C}$ over the whole range of temperature over which the apparatus is to be used.

The temperature sensor shall be positioned near the test pieces.

4.6 Temperature control, capable of maintaining the temperature of the heat-transfer medium to within $\pm 1^\circ\text{C}$.

4.7 Container for heat-transfer medium, a bath for a liquid medium, or a test chamber for a gaseous medium, with means of heating the coolant

4.8 Stirrer, for liquids, or **fan** or **blower**, for gases, which ensures thorough circulation of the heat-transfer medium. It is important that the stirrer also moves the liquid vertically to ensure a uniform temperature in the liquid.

4.9 Stopwatch, or other timing device, calibrated in seconds.

5 Calibration

The requirements for calibration of the test apparatus are given in Annex A.

6 Test piece

6.1 Preparation of test piece

Test pieces shall be prepared in accordance with ISO 23529.

The dimensions of the test piece shall be length of 40 mm \pm 2,5 mm, width of 3 mm \pm 0,2 mm and thickness of 2 mm \pm 0,2 mm. It shall be moulded or cut with a suitable die from a moulded sheet of suitable thickness.

6.2 Conditioning of test piece

6.2.1 The minimum time between forming and testing shall be 16 h.

For non-product tests, the maximum time between forming and testing shall be 4 weeks and, for evaluations intended to be comparable, the tests should be carried out, as far as possible, after the same time interval.

For product tests, whenever possible, the time between forming and testing should not exceed 3 months. In other cases, tests shall be made within 2 months of the date of receipt by the customer of the product.

6.2.2 Samples and test pieces shall be protected from light as completely as possible during the interval between forming and testing.

6.2.3 Prepared test pieces shall be conditioned in accordance with ISO 23529 immediately before testing for a minimum of 3 h at a Standard laboratory temperature, the same temperature being used throughout any one test or series of tests intended to be comparable.

7 Procedure

7.1 Mounting of test piece

Clamp each test piece used in such a manner that 25 mm \pm 3 mm of the test piece is free between the clamps. The test piece clamp shall be located in such a position that the specimen is under zero torque or with a slight pre-load to keep the test piece straight when the temperature changes.

If the absolute modulus is required measure the test length of the test pieces to the nearest 0,5 mm, the width to the nearest 0,1 mm and the thickness to the nearest 0,01 mm.

7.2 Stiffness measurements in liquid media

Make the reference measurement with the standard torsion wire (2,8 mNm) at 23 °C \pm 2 °C, either in air or in the liquid bath.

If the test is made in the liquid, place the rack containing the test pieces in the liquid bath with a minimum of 25 mm of liquid covering the test pieces.

Adjust the angle measuring device to zero. Then turn all test pieces at the same time, or in sequence, quickly but smoothly through 180° and record the torsion angle after 10 s. If the test pieces are measured in sequence, ensure that all the measurements are completed within approximately 2 min. If the reading at 23 °C does not fall in the range of 120° to 170° the standard torsion wire is not suitable for testing the test piece. Test pieces producing twists of more than 170° shall be tested with a wire having a torsional constant of 0,7 mN·m. Test pieces producing twists of less than 120° shall be tested with a wire having a torsional constant of 11,2 mN·m.

If the reference measurement has been made in the liquid, remove the test pieces from the liquid bath and adjust the temperature of the liquid to the lowest temperature desired.

Place the test pieces in the bath with a minimum of 25 mm of liquid covering the test pieces and maintain them at this temperature for approximately 15 min.

Then increase the bath temperature by one of the two following methods:

- a) by stepwise 5 °C intervals, each increase being made after approximately 5 min;
- b) increase the temperature continuously with a heating rate of about 1 °C/min.

Make the stiffness measurements in the stepwise case after conditioning of the test piece for 5 min at each temperature and in the continuous case at intervals of 1 min maximum. Continue the tests until a temperature is reached at which the angular twist is within 5° to 10° of the twist at 23 °C.

Record the angle of twist and the temperature at each measurement.

The relative modulus may be plotted on a graph during the test.

7.3 Stiffness measurement in gaseous media

7.3.1 General

Procedures with air, carbon dioxide or nitrogen differ from those with liquid media only in that cooling is done with the test pieces in the medium and the length of the conditioning period is different.

7.3.2 Increase of temperature in steps

With the test pieces in the test chamber, adjust the temperature of the chamber to the lowest temperature desired in approximately 30 min. After this temperature has been maintained constant for 10 min, make the measurements in a similar way as in the liquid media, ensuring that all the test pieces in the rack are tested within 2 min.

Increase the temperature of the chamber by 5 °C intervals, each increase being made in approximately 10 min, and make stiffness measurements after conditioning of the test pieces for 10 min at each temperature.

7.3.3 Continuous increase of temperature

With the test pieces in the test chamber adjust the temperature of the chamber to the lowest temperature desired, by application of a linear time programme, preferably with a rate of 3 °C/min. After this temperature has been reached, increase the temperature linearly at a rate of about 1 °C/min. Carry out measurements of the twist angle at 5 °C intervals.

Record the angle of twist and the temperature at each measurement.

7.4 Crystallization

When it is desired to study crystallization or plasticizer effects, the time of conditioning at the desired temperature should be increased.

8 Number of tests

At least three test pieces of each material shall be tested. It is good practice to include a control rubber with known twist temperature characteristics.

9 Expression of results

9.1 Torsional modulus

The torsional modulus of the test piece at any temperature is proportional to the quantity

$$\frac{180 - \alpha}{\alpha}$$

where α is the angle of twist, in degrees, of the test piece.

9.2 Relative modulus

The relative modulus at any temperature is the ratio of the torsional modulus at that temperature to the torsional modulus at 23 °C.

The value of the relative modulus for any temperature is readily determined from the angles of twist at that temperature and at 23 °C and the ratio of the values of the factor $(180 - \alpha)/\alpha$ corresponding to those angles.

The temperatures at which the relative modulus is 2; 5; 10 and 100 respectively, are determined by the use of Table 1 and the twist versus temperature values for the test piece. The first column of table 1 lists each degree of twist in the range of 120° to 170°, so that the value corresponding to the twist of the test piece at 23 °C can be selected.

Successive columns give the twist angles which correspond to values 2; 5; 10 and 100 respectively, for the relative modulus. The temperatures corresponding to these angles are designated as t_2 , t_5 , t_{10} and t_{100} respectively.

9.3 Apparent torsional modulus of rigidity

When it is desired to calculate the apparent torsional modulus of rigidity in pascals at various temperatures, the free length of the test piece shall be accurately measured.

The apparent torsional modulus of rigidity, G , in pascals, is given by the equation

$$G = \frac{16KL(180 - \alpha)}{bd^3 \mu \alpha}$$

where

K is the torsional constant, in newton metres, of the torsion wire found at calibration;

L is the measured free length, in metres, of the test piece;

b is the width, in metres, of the test piece;

d is the thickness, in metres, of the test piece;

μ is the factor based on the ratio b/d taken from table 2;

α is the angle of twist, in degrees, of the test piece.