



Designation: A 724/A 724M – 99

# Standard Specification for Pressure Vessel Plates, Carbon-Manganese-Silicon Steel, Quenched and Tempered, for Welded Layered Pressure Vessels<sup>1</sup>

This standard is issued under the fixed designation A 724/A 724M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ε) indicates an editorial change since the last revision or reappraisal.

## 1. Scope

1.1 This specification<sup>2</sup> covers three grades of carbon-manganese-silicon steel, designated Grades A, B, and C. Grade C may be produced with a boron addition. The plates are quenched and tempered and are intended for welded-layered pressure vessels.

1.2 The maximum thickness of plates supplied under this specification is limited only by the capability of the chemical composition to meet the specified mechanical requirements. However, current practice normally limits the maximum thickness to 7/8 in. [22 mm] for Grades A and B, and to 2 in. [50 mm] for Grade C.

1.3 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

## 2. Referenced Documents

### 2.1 ASTM Standards:

A 20/A 20M Specification for General Requirements for Steel Plates for Pressure Vessels<sup>3</sup>

## 3. General Requirements and Ordering Information

3.1 Material supplied to this material specification shall conform to Specification A 20/A 20M. These requirements outline the testing and retesting methods and procedures, permissible variations in dimensions and weight, quality and repair of defects, marking, loading, etc.

3.2 Specification A 20/A 20M also establishes the rules for the ordering information that should be complied with when purchasing material to this specification.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved March 10, 1999. Published June 1999. Originally published as A 724 – 75. Last previous edition A 724/A 724M – 90(1996)<sup>ε1</sup>.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-724/SA-724M in Section II of that Code.

<sup>3</sup> Annual Book of ASTM Standards, Vol 01.04.

3.3 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements. These include:

- 3.3.1 Vacuum treatment,
- 3.3.2 Additional or special tension testing,
- 3.3.3 Impact testing, and
- 3.3.4 Nondestructive examination.

3.4 The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification A 20/A 20M.

3.5 If the requirements of this specification are in conflict with the requirements of Specification A 20/A 20M, the requirements of this specification shall prevail.

## 4. Manufacture

4.1 *Steelmaking Process*—The steel shall be killed and shall conform to the fine austenitic grain size requirement of Specification A 20/A 20M.

## 5. Heat Treatment

5.1 All plates shall be quenched from a temperature in the range from 1600 to 1700°F [870 to 925°C]. Grades A and B shall then be tempered at not less than 1100°F [595°C], and Grade C shall then be tempered at not less than 1150°F [620°C]. The tempering soaking time shall be not less than 1/2 h.

**TABLE 1 Chemical Requirements**

| Element                      | Composition, % |           |           |
|------------------------------|----------------|-----------|-----------|
|                              | Grade A        | Grade B   | Grade C   |
| Carbon, max:                 |                |           |           |
| Heat analysis                | 0.18           | 0.20      | 0.22      |
| Product analysis             | 0.22           | 0.24      | 0.26      |
| Manganese:                   |                |           |           |
| Heat analysis                | 1.00–1.60      | 1.00–1.60 | 1.10–1.60 |
| Product analysis             | 0.92–1.72      | 0.92–1.72 | 1.02–1.72 |
| Phosphorus, max <sup>A</sup> | 0.035          | 0.035     | 0.035     |
| Sulfur, max <sup>A</sup>     | 0.035          | 0.035     | 0.035     |
| Silicon, max:                |                |           |           |
| Heat analysis                | 0.55           | 0.50      | 0.20–0.60 |
| Product analysis             | 0.60           | 0.55      | 0.18–0.65 |
| Copper, max: <sup>B</sup>    |                |           |           |
| Heat analysis                | 0.35           | 0.35      | 0.35      |