INTERNATIONAL STANDARD

ISO 9187-2

Second edition 2010-10-15

Injection equipment for medical use — Part 2: One-point-cut (OPC) ampoules

Matériel d'injection à usage médical —
Partie 2: Ampoules à un seul point de cassure (OPC)

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 9187-2:2010 https://standards.iteh.ai/catalog/standards/sist/a1ed9be9-1c0c-4a97-ac07-26e89a1d879c/iso-9187-2-2010



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 9187-2:2010

https://standards.iteh.ai/catalog/standards/sist/a1ed9be9-1c0c-4a97-ac07-26e89a1d879c/iso-9187-2-2010



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9187-2 was prepared by Technical Committee ISO/TC 76, *Transfusion, infusion and injection equipment for medical and pharmaceutical use.*

This second edition cancels and replaces the first edition (ISO 9187-2:1993), which has undergone a minor revision with the following modifications and ards.iteh.ai)

- the reference to ISO 9187-1 has been updated;
- the diameter of the point has been designated a_8 (instead of a_7) to be in line with the designation in ISO 9187-1.

ISO 9187 consists of the following parts, under the general title Injection equipment for medical use:

- Part 1: Ampoules for injectables
- Part 2: One-point-cut (OPC) ampoules

Introduction

Ampoules are suitable packaging materials for storing pharmaceutical products until they are administered to the patient. Owing to the direct contact between injectables and the primary container over extended storage periods, possible interactions are to be avoided in order to guarantee patient safety. Adequate means to achieve this objective include proper selection of primary packaging materials, the choice of suitable package design and the availability of specific requirements and methods for testing individual container systems.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 9187-2:2010 https://standards.iteh.ai/catalog/standards/sist/a1ed9be9-1c0c-4a97-ac07-26e89a1d879c/iso-9187-2-2010

Injection equipment for medical use —

Part 2:

One-point-cut (OPC) ampoules

1 Scope

This part of ISO 9187 specifies materials, dimensions and requirements for forms of one-point-cut (OPC) ampoules (forms B, C and D) for injectables.

Ampoules complying with this part of ISO 9187 are intended for single use only.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies. To site 1.21

ISO 9187-1:2010, Injection equipment for medical use — Part 1: Ampoules for injectables

https://standards.iteh.ai/catalog/standards/sist/a1ed9be9-1c0c-4a97-ac07-

B Dimensions and designation 26e89a1d879c/iso-9187-2-2010

3.1 Dimensions

The dimensions of OPC ampoules shall be as specified in ISO 9187-1 and as given in Table 1 and Figure 1 of this part of ISO 9187.

3.2 Designation

Designation of OPC ampoules shall consist of the descriptor word "ampoule", followed by a reference to this part of ISO 9187, followed by the ampoule form, the nominal volume and the colour of the glass.

EXAMPLE Designation of a form B OPC ampoule with a nominal volume of 10 ml, made of colourless glass (cl) complying with the requirements of this part of ISO 9187:

Ampoule ISO 9187-2 - OPC - B - 10 - cl

4 Material

The material shall be in accordance with ISO 9187-1:2010, Clause 4.

Table 1 — Dimensions of OPC ampoules

Dimensions in millimetres

Nominal volume ml	Diameter of point d_8	Distance from bottom line to upper line of point h9 max.	Wall thickness at constriction w_4
1	2 ± 0,5	32,5	0.7 ± 0.1
2		44,5	
3		46,5	
5		54,0	0.7 ± 0.15
10		70,0	0,8 ± 0,15
20		84,5	
25		99,5	1 ± 0,20
30		114,5	

Requirements

iTeh STANDARD PREVIEW

Hydrolytic resistance

(standards.iteh.ai)

The hydrolytic resistance shall be in accordance with ISO 9187-1:2010, 5.1.

ISO 9187-2:2010

Annealing quality https://standards.iteh.ai/catalog/standards/sist/a1ed9be9-1c0c-4a97-ac07-26e89a1d879c/iso-9187-2-2010

The annealing quality shall be in accordance with ISO 9187-1:2010, 5.2.

Breaking force 5.3

When tested in accordance with ISO 9187-1:2010, Clause 6, the breaking force shall comply with the values specified in Table 2.

In special cases, it may be possible to agree to a breaking force with a lower tolerance. This tolerance shall be agreed between manufacturer and user.

Position and stability of breaking point 5.4

The breaking point, consisting of colour pigments, shall be fixed in the centre above the cut. The maximum deviation from the centerline shall not exceed ±1 mm.

Table 2 —	Breaking	force
-----------	----------	-------

Nominal volume ml	Length	Breaking force	
	$l (= l_1 + l_2)$ mm	$F_{min.}$ N	$F_{\sf max.}$ N
1	36 (= 18 + 18)	25	65
2			
3			
5			70
10	60 (= 22 + 38)	30	80
20			
25			
30			

When testing the breaking force, the equipment shall be positioned on the centre of the cut otherwise a considerable increase in breaking force will result.

- **5.4.2** The breaking point shall withstand a heating period of 30 min in a drying oven at a temperature of 120 °C, followed by dipping into water at 30 °C ARD PREVIEW
- **5.4.3** The breaking point shall withstand usual cleaning and sterilization conditions.




Figure 1 — Typical examples of OPC ampoules

6 Delivery

Delivery conditions shall be in accordance with ISO 9187-1:2010, Clause 7.

7 Packaging

Packaging shall be in accordance with ISO 9187-1:2010, Clause 8.

8 Marking

Marking shall be in accordance with ISO 9187-1:2010, Clause 9.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 9187-2:2010 https://standards.iteh.ai/catalog/standards/sist/a1ed9be9-1c0c-4a97-ac07-26e89a1d879c/iso-9187-2-2010

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 9187-2:2010

https://standards.iteh.ai/catalog/standards/sist/a1ed9be9-1c0c-4a97-ac07-26e89a1d879c/iso-9187-2-2010