
**Packaging and the environment —
Processes for chemical recovery**

Emballage et environnement — Processus de valorisation chimique

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/TR 16218:2013](https://standards.iteh.ai/catalog/standards/sist/3906affd-4166-4f8c-bd3a-05fd825a5ef/iso-tr-16218-2013)

<https://standards.iteh.ai/catalog/standards/sist/3906affd-4166-4f8c-bd3a-05fd825a5ef/iso-tr-16218-2013>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/TR 16218:2013

<https://standards.iteh.ai/catalog/standards/sist/3906affd-4166-4f8c-bd3a-05fd825a5ef/iso-tr-16218-2013>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Inventory of relevant existing documents	2
5 Identification of further packaging-specific needs related to chemical recovery	2
6 Suitability for chemical recovery process	2
Annex A (informative) Examples of monomer recovery of PET	4
Annex B (informative) An example of oil recovery	6
Annex C (informative) An example of gas recovery	7
Annex D (informative) An example of reduction agent in blast furnaces	8
Annex E (informative) An example of raw material for coke manufacturing	9
Annex F (informative) Assessment checklist — suitability for chemical recovery process	10
Bibliography	11

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/TR 16218:2013](https://standards.iteh.ai/catalog/standards/sist/3906affd-4166-4f8c-bd3a-05fd825a5ef/iso-tr-16218-2013)

<https://standards.iteh.ai/catalog/standards/sist/3906affd-4166-4f8c-bd3a-05fd825a5ef/iso-tr-16218-2013>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

In exceptional circumstances, when a technical committee has collected data of a different kind from that which is normally published as an International Standard ("state of the art", for example), it may decide by a simple majority vote of its participating members to publish a Technical Report. A Technical Report is entirely informative in nature and does not have to be reviewed until the data it provides are considered to be no longer valid or useful.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO/TR 16218 was prepared by Technical Committee ISO/TC 122, *Packaging*, Subcommittee SC 4, *Packaging and Environment*.

[ISO/TR 16218:2013](https://standards.iteh.ai/catalog/standards/sist/3906affd-4166-4f8c-bd3a-05fd825a5ef/iso-tr-16218-2013)

<https://standards.iteh.ai/catalog/standards/sist/3906affd-4166-4f8c-bd3a-05fd825a5ef/iso-tr-16218-2013>

Introduction

Resource use optimization, resource savings, environmental impacts' minimization are among priorities in a perspective of sustainable development. These priorities apply also to the packaging sector. Since many years, this latter has developed initiatives in these directions, working on the packaging design aspects as well as on the organization of the logistic chain, on setting up recovery and recycling schemes or on the development of used packaging recovery or recycling technologies.

For various reasons, including the diversity of national or regional contexts, some confusion arose from the fact that neither legislations nor communication messages from the concerned stakeholders could rely on clear and unanimously agreed upon definitions of the terms used and of the respective benefits of the various recovery/recycling options.

ISO/TC 122/SC 4 is developing standards on the optimization of the packaging system (ISO 18602), on reuse (ISO 18603), on material recycling (ISO 18604), on energy recovery (ISO 18605) and on organic recycling (ISO 18606). ISO 18601 will define the general requirements for the use of these ISO standards in the field of packaging and the environment.

This Technical Report is an attempt to clarify some ideas relating to the concept of "Chemical Recovery", to put it in the perspective of the other recovery options and to help local stakeholders to identify the locally most appropriate treatment option, on the basis of a common understanding of the terms and of the basic requirements specific to each recovery technology. In this Technical Report, the methodologies of chemical recovery of used packaging are described.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO/TR 16218:2013](https://standards.iteh.ai/catalog/standards/sist/3906affd-4166-4f8c-bd3a-05fd825a5ef/iso-tr-16218-2013)

<https://standards.iteh.ai/catalog/standards/sist/3906affd-4166-4f8c-bd3a-05fd825a5ef/iso-tr-16218-2013>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/TR 16218:2013

<https://standards.iteh.ai/catalog/standards/sist/3906affd-4166-4f8c-bd3a-05fd825a5ef/iso-tr-16218-2013>

Packaging and the environment — Processes for chemical recovery

1 Scope

Several processes for chemical recovery of used packaging are considered to be material recycling. The focus of this Technical Report is for used packaging, although the processes described are not specific for used packaging and can be used for recovery of other materials of same type. Processes for chemical recovery of used packaging are applicable for plastic packaging or biomass-based packaging, which might be interpreted in two different ways:

- processes to recover valuable chemical substances by chemical treatment of used packaging, for example, to recover monomers of polyethylene terephthalate (PET) by hydrolysis, glycolysis or methanolysis, to recover oil by catalytic reaction or pyrolysis, to recover valuable gases such as hydrogen by gasification, to recover coke, oil and gasses by cokefaction;
- processes to directly substitute used packaging for natural resources without chemical pretreatment, for example, flakes of used plastic packaging may use in blast furnace in the place of coke as a reducing agent.

Examples and key characteristics of chemical recovery processes are given in [Annexes A to E](#).

NOTE For the purpose of this Technical Report, “Chemical recovery” means the production of chemicals, identical to or differing from, the starting raw materials that were used for the production of the packaging materials, or the direct substitution of natural resources by using used packaging. These recovered chemicals can be used as such, or as reactants in further chemical syntheses; directly ‘*in situ*’ or in another production process.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 21067, *Packaging — Vocabulary*

ISO 18601, *Packaging and the environment — General requirements for the use of ISO standards in the field of packaging and the environment*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 21067, ISO 18601, and the following apply.

3.1

monomer recovery

processes to recover monomers such as by decomposition of used packaging

Note 1 to entry: The industrial processes are established to recover monomers to produce polyethylene terephthalate (PET) such as dimethyl-terephthalate (DMT), bis-hydroxyethyl-terephthalate (BHET) and ethylene glycol (EG) by chemical decomposition of PET. The processes to recover monomers from the following polymers are at the development stage for polymers such as; polycarbonate (PC), polyamide (PA), polystyrene (PS) and poly lactic acid (PLA) polymer.

3.2

oil recovery

processes to recover oil from used packaging such as by decomposition with or without catalyst

3.3

gas recovery

processes to recover gases useful for chemical industries as their raw materials (hydrogen and carbon mono-oxide) such as by carbonization and partial burning of used packaging

3.4

reduction agent in blast furnaces

product providing carbon and hydrogen to replace coke with used packaging in blast furnaces for steel production

Note 1 to entry: In the conventional steel production processes, coke is used as a reduction agent.

3.5

raw material for coke manufacturing

product to partially replace coal with used packaging for raw material of coke furnaces to produce coke

4 Inventory of relevant existing documents

Various options of chemical recovery are also addressed in some standardization documents, for example

- ISO 15270:2008, Plastics — Guidelines for the recovery and recycling of plastics waste
- ISO 18601, Packaging and the environment — General requirements for the use of ISO standards in the field of packaging and the environment
- ISO 18604, Packaging and the environment — Material recycling
- ISO 21067, Packaging — Vocabulary

5 Identification of further packaging-specific needs related to chemical recovery

The prime objective of this Technical Report is specific for used packaging. In order to meet the needs of the market, the used packaging fraction ending up in a chemical recovery process is in many cases used in combination with other material fractions of the same type. Therefore the processes described in this Technical Report are in practise not restricted to used packaging.

Each recovery option has its own specifications, e.g. number of materials, maximum levels of contamination, etc. Certain materials may be incompatible with some chemical recovery processes. In cases of significant amount of such materials being included, pre-treatment to remove these should be introduced to avoid those problems.

6 Suitability for chemical recovery process

Chemical recovery is included as material recycling as an option. If used packaging, i.e. source material, is collected in mono-material route, the used packaging is feasible for mechanical recycling. In the case of PET bottles, however, chemical recovery by monomer recovery is also feasible to obtain high grade PET resin. In the case of expanded polystyrene (PS), some parts of source material can be recycled by mechanical recycling, and the other parts, i.e. contaminated material, are generally used as source of chemical recovery. If used packaging, i.e. source material, is collected in commingled material route, such material can be used as sources of chemical recovery other than monomer recovery. These recovery options possess wide acceptability of source material, commingled or contaminated, if only it does not impede the operation of facilities.

An example of assessment checklist is given in [Annex F](#).

NOTE Plastic materials are most suitable for these processes. However, if there is no obstacle on the operation of facilities, biomass-based materials such as wood, paper and fibre can be incorporated into the process.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/TR 16218:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/3906affd-4166-4f8c-bd3a-05fd825a5ef/iso-tr-16218-2013>