



Designation: A981 – 97 (Reapproved 2007)

# Standard Test Method for Evaluating Bond Strength for 15.2 mm (0.6 in.) Diameter Prestressing Steel Strand, Grade 270, Uncoated, Used in Prestressed Ground Anchors<sup>1</sup>

This standard is issued under the fixed designation A981; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method describes procedures to establish the relative bond strength of 15.2 mm (0.6 in.) diameter, Grade 270 prestressing steel strand in cement grout as used in prestressed ground anchors for the purpose of evaluating the effects of manufacturing practices on bond strength.

1.2 The bond strength values obtained shall not be used to design the bond length of ground anchors that depend on field conditions.

1.3 This test method is not intended to be used as a bond test for pretensioned concrete applications.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

[A416/A416M Specification for Steel Strand, Uncoated Seven-Wire for Prestressed Concrete](#)

[C150 Specification for Portland Cement](#)

[C511 Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes](#)

[C1019 Test Method for Sampling and Testing Grout](#)

[E4 Practices for Force Verification of Testing Machines](#)

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved Sept. 1, 2007. Published September 2007. Originally approve din 1997. Last previous edition approved in 2002 as A981 – 97 (2002). DOI: 10.1520/A0981-97R07.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *bond strength*—maximum measured load in a pull test on a 15.2 mm (0.6 in.) diameter prestressing steel strand embedded in cement grout.

3.1.2 *bonded length*—the length of the test strand that is in contact with the cement grout.

## 4. Apparatus

4.1 *Equipment*—A suitable tensile test machine or load frame shall be used. The loading system shall be calibrated in accordance with Practices E4. The test system shall have sufficient capacity to prevent yielding of its various components and shall ensure that the applied tensile load remains parallel to the axis of the prestressing steel strand during testing.

4.2 *Strand Displacement Measurements*—Displacements of the free end of the prestressing steel strand shall be measured with respect to the loaded surface of the test specimen using suitable measurement devices. Dial gages having the smallest division of not more than 25  $\mu\text{m}$  (0.001 in.) or linear variable differential transformers (LVDTs) with equal or superior accuracy are examples of satisfactory devices.

## 5. Test Specimen

5.1 *Prestressing Steel Strand*—shall be 15.2 mm (0.6 in.) diameter, Grade 270 and comply with Specification A416/A416M and shall be cut from standard production coils. The surface of the test samples shall not be wiped or cleaned in order to preserve their original condition. Minimum recommended sample length is 750 mm (30 in.).

5.2 *Strand Bond Test Specimen*—The test specimen shall consist of the prestressing steel strand embedded in cement grout and centered inside a steel pipe, 125 mm (5 in.) O.D. with a 3 mm (0.125 in.) wall, 450 mm (18 in.) long with a 150 by 150 by 6 mm (6 by 6 by 0.25 in.) base plate welded, or otherwise leakproof connected to one end of the steel pipe. Other mold designs, including reusable molds, shall be permissible, provided that the dimensions and confinement in regard to circumferential stress provided for the grout body are