
**Machine-made textile floor
coverings — Determination of
dimensional changes after exposure to
heat and/or water**

*Revêtements de sol textiles fabriqués à la machine — Détermination
de la variation dimensionnelle après exposition à la chaleur et/ou à
l'eau*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 17984:2014

<https://standards.iteh.ai/catalog/standards/sist/c865d3c2-4b18-4f86-a0d1-18e2659d0ce4/iso-17984-2014>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 17984:2014

<https://standards.iteh.ai/catalog/standards/sist/c865d3c2-4b18-4f86-a0d1-18e2659d0ce4/iso-17984-2014>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	1
5.1 Methods 1, 2, and 3.....	1
5.2 Methods 1 and 3.....	2
5.3 Methods 2 and 3.....	2
5.4 Method 4 (if used in conjunction with methods 1, 2, or 3).....	2
6 Sampling and selection of test specimens	2
6.1 Sampling.....	2
6.2 Number and dimensions of test specimens.....	2
6.3 Conditioning.....	2
7 Procedure	2
7.1 Method 1: Determination of dimensional changes after exposure to heat.....	2
7.2 Method 2: Determination of dimensional changes after immersion in water.....	3
7.3 Method 3: Determination of dimensional changes due to the effects of varied heat and water conditions.....	3
7.4 Method 4: Dimensional changes out of the plane.....	4
8 Dimensional stability calculation	4
9 Test report	4
Annex A (informative) Determination of dimensions of textile floor covering test specimens	5
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 219, *Floor coverings*.

This first edition of ISO 17984 cancels and replaces ISO/PAS 17984:2001.

<https://standards.iteh.ai/catalog/standards/sist/c865d3c2-4b18-4f86-a0d1-18e2659d0ce4/iso-17984-2014>

Introduction

When ISO/TC 38/SC 12 reviewed ISO 2551:1981, it decided that because the original method gave rise to technical difficulties, any revision should incorporate a number of test method options for dimensional stability to heat, water and combined heat, and water and stability out of the plane. In order to establish the utility of this new approach, and to allow the precision of each test method to be established, it was decided to initially publish a document that would allow for further development based on some or all of these methods.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 17984:2014](https://standards.iteh.ai/catalog/standards/sist/c865d3c2-4b18-4f86-a0d1-18e2659d0ce4/iso-17984-2014)

<https://standards.iteh.ai/catalog/standards/sist/c865d3c2-4b18-4f86-a0d1-18e2659d0ce4/iso-17984-2014>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 17984:2014

<https://standards.iteh.ai/catalog/standards/sist/c865d3c2-4b18-4f86-a0d1-18e2659d0ce4/iso-17984-2014>

Machine-made textile floor coverings — Determination of dimensional changes after exposure to heat and/or water

1 Scope

This International Standard specifies procedures for the determination of both planar and out-of-plane dimensional changes that take place when machine-made textile floor coverings are subjected to heat, water, or varied heat and water conditions.

The following methods are applicable to all machine-made textile floor coverings including those produced in tile form.

- Method 1: Determination of dimensional changes after exposure to heat.
- Method 2: Determination of dimensional changes after immersion in water.
- Method 3: Determination of dimensional changes due to the effects of varied heat and water conditions.
- Method 4: Dimensional changes out of the plane.

iTeh STANDARD PREVIEW

2 Normative references

(standards.iteh.ai)

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1957, *Machine-made textile floor coverings — Selection and cutting of specimens for physical tests*

ISO 2424, *Textile floor coverings — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 2424 apply.

4 Principle

Comparison is made between either planar or out-of-plane dimensions of a test specimen after conditioning in the standard atmosphere for testing textiles and after being subjected to either heat, water, or specified varied heat and water conditions.

5 Apparatus

5.1 Methods 1, 2, and 3

5.1.1 Instrument capable of measuring length to the nearest 0,1 mm, e.g. an optical bench or mechanical device with gauge.

5.1.2 Plate glass sheet, marginally smaller than the test specimen, or other means of keeping the specimen flat while measurements are made.

This will not be required if the instrument in [5.1.1](#) incorporates such a glass or metal plate.

5.1.3 Steel pins or other appropriate means of indicating the reference points on the test specimen, if necessary.

NOTE A suitable piece of equipment incorporating [5.1.1](#), [5.1.2](#), and [5.1.3](#) is given in [Annex A](#).

5.2 Methods 1 and 3

5.2.1 Ventilated drying oven, capable of being controlled at $60\text{ °C} \pm 2\text{ °C}$, with perforated and lacquered shelves that can be placed in the oven.

5.2.2 Desiccator or similar apparatus, for maintaining specimens in a dry condition.

5.3 Methods 2 and 3

5.3.1 Container, for holding water at $20\text{ °C} \pm 2\text{ °C}$, with dimensions at least 20 mm greater than the test specimen and deep enough to accommodate the submerged test specimen.

5.3.2 Rigid perforated tray, of a sufficient size to carry the test specimen.

5.3.3 Efficient wetting agent, e.g. sodium dioctyl sulfosuccinate or dodecylbenzene sodium sulfonate.

5.3.4 Means of ensuring a forced draught of ambient air, if required.

5.4 Method 4 (if used in conjunction with methods 1, 2, or 3)

5.4.1 Gauge or instrument, capable of measuring in the vertical dimension, to an accuracy of 0,5 mm.

<https://standards.iteh.ai/catalog/standards/sist/c865d3c2-4b18-4f86-a0d1-18e2659d0cc4/iso-17984-2014>

6 Sampling and selection of test specimens

6.1 Sampling

Select the specimens in accordance with ISO 1957.

6.2 Number and dimensions of test specimens

Take at least three test specimens each measuring not less than 450 mm × 450 mm, noting the direction of manufacture.

6.3 Conditioning

Lay out the specimens flat, singly and with the use surface uppermost in the standard atmosphere for testing for at least 48 h and until they reach constant mass (defined as no change in mass greater than 1 %) when determined at hourly intervals over a period of 3 h.

7 Procedure

7.1 Method 1: Determination of dimensional changes after exposure to heat

Make the first measurements (l_0) on the fully conditioned specimen using, e.g. the method described in [Annex A](#).

Place the specimen on the rigid perforated tray (see [5.3.2](#)) with the use surface uppermost, and put it on a shelf in the drying oven (see [5.2.1](#)) at $60\text{ °C} \pm 2\text{ °C}$. Keep the specimen in the drying oven for a period of

24 h. Remove it and place it immediately in a desiccator or similar apparatus (see 5.2.2) to allow cooling to take place. When its temperature has reached $20\text{ °C} \pm 2\text{ °C}$, remove the specimen from the desiccator and immediately measure the dimensions (l_1) using, e.g. the method described in Annex A.

Leave the specimens in the standard atmosphere for testing for 24 h to allow reconditioning to take place, until constant mass is again obtained (see 6.3). Measure the dimensions (l_2) to the nearest 0,1 mm using, e.g. the method described in Annex A. Note the final appearance of the specimen.

7.2 Method 2: Determination of dimensional changes after immersion in water

Make the first measurements (l_0) on the fully conditioned specimen using, e.g. the method described in Annex A.

Place the specimen on the rigid perforated tray with the use surface uppermost, and immerse it, laid flat, in water to which has been added 0,5 g/l of an efficient wetting agent (see 5.3.3), calculated on active matter content, at a temperature of $20\text{ °C} \pm 2\text{ °C}$. Allow the specimen to soak in the water for 2 h, ensuring that it remains submerged throughout. Lift the tray with the specimen from the water, taking precautions to avoid distorting its shape. Leave to drain in a horizontal position for $5\text{ min} \pm 1\text{ min}$. Place the specimen on the measuring board (see 5.1.1) and again measure the dimensions (l_1) using, e.g. the method described in Annex A.

Dry the specimen on the tray in the standard atmosphere for testing, as described in Clause 6, using a forced air draught (see 5.3.4) if necessary, until constant mass is again obtained as in 6.3. Measure the dimensions (l_2) using, e.g. the method described in Annex A. Note the final appearance of the specimen.

7.3 Method 3: Determination of dimensional changes due to the effects of varied heat and water conditions

7.3.1 Initial measurement of the specimen

Make all measurements on the conditioned specimen when it is completely flat; this can be achieved by use of the glass plate (see 5.1.2) or other means.

On the conditioned specimen, measure the distance between the edges parallel to the direction of manufacture and between the edges at right angles to the direction of manufacture, each at two locations approximately 200 mm apart. If required by the method of measuring adopted, mark the pair of reference points, e.g. by the use of steel pins (see 5.1.3), approximately 200 mm apart on the edge parallel to the direction of manufacture and also on the edge at right angles to the direction of manufacture. Make all measurements on the back of the specimen to the nearest 0,1 mm.

Products made of discrete layers, e.g. foam-backed constructions, should be measured on both the backing and the use-surface, and the results of both measurements given in the test report.

7.3.2 Determination

Place the test specimen, lying freely on the perforated and lacquered shelves, in the drying oven (see 5.2.1), controlled at $60\text{ °C} \pm 2\text{ °C}$. Keep the specimen in the drying oven for 2 h, then remove it and measure the distance between the two parallel edges or the two sets of marks to the nearest 0,1 mm, within 6 min to 7 min of removing the specimen from the oven.

Immerse the test specimen, laid flat, in water at a temperature of $20\text{ °C} \pm 2\text{ °C}$ and allow it to soak in the water for 2 h. Remove the specimen from the water, taking precautions to avoid distorting its shape. Excess moisture can be removed by placing the specimen between sheets of blotting paper. Within $5\text{ min} \pm 1\text{ min}$ of removing the specimen from the water, again measure the distance between the two parallel edges or the two sets of marks as specified in 7.1.

Dry the test specimen for 24 h in the drying oven at $60\text{ °C} \pm 2\text{ °C}$ under the same conditions as before. Within 6 min to 7 min of removing the specimen from the oven again measure the distance between the two parallel edges or two sets of marks as specified in 7.1.