



Designation: A472/A472M – 07

## Standard Specification for Heat Stability of Steam Turbine Shafts and Rotor Forgings<sup>1</sup>

This standard is issued under the fixed designation A472/A472M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 This specification covers the determination of heat stability of steam turbine shafts and rotor forgings to ensure stability at operating temperature. This specification is not ordinarily applicable to generator rotor forgings.

1.2 This specification is expressed in both inch-pound unit and in SI units; however, unless the purchase order or contract specifies the applicable M specification designation (SI units), the inch-pound units shall apply. The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the specification, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.3 Supplementary requirements of an optional nature are provided for use at the option of the purchaser. The supplementary requirements shall apply only when specified individually by the purchaser in the purchase order or contract.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Ordering Information

2.1 It shall be the responsibility of the purchaser to specify all requirements necessary for testing under this specification. Requirements to be considered include, but are not limited to, the following:

2.1.1 ASTM designation and year date,

2.1.2 The minimum test temperature,

2.1.3 The portion of the forging to be subjected to the heat stability test temperature, and

2.1.4 Supplementary or other special requirements.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved Sept. 1, 2007. Published September 2007. Originally approved in 1962. Last previous edition approved in 2005 as A472/A472M – 05. DOI: 10.1520/A0472\_A0472M-07.

### 3. Procedure

3.1 The heat stability test shall be conducted by the forging supplier after final heat treatment and after the forging has been centered and machined with allowance to finish to the purchaser's drawing. Material for mechanical tests may be removed before or after the stability test at the manufacturer's option, unless check tests after the stability test are required by the purchaser.

3.2 With prior approval from the purchaser, the forgings may be stress-relieved as part of the heat stability test. When this is done, the stress-relieving temperature shall be within 50 to 100°F [30 to 55°C] below final tempering temperature. Rotate the forgings at 2 to 4 r/min and hold at stress-relieving temperature for at least 2 h/in. [2 h/25 mm] of maximum radial thickness, after which the temperature may be decreased to the specified heat stability test temperature and the test performed.

### 4. Heat Stability Test Bands

4.1 The supplier shall mark positions A, B, C, and D, spaced 90° apart circumferentially, preferably on an end of the forging. Markings shall be retained throughout all subsequent operations.

4.2 Preferably, there shall be a minimum of 5 test bands, denoted as 1, 2, 3, 4, and 5, machined on the circumference of the forging. Numbering shall start at the left side of the forging drawing. Bands 1 and 5 shall be located as close to the end of the forging as practical. Band 3 shall be located as near to midlength as practical. Bands 2 and 4 shall be located approximately equidistant between 1 and 3, and 3 and 5, respectively.

4.3 When the shipped length of the barrel portion of the forging is less than 8 ft [2.4 m], bands 2 and 4 may be omitted.

4.4 The purchaser's drawing may show the desired number and location of bands and shall indicate that portion of the forging that shall be located within the heating chamber. Bands 1 and 5 are to be located outside of the heating chamber. Preferably, the gland areas/packing seal areas are inside the heating chamber.

4.5 The test bands shall be machined with the forging running on centers except in the cases of forgings weighing over 125 000 lb [56.7 metric tons] the machining shall be performed with the forgings running on steady rests. Readings

\*A Summary of Changes section appears at the end of this standard.