

---

---

**Plastics — Polycarbonate sheets —  
Types, dimensions and characteristics**

*Plastiques — Plaques en polycarbonate — Types, dimensions et  
caractéristiques*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 11963:2012](https://standards.iteh.ai/catalog/standards/sist/5f0d387c-494d-4ae0-a7a1-7a58aac41261/iso-11963-2012)

<https://standards.iteh.ai/catalog/standards/sist/5f0d387c-494d-4ae0-a7a1-7a58aac41261/iso-11963-2012>



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 11963:2012

<https://standards.iteh.ai/catalog/standards/sist/5f0d387c-494d-4ae0-a7a1-7a58aac41261/iso-11963-2012>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Composition</b> .....	<b>2</b>
<b>4 Requirements</b> .....	<b>2</b>
4.1 Masking.....	2
4.2 Appearance.....	2
4.3 Colour.....	2
4.4 Dimensions.....	3
4.5 Shrinkage.....	3
4.6 Basic properties.....	4
4.7 Weathering behaviour.....	4
4.8 Other properties.....	4
<b>5 Test methods</b> .....	<b>4</b>
5.1 General.....	4
5.2 Colour.....	5
5.3 Dimensions.....	5
5.4 Mechanical properties.....	5
5.5 Thermal properties.....	6
5.6 Optical properties.....	6
5.7 Weathering behaviour.....	6
<b>6 Reaction to fire</b> .....	<b>7</b>
<b>7 Use in contact with food</b> .....	<b>7</b>
<b>8 Retest and rejection</b> .....	<b>7</b>
<b>Annex A (normative) Determination of change in dimensions at elevated temperature (shrinkage)</b> .....	<b>8</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11963 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

This second edition cancels and replaces the first edition (ISO 11963:1995), which has been technically revised.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 11963:2012

<https://standards.iteh.ai/catalog/standards/sist/5f0d387c-494d-4ae0-a7a1-7a58aac41261/iso-11963-2012>

# Plastics — Polycarbonate sheets — Types, dimensions and characteristics

## 1 Scope

This International Standard specifies the requirements for solid, flat extruded sheets of polycarbonate (PC) for general applications. It applies specifically to sheets made of poly(*p,p'*-isopropylidene-diphenyl carbonate). The sheets may be coloured or colourless, and they may be transparent, translucent or opaque. The sheets may also have a special weather-protective layer on one or both surfaces.

This International Standard applies only to thicknesses equal to or greater than 1,5 mm.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 62:2008, *Plastics — Determination of water absorption*

ISO 75-1, *Plastics — Determination of temperature of deflection under load — Part 1: General test method*

ISO 75-2:2004, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite*

ISO 179-1:2010, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 306:2004, *Plastics — Thermoplastic materials — Determination of Vicat softening temperature (VST)*

ISO 489:1999, *Plastics — Determination of refractive index*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 877-1, *Plastics — Methods of exposure to solar radiation — Part 1: General guidance*

ISO 877-2, *Plastics — Methods of exposure to solar radiation — Part 2: Direct weathering and exposure behind window glass*

ISO 877-3, *Plastics — Methods of exposure to solar radiation — Part 3: Intensified weathering using concentrated solar radiation*

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 2859-1, *Sampling procedures for inspection by attributes — Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection*

ISO 2859-10, *Sampling procedures for inspection by attributes — Part 10: Introduction to the ISO 2859 series of standards for sampling for inspection by attributes*

ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance*

## ISO 11963:2012(E)

ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps*

ISO 7391-1, *Plastics — Polycarbonate (PC) moulding and extrusion materials — Part 1: Designation system and basis for specifications*

ISO 8256:2004, *Plastics — Determination of tensile-impact strength*

ISO 11359-2, *Plastics — Thermomechanical analysis (TMA) — Part 2: Determination of coefficient of linear thermal expansion and glass transition temperature*

ISO 13468-1, *Plastics — Determination of the total luminous transmittance of transparent materials — Part 1: Single-beam instrument*

ISO 14782, *Plastics — Determination of haze for transparent materials*

IEC 60093, *Methods of test for volume resistivity and surface resistivity of solid electrical insulating materials*

CIE 15, *Colorimetry*

CIE 85, *Solar spectral irradiance*

### 3 Composition

3.1 The following type of PC is preferred for PC sheet extrusion:

Thermoplastics ISO 7391-PC E 61-09

(see ISO 7391-1 for explanation of designation system for PC)

3.2 The sheet may contain colorants, additives, processing aids and stabilizers (e.g. UV-absorbers) up to a total mass content of 5 %.

3.3 Sheets of the type specified in Clause 4 may have a protective layer (on one or both surfaces) with a UV-absorber content higher than that of the substrate. The composition of the protective layer (e.g. polycarbonate and UV-absorber, or PMMA and UV-absorber, or other materials) and the application techniques (e.g. co-extrusion, coating, lamination, flow-coating, dipping) are not specified by this International Standard.

### 4 Requirements

#### 4.1 Masking

The surface of the sheet as delivered shall be protected by plastic film or paper or a combination of both.

#### 4.2 Appearance

Requirements concerning defects and optical quality shall be agreed upon between the interested parties.

#### 4.3 Colour

The colorant(s) shall be homogeneously and uniformly distributed throughout the material, unless otherwise specified. For critical requirements, the degree of homogeneity shall be specified by the interested parties.

## 4.4 Dimensions

### 4.4.1 Conditions of measurement

Measurements should preferably be made under the standard conditions  $23\text{ °C} \pm 2\text{ °C}$  and  $(50 \pm 10)\%$  relative humidity. For measurements made under ambient conditions, allowance shall be made for dimensional changes due to the differences in temperature and relative humidity at the place of measurement from the preferred temperature and relative humidity.

### 4.4.2 Length and width

The length and width of the sheets shall be agreed upon between the interested parties. The tolerances on length and width shall be as specified in Table 1.

**Table 1 — Tolerances on length and width**

Length or width mm	Tolerance
Up to 1 000	$+3_0$ mm
From 1 001 to 2 000	$+6_0$ mm
From 2 001 to 3 000	$+9_0$ mm
3 001 and over	$+0,3_0\%$

### 4.4.3 Deviation of shape from rectangular

The difference  $\Delta l$  between the lengths of the two diagonals of the rectangular sheet shall be less than  $3,5 \times 10^{-3} \times b$  (where  $b$  is the width, in millimetres, of the sheet, measured perpendicular to the direction of extrusion), but need not be less than 2 mm.

### 4.4.4 Thickness

The tolerance on the thickness of the sheets shall be as specified in Table 2.

**Table 2 — Tolerances on thickness**

Thickness, $d$ mm	Tolerance %
$1,5 \leq d \leq 5$	$\pm 10$
$5 < d$	$\pm 5$

## 4.5 Shrinkage

The maximum shrinkage (see 5.5.3) shall be as specified in Table 3.

**Table 3 — Maximum shrinkage**

Thickness, $d$ mm	Maximum shrinkage %
$1,5 \leq d \leq 5$	10
$5 < d$	5

#### 4.6 Basic properties

The basic mechanical, thermal and optical properties of transparent, colourless sheets shall be as specified in Table 5. For other grades, the required properties shall be agreed upon between the interested parties.

#### 4.7 Weathering behaviour

Any requirements on natural- or artificial-weathering behaviour shall be agreed upon between the interested parties, as required.

#### 4.8 Other properties

Other properties of transparent, colourless sheets, needed for specific applications, shall be agreed upon between the interested parties. Examples of, and test methods for, such properties are presented in Table 4.

**Table 4 — Typical values of other properties of transparent, colourless sheets**

	Unit	Test method	Typical value
Density	g/cm <sup>3</sup>	ISO 1183-1	1,2
Coefficient of linear thermal expansion	K <sup>-1</sup>	ISO 11359-2	65 × 10 <sup>-6</sup>
Refractive index, $n_D^{20}$		ISO 489:1999, method A	1,59
Haze (3 mm)	%	ISO 14782	1
Surface resistivity	Ω	IEC 60093	10 <sup>15</sup>
Water absorption (pre-conditioning: 50 °C/24 h; immersion time in water: 24 h)	mg	ISO 62:2008, method 1	16

For other grades, the required properties shall be agreed upon between the interested parties.

### 5 Test methods

#### 5.1 General

##### 5.1.1 Sampling

The sampling procedure shall be agreed upon between the interested parties. The procedures described in ISO 2859-1 and ISO 2859-10 are widely accepted and frequently used. Hence these are recommended for sampling.

##### 5.1.2 Conditioning and testing of specimens

Conditioning (48 h) and testing of specimens shall be carried out at 23 °C ± 2 °C and (50 ± 10) % relative humidity, in accordance with ISO 291, except for the Vicat softening temperature and the temperature of deflection under load (see 5.5.1 and 5.5.2).

##### 5.1.3 Preparation of specimens

Specimens shall be prepared, wherever applicable, in accordance with the procedures described in ISO 2818. When it is necessary to machine the sheet to reduce its thickness to the dimension required for a particular test method, one original surface shall be left intact.



With PC sheets coated on one side, the coated side shall remain unmachined. With PC sheets coated on both sides, two groups of specimens shall be prepared. One group shall retain one of the original coated sides and the other group, the other original coated side. The two groups shall be tested separately.

## 5.2 Colour

Colour differences between a reference material (standard) and the specimens shall be determined using a differential colorimetric instrument, as agreed between the parties concerned: e.g. CIELAB data (CIE 15) may be used.

## 5.3 Dimensions

**5.3.1** The length and width of the sheets shall be measured to the nearest 1 mm.

**Table 5 — Requirements on basic properties**

	Unit	Test method	Type of specimen	Required value	Sub-clause
<b>Mechanical properties</b>					
Tensile stress at yield, $\sigma_y$	MPa	ISO 527-2/1A/50 ISO 527-2/1B/50	1A 1B	$\geq 55$	5.4.1
Modulus of elasticity in tension, $E_t$	MPa	ISO 527-2/1A/1 ISO 527-2/1B/1	1A 1B	$\geq 2\,200$	5.4.1
Nominal tensile strain at break, $\varepsilon_{tB}$	%	ISO 527-2/1A/50 ISO 527-2/1B/50	1A 1B	$\geq 60$	5.4.1
Charpy impact strength (notched, notch radius 0,25 mm; thickness $\geq 4$ mm)	kJ/m <sup>2</sup>	ISO 179-1/1eA ISO 11963:2012	1	$\geq 6$	5.4.2
Tensile impact strength (double-notched, thickness $< 4$ mm)	kJ/m <sup>2</sup>	ISO 8256:2004, method A	1	$\geq 150$	5.4.2
<b>Thermal properties</b>					
Vicat softening temperature	°C	ISO 306:2004, method B50		$\geq 145$	5.5.1
Temperature of deflection under load (thickness $\geq 3$ mm)	°C	ISO 75-2:2004, method A		$\geq 130$	5.5.2
<b>Optical properties</b>					
Light transmittance, $\tau_t$ (380 nm to 780 nm)		ISO 13468-1			5.6
Thickness, $t$	1,5 mm $\leq t < 4$ mm 4 mm $\leq t < 6$ mm 6 mm $\leq t < 12$ mm 12 mm $\leq t$ mm			$\geq 85$ $\geq 82$ $\geq 80$ $\geq 75$	

**5.3.2** The thickness of the sheets shall be measured to the nearest 0,05 mm, excluding the masking film or paper, and without damaging the surface. Measurements shall be made at points not less than 100 mm from the sheet edge.

## 5.4 Mechanical properties

**5.4.1** Tensile properties shall be determined in accordance with ISO 527-1 and ISO 527-2, using specimen type 1A or 1B. The test speed for tensile stress at yield and nominal strain at break shall be 50 mm/min and for the modulus of elasticity in tension, 1 mm/min.