
**Metallic powders — Determination of tap
density**

*Poudres métalliques — Détermination de la masse volumique après
tassement*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 3953:2011](https://standards.iteh.ai/catalog/standards/sist/1c802552-e4d0-4044-ae88-12c4763e7927/iso-3953-2011)

[https://standards.iteh.ai/catalog/standards/sist/1c802552-e4d0-4044-ae88-
12c4763e7927/iso-3953-2011](https://standards.iteh.ai/catalog/standards/sist/1c802552-e4d0-4044-ae88-12c4763e7927/iso-3953-2011)



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 3953:2011](#)

<https://standards.iteh.ai/catalog/standards/sist/1c802552-e4d0-4044-ae88-12c4763e7927/iso-3953-2011>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 3953 was prepared by Technical Committee ISO/TC 119, *Powder metallurgy*, Subcommittee SC 2, *Sampling and testing methods for powders (including powders for hardmetals)*.

This fourth edition cancels and replaces the third edition (ISO 3953:1993), of which it constitutes a minor revision.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/1c802552-e4d0-4044-ae88-12c4763e7927/iso-3953-2011>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 3953:2011

<https://standards.iteh.ai/catalog/standards/sist/1c802552-e4d0-4044-ae88-12c4763e7927/iso-3953-2011>

Metallic powders — Determination of tap density

1 Scope

This International Standard specifies a method for the determination of tap density, i.e. the density of a powder that has been tapped into a container under specified conditions.

2 Principle

A specified amount of powder in a container is tapped by means of a tapping apparatus until no further decrease in the volume of the powder takes place. The mass of the powder divided by its volume after the test gives its tap density.

3 Symbols

For the purposes of this document, the symbols in Table 1 apply.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Table 1 — Symbols

Symbol	Meaning	Unit
ρ_t	Tap density	g/cm ³
m	Mass of the powder	g
V	Volume of the tapped powder	cm ³

4 Apparatus

4.1 Balance, of appropriate capacity to satisfy the requirements shown in Table 2 and of an accuracy to weigh to the nearest 0,1 g.


4.2 Graduated glass cylinder, calibrated to contain 100 cm³, the height of the graduated portion being approximately 175 mm. The graduations shall be at 1 cm³ intervals, thus allowing a measuring accuracy of $\pm 0,5$ cm³.

Alternatively:

Graduated glass cylinder, calibrated to contain 25 cm³, the height of the graduated portion being approximately 135 mm. The graduations shall be at 0,2 cm³ intervals.

A 25 cm³ cylinder shall be used for powders of apparent density higher than 4 g/cm³, in particular for refractory metal powders, but may also be used for powders of lower apparent density.

4.3 Tapping apparatus, which permits the tapping of the graduated cylinder against a firm base. The tapping shall be such that a densification of the powder can take place without any loosening of its surface layers. The stroke shall be 3 mm and the tapping frequency shall be between 100 and 300 taps/min. An example of a tapping apparatus is shown in Figure 1.



Key

- 1 graduated measuring cylinder
- 2 holder with guide-pin
- 3 guide-bearing
- 4 anvil (steel)
- 5 cam

^a Height of stroke.

Figure 1 — Example of tapping apparatus

5 Sampling

5.1 For the quantities of powder required for each test, see Table 2.

Table 2 — Required sample quantities

Apparent density g/cm ³	Cylinder capacity cm ³	Mass of test portion g
1 to 4	100	100 ± 0,5
< 1	100	50 ± 0,2
> 7	25	100 ± 0,5
> 2 to 7	25	50 ± 0,2
0,8 to 2	25	20 ± 0,1
< 0,8	25	10 ± 0,1

5.2 In general, the powder should be tested in the as-received condition. In certain instances, the powder may be dried. However, if the powder is susceptible to oxidation, the drying shall take place in a vacuum or in an inert gas. If the powder contains volatile substances, it shall not be dried.

5.3 The test shall be carried out on three test portions, if possible.

6 Procedure

ISO 3953:2011

[https://standards.iteh.ai/catalog/standards/sist/1c802552-e4d0-4044-ae88-](https://standards.iteh.ai/catalog/standards/sist/1c802552-e4d0-4044-ae88-13e4763e7927/iso-3953-2011)

6.1 Clean the inside wall of the graduated cylinder (4.2) with a suitable clean brush or, if necessary, by rinsing with a solvent, such as acetone. If a solvent is used, thoroughly dry the cylinder before re-use.

6.2 Weigh, to the nearest 0,1 g, the mass of the test portion as indicated in Table 2, using the balance (4.1).

6.3 Pour the test portion into the graduated cylinder. Take care that a level surface of the powder is formed. Place the cylinder in the tapping apparatus (4.3). Tap the cylinder until no further decrease in the volume of the powder takes place (see Note).

NOTE In practice, the minimum number of taps, N , would be determined such that no further change in volume takes place. For all further tests on the same type of powder, the cylinder would be subjected to $2N$ taps, except where general experience and acceptance has established a specific number of taps (no less than N taps) as being satisfactory. For fine refractory metal powders, 3 000 taps has been found to be satisfactory for all sizes.

6.4 If the tapped surface is level, read the volume directly. If the tapped surface is not level, determine the tap volume by calculating the mean value between the highest and the lowest reading of the tapped surface. Read the final volume to the nearest 0,5 cm³ when using a 100 cm³ cylinder, and to the nearest 0,2 cm³ when using a 25 cm³ cylinder.

7 Expression of results

The tap density is given by the following equation:

$$\rho_t = \frac{m}{V}$$

where ρ_t , m and V are as defined in Table 1.

Report the arithmetical mean of the number of determinations rounded to the nearest 0,1 g/cm³ for values up to and including 4 g/cm³, and to the nearest 0,2 g/cm³ for values greater than 4 g/cm³.

8 Test report

The test report shall include the following information:

- a) a reference to this International Standard, i.e. ISO 3953:2011;
 - b) all details necessary for identification of the test sample;
 - c) the drying procedure, if the powder has been dried;
 - d) the cylinder capacity, mass of the test portion and method used;
 - e) the result obtained;
 - f) all operations not specified in this International Standard or regarded as optional;
 - g) details of any occurrence which may have affected the result.
- ITeH STANDARD PREVIEW**
(standards.iteh.ai)
[ISO 3953:2011](https://standards.iteh.ai/catalog/standards/sist/c802552-e4d0-4044-ae88-12c4763e7927/iso-3953-2011)
<https://standards.iteh.ai/catalog/standards/sist/c802552-e4d0-4044-ae88-12c4763e7927/iso-3953-2011>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 3953:2011

<https://standards.iteh.ai/catalog/standards/sist/1c802552-e4d0-4044-ae88-12c4763e7927/iso-3953-2011>