



Designation: B139/B139M – 07

Standard Specification for Phosphor Bronze Rod, Bar, and Shapes¹

This standard is issued under the fixed designation B139/B139M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification establishes the requirements for phosphor bronze rod, bar, and shapes.

1.2 *Units*—The values stated in inch-pound units or SI units are to be regarded separately in the standard. Within the text, the SI values are given in brackets. The values stated in each system are not exact equivalents; each system of units is independent of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

2.1 *ASTM Standards*:²

[B249/B249M Specification for General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, Shapes and Forgings](#)

[E8 Test Methods for Tension Testing of Metallic Materials](#)

[E8M Test Methods for Tension Testing of Metallic Materials \[Metric\] \(Withdrawn 2008\)](#)³

[E62 Test Methods for Chemical Analysis of Copper and Copper Alloys \(Photometric Methods\) \(Withdrawn 2010\)](#)³

[E478 Test Methods for Chemical Analysis of Copper Alloys](#)

3. General Requirements

3.1 The following sections of Specification [B249/B249M](#) constitute a part of this specification.

3.1.1 Terminology.

3.1.2 Materials and Manufacture.

3.1.3 Workmanship, Finish and Appearance.

3.1.4 Sampling.

3.1.5 Number of Tests and Retests.

3.1.6 Specimen Preparation.

3.1.7 Test Methods.

3.1.8 Significance of Numerical Limits.

3.1.9 Inspection.

3.1.10 Rejection and Rehearing.

3.1.11 Certification.

3.1.12 Mill Test Report.

3.1.13 Packaging and Package Marking.

3.2 In addition, when a section with a title identical to that referenced in [3.1](#) above appears in this specification, it contains additional information which supplements that appearing in Specification [B249/B249M](#). In case of conflict, this specification shall prevail.

4. Ordering Information

4.1 Include the following information when placing orders for product under this specification, as applicable:

4.1.1 ASTM designation and year of issue,

4.1.2 Copper Alloy UNS No. designation (for example, C51000),

4.1.3 Temper (for example, H04),

4.1.4 Form of product (rod, bar or shape),

4.1.5 Dimensions and permissible variations,

4.1.6 Edge Contours,

4.1.7 Quantity—total weight of each copper alloy, temper, form, and size, and

4.1.8 If product is purchased for an agency of the U.S. government (see Supplementary Requirements section of [B249/B249M](#)).

4.2 The following options are available and should be specified at the time of placing the order when required:

4.2.1 Piston-finish rod or shafting (Other Requirements section),

4.2.2 Certification (Specification [B249/B249M](#)), and

4.2.3 Mill test report (Specification [B249/B249M](#)).

5. Material and Manufacture

5.1 *Material*:

5.1.1 The material of manufacture shall be cast rod, bar, or billets of Copper Alloy UNS Nos. C51000, C52100, C52400, C53400, or C54400 and of such soundness as to be suitable for processing in to the products prescribed herein.

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.02 on Rod, Bar, Wire, Shapes and Forgings.

Current edition approved Oct. 1, 2007. Published October 2007. Originally approved in 1941. Last previous edition approved in 2006 as B139/B139M – 06. DOI: 10.1520/B0139_B0139M-07.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard

NOTE 1—Copper Alloy UNS Nos. C51000, C52100, and C52400 are suitable for structural applications, pump parts, rods, bolts, gears, and similar applications.

NOTE 2—Copper Alloys UNS Nos. C53400 and C54400 are free machining and are suitable for screw-machine products.

5.2 Manufacture:

5.2.1 The product shall be manufactured by such hot-working, cold-working, and annealing processes as to produce a uniform wrought structure in the finished product.

5.2.2 The product shall be hot or cold worked to the finished size and subsequently annealed, when required, to meet the temper properties specified.

6. Chemical Composition

6.1 The material shall conform to the chemical composition requirements in **Table 1** for the Copper Alloy UNS No. designation specified in the ordering information.

6.1.1 These composition limits do not preclude the presence of other elements. By agreement between the manufacturer and the purchaser, limits may be established and analysis required for unnamed elements.

6.2 For alloys in which copper is listed as “remainder,” copper is the difference between the sum of all elements determined and 100 %.

6.3 When all elements specified in **Table 1**, for the Copper Alloy UNS No. named in the ordering information are determined, the sum of results shall be 99.5 % min.

7. Temper

7.1 *Rod and Bar*—The standard tempers for rod and bar produced under this specification are identified in **Table 2** or **Table 3**.

7.1.1 Soft anneal temper (O60),

7.1.2 Hard temper (H04), and

7.1.3 Spring temper (H08).

7.2 *Shapes*—The temper for shapes is subject to agreement between the manufacturer and the purchaser and the agreement shall be a part of the contract or purchase order.

8. Mechanical Property Requirements

8.1 Tensile Strength Requirements :

8.1.1 *Rod and Bar*—Rod and bar furnished under this specification shall conform to the tensile requirements prescribed in **Table 2** or **Table 3** for the specified Copper Alloy UNS No. designation, temper, cross-section, and size when tested in accordance with Test Methods **E8** or **E8M**.

8.1.2 *Shapes*—The tensile requirements for shapes shall be subject to agreement between the manufacturer and the purchaser and the agreement shall be a part of the contract or purchase order.

9. Other Requirements

9.1 *Piston-Finish Rod or Shafting*—When specified in the contract or purchase order, round rod over ½-in. [12-mm] diameter shall be furnished as piston-finish rod or shafting.

9.2 *Purchases for U.S. Government*—When specified in the contract or purchase order, product purchased for agencies of the U.S. government shall conform to the additional requirements prescribed in the Supplementary Requirements section of Specification **B249/B249M**.

10. Dimensions, Mass, and Permissible Variations

10.1 The dimensions and tolerances for product described by this specification shall be as specified in Specification **B249/B249M** with particular reference to the following tables and related paragraphs in that specification:

10.1.1 *Diameter or Distance Between Parallel Surfaces:*

10.1.1.1 *Rod: Round, Hexagonal, Octagonal*—Table 2.

10.1.1.2 *Piston-Finish Rod*—Table 3.

10.1.1.3 *Bar: Rectangular and Square*—Tables 9 and 11.

10.1.2 *Shapes:*

10.1.2.1 The dimensional tolerances for shapes shall be subject to agreement between the manufacturer and the purchaser and the agreement shall be a part of the contract or purchase order.

10.1.3 *Length:*

10.1.3.1 *Rod, Bar, and Shapes*—Tables 13 and 15.

10.1.4 *Straightness:*

10.1.4.1 *Rod and Bar*—Table 16.

10.1.4.2 *Shafting Rod*—Table 17.

10.1.4.3 *Piston-Finish Rod*—The tolerance is subject to agreement between the manufacturer and the purchaser and the agreement shall be a part of the contract or purchase order.

10.1.5 *Edge Contours:*

10.1.5.1 For a description of edge contours, refer to the section titled “Edge Contours” and Figs. 1, 2, and 3 in Specification **B249/B249M**.

11. Test Methods

11.1 Chemical Analysis:

11.1.1 In cases of disagreement, determine the composition using the following test methods:

TABLE 1 Chemical Requirements

Element, %	Copper Alloy UNS No.				
	C51000	C52100	C52400	C53400	C54400
Tin	4.2–5.8	7.0–9.0	9.0–11.0	3.5–5.8	3.5–4.5
Phosphorus	0.03–0.35	0.03–0.35	0.03–0.35	0.03–0.35	0.01–0.50
Iron, max	0.10	0.10	0.10	0.10	0.10
Lead	0.05 max	0.05 max	0.05 max	0.8–1.2	3.0–4.0
Zinc	0.30 max	0.20 max	0.20 max	0.30 max	1.5–4.5
Copper	remainder	remainder	remainder	remainder	remainder