This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.

INTERNATIONAL

Designation: B101-02 Designation: B 101 - 07

Standard Specification for Lead-Coated Copper Sheet and Strip for Building Construction¹

This standard is issued under the fixed designation B 101; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification establishes the requirements for lead-coated copper sheet and strip in flat lengths (or in coils) in ounce-weight thicknesses for roofing, flashing, gutters, downspouts, and for the general sheet metalwork in building construction. The lead coating is applied by hot dipping.

1.2 Materials made to this specification are not intended for electrical applications.

1.3 Units—The values____Values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units, which are provided for information only and are not considered standard.

NOTE 1-A companion specification for copper sheet and strip for building construction is Specification B 370.

1.4 The following hazard caveat pertains to the test method portion, Section 17, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1The following documents in the current issue of the *Annual Book of ASTM Standards* form a part of this specification to the extent referenced herein:

 $\frac{2.2}{2.2}$

2.1 ASTM Standards:²

B 248 Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar B 370 Specification for Copper Sheet and Strip for Building Construction

B 601 Classification for Temper Designations for Copper and Copper Alloys-Wrought and Cast

B 846 Terminology for Copper and Copper AlloysASTM B101-

E 8 Test Methods for Tension Testing of Metallic Materials Test Methods for Tension Testing of Metallic Materials

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E 37 Test Methods for Chemical Analysis of Pig Lead

E 46 Test Methods for Chemical Analysis of Lead- and Tin-Base Solders³

- E 62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods)
- E 112 Test Methods for Determining Average Grain Size

E 478 Test Methods for Chemical Analysis of Copper Alloys

3. General Requirements

3.1The following sections of Specification B248 constitute a part of this specification:

3.1.1Significance of numerical limits,

3.1.2Inspection,

3.1.3Rejection and rehearing,

3.1.4Certification,

Current edition approved Apr. 10, 2002. Published June 2002. Originally published as B101-35T. Last previous edition B101-01.

Current edition approved Oct. 1, 2007. Published October 2007. Originally approved in 1935. Last previous edition approved in 2002 as B 101 - 02.

³ Annual Book of ASTM Standards, Vol 03.01.

³ Discontinued

*A Summary of Changes section appears at the end of this standard.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

¹ This specification is under the jurisdiction of Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards , Vol 02.01.volume information, refer to the standard's Document Summary page on the ASTM website.



3.1.5Mill test reports, and

3.1.6Packaging and package marking.

4.Terminology

4.1For3.1 For definitions of terms related to copper and copper alloys, refer to Terminology B 846.

<u>3.2</u> Definitions of Terms Specific to This Standard:

4.2.1

4.2

3.2.1 coil—a length of the product wound into a series of connected turns.

4.2.1.1

<u>3.2.1.1</u> *Discussion*—The unqualified term "coil" as applied to "flat product" usually refers to a coil in which the product is spirally wound, with the successive layers on top of one another. (Sometimes called a "roll.")

4.2.2

<u>3.2.2</u> lead-coated copper sheet (for building construction), n—a rolled flat product over 24 in. (610 mm) in width and of ounce-weight thickness from 8 oz (227 g) to 48 oz (1361 g).

4.2.3

<u>3.2.3</u> *lead-coated strip (for building construction)*, n—a rolled flat product up to and including 24 in. (610 mm) in width and of ounce-weight thickness from 8 oz (227 g) to 48 oz (1361 g).

4.2.4

3.2.4 lengths, mill, n-straight lengths, including ends, that are conveniently manufactured in the mills.

4.2.4.1

<u>3.2.4.1</u> Discussion—Full length pieces are usually 8, 10, or 12 ft (2.44, 3.05, or 3.66 m) and subject to established length tolerances.

4.2.5

<u>3.2.5</u> *lengths, specific, n*—straight lengths that are uniform in length, as specified, and subject to established length tolerances. $\frac{3.2.5}{4.2.6}$

3.2.6 ounce-weight-the weight of uncoated copper sheet or strip expressed in ounces per square foot.

42.7 (https://standards.iteh.a

<u>3.2.7</u> thickness, ounce-weight, n—the metal thickness that corresponds to the ounce weight.

4. General Requirements

4.1 The following sections of Specification B 248 constitute a part of this specification:

4.1.1 Significance of numerical limits,

4.1.2 Inspection,

4.1.3 Rejection and rehearing, dards/astm/09179dde-8f9a-45e2-8794-cf5951a458b7/astm-b101-07

4.1.4 Certification,

4.1.5 Mill test reports, and

4.1.6 Packaging and package marking.

4.2 In addition, when a section with a title identical to that referenced in 4.1, above, appears in this specification, it contains additional requirements that supplement those appearing in Specification B 248.

5. Ordering Information

5.1Include the following information:

5.1 Include the following information when placing orders for product under this specification, as applicable:

5.1.1 ASTM designation and year of issue.

5.1.2 Temper (Section 8 and Table 1),

5.1.3 How furnished: flat lengths or in coils,

5.1.4 Quantity: total weight or sheets of each size,

Temper Designation		Tensile Strength, ksi ^A (MPa)		Yield Strength, at 0.5 % Extension	Approximate Rockwell Hardness ^a (for Information Only)			
Standard	Former	Min	Max	Under Load, min, ksi (MPa)	F Scale		Superficial 30 T	
Stanuaru					Min	Max	Min	Max
O60	soft	30 (210)	38 (265)			65		31
H00	cold-rolled	32 (225)	40 (280)	20 (140)	54	82	15	49
H01	cold-rolled (high yield)	34 (240)	42 (295)	28 (195)	60	84	18	51

TABLE 1 Mechanical Properties of Uncoated Sheet

^A ksi = 100 psi.

^B Rockwell hardness values apply as follows: The F scale applies to metal 0.020 in. (0.508 mm) and over in thickness; the superficial 30T scale applies to metal 0.012 in. (0.305 mm) to 0.020 in. (0.508 mm) in thickness.