



Designation: B248 – 07

# Standard Specification for General Requirements for Wrought Copper and Copper- Alloy Plate, Sheet, Strip, and Rolled Bar<sup>1</sup>

This standard is issued under the fixed designation B248; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope\*

1.1 This specification establishes the general requirements common to several wrought product specifications. Unless otherwise specified in the purchase order or in an individual specification, these general requirements shall apply to copper and copper-alloy plate, sheet, strip, and rolled bar supplied under each of the following product specifications issued by ASTM: **B36/B36M**, **B96/B96M**, **B103/B103M**, **B121/B121M**, **B122/B122M**, **B152/B152M**, **B169/B169M**, **B194**, **B422**, **B465**, **B534**, **B543**, **B591**, **B592**, **B694**, **B740**, **B747**, and **B768**.<sup>2</sup>

NOTE 1—A complete metric companion to Specification B248 has been developed—B248M; therefore no metric equivalents are presented in this specification.

1.2 *Units*—This specification is the companion specification to SI Specification **B248M**; therefore, no SI equivalents are shown in this specification.

## 2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards*:<sup>3</sup>

**B36/B36M** Specification for Brass Plate, Sheet, Strip, and Rolled Bar

**B96/B96M** Specification for Copper-Silicon Alloy Plate, Sheet, Strip, and Rolled Bar for General Purposes and Pressure Vessels

**B103/B103M** Specification for Phosphor Bronze Plate, Sheet, Strip, and Rolled Bar

**B121/B121M** Specification for Leaded Brass Plate, Sheet, Strip, and Rolled Bar

**B122/B122M** Specification for Copper-Nickel-Tin Alloy, Copper-Nickel-Zinc Alloy (Nickel Silver), and Copper-Nickel Alloy Plate, Sheet, Strip, and Rolled Bar

**B152/B152M** Specification for Copper Sheet, Strip, Plate, and Rolled Bar

**B169/B169M** Specification for Aluminum Bronze Sheet, Strip, and Rolled Bar

**B193** Test Method for Resistivity of Electrical Conductor Materials

**B194** Specification for Copper-Beryllium Alloy Plate, Sheet, Strip, and Rolled Bar

**B248M** Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar (Metric)

**B422** Specification for Copper-Aluminum-Silicon-Cobalt Alloy, Copper-Nickel-Silicon-Magnesium Alloy, Copper-Nickel-Silicon Alloy, Copper-Nickel-Aluminum-Magnesium Alloy, and Copper-Nickel-Tin Alloy Sheet and Strip

**B465** Specification for Copper-Iron Alloy Plate, Sheet, Strip, and Rolled Bar

**B534** Specification for Copper-Cobalt-Beryllium Alloy and Copper-Nickel-Beryllium Alloy Plate, Sheet, Strip, and Rolled Bar

**B543** Specification for Welded Copper and Copper-Alloy Heat Exchanger Tube

**B591** Specification for Copper-Zinc-Tin and Copper-Zinc-Tin-Iron-Nickel Alloys Plate, Sheet, Strip, and Rolled Bar

**B592** Specification for Copper-Zinc-Aluminum-Cobalt Alloy, Copper-Zinc-Tin-Iron Alloy Plate, Sheet, Strip, and Rolled Bar

**B694** Specification for Copper, Copper-Alloy, Copper-Clad Bronze (CCB), Copper-Clad Stainless Steel (CCS), and Copper-Clad Alloy Steel (CAS) Sheet and Strip for Electrical Cable Shielding

**B740** Specification for Copper-Nickel-Tin Spinodal Alloy Strip

<sup>1</sup> This specification is under the jurisdiction of the ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved Oct. 1, 2007. Published October 2007. Originally approved in 1951. Last previous edition approved in 2006 as B248 – 06. DOI: 10.1520/B0248-07.

<sup>2</sup> The UNS system for copper and copper alloys (see Practice E527) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00”. The suffix can be used to accommodate composition variations of the base alloy.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard.

- B747 Specification for Copper-Zirconium Alloy Sheet and Strip
- B768 Specification for Copper-Cobalt-Beryllium Alloy and Copper-Nickel-Beryllium Alloy Strip and Sheet
- B846 Terminology for Copper and Copper Alloys
- E8 Test Methods for Tension Testing of Metallic Materials
- E18 Test Methods for Rockwell Hardness of Metallic Materials
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials
- E53 Test Method for Determination of Copper in Unalloyed Copper by Gravimetry
- E54 Test Methods for Chemical Analysis of Special Brasses and Bronzes<sup>4</sup>
- E62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods)<sup>4</sup>
- E75 Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys<sup>4</sup>
- E106 Test Methods for Chemical Analysis of Copper-Beryllium Alloys<sup>4</sup>
- E112 Test Methods for Determining Average Grain Size
- E118 Test Methods for Chemical Analysis of Copper-Chromium Alloys<sup>4</sup>
- E121 Test Methods for Chemical Analysis of Copper-Tellurium Alloys<sup>4</sup>
- E255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition
- E478 Test Methods for Chemical Analysis of Copper Alloys
- E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

### 3. Terminology

3.1 For definitions of terms related to copper and copper alloys, see Terminology B846.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *coil, n*—a length of the product wound into a series of connected turns. The unqualified term “coil” as applied to “flat product” usually refers to a coil in which the product is spirally wound, with the successive layers on top of one another. (Sometimes called a “roll.”)

3.2.2 *lengths, mill, n*—straight lengths, including ends, that can be conveniently manufactured in the mills. Full-length pieces are usually 8, 10, or 12 ft and subject to established length tolerances.

3.2.3 *lengths, stock, n*—straight lengths that are mill cut and stored in advance of orders. They are usually 8, 10, or 12 ft and subject to established length tolerances.

3.2.4 *rolled bar, n*—a rolled flat product over 0.188 in. thick and up to and including 12 in. wide, with sheared, sawed, or machined edges, in straight lengths or coils (rolls).

### 4. Materials and Manufacture

4.1 *Materials:*

4.1.1 The material of manufacture shall be a cast bar, cake, or slab of such purity and soundness as to be suitable for processing into the products to the product specification listed in Section 1.

4.1.2 In the event heat identification or traceability is required, the purchaser shall specify the details desired.

4.2 *Manufacture:*

4.2.1 The product shall be manufactured by such hot-working or cold-working and annealing processes as to produce a uniform wrought structure in the finished product.

4.2.2 The product shall be hot or cold-worked to the finished size and subsequently annealed when required, to meet the temper properties specified.

4.3 *Edges*—The edges shall be slit, sheared, sawed, or rolled edges, as specified. Slit edges shall be furnished unless otherwise specified in the contract or purchase order. See 5.6 for edge descriptions and corresponding tables for tolerances.

### 5. Dimensions, Weights, and Permissible Variations

5.1 *General*—For the purpose of determining conformance with the dimensional requirements prescribed in this specification, any measured value outside the specified limiting values for any dimension may be cause for rejection.

NOTE 2—Blank spaces in the tolerance tables indicate either that the material is not available or that no tolerances have been established.

5.2 *Thickness*—The standard method of specifying thickness shall be in decimal fractions of an inch. For material 0.021 in. and under in thickness, it is recommended that the nominal thicknesses be stated not closer than the nearest half-thousandth. (For example, specify 0.006 or 0.0065 in., but not 0.0063 in.) For material over 0.021 in. in thickness, it is recommended that the nominal thicknesses be stated not closer than the nearest thousandth. (For example, specify 0.128 or 0.129 in., but not 0.1285 in.) A list of preferred thicknesses is shown in Appendix X1. The thickness tolerances shall be those shown in Tables 1-3 for the product specification indicated:

5.2.1 *Table 1*—Thickness tolerances applicable to Specifications B36/B36M, B103/B103M, B121/B121M, B152/B152M, B465, B591, B592, and B747.

5.2.2 *Table 2*—Thickness tolerances applicable to Specifications B96/B96M, B122/B122M, B169/B169M, B194, B422, B534, B543, B740, and B768.

5.2.3 *Table 3*—Special thickness tolerances applicable to Copper Alloy UNS No. C72500 when ordered to Specification B122/B122M, and to Specifications B194, B534, B543, B740, and B768 as noted in the table.

5.3 *Width*—The width tolerances shall be those shown in Tables 4-6, depending on the type of edge required (see 5.3.1, 5.3.2, and 5.3.3):

5.3.1 *Table 4*—Width tolerances for slit metal and slit metal with rolled edges.

5.3.2 *Table 5*—Width tolerances for square-sheared metal.

5.3.3 *Table 6*—Width tolerances for sawed metal.

5.4 *Length*—The material shall be furnished in coils or straight lengths of plate, sheet, strip, or rolled bar as specified. The length tolerances for straight lengths shall be those shown in Tables 7-10, depending on the method of cutting required

<sup>4</sup> Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

**TABLE 1 Thickness Tolerances**  
(Applicable to Specifications B36/B36M, B103/B103M, B121/B121M, B152/B152M, B465, B591, B592, and B747)

Thickness, in.	Thickness Tolerances, plus and minus, <sup>A</sup> in.								
	Strip					Sheet			
	8 in. and Under in Width	Over 8 to 12 in., incl, in Width	Over 12 to 14 in., incl, in Width	Over 14 to 20 in., incl, in Width	Over 20 to 24 in., incl, in Width	Over 24 to 28 in., incl, in Width	Over 28 to 36 in., incl, in Width	Over 36 to 48 in., incl, in Width	Over 48 to 60 in., incl, in Width
0.004 and under	0.0003	0.0006	0.0006	...	...	...	...	...	...
Over 0.004 to 0.006, incl	0.0004	0.0008	0.0008	0.0013	...	...	...	...	...
Over 0.006 to 0.009, incl	0.0006	0.0010	0.0010	0.0015	...	...	...	...	...
Over 0.009 to 0.013, incl	0.0008	0.0013	0.0013	0.0018	0.0025	0.0025	0.003	0.0035	0.004
Over 0.013 to 0.017, incl	0.0010	0.0015	0.0015	0.002	0.0025	0.0025	0.003	0.0035	0.0045
Over 0.017 to 0.021, incl	0.0013	0.0018	0.0018	0.002	0.003	0.003	0.0035	0.004	0.005
Over 0.021 to 0.026, incl	0.0015	0.002	0.002	0.0025	0.003	0.003	0.0035	0.004	0.005
Over 0.026 to 0.037, incl	0.002	0.002	0.002	0.0025	0.0035	0.0035	0.004	0.005	0.006
Over 0.037 to 0.050, incl	0.002	0.0025	0.0025	0.003	0.004	0.004	0.005	0.006	0.007
Over 0.050 to 0.073, incl	0.0025	0.003	0.003	0.0035	0.005	0.005	0.006	0.007	0.008
Over 0.073 to 0.130, incl	0.003	0.0035	0.0035	0.004	0.006	0.006	0.007	0.008	0.010
Over 0.130 to 0.188, incl	0.0035	0.004	0.004	0.0045	0.007	0.007	0.008	0.010	0.012
	Rolled Bar					Plate			
Over 0.188 to 0.205, incl	0.0035	0.004	0.004	0.0045	0.007	0.007	0.008	0.010	0.012
Over 0.205 to 0.300, incl	0.004	0.0045	0.0045	0.005	0.009	0.009	0.010	0.012	0.014
Over 0.300 to 0.500, incl	0.0045	0.005	0.005	0.006	0.012	0.012	0.013	0.015	0.018
Over 0.500 to 0.750, incl	0.0055	0.007	0.007	0.009	0.015	0.015	0.017	0.019	0.023
Over 0.750 to 1.00, incl	0.007	0.009	0.009	0.011	0.018	0.018	0.021	0.024	0.029
Over 1.00 to 1.50, incl	0.022	0.022	0.022	0.022	0.022	0.022	0.025	0.029	0.036
Over 1.50 to 2.00, incl	0.026	0.026	0.026	0.026	0.026	0.026	0.030	0.036	0.044

<sup>A</sup> When tolerances are specified as all plus or all minus, double the values given.

(see 5.4.1-5.4.4). When ends are permitted, the length and quantity of the ends shall be in accordance with the schedule in Table 8.

5.4.1 Table 7—Length tolerances, for straight lengths.

5.4.2 Table 8—Schedule of minimum length and maximum weight of ends for lengths with ends.

5.4.3 Table 9—Length tolerances for square-sheared metal.

5.4.4 Table 10—Length tolerances for sawed metal.

5.5 Straightness—The straightness tolerances, which are the maximum edgewise curvature (depth of arc) in any 72-in. portion of the total length, shall be those shown in Tables 11-13, depending on the type of edge required.

5.5.1 Table 11—Straightness tolerances for metal as slit, or as slit and straightened, or as slit and edge-rolled, or metal with drawn edges.

5.5.2 Table 12—Straightness tolerances for square-sheared metal.

5.5.3 Table 13—Straightness tolerances for sawed metal.

5.6 Edges—When rolled edges are required, they may be produced by either rolling or drawing to one of the following specified edge contours:

5.6.1 Square Edges (Square Corners)—Edges shall have commercially-squared corners and with a maximum corner radius as prescribed in Table 14.

5.6.2 Rounded Corners—Edges shall have rounded corners as shown in Fig. 1 with a radius as prescribed in Table 15.

5.6.3 Rounded Edges—Edges shall be rounded as shown in Fig. 2 with a radius as prescribed in Table 16.

5.6.4 Full-Rounded Edges—Edges shall be full rounded as shown in Fig. 3 with a radius as prescribed in Table 17.

5.7 Weight Tolerances for Hot-Rolled Material:

5.7.1 Table 18—Lot weight tolerances for hot-rolled sheet and plate applicable to Specifications B36/B36M, B96/B96M (Copper Alloy UNS No. C65500), B103/B103M, B122/B122M, B152/B152M, and B591.

5.7.2 The weight of each lot of five or more plates or sheets of the same type and the same specified dimensions when ordered to thickness, shall not vary from the theoretical by more than the amount prescribed in Table 18 for the product specification indicated. The weight of any individual plate or sheet may vary from the nominal by not more than one third in excess of the tolerances prescribed in Table 18 for the product specification indicated. The tolerances for lots of less than five plates or sheets shall be governed by the tolerances for individual plates or sheets.

5.7.3 For the purpose of calculation, the densities of the materials covered by these specifications are listed in Appendix X2.

## 6. Workmanship, Finish and Appearance

6.1 The material shall be free of defects, but blemishes of a nature that do not interfere with the intended application are acceptable. A superficial film of residual light lubricant is normally present and is acceptable unless otherwise specified.

## 7. Sampling

7.1 Sampling—The lot size, portion size, and selection of sample pieces shall be as follows:

7.1.1 Lot Size—An inspection lot shall be 10 000 lb or less material of the same mill form, alloy, temper, and nominal dimensions, subject to inspection at one time or shall be the product of one cast bar from a single melt charge, whose

**TABLE 2 Thickness Tolerances**  
(Applicable to Specifications B96/B96M, B122/B122M, B169/B169M, B194, B422, B534, B543, B740, and B768)

Thickness, in.		Thickness Tolerances, Plus and Minus, <sup>A</sup> in.											
		Strip				Sheet							
8 in. and Under in Width		Over 8 to 12 in., incl, in Width	Over 12 to 14 in., incl, in Width	Over 14 to 20 in., incl, in Width	Over 20 to 24 in., incl, in Width	Over 24 to 28 in., incl, in Width	Over 28 to 36 in., incl, in Width	Over 36 to 48 in., incl, in Width	Over 48 to 60 in., incl, in Width				
0.004 and under	0.0004	0.0008	0.0008	...	...	...	...	...	...				
Over 0.004 to 0.006, incl	0.0006	0.0010	0.0010	0.0015	...	...	...	...	...				
Over 0.006 to 0.009, incl	0.0008	0.0013	0.0013	0.002	...	...	...	...	...				
Over 0.009 to 0.013, incl	0.0010	0.0015	0.0015	0.0025	...	...	...	...	...				
Over 0.013 to 0.017, incl	0.0013	0.002	0.002	0.0025	...	...	...	...	...				
Over 0.017 to 0.021, incl	0.0015	0.0025	0.0025	0.003	...	...	...	...	...				
Over 0.021 to 0.026, incl	0.002	0.0025	0.0025	0.003	0.004	0.004	0.005	0.006	0.007				
Over 0.026 to 0.037, incl	0.0025	0.003	0.003	0.0035	0.005	0.005	0.006	0.007	0.008				
Over 0.037 to 0.050, incl	0.003	0.0035	0.0035	0.004	0.006	0.006	0.007	0.008	0.010				
Over 0.050 to 0.073, incl	0.0035	0.004	0.004	0.0045	0.007	0.007	0.008	0.010	0.012				
Over 0.073 to 0.130, incl	0.004	0.0045	0.0045	0.005	0.008	0.008	0.010	0.012	0.014				
Over 0.130 to 0.188, incl	0.0045	0.005	0.005	0.006	0.010	0.010	0.012	0.014	0.016				
Rolled Bar		Plate											
		Over 0.188 to 0.205, incl	Over 0.205 to 0.300, incl	Over 0.300 to 0.500, incl	Over 0.500 to 0.750, incl	Over 0.750 to 1.00, incl	Over 1.00 to 1.50, incl	Over 1.50 to 2.00, incl	0.005	0.006	0.010	0.010	0.012
Over 0.188 to 0.205, incl	0.0045	0.005	0.005	0.006	0.010	0.010	0.012	0.014	0.016				
Over 0.205 to 0.300, incl	0.005	0.006	0.006	0.007	0.012	0.012	0.014	0.016	0.018				
Over 0.300 to 0.500, incl	0.006	0.007	0.007	0.008	0.015	0.015	0.017	0.019	0.023				
Over 0.500 to 0.750, incl	0.008	0.010	0.010	0.012	0.019	0.019	0.021	0.024	0.029				
Over 0.750 to 1.00, incl	0.010	0.012	0.012	0.015	0.023	0.023	0.026	0.030	0.037				
Over 1.00 to 1.50, incl	0.028	0.028	0.028	0.028	0.028	0.028	0.032	0.037	0.045				
Over 1.50 to 2.00, incl	0.033	0.033	0.033	0.033	0.033	0.033	0.038	0.045	0.055				

<sup>A</sup> When tolerances are specified as all plus or all minus, double the values given.

**TABLE 3 Special Thickness Tolerances**

Thickness, in.	Tolerances Applicable to Copper Alloy UNS No. C72500, Specification B122/B122M and B740	Tolerances Applicable to Specifications B194, B534, B543, and B768
	Tolerances, Plus and Minus, <sup>A</sup> in., for Strip 8 in. and Under in Width	Tolerances, Plus and Minus, <sup>A</sup> in., for Strip 4 in. and Under in Width
0.004 and under	0.0002	0.0002
Over 0.004 to 0.006, incl	0.0003	0.0003
Over 0.006 to 0.009, incl	0.0004	0.0005
Over 0.009 to 0.013, incl	0.0005	0.0006
Over 0.013 to 0.017, incl	0.0007	0.0007
Over 0.017 to 0.021, incl	0.0008	0.0008
Over 0.021 to 0.026, incl	0.0010	0.0010
Over 0.026 to 0.032, incl	0.0013	0.0010
Over 0.032 to 0.050, incl	0.0015	...

<sup>A</sup> If tolerances are specified as all plus or all minus, double the values given.

**TABLE 4 Width Tolerances for Slit Metal and Slit Metal with Rolled Edges**  
(Applicable to all specifications listed in 1.1)

Width, in.	Width Tolerances, <sup>A</sup> Plus and Minus, in.			
	For Thicknesses 0.004 to 0.032 in.	For Thicknesses Over 0.032 to 0.125 in.	For Thicknesses Over 0.125 to 0.188 in.	For Thicknesses Over 0.188 to 0.500 in.
	2 and under	0.005	0.010	0.012
Over 2 to 8, incl	0.008	0.013	0.015	0.015
Over 8 to 24, incl	1/64	1/64	1/64	1/32
Over 24 to 50, incl	1/32	1/32	1/32	3/64

<sup>A</sup> If tolerances are specified as all plus or all minus, double the values given.

7.1.2 *Portion Size*—A portion shall be two representative samples taken from the product of one cast bar that has been continually processed to the finished temper and dimensions.

7.1.2.1 *Chemical Analysis*—The sample for chemical analysis shall be taken in accordance with Practice E255 for product in its final form. Unless otherwise required by the purchaser, at the time the order is placed, the manufacturer shall have the

weight shall not exceed 25 000 lb that has been continuously processed and subject to inspection at one time.

**TABLE 5 Width Tolerances for Square-Sheared Metal**  
(Applicable to all specifications listed in 1.1)

NOTE 1—All lengths up to 120 in., incl.

Width, in.	Width Tolerances, <sup>A</sup> Plus and Minus, in.		
	1/16 in. and Under in Thickness	Over 1/16 to 1/8 in., incl. in Thickness	Over 1/8 in. in Thickness
20 and under	1/32	3/64	1/16
Over 20 to 36, incl	3/64	3/64	1/16
Over 36 to 120, incl	1/16	1/16	1/16

<sup>A</sup> If tolerances are specified as all plus or all minus, double the values given.

**TABLE 6 Width Tolerances for Sawed Metal**  
(Applicable to all specifications listed in 1.1)

Width, in.	Width Tolerances, <sup>A</sup> Plus and Minus, in.		
	For Lengths Up to 10 ft, incl		For Lengths Over 10 ft.
	For Thicknesses Up to 1 1/2 in., incl	For Thicknesses Over 1 1/2 in.	All Thicknesses
Up to 12, incl	1/32	1/16	1/16
Over 12 to 120, incl	1/16	1/16	1/16

<sup>A</sup> If tolerances are specified as all plus or all minus, double the values given.

**TABLE 7 Length Tolerances for Straight Lengths**  
(Applicable to all specifications listed in 1.1 except B694)

NOTE 1—The following length tolerances are all plus; if all minus tolerances are desired, use the same values; if tolerances are desired plus and minus, halve the values given.

Length ft.	Length Tolerances in.
Specific lengths, mill lengths, multiple lengths, and specific lengths with ends 10 and under	1/4
Over 10 to 20, incl	1/2
Stock lengths and stock lengths with ends	1 <sup>A</sup>

<sup>A</sup> As stock lengths are cut and placed in stock in advance of orders, departure from the tolerance is not practicable.

option of determining conformance to chemical composition by analyzing samples taken at the time the castings are poured or samples taken from the semi-finished product if heat identity can be maintained throughout all operations. If the manufacturer determines the chemical composition during manufacture, he shall not be required to sample and analyze the finished product. The minimum weight of the composite sample in accordance with Practice E255 that is to be divided into three equal parts shall be as follows:

ASTM Designation	Weight of Sample, min, g
B36/B36M, B96/B96M, B121/B121M, B122/B122M, B152/B152M, B169/B169M, B194, B422, B465, B534, B591, B592, B740, B747, and B768	150
B103/B103M	225

7.1.2.2 *Samples for All Other Tests*—Samples for all other tests shall be taken from the sample portion in 7.1.2 and be of a convenient size to accommodate the test and comply with the requirements of the appropriate ASTM Product Standards and Test Methods.

## 8. Number of Tests and Retests

### 8.1 Chemical Requirements:

8.1.1 When samples are taken at the time the castings are poured, at least one sample shall be analyzed for each group of castings poured simultaneously from the same source of molten metal.

8.1.2 When samples are taken from the semi-finished or finished product, at least one sample representative of the product of each cast bar from a single melt charge continuously processed with heat identity maintained shall be analyzed.

8.1.3 When samples are taken from the semi-finished or finished product and heat identity has not been maintained, a single sample representative of each 10 000 lb lot, or fraction thereof, shall be analyzed. When the product piece is greater than 10 000 lb, one sample to be representative of the product piece shall be analyzed.

8.2 *Mechanical and Electrical Requirements and Grain Size*—Unless otherwise provided in the product specification, test specimens shall be taken from each of the two of the sample pieces selected in accordance with 7.1.2. The required tests shall be made on each of the specimens. In the case of copper alloy Specifications B194, B534, B543, and B740, one specimen shall be tested without further treatment, and the other specimen shall be tested after precipitation hardening. In the case of the requirements in Table 4, Mill Hardened Tempers, in Specifications B194 and B740, the two specimens need to be tested, because the product is in the precipitation hardened temper as supplied. The reported value shall be the arithmetic average of the readings. In the case of hardness, three readings shall be taken and averaged for each sample.

### 8.3 Retests:

8.3.1 If the chemical analysis of the specimens prepared from samples selected in accordance with 7.1.2 fails to conform to the specified limits, analysis shall be made on a new composite sample prepared from the samples selected in accordance with 7.1.2.

8.3.2 If one of the two tests made to determine any of the mechanical or physical properties fails to meet a specified limit, this test shall be repeated on the remaining sample pieces, selected in accordance with 7.1.2, and the results of these tests shall comply with the specified requirements.

8.3.3 If any test specimen shows defective machining or develops flaws, it may be discarded and another specimen substituted.

8.3.4 If the percentage of elongation of any tension test specimen is less than that specified and any part of the fracture is outside the middle two thirds of the gage length or in a punched or scribed mark within the reduced section, a retest shall be allowed.

8.3.5 If a bend test specimen fails because of conditions of bending more severe than required by the specification, a retest shall be permitted, either on a duplicate specimen or on a remaining portion of the failed specimen.

8.3.6 After removal of defective specimens and correction of test methods, only one retest cycle is permitted. If after the retest the material fails to meet the requirements of this specification, it shall be rejected.

**TABLE 8 Schedule of Minimum Length and Maximum Weight of Ends for Mill Lengths, Specific Lengths with Ends, and Stock Lengths with Ends**

(Applicable to all specifications listed in 1.1 except B694)

Nominal Length, ft	0.050 in. and Under in Thickness		Over 0.050 to 0.125 in., incl, in Thickness		Over 0.125 to 0.250 in., incl, in Thickness	
	Minimum Length of Shortest Piece, ft	Maximum Permissible Weight of Ends, % of Lot Weight	Minimum Length of Shortest Piece, ft	Maximum Permissible Weight of Ends, % of Lot Weight	Minimum Length of Shortest Piece, ft	Maximum Permissible Weight of Ends, % of Lot Weight
6 to 8, incl	4	20	4	25	3	30
8 to 10, incl	6	25	5	30	4	35
10 to 14, incl	7	30	6	35	5	40

**TABLE 9 Length Tolerances for Square-Sheared Metal in All Widths 120 in. (3.05 m) and Under**

(Applicable to all specifications listed in 1.1 except B694)

Length, in.	Length Tolerance, <sup>A</sup> Plus and Minus, in.		
	For Thicknesses Up to 1/16 in., incl	For Thicknesses Over 1/16 to 1/8 in., incl	For Thicknesses Over 1/8 in.
20 and under	1/32	3/64	1/16
Over 20 to 36, incl	3/64	3/64	1/16
Over 36 to 120, incl	1/16	1/16	1/16

<sup>A</sup> If tolerances are specified as all plus or all minus, double the values given.

**TABLE 10 Length Tolerances for Sawed Metal**

(Applicable to all specifications listed in 1.1 except B694)

NOTE 1—The following tolerances are all plus; if all minus tolerances are desired, use the same values; if tolerances are desired plus and minus, halve the values given.

Width, in.	Length Tolerance, in.
Up to 120, incl	1/4

**TABLE 11 Straightness Tolerances for Slit Metal or Slit Metal Either Straightened or Edge-Rolled**

(Applicable to all specifications listed in 1.1)

Width, in.	Maximum Edgewise Curvature (Depth of Arc) in any 72-in. Portion of the Total Length		
	Straightness Tolerance, in.		
	As Slit Only	As Slit and Either Straightened or Edge Rolled	
	Shipped in Rolls	Shipped Flat	Shipped Flat, in Rolls, or on Bucks
Over 1/4 to 3/8, incl	2	1 1/2	1/2
Over 3/8 to 1/2, incl	1 1/2	1	1/2
Over 1/2 to 1, incl	1	3/4	1/2
Over 1 to 2, incl	5/8	5/8	3/8
Over 2 to 4, incl	1/2	1/2	3/8
Over 4	3/8	3/8	3/8

## 9. Specimen Preparation

9.1 *Chemical Analysis*—A composite sample of the semi-finished or finished product shall be prepared in accordance with Practice E255, or as described in 7.1.2.1.

9.2 Specimens shall be prepared in accordance with the method prescribed in 10.3 for all other tests. Full cross-section specimens shall be used whenever possible. Samples shall be representative of the condition of the material, and particular specimen preparation techniques shall be stated in the specific product specification.

**TABLE 12 Straightness Tolerances for Square-Sheared Metal**

(Applicable to all specifications listed in 1.1)

(Not applicable to metal over 120 in. in length)

Thickness, in.	Maximum Edgewise Curvature (Depth of Arc) in any 72-in. Portion of the Total Length	
	Straightness Tolerances, in.	
	Up to 10 in., incl, in Width	Over 10 in., in Width
1/8 and under	1/16	1/32
Over 1/8 to 3/16, incl	1/8	3/64
Over 3/16	1/8	1/16

**TABLE 13 Straightness Tolerances for Sawed Metal**

(Applicable to all specifications listed in 1.1)

(Not applicable to metal over 144 in. in length)

Width, in.	Maximum Edgewise Curvature (Depth of Arc) in any 72-in. Portion of the Total Length	
	Straightness Tolerances, in.	
3 and under	1/16	
Over 3	3/64	

**TABLE 14 Tolerances for Radius of Commercially Square Corners of Rolled or Drawn Edges with Square Corners**

(Applicable to all specifications listed in 1.1 except B694)

Thickness, in.	Permissible Radius of Corners, max, in.
0.032 to 0.064, incl	0.010
Over 0.064 to 0.188, incl	0.016
Over 0.188 to 1, incl	1/32

## 10. Test Methods

10.1 The test method used for routine chemical analysis for specification compliance and preparation of certifications and test reports, when required, shall be at the discretion of the reporting laboratory.

10.1.1 Commonly accepted technique for routine chemical analysis of copper and copper alloys include, but are not limited to, X-ray fluorescence spectroscopy, atomic absorption spectrophotometry, argon plasma spectroscopy, and emission spectroscopy.

10.2 In case of disagreement concerning chemical composition, an applicable test method for chemical analysis may be found in Test Methods E53, E54, E62, E75, E106, E118, E121, or E478.

10.2.1 The specific test method(s) to be used will be stated in the particular product specification.

10.2.2 In case of disagreement concerning sulfur content, the test method described in the Annex shall be used.