



Designation: D3198 – 97(Reapproved 2007)

Standard Test Method for Application and Removal Torque of Threaded or Lug-Style Closures¹

This standard is issued under the fixed designation D3198; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the application with a given torque of a threaded or lug-style closure to a container, and measures the torque required to unscrew the closure from a container.

1.2 The values stated in SI units are to be regarded as the standard. The inch-pound units given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D3474 Practice for Calibration and Use of Torque Meters Used in Packaging Applications

E105 Practice for Probability Sampling of Materials

E122 Practice for Calculating Sample Size to Estimate, With Specified Precision, the Average for a Characteristic of a Lot or Process

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *application torque*—the moment of a force or system of forces tending to cause rotation of a closure over the neck finish of an appropriate container, causing the closure to be applied and secured to the container.

3.1.2 *removal torque*—the moment of a force or system of forces tending to cause rotation of an appropriate closure in a

direction opposite to that of application, causing the closure to be unsecured from its position on the neck finish of an appropriate container.

4. Summary of Test Method

4.1 Representative specimens of a threaded or lug-style container are held in a torque-measuring device and either the predetermined amount of torque is applied to its closure, or the amount of torque necessary to loosen the closure is determined, or both.

5. Significance and Use

5.1 These torque measurements are of value in:

5.1.1 Rating the performance of automatic capping machines,

5.1.2 Measuring any tendency for threaded or lug-style closures to loosen during storage or shipment of the package, and

5.1.3 Measuring the force required to break hard plastic and overturn or “strip” soft plastic and metal closures.

5.2 The method may be used to establish performance specifications.

6. Apparatus

6.1 *Torque Meter* (see **Note 1**) with a scale that will read with the maximum point reading accuracy within the torque range expected to be measured (use a 0 to 25 torque inch pounds-force (T.I.P.) torque meter for readings under 25 T.I.P., not a 0 to 100 T.I.P. torque meter).

NOTE 1—A digital or automated torque instrument, if used, will have an appropriate design and scale capacity for the container/closure system to be evaluated. Torque results will be available in either electronic display or printout formats.

7. Sampling, Test Specimens, and Test Units

7.1 The number of samples will depend on the desired purpose for which this test is being run. However, for a given set of samples, sufficient measurements shall be taken in accordance with established statistical sampling procedures in order to obtain consistent results.

NOTE 2—Refer to Practices **E105** and **E122** for more specific information.

¹ This test method is under the jurisdiction of ASTM Committee D10 on Packaging and is the direct responsibility of Subcommittee D10.32 on Consumer, Pharmaceutical and Medical Packaging.

Current edition approved Oct. 1, 2007. Published October 2007. Originally approved in 1973. Last previous edition approved in 2002 as D3198 – 97 (2002). DOI: 10.1520/D3198-97R07.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.